

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 1

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

1500	Phantom White		
1554	TINTING WHITE	392.1	784.2
1559	YELLOW OXIDE	437.7	875.5
1501	LANDAU BLACK	442.6	885.2
1550	RED OXIDE	445.7	891.4

1506	BURGUNDY		
1552	FAST RED	189.0	377.9
1550	RED OXIDE	342.9	685.7
1553	FAST BLUE	399.0	798.0
1559	YELLOW OXIDE	407.7	815.5

1501	LANDAU BLACK	Chrysler Motors	X9
1501	LANDAU BLACK	405.1	810.2

1507	SEA MOSS		
1559	YELLOW OXIDE	250.6	501.2
1501	LANDAU BLACK	355.0	710.0
1556	FAST GREEN	392.0	783.9
1554	TINTING WHITE	411.3	822.5

1501	LANDAU BLACK	General Motors	WA848
1501	LANDAU BLACK	405.1	810.2

1508	SILVER		
1508	SILVER	408.9	817.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1502	Cordovan Brown		
1550	RED OXIDE	114.8	229.7
1559	YELLOW OXIDE	225.0	450.1
1501	LANDAU BLACK	338.0	675.9
1302	LOW LUSTER CLEAR	409.1	818.2

1509	Light Buckskin		
1554	TINTING WHITE	254.7	509.5
1559	YELLOW OXIDE	408.8	817.7
1550	RED OXIDE	431.4	862.9
1501	LANDAU BLACK	437.9	875.8

1503	SADDLE TAN		
1559	YELLOW OXIDE	243.3	486.6
1554	TINTING WHITE	327.6	655.1
1550	RED OXIDE	386.8	773.7
1501	LANDAU BLACK	417.3	834.7

1510	SUPER WHITE		
1554	TINTING WHITE	410.8	821.6
1559	YELLOW OXIDE	428.3	856.5
1550	RED OXIDE	433.7	867.4
1556	FAST GREEN	435.9	871.7

1504	SHADOW BLUE		
1553	FAST BLUE	180.7	361.4
1501	LANDAU BLACK	354.1	708.1
1554	TINTING WHITE	405.8	811.7

1511	FIRETHORN RED		
1550	RED OXIDE	290.0	580.1
1552	FAST RED	406.9	813.8
1554	TINTING WHITE	411.4	822.9

1505	Granite		
1554	TINTING WHITE	154.7	309.4
1302	LOW LUSTER CLEAR	297.4	594.8
1501	LANDAU BLACK	382.3	764.6
1550	RED OXIDE	415.0	830.0
1559	YELLOW OXIDE	426.3	852.6

1512	SANTA FE		
1554	TINTING WHITE	326.8	653.6
1559	YELLOW OXIDE	420.0	840.0
1550	RED OXIDE	426.8	853.7
1501	LANDAU BLACK	431.1	862.2

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 2

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

1513	WEDGEWOOD BLU				
1554	TINTING WHITE	305.8	611.6		
1553	FAST BLUE	378.8	757.5		
1501	LANDAU BLACK	422.0	844.0		
1552	FAST RED	424.1	848.2		

1545	Gloss White				
1554	TINTING WHITE	286.5	572.9		
1300	HIGH GLOSS CLEAR	431.7	863.3		
1559	YELLOW OXIDE	433.6	867.2		
1501	LANDAU BLACK	435.3	870.6		
1558	BRITE RED	435.6	871.2		

1514	YELLOW GOLD				
1554	TINTING WHITE	275.6	551.2		
1559	YELLOW OXIDE	417.6	835.2		
1550	RED OXIDE	423.6	847.2		
1556	FAST GREEN	428.4	856.7		

1575	Light Oak				
1302	LOW LUSTER CLEAR	167.3	334.6		
1559	YELLOW OXIDE	291.9	583.9		
1554	TINTING WHITE	393.3	786.6		
1550	RED OXIDE	414.6	829.1		
1501	LANDAU BLACK	424.0	848.1		

1515	MOCHA COFFEE				
1550	RED OXIDE	191.0	381.9		
1559	YELLOW OXIDE	330.7	661.4		
1501	LANDAU BLACK	395.6	791.2		
1554	TINTING WHITE	413.3	826.7		

1601	DK BLUE MET	General Motors			29T
1553	FAST BLUE	174.1	348.3		
1501	LANDAU BLACK	298.4	596.8		
1508	SILVER	378.4	756.8		
1551	INDO YELLOW	403.2	806.4		

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1521	Dk. Blue Mist				
1501	LANDAU BLACK	168.8	337.7		
1554	TINTING WHITE	330.4	660.8		
1302	LOW LUSTER CLEAR	386.0	772.1		
1553	FAST BLUE	426.5	852.9		

1602	DK BLUE GREEN	General Motors			32T
1559	YELLOW OXIDE	206.1	412.1		
1553	FAST BLUE	329.1	658.2		
1501	LANDAU BLACK	390.9	781.9		
1554	TINTING WHITE	409.6	819.3		

1523	Gloss Black				
1300	HIGH GLOSS CLEAR	275.3	550.6		
1501	LANDAU BLACK	412.8	825.5		

1603	DK BLUE MET	General Motors			35T
1553	FAST BLUE	265.4	530.9		
1508	SILVER	327.8	655.5		
1501	LANDAU BLACK	378.9	757.7		
1551	INDO YELLOW	403.8	807.5		

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1524	Satin Black				
1501	LANDAU BLACK	207.1	414.2		
1301	SATIN GLOSS CLEAR	414.2	828.4		

1604	IVORY	General Motors			52T
1554	TINTING WHITE	357.5	715.0		
1559	YELLOW OXIDE	426.0	852.0		
1556	FAST GREEN	429.6	859.2		
1501	LANDAU BLACK	432.8	865.6		

1537	Flame Red				
1558	BRITE RED	251.2	502.5		
1552	FAST RED	310.9	621.9		
1302	LOW LUSTER CLEAR	363.6	727.3		
1551	INDO YELLOW	403.6	807.2		

1605	BUCKSKIN	General Motors			64T
1559	YELLOW OXIDE	241.8	483.6		
1554	TINTING WHITE	382.0	764.0		
1550	RED OXIDE	411.1	822.1		
1501	LANDAU BLACK	420.8	841.5		

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 3

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	DK BROWN MET	General Motors	69T
1501	LANDAU BLACK	110.8	221.5
1551	INDO YELLOW	219.7	439.5
1552	FAST RED	327.8	655.7
1508	SILVER	405.2	810.4

	MIDNIGHT LIME	General Motors	47
1559	YELLOW OXIDE	253.7	507.3
1556	FAST GREEN	330.2	660.4
1554	TINTING WHITE	384.0	768.0
1501	LANDAU BLACK	413.8	827.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	SILVER BLUE MET	General Motors	92T
1508	SILVER	348.0	696.0
1553	FAST BLUE	387.5	775.0
1554	TINTING WHITE	405.2	810.4
1501	LANDAU BLACK	409.3	818.5

	LT IVORY GOLD	General Motors	53
1559	YELLOW OXIDE	223.1	446.1
1554	TINTING WHITE	404.2	808.5
1501	LANDAU BLACK	416.5	833.0
1556	FAST GREEN	422.8	845.7

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	DK GRAY	General Motors	14
1501	LANDAU BLACK	194.1	388.2
1554	TINTING WHITE	325.7	651.3
1559	YELLOW OXIDE	394.4	788.9
1550	RED OXIDE	416.7	833.3

	DK IVORY GOLD	General Motors	53
1559	YELLOW OXIDE	293.0	586.0
1554	TINTING WHITE	377.2	754.5
1501	LANDAU BLACK	415.4	830.9
1556	FAST GREEN	417.1	834.1

	LT SMOKE GRAY	General Motors	15
1554	TINTING WHITE	348.9	697.9
1559	YELLOW OXIDE	397.3	794.6
1501	LANDAU BLACK	428.8	857.7
1550	RED OXIDE	431.9	863.7

	DK YELLOW GOLD	General Motors	54
1559	YELLOW OXIDE	357.7	715.4
1554	TINTING WHITE	400.3	800.7
1501	LANDAU BLACK	411.4	822.9
1556	FAST GREEN	415.2	830.5

	LT BLUE	General Motors	24
1554	TINTING WHITE	322.0	643.9
1501	LANDAU BLACK	372.5	745.0
1553	FAST BLUE	405.9	811.9
1559	YELLOW OXIDE	429.1	858.2

	BUCKSKIN	General Motors	64
1559	YELLOW OXIDE	217.9	435.9
1554	TINTING WHITE	383.9	767.8
1550	RED OXIDE	412.0	824.0
1501	LANDAU BLACK	422.3	844.6

	DK BLUE	General Motors	26
1554	TINTING WHITE	214.8	429.6
1501	LANDAU BLACK	307.1	614.3
1553	FAST BLUE	366.9	733.8
1559	YELLOW OXIDE	421.6	843.2

	DK SADDLE	General Motors	64
1559	YELLOW OXIDE	240.0	479.9
1550	RED OXIDE	337.0	673.9
1554	TINTING WHITE	376.8	753.5
1501	LANDAU BLACK	414.9	829.7

	DK BLUE GREEN	General Motors	32
1556	FAST GREEN	282.9	565.8
1559	YELLOW OXIDE	340.8	681.5
1501	LANDAU BLACK	388.2	776.3
1554	TINTING WHITE	406.9	813.8

	LT BLUE MET	General Motors	22T
1508	SILVER	302.1	604.2
1553	FAST BLUE	379.0	757.9
1501	LANDAU BLACK	399.2	798.4
1556	FAST GREEN	407.3	814.5

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 4

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	MED GREEN MET	General Motors	44T
1508	SILVER	269.7	539.4
1553	FAST BLUE	337.9	675.8
1551	INDO YELLOW	381.0	761.9
1501	LANDAU BLACK	397.0	794.0
1554	TINTING WHITE	407.1	814.2

	LT ORANGE MET	General Motors	96T
1552	FAST RED	212.4	424.8
1508	SILVER	308.2	616.4
1551	INDO YELLOW	394.8	789.6
1501	LANDAU BLACK	400.1	800.3
1554	TINTING WHITE	405.5	810.9

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	YELLOW	General Motors	50T
1554	TINTING WHITE	365.4	730.7
1551	INDO YELLOW	428.0	856.0
1501	LANDAU BLACK	432.0	863.9

	DK RED MET	General Motors	98T
1552	FAST RED	356.6	713.3
1508	SILVER	378.7	757.3
1553	FAST BLUE	388.6	777.3
1551	INDO YELLOW	398.6	797.2
1554	TINTING WHITE	404.6	809.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	GOLD MET	General Motors	58T
1508	SILVER	306.4	612.8
1551	INDO YELLOW	407.6	815.3

	DK AQUA	General Motors	03
1553	FAST BLUE	203.2	406.4
1554	TINTING WHITE	289.1	578.2
1551	INDO YELLOW	336.3	672.6
1552	FAST RED	379.6	759.2
1556	FAST GREEN	409.8	819.7

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	LT BEIGE	General Motors	62T
1554	TINTING WHITE	348.5	696.9
1559	YELLOW OXIDE	415.1	830.1
1550	RED OXIDE	431.1	862.2
1501	LANDAU BLACK	432.4	864.9

	Dark Aqua	General Motors	3
1553	FAST BLUE	247.8	495.6
1554	TINTING WHITE	350.7	701.4
1551	INDO YELLOW	411.9	823.7
1501	LANDAU BLACK	421.0	841.9

	CLARET	General Motors	79T
1552	FAST RED	276.5	553.1
1501	LANDAU BLACK	349.8	699.6
1550	RED OXIDE	401.6	803.1
1554	TINTING WHITE	405.7	811.5

	DK SAGE GREEN	General Motors	44
1559	YELLOW OXIDE	221.7	443.5
1554	TINTING WHITE	316.4	632.7
1553	FAST BLUE	378.0	756.0
1550	RED OXIDE	416.8	833.5

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	SILVER BLUE MET	General Motors	90T
1508	SILVER	177.0	354.0
1553	FAST BLUE	327.3	654.6
1552	FAST RED	383.2	766.5
1551	INDO YELLOW	398.8	797.6
1554	TINTING WHITE	406.1	812.3

	LT YELLOW GOLD	General Motors	54
1554	TINTING WHITE	262.9	525.7
1559	YELLOW OXIDE	352.7	705.5
1551	INDO YELLOW	420.5	840.9
1501	LANDAU BLACK	426.0	852.0

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	BUCKSKIN MET	General Motors	95T
1508	SILVER	215.0	430.0
1551	INDO YELLOW	317.4	634.8
1552	FAST RED	405.2	810.4
1501	LANDAU BLACK	406.6	813.2

	LT BUCKSKIN	General Motors	61
1559	YELLOW OXIDE	240.0	479.9
1554	TINTING WHITE	376.6	753.2
1550	RED OXIDE	411.9	823.8
1501	LANDAU BLACK	420.8	841.5

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 5

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	DK SADDLE	General Motors	65
1559	YELLOW OXIDE	273.1	546.3
1550	RED OXIDE	354.0	707.9
1554	TINTING WHITE	385.5	771.0
1501	LANDAU BLACK	414.5	829.0

	LT BEIGE	General Motors	62T
1554	TINTING WHITE	283.8	567.5
1559	YELLOW OXIDE	383.9	767.8
1550	RED OXIDE	422.4	844.7
1501	LANDAU BLACK	428.8	857.7

	MED SAFFRON	General Motors	67
1550	RED OXIDE	228.5	457.0
1559	YELLOW OXIDE	388.3	776.5
1554	TINTING WHITE	410.8	821.6
1501	LANDAU BLACK	415.0	829.9

	DK CAMEL MET	General Motors	69T
1552	FAST RED	178.8	357.6
1551	INDO YELLOW	316.8	633.7
1508	SILVER	376.4	752.8
1501	LANDAU BLACK	404.8	809.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	DK CRIMSON	General Motors	73
1552	FAST RED	295.4	590.7
1559	YELLOW OXIDE	397.9	795.7
1554	TINTING WHITE	406.0	812.1
1501	LANDAU BLACK	406.9	813.8

	MULBERRY MET	General Motors	74T
1552	FAST RED	323.8	647.5
1551	INDO YELLOW	363.0	726.0
1508	SILVER	387.2	774.4
1553	FAST BLUE	404.2	808.5

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	DK CLARET	General Motors	79
1552	FAST RED	252.7	505.4
1501	LANDAU BLACK	336.0	672.0
1550	RED OXIDE	401.4	802.8
1554	TINTING WHITE	406.2	812.4

	DK CARMINE MET	General Motors	79T
1552	FAST RED	227.5	455.1
1550	RED OXIDE	319.8	639.5
1501	LANDAU BLACK	399.4	798.8
1554	TINTING WHITE	407.1	814.2

	SILVER	General Motors	15T
1508	SILVER	389.2	778.4
1501	LANDAU BLACK	399.9	799.7
1554	TINTING WHITE	403.9	807.9
1552	FAST RED	407.3	814.5
1551	INDO YELLOW	408.9	817.8

	MED BLUE MET	General Motors	90T
1553	FAST BLUE	179.1	358.2
1508	SILVER	324.5	649.0
1501	LANDAU BLACK	372.4	744.8
1554	TINTING WHITE	407.8	815.7

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	DK GREEN MET	General Motors	49T
1553	FAST BLUE	139.7	279.3
1501	LANDAU BLACK	265.8	531.6
1508	SILVER	344.8	689.5
1551	INDO YELLOW	404.6	809.2

	MED GREEN MET	General Motors	94T
1508	SILVER	203.6	407.2
1556	FAST GREEN	326.4	652.8
1501	LANDAU BLACK	369.8	739.7
1551	INDO YELLOW	406.5	813.0

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	CAMEL BEIGE	General Motors	61T
1554	TINTING WHITE	313.4	626.8
1559	YELLOW OXIDE	424.0	848.0
1552	FAST RED	430.0	859.9
1501	LANDAU BLACK	430.4	860.7

	GOLD MET	General Motors	95T
1508	SILVER	276.9	553.9
1551	INDO YELLOW	374.2	748.4
1552	FAST RED	407.3	814.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 6

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	MED SADDLE MET	General Motors	96T
1552	FAST RED	153.4	306.9
1508	SILVER	298.2	596.4
1551	INDO YELLOW	401.0	802.0
1501	LANDAU BLACK	405.6	811.1

	DK CARMEL TAN	General Motors	62
1559	YELLOW OXIDE	283.1	566.2
1550	RED OXIDE	346.8	693.7
1554	TINTING WHITE	405.9	811.9
1501	LANDAU BLACK	416.4	832.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	MED BEIGE MET	General Motors	98T
1508	SILVER	196.4	392.7
1552	FAST RED	329.0	658.0
1551	INDO YELLOW	377.2	754.3
1556	FAST GREEN	399.4	798.8
1554	TINTING WHITE	406.8	813.6

	DK CARMINE	General Motors	74
1552	FAST RED	312.7	625.5
1550	RED OXIDE	395.7	791.4
1554	TINTING WHITE	403.8	807.7
1501	LANDAU BLACK	406.7	813.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	LT GRAY	General Motors	16
1554	TINTING WHITE	300.6	601.2
1559	YELLOW OXIDE	379.1	758.1
1501	LANDAU BLACK	413.0	825.9
1550	RED OXIDE	429.2	858.4

	DK MULBERRY	General Motors	78
1552	FAST RED	217.6	435.1
1550	RED OXIDE	383.1	766.3
1553	FAST BLUE	403.5	806.9
1554	TINTING WHITE	408.3	816.6

	DK GRAY	General Motors	16
1554	TINTING WHITE	218.9	437.8
1559	YELLOW OXIDE	337.6	675.3
1501	LANDAU BLACK	405.3	810.5
1550	RED OXIDE	423.9	847.8

	DK SAGE GREEN	General Motors	4
1559	YELLOW OXIDE	246.1	492.3
1554	TINTING WHITE	337.9	675.8
1553	FAST BLUE	389.6	779.2
1501	LANDAU BLACK	416.3	832.6

	DK GREEN	General Motors	49
1501	LANDAU BLACK	176.0	352.1
1556	FAST GREEN	292.6	585.2
1551	INDO YELLOW	352.5	704.9
1554	TINTING WHITE	408.7	817.4

	PASTEL BEIGE	General Motors	62T
1554	TINTING WHITE	359.9	719.7
1559	YELLOW OXIDE	430.1	860.1
1550	RED OXIDE	432.3	864.5
1501	LANDAU BLACK	433.1	866.2

	DK YELLOW	General Motors	50
1559	YELLOW OXIDE	312.6	625.1
1554	TINTING WHITE	398.0	795.9
1501	LANDAU BLACK	414.6	829.2
1550	RED OXIDE	417.5	835.1

	MED BEIGE	General Motors	61T
1554	TINTING WHITE	272.0	544.0
1559	YELLOW OXIDE	407.2	814.3
1550	RED OXIDE	420.9	841.7
1501	LANDAU BLACK	428.2	856.3

	DK SADDLE	General Motors	60
1559	YELLOW OXIDE	269.9	539.8
1550	RED OXIDE	373.4	746.9
1554	TINTING WHITE	405.5	810.9
1501	LANDAU BLACK	415.1	830.1

	DK BROWN MET	General Motors	69T
1559	YELLOW OXIDE	163.5	327.0
1550	RED OXIDE	303.5	607.1
1501	LANDAU BLACK	401.6	803.1
1554	TINTING WHITE	412.3	824.6

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 7

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	DK GREEN MET	General Motors	48T
1508	SILVER	308.3	616.6
1553	FAST BLUE	346.9	693.9
1551	INDO YELLOW	380.3	760.6
1501	LANDAU BLACK	407.6	815.1

	DK AQUA	General Motors	31
1554	TINTING WHITE	169.6	339.2
1553	FAST BLUE	320.7	641.4
1551	INDO YELLOW	385.5	771.0
1501	LANDAU BLACK	416.4	832.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	LT SILVER GRAY M	General Motors	90T
1508	SILVER	353.4	706.8
1501	LANDAU BLACK	408.3	816.6

	DK CEDAR	General Motors	70
1550	RED OXIDE	267.9	535.8
1559	YELLOW OXIDE	337.5	675.1
1501	LANDAU BLACK	382.8	765.5
1554	TINTING WHITE	414.7	829.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	LT GOLD MET	General Motors	91T
1508	SILVER	168.3	336.7
1551	INDO YELLOW	289.8	579.5
1552	FAST RED	361.4	722.8
1501	LANDAU BLACK	406.1	812.3

	DK WILLOW GREE	General Motors	44
1559	YELLOW OXIDE	330.1	660.3
1554	TINTING WHITE	374.9	749.7
1553	FAST BLUE	401.8	803.5
1501	LANDAU BLACK	414.6	829.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	LT GRAY	General Motors	89T
1554	TINTING WHITE	406.3	812.6
1501	LANDAU BLACK	425.3	850.6
1559	YELLOW OXIDE	433.1	866.2
1550	RED OXIDE	435.3	870.6

	DK GOLD	General Motors	51
1554	TINTING WHITE	145.1	290.1
1551	INDO YELLOW	286.5	573.0
1552	FAST RED	362.9	725.8
1501	LANDAU BLACK	415.2	830.5

	LT CEDAR MET	General Motors	93T
1552	FAST RED	187.9	375.8
1508	SILVER	319.3	638.6
1551	INDO YELLOW	398.3	796.7
1501	LANDAU BLACK	405.7	811.3

	DK SLATE GRAY	General Motors	8046
1554	TINTING WHITE	251.8	503.5
1501	LANDAU BLACK	349.1	698.3
1559	YELLOW OXIDE	407.4	814.7
1550	RED OXIDE	425.2	850.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	PASTEL GREEN	General Motors	40T
1554	TINTING WHITE	403.7	807.3
1551	INDO YELLOW	422.3	844.6
1556	FAST GREEN	429.2	858.4
1501	LANDAU BLACK	434.8	869.6

	LT SLATE GRAY	General Motors	13
1554	TINTING WHITE	362.6	725.2
1559	YELLOW OXIDE	396.2	792.5
1501	LANDAU BLACK	423.0	846.1
1550	RED OXIDE	432.7	865.5

	DK AQUA MET	General Motors	41T
1556	FAST GREEN	158.7	317.5
1553	FAST BLUE	311.6	623.2
1508	SILVER	372.4	744.8
1501	LANDAU BLACK	404.1	808.3

	OYSTER WHITE	General Motors	12
1554	TINTING WHITE	398.9	797.8
1559	YELLOW OXIDE	426.5	852.9
1501	LANDAU BLACK	432.3	864.5
1550	RED OXIDE	435.2	870.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 8

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

1677	VERY DK YELLOW	General Motors	50
1552	FAST RED	138.7	277.4
1554	TINTING WHITE	259.9	519.8
1551	INDO YELLOW	369.1	738.2
1556	FAST GREEN	413.2	826.3

1684	LT BLUE MET	General Motors	90T
1508	SILVER	276.2	552.3
1554	TINTING WHITE	368.8	737.6
1553	FAST BLUE	393.2	786.4
1501	LANDAU BLACK	409.6	819.3
1552	FAST RED	414.3	828.6

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1678	DK GOLD	General Motors	8050
1559	YELLOW OXIDE	271.4	542.8
1554	TINTING WHITE	331.3	662.5
1501	LANDAU BLACK	376.6	753.2
1550	RED OXIDE	415.6	831.3

1685	TAN MET	General Motors	91T
1508	SILVER	237.8	475.6
1552	FAST RED	327.0	654.0
1551	INDO YELLOW	370.5	741.0
1501	LANDAU BLACK	407.0	814.0

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1679	VERY DK CAMEL	General Motors	62
1559	YELLOW OXIDE	272.7	545.3
1550	RED OXIDE	350.4	700.7
1554	TINTING WHITE	391.9	783.8
1501	LANDAU BLACK	415.2	830.3

1686	CLARET MET	General Motors	92T
1552	FAST RED	342.8	685.5
1551	INDO YELLOW	372.3	744.6
1508	SILVER	392.9	785.8
1553	FAST BLUE	404.2	808.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1680	VERY DK GRAY	General Motors	12
1559	YELLOW OXIDE	182.6	365.2
1554	TINTING WHITE	320.0	639.9
1501	LANDAU BLACK	398.2	796.5
1550	RED OXIDE	419.1	838.3

1687	MED SILVER GRAY	General Motors	94T
1508	SILVER	206.4	412.9
1501	LANDAU BLACK	344.5	688.9
1553	FAST BLUE	375.3	750.7
1552	FAST RED	399.5	799.0
1554	TINTING WHITE	407.3	814.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1681	DK SADDLE	General Motors	7044
1559	YELLOW OXIDE	258.1	516.2
1550	RED OXIDE	359.5	719.0
1554	TINTING WHITE	403.9	807.9
1501	LANDAU BLACK	415.6	831.3

1688	CAMEL TAN	General Motors	63T
1508	SILVER	173.1	346.2
1551	INDO YELLOW	287.8	575.5
1552	FAST RED	401.5	802.9
1501	LANDAU BLACK	406.0	812.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1682	DK BLUE MET	General Motors	29T
1553	FAST BLUE	227.9	455.8
1501	LANDAU BLACK	349.5	699.0
1508	SILVER	404.1	808.3

1689	LT BLUE MET	General Motors	21T
1508	SILVER	164.4	328.7
1554	TINTING WHITE	285.9	571.7
1553	FAST BLUE	359.1	718.2
1501	LANDAU BLACK	414.7	829.4
1556	FAST GREEN	415.1	830.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1683	PASTEL GREEN	General Motors	41T
1554	TINTING WHITE	429.9	859.8
1551	INDO YELLOW	433.3	866.6
1553	FAST BLUE	436.7	873.4

1690	DK GREEN MET	General Motors	44T
1501	LANDAU BLACK	137.8	275.5
1551	INDO YELLOW	261.9	523.8
1508	SILVER	370.2	740.4
1556	FAST GREEN	405.7	811.5

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 9

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

1691	BROWN MET	General Motors	67T
1552	FAST RED	216.5	433.0
1551	INDO YELLOW	285.4	570.8
1553	FAST BLUE	349.9	699.8
1508	SILVER	404.4	808.8

1698	DK CLARET	General Motors	79
1552	FAST RED	302.4	604.8
1559	YELLOW OXIDE	350.7	701.5
1501	LANDAU BLACK	397.1	794.2
1554	TINTING WHITE	405.7	811.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1692	DK CLARET MET	General Motors	76T
1552	FAST RED	288.1	576.3
1553	FAST BLUE	340.4	680.8
1551	INDO YELLOW	377.9	755.8
1508	SILVER	404.0	808.1

1699	DK YELLOW	General Motors	50
1559	YELLOW OXIDE	262.5	525.0
1554	TINTING WHITE	323.0	646.0
1501	LANDAU BLACK	377.3	754.7
1550	RED OXIDE	415.5	831.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1693	DK GRAY	General Motors	14
1554	TINTING WHITE	262.8	525.5
1501	LANDAU BLACK	413.6	827.3
1551	INDO YELLOW	424.5	848.9

1700	DK BROWN MET	Ford Motor	J
1552	FAST RED	242.3	484.7
1551	INDO YELLOW	344.2	688.4
1501	LANDAU BLACK	379.3	758.7
1508	SILVER	404.4	808.8

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

1694	DK BLUE	General Motors	26
1501	LANDAU BLACK	180.7	361.4
1553	FAST BLUE	337.5	675.1
1554	TINTING WHITE	382.8	765.5
1550	RED OXIDE	407.8	815.7

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1700	DK BROWN MET	Ford Motor	T
1552	FAST RED	242.3	484.7
1551	INDO YELLOW	344.2	688.4
1501	LANDAU BLACK	379.3	758.7
1508	SILVER	404.4	808.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1695	BEIGE	General Motors	61
1554	TINTING WHITE	234.8	469.7
1559	YELLOW OXIDE	369.3	738.5
1550	RED OXIDE	409.3	818.5
1501	LANDAU BLACK	425.9	851.8

1701	RUSSET	Ford Motor	D
1552	FAST RED	348.2	696.4
1551	INDO YELLOW	375.4	750.9
1508	SILVER	397.7	795.3
1553	FAST BLUE	404.2	808.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1696	DK BEIGE	General Motors	61
1559	YELLOW OXIDE	209.3	418.6
1550	RED OXIDE	294.2	588.4
1554	TINTING WHITE	368.7	737.4
1501	LANDAU BLACK	416.6	833.2

1702	LT CHAMPAGNE	Ford Motor	6
1554	TINTING WHITE	251.8	503.5
1559	YELLOW OXIDE	390.0	780.0
1550	RED OXIDE	414.7	829.4
1501	LANDAU BLACK	427.0	854.1

1697	DK BROWN	General Motors	68
1559	YELLOW OXIDE	155.1	310.3
1501	LANDAU BLACK	283.5	567.0
1550	RED OXIDE	409.4	818.7
1554	TINTING WHITE	411.0	821.9

1703	MIDNIGHT JADE M	Ford Motor	4
1556	FAST GREEN	209.1	418.2
1501	LANDAU BLACK	313.9	627.8
1559	YELLOW OXIDE	384.8	769.7
1554	TINTING WHITE	407.6	815.3

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 10

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
1705	DK CHAMPAGNE M	Ford Motor		6	1713	DK JADE GREEN	Ford Motor	R
1552	FAST RED	154.6	309.1		1553	FAST BLUE	201.9	403.8
1501	LANDAU BLACK	269.6	539.2		1551	INDO YELLOW	309.2	618.5
1551	INDO YELLOW	360.9	721.8		1508	SILVER	367.2	734.4
1508	SILVER	394.9	789.8		1554	TINTING WHITE	391.3	782.6
1554	TINTING WHITE	405.6	811.1		1501	LANDAU BLACK	403.8	807.5
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				
1706	JUBILEE GOLD	Ford Motor		B	1714	TAN	Ford Motor	U
1559	YELLOW OXIDE	259.2	518.3		1559	YELLOW OXIDE	248.3	496.7
1554	TINTING WHITE	397.4	794.8		1554	TINTING WHITE	371.3	742.5
1501	LANDAU BLACK	413.7	827.5		1550	RED OXIDE	412.8	825.6
1550	RED OXIDE	420.5	840.9		1501	LANDAU BLACK	419.9	839.8
1708	LT CHAMPAGNE	Ford Motor		V	1715	DK CHAMOIS	Ford Motor	T
1554	TINTING WHITE	263.7	527.4		1559	YELLOW OXIDE	324.7	649.4
1559	YELLOW OXIDE	392.9	785.8		1550	RED OXIDE	396.7	793.4
1550	RED OXIDE	414.6	829.2		1554	TINTING WHITE	410.4	820.8
1501	LANDAU BLACK	427.6	855.2		1501	LANDAU BLACK	414.1	828.2
1709	PASTEL CAMEL	Ford Motor		Y	1716	ORANGE	Ford Motor	N
1554	TINTING WHITE	285.9	571.7		1551	INDO YELLOW	259.6	519.3
1559	YELLOW OXIDE	423.4	846.8		1552	FAST RED	334.4	668.8
1550	RED OXIDE	426.8	853.7		1554	TINTING WHITE	408.8	817.6
1501	LANDAU BLACK	429.0	858.0		1501	LANDAU BLACK	409.6	819.3
1710	MED CAMEL	Ford Motor		Y	1717	CHAMOIS	Ford Motor	T
1554	TINTING WHITE	242.5	485.1		1559	YELLOW OXIDE	278.9	557.8
1551	INDO YELLOW	358.7	717.4		1554	TINTING WHITE	376.0	752.0
1552	FAST RED	414.1	828.2		1550	RED OXIDE	417.1	834.3
1556	FAST GREEN	422.6	845.1		1501	LANDAU BLACK	418.7	837.3
1711	PASTEL DOVE GRA	Ford Motor		S	1718	MED BLUE MET	Ford Motor	B
1554	TINTING WHITE	370.4	740.8		1553	FAST BLUE	203.1	406.2
1559	YELLOW OXIDE	400.7	801.4		1501	LANDAU BLACK	293.9	587.9
1501	LANDAU BLACK	423.2	846.5		1508	SILVER	376.4	752.8
1550	RED OXIDE	433.2	866.4		1554	TINTING WHITE	396.7	793.4
					1556	FAST GREEN	405.8	811.7
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				
1712	MED EMBER	General Motors		T	1719	SADDLE	Ford Motor	Z
1559	YELLOW OXIDE	331.9	663.9		1552	FAST RED	207.4	414.8
1552	FAST RED	411.4	822.7		1551	INDO YELLOW	304.9	609.7
					1508	SILVER	356.8	713.6
					1556	FAST GREEN	383.8	767.6
					1554	TINTING WHITE	406.3	812.6
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 11

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

1720	RUSSET	Ford Motor	E
1552	FAST RED	249.8	499.5
1551	INDO YELLOW	333.0	666.0
1508	SILVER	374.6	749.2
1554	TINTING WHITE	405.8	811.7
1501	LANDAU BLACK	406.9	813.8

1729	SILVER BLUE MET	Ford Motor	P
1508	SILVER	308.8	617.7
1553	FAST BLUE	364.8	729.6
1501	LANDAU BLACK	387.0	774.1
1554	TINTING WHITE	401.7	803.3
1552	FAST RED	408.7	817.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1722	AQUA	Ford Motor	K
1554	TINTING WHITE	263.6	527.3
1556	FAST GREEN	337.0	673.9
1553	FAST BLUE	386.7	773.5
1501	LANDAU BLACK	424.0	848.0

1730	LT GOLD	Ford Motor	Y
1559	YELLOW OXIDE	330.1	660.3
1554	TINTING WHITE	403.4	806.7
1552	FAST RED	411.7	823.5
1553	FAST BLUE	417.0	833.9

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

1723	BRIGHT RED	Ford Motor	D
1552	FAST RED	328.2	656.5
1554	TINTING WHITE	370.0	740.1
1551	INDO YELLOW	407.3	814.5

1731	DK CORDOVAN	Ford Motor	F
1552	FAST RED	273.5	547.0
1559	YELLOW OXIDE	392.4	784.7
1553	FAST BLUE	405.7	811.5
1554	TINTING WHITE	406.6	813.2

1725	LT JADE GREEN	Ford Motor	R
1508	SILVER	281.1	562.2
1556	FAST GREEN	349.2	698.4
1501	LANDAU BLACK	373.3	746.5
1551	INDO YELLOW	393.6	787.2
1554	TINTING WHITE	408.4	816.8

1732	DK RED MET	Ford Motor	D
1552	FAST RED	360.8	721.6
1551	INDO YELLOW	378.7	757.3
1508	SILVER	395.7	791.4
1553	FAST BLUE	401.7	803.3
1554	TINTING WHITE	404.4	808.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1726	CREAM	Ford Motor	V
1554	TINTING WHITE	332.6	665.2
1559	YELLOW OXIDE	426.6	853.3
1550	RED OXIDE	430.1	860.1
1553	FAST BLUE	431.5	863.0

1733	RED	Ford Motor	D
1552	FAST RED	351.4	702.8
1550	RED OXIDE	394.7	789.5
1553	FAST BLUE	402.0	804.1
1554	TINTING WHITE	405.3	810.5

1727	MED GREEN	Ford Motor	G
1551	INDO YELLOW	187.2	374.5
1501	LANDAU BLACK	279.7	559.4
1508	SILVER	368.9	737.8
1556	FAST GREEN	405.4	810.7

1734	TANGERINE	Ford Motor	J
1551	INDO YELLOW	237.0	474.1
1552	FAST RED	333.3	666.5
1554	TINTING WHITE	409.9	819.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1728	LT GREEN	Ford Motor	G
1559	YELLOW OXIDE	289.4	578.7
1554	TINTING WHITE	395.5	791.0
1556	FAST GREEN	408.0	816.1
1501	LANDAU BLACK	418.5	837.0

1735	MED BLUE MET	Ford Motor	B
1553	FAST BLUE	192.8	385.5
1508	SILVER	381.9	763.8
1552	FAST RED	405.5	810.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 12

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
1736	MED BLUE	Ford Motor		B	1743	AQUA	Ford Motor	L
1553	FAST BLUE	287.8	575.5		1554	TINTING WHITE	231.0	462.1
1554	TINTING WHITE	350.6	701.3		1556	FAST GREEN	312.8	625.7
1501	LANDAU BLACK	407.8	815.7		1553	FAST BLUE	375.1	750.1
					1501	LANDAU BLACK	421.5	843.0
1737	EMBER	Ford Motor		C	1744	SILVER BLUE MET	Ford Motor	S
1552	FAST RED	168.3	336.7		1508	SILVER	208.4	416.9
1551	INDO YELLOW	294.6	589.2		1553	FAST BLUE	331.7	663.5
1508	SILVER	405.3	810.5		1501	LANDAU BLACK	364.0	728.1
					1554	TINTING WHITE	386.1	772.2
					1551	INDO YELLOW	407.7	815.5
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR					MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR			
1738	DK RED	Ford Motor		D	1745	LT GREEN MET	Ford Motor	G
1552	FAST RED	342.8	685.5		1508	SILVER	188.8	377.5
1551	INDO YELLOW	372.3	744.6		1551	INDO YELLOW	334.0	668.0
1508	SILVER	392.9	785.8		1501	LANDAU BLACK	388.6	777.3
1553	FAST BLUE	404.2	808.5		1556	FAST GREEN	406.4	812.8
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR					MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR			
1739	BRIGHT RED	Ford Motor		D	1746	DK GREEN MET	Ford Motor	G
1552	FAST RED	312.2	624.3		1551	INDO YELLOW	158.4	316.7
1551	INDO YELLOW	382.4	764.8		1501	LANDAU BLACK	297.3	594.5
1554	TINTING WHITE	405.7	811.5		1508	SILVER	370.6	741.2
					1556	FAST GREEN	405.2	810.4
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR					MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR			
1740	DOVE GRAY	Ford Motor		E	1747	EMERALD MET	Ford Motor	Q
1554	TINTING WHITE	336.7	673.4		1553	FAST BLUE	175.5	350.9
1501	LANDAU BLACK	379.7	759.4		1508	SILVER	301.2	602.3
1559	YELLOW OXIDE	417.6	835.2		1551	INDO YELLOW	404.7	809.4
1550	RED OXIDE	430.9	861.8					
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR					MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR			
1741	CORDOVAN	Ford Motor		F	1748	JADE	Ford Motor	Q
1552	FAST RED	306.5	612.9		1553	FAST BLUE	234.7	469.3
1551	INDO YELLOW	351.7	703.4		1551	INDO YELLOW	352.0	704.0
1501	LANDAU BLACK	385.1	770.3		1508	SILVER	403.7	807.3
1508	SILVER	404.2	808.5					
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR					MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR			
1742	ROSE MET	Ford Motor		H	1749	GOLD MET	Ford Motor	Q
1508	SILVER	209.9	419.7		1508	SILVER	170.9	341.8
1554	TINTING WHITE	336.5	673.0		1551	INDO YELLOW	305.1	610.3
1552	FAST RED	390.1	780.1		1552	FAST RED	400.7	801.4
1551	INDO YELLOW	409.3	818.5		1501	LANDAU BLACK	406.0	812.1
1501	LANDAU BLACK	416.1	832.2					
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR					MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR			

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 13

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
1750	BROWN	Ford Motor		T	1757	GOLD	Ford Motor	Y
1501	LANDAU BLACK	181.1	362.1		1559	YELLOW OXIDE	275.4	550.8
1559	YELLOW OXIDE	315.3	630.6		1554	TINTING WHITE	399.7	799.3
1550	RED OXIDE	399.8	799.5		1550	RED OXIDE	410.1	820.2
1554	TINTING WHITE	410.4	820.8		1501	LANDAU BLACK	419.8	839.6
1751	CINNAMON	Ford Motor		U	1758	GOLD MET	Ford Motor	Y
1552	FAST RED	150.1	300.2		1508	SILVER	155.8	311.6
1508	SILVER	279.2	558.4		1551	INDO YELLOW	307.5	615.0
1551	INDO YELLOW	405.6	811.1		1552	FAST RED	405.8	811.7
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				
1752	CHAMOIS	Ford Motor		U	1759	GOLD	Ford Motor	Y
1559	YELLOW OXIDE	243.5	487.0		1559	YELLOW OXIDE	275.4	550.8
1554	TINTING WHITE	378.5	757.0		1554	TINTING WHITE	399.7	799.3
1550	RED OXIDE	419.9	839.8		1550	RED OXIDE	410.1	820.2
1501	LANDAU BLACK	420.8	841.5		1501	LANDAU BLACK	419.8	839.6
1753	LT TAN	Ford Motor		U	1760	DIAMOND BLUE	Ford Motor	Z
1559	YELLOW OXIDE	240.0	479.9		1508	SILVER	367.5	734.9
1554	TINTING WHITE	376.6	753.2		1553	FAST BLUE	401.5	802.9
1550	RED OXIDE	411.9	823.8		1551	INDO YELLOW	408.1	816.2
1501	LANDAU BLACK	420.8	841.5					
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				
1754	CREAM	Ford Motor		V	1761	DK SADDLE MET	Ford Motor	Z
1554	TINTING WHITE	377.7	755.4		1552	FAST RED	214.1	428.3
1551	INDO YELLOW	414.7	829.4		1501	LANDAU BLACK	279.9	559.7
1552	FAST RED	428.9	857.9		1551	INDO YELLOW	339.0	677.9
1556	FAST GREEN	432.8	865.6		1508	SILVER	397.6	795.2
					1554	TINTING WHITE	405.5	810.9
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				
1755	ANTIQUÉ CREAM	Ford Motor		V	1762	MED BLUE MET	Ford Motor	B
1554	TINTING WHITE	283.0	566.0		1508	SILVER	218.4	436.8
1559	YELLOW OXIDE	426.2	852.3		1553	FAST BLUE	330.9	661.8
1552	FAST RED	427.9	855.8		1552	FAST RED	375.3	750.5
1553	FAST BLUE	428.7	857.5		1554	TINTING WHITE	396.0	791.9
					1551	INDO YELLOW	407.6	815.3
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				
1756	WHITE	Ford Motor		W	1763	LT BLUE	Ford Motor	2
1554	TINTING WHITE	272.8	545.7		1554	TINTING WHITE	399.8	799.5
1302	LOW LUSTER CLEAR	414.2	828.4		1553	FAST BLUE	415.0	829.9
1559	YELLOW OXIDE	422.7	845.3		1501	LANDAU BLACK	429.3	858.6
1501	LANDAU BLACK	423.5	847.0		1556	FAST GREEN	434.5	869.1
1550	RED OXIDE	424.1	848.2					

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 14

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

1764	MIDNIGHT BLUE M	Ford Motor	Q
1553	FAST BLUE	202.5	405.1
1501	LANDAU BLACK	359.5	719.0
1554	TINTING WHITE	383.8	767.6
1556	FAST GREEN	405.5	810.9

1771	MED RED	Ford Motor	D
1552	FAST RED	351.6	703.2
1550	RED OXIDE	381.0	762.1
1501	LANDAU BLACK	395.3	790.6
1554	TINTING WHITE	405.6	811.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1765	DK RED	Ford Motor	D
1552	FAST RED	342.8	685.5
1551	INDO YELLOW	372.3	744.6
1508	SILVER	392.9	785.8
1553	FAST BLUE	404.2	808.5

1773	MED PINE GREEN	Ford Motor	R
1554	TINTING WHITE	195.8	391.6
1501	LANDAU BLACK	276.3	552.5
1551	INDO YELLOW	355.2	710.4
1556	FAST GREEN	419.2	838.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1766	MAROON	Ford Motor	9
1552	FAST RED	380.3	760.6
1501	LANDAU BLACK	397.2	794.4
1554	TINTING WHITE	404.6	809.2

1774	MED VAQUERO	Ford Motor	Z
1552	FAST RED	240.3	480.5
1559	YELLOW OXIDE	395.4	790.8
1501	LANDAU BLACK	405.9	811.9
1554	TINTING WHITE	407.6	815.1

1767	DK VAQUERO	Ford Motor	Z
1552	FAST RED	297.8	595.7
1551	INDO YELLOW	355.7	711.4
1508	SILVER	385.4	770.8
1501	LANDAU BLACK	404.3	808.6

1775	DK BLUE MET	Ford Motor	B
1553	FAST BLUE	189.6	379.2
1501	LANDAU BLACK	305.6	611.2
1508	SILVER	403.0	806.0
1556	FAST GREEN	404.7	809.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1768	PINE GREEN	Ford Motor	M
1553	FAST BLUE	166.3	332.5
1551	INDO YELLOW	314.7	629.5
1508	SILVER	344.8	689.5
1554	TINTING WHITE	374.8	749.6
1501	LANDAU BLACK	404.2	808.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1776	BITTERSWEET	Ford Motor	C
1552	FAST RED	250.8	501.6
1551	INDO YELLOW	323.5	647.0
1508	SILVER	387.3	774.6
1554	TINTING WHITE	397.7	795.3
1501	LANDAU BLACK	405.5	810.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1769	CREAM	Ford Motor	V
1554	TINTING WHITE	321.0	642.0
1559	YELLOW OXIDE	426.6	853.1
1552	FAST RED	428.7	857.5
1556	FAST GREEN	430.9	861.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1777	MED RED MET	Ford Motor	D
1552	FAST RED	340.9	681.7
1508	SILVER	369.9	739.9
1551	INDO YELLOW	392.5	785.1
1553	FAST BLUE	404.2	808.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1770	BLUE	Ford Motor	B
1554	TINTING WHITE	214.3	428.6
1501	LANDAU BLACK	317.5	635.0
1553	FAST BLUE	404.2	808.5
1559	YELLOW OXIDE	420.7	841.3

1778	CORDOVAN BROW	Ford Motor	F
1552	FAST RED	235.6	471.2
1501	LANDAU BLACK	299.5	599.1
1508	SILVER	353.4	706.8
1551	INDO YELLOW	404.8	809.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 15

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

1779	DK PINE MET	Ford Motor		M
1556	FAST GREEN	185.3	370.7	
1501	LANDAU BLACK	351.2	702.4	
1508	SILVER	405.2	810.4	

1791	BLACK MET	Ford Motor		A
1501	LANDAU BLACK	400.3	800.7	
1508	SILVER	402.8	805.6	
1554	TINTING WHITE	405.3	810.5	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1783	MED RED	Ford Motor		D
1552	FAST RED	344.9	689.9	
1551	INDO YELLOW	388.7	777.5	
1554	TINTING WHITE	402.7	805.4	
1553	FAST BLUE	405.1	810.2	

1792	MED FAWN	Ford Motor		L
1559	YELLOW OXIDE	204.6	409.3	
1554	TINTING WHITE	314.3	628.5	
1550	RED OXIDE	387.9	775.8	
1501	LANDAU BLACK	418.9	837.7	

1784	BITTERSWEET	Ford Motor		E
1559	YELLOW OXIDE	245.5	491.0	
1552	FAST RED	401.5	802.9	
1554	TINTING WHITE	410.1	820.2	

1793	SPRUCE	Ford Motor		R
1554	TINTING WHITE	167.6	335.2	
1559	YELLOW OXIDE	271.7	543.4	
1556	FAST GREEN	351.3	702.6	
1501	LANDAU BLACK	419.3	838.7	

1787	MED PINE GREEN	Ford Motor		M
1554	TINTING WHITE	223.9	447.8	
1501	LANDAU BLACK	302.0	604.0	
1551	INDO YELLOW	364.8	729.6	
1556	FAST GREEN	421.3	842.7	

1794	MED GRAY MET	Ford Motor		S
1508	SILVER	206.0	411.9	
1501	LANDAU BLACK	343.4	686.9	
1553	FAST BLUE	379.2	758.5	
1552	FAST RED	403.2	806.4	
1554	TINTING WHITE	407.0	814.0	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1788	CARMEL	Ford Motor		T
1559	YELLOW OXIDE	224.9	449.7	
1302	LOW LUSTER CLEAR	361.4	722.8	
1550	RED OXIDE	396.4	792.9	
1554	TINTING WHITE	407.1	814.2	
1501	LANDAU BLACK	409.8	819.7	

1795	MED PEWTER	Ford Motor		H
1554	TINTING WHITE	201.7	403.4	
1559	YELLOW OXIDE	347.9	695.8	
1501	LANDAU BLACK	398.1	796.1	
1550	RED OXIDE	423.4	846.8	

1789	LT GOLD	General Motors		Y
1559	YELLOW OXIDE	286.0	571.9	
1554	TINTING WHITE	411.4	822.9	
1501	LANDAU BLACK	417.8	835.6	
1550	RED OXIDE	419.9	839.8	

1796	NUTMEG	Ford Motor		T
1551	INDO YELLOW	234.5	468.9	
1552	FAST RED	360.6	721.2	
1554	TINTING WHITE	392.3	784.5	
1501	LANDAU BLACK	406.5	813.0	

1790	LT PEWTER	Ford Motor		H
1554	TINTING WHITE	299.7	599.5	
1559	YELLOW OXIDE	392.4	784.9	
1501	LANDAU BLACK	413.7	827.5	
1550	RED OXIDE	429.5	859.0	

1797	LT FAWN	Ford Motor		U
1554	TINTING WHITE	338.5	677.0	
1559	YELLOW OXIDE	407.6	815.3	
1550	RED OXIDE	426.6	853.3	
1501	LANDAU BLACK	431.9	863.7	

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 16

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

1798	LT SAND	Ford Motor	Y
1554	TINTING WHITE	271.4	542.8
1559	YELLOW OXIDE	416.1	832.2
1550	RED OXIDE	422.6	845.1
1501	LANDAU BLACK	428.2	856.3

1806	MED GREEN MET	Chrysler Motors	F6
1508	SILVER	203.7	407.4
1551	INDO YELLOW	300.9	601.7
1553	FAST BLUE	378.5	757.0
1501	LANDAU BLACK	406.2	812.4

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

1799	MED SAND	Ford Motor	Y
1559	YELLOW OXIDE	278.3	556.5
1554	TINTING WHITE	362.5	725.0
1550	RED OXIDE	398.2	796.5
1501	LANDAU BLACK	417.5	835.1

1807	LT GOLD	Chrysler Motors	Y3
1554	TINTING WHITE	228.0	456.0
1551	INDO YELLOW	332.4	664.8
1552	FAST RED	404.8	809.6
1556	FAST GREEN	421.4	842.8

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

1801	DK BLUE	Chrysler Motors	B6
1553	FAST BLUE	173.0	346.0
1554	TINTING WHITE	279.6	559.2
1501	LANDAU BLACK	361.5	723.0
1556	FAST GREEN	409.4	818.7

1808	DK CHESTNUT	Chrysler Motors	T7
1559	YELLOW OXIDE	224.2	448.4
1550	RED OXIDE	360.0	719.9
1501	LANDAU BLACK	409.0	818.0
1554	TINTING WHITE	412.8	825.6

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

1802	DK RED	Chrysler Motors	E7
1550	RED OXIDE	280.8	561.6
1553	FAST BLUE	408.1	816.2
1554	TINTING WHITE	410.6	821.2

1809	CARMEL	Chrysler Motors	U5
1559	YELLOW OXIDE	277.8	555.6
1550	RED OXIDE	359.4	718.8
1554	TINTING WHITE	403.6	807.1
1501	LANDAU BLACK	415.6	831.3

1803	LT PARCHMENT	Chrysler Motors	L3
1554	TINTING WHITE	323.0	646.0
1552	FAST RED	379.0	757.9
1551	INDO YELLOW	415.1	830.1
1556	FAST GREEN	428.7	857.5

1810	MED GREEN MET	Chrysler Motors	MF7
1551	INDO YELLOW	137.6	275.1
1556	FAST GREEN	270.6	541.1
1508	SILVER	348.7	697.3
1501	LANDAU BLACK	405.2	810.4

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

1804	WHITE	Chrysler Motors	GW1
1554	TINTING WHITE	410.8	821.6
1559	YELLOW OXIDE	428.3	856.5
1550	RED OXIDE	433.7	867.4
1556	FAST GREEN	435.9	871.7

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

1811	MED BLUE	Chrysler Motors	MB9
1501	LANDAU BLACK	152.2	304.4
1553	FAST BLUE	287.5	574.9
1554	TINTING WHITE	410.8	821.6
1552	FAST RED	413.3	826.5

1805	DK GREEN MET	Chrysler Motors	G6
1553	FAST BLUE	183.2	366.3
1551	INDO YELLOW	325.6	651.1
1508	SILVER	381.5	763.0
1501	LANDAU BLACK	403.9	807.9

1812	CHESTNUT	Chrysler Motors	KT7
1559	YELLOW OXIDE	158.0	316.0
1550	RED OXIDE	307.8	615.6
1501	LANDAU BLACK	411.4	822.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 17

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

1813	MED CARMEL MET	Chrysler Motors	MU6
1551	INDO YELLOW	158.9	317.9
1552	FAST RED	313.9	627.8
1508	SILVER	360.4	720.9
1554	TINTING WHITE	387.0	774.1
1501	LANDAU BLACK	406.6	813.2

1820	YELLOW	Chrysler Motors	RY3
1554	TINTING WHITE	303.0	605.9
1559	YELLOW OXIDE	427.3	854.6
1550	RED OXIDE	429.3	858.6
1553	FAST BLUE	430.0	859.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1814	GOLD	Chrysler Motors	KY4
1554	TINTING WHITE	188.3	376.6
1551	INDO YELLOW	307.5	615.0
1552	FAST RED	396.6	793.3
1556	FAST GREEN	418.4	836.8

1821	MED BLUE MET	Chrysler Motors	B
1553	FAST BLUE	179.1	358.2
1508	SILVER	269.0	538.1
1552	FAST RED	334.0	668.0
1501	LANDAU BLACK	396.4	792.9
1554	TINTING WHITE	405.1	810.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1815	BLUE MET	Chrysler Motors	PB1
1553	FAST BLUE	146.3	292.6
1508	SILVER	286.3	572.7
1552	FAST RED	385.8	771.6
1556	FAST GREEN	405.1	810.2

1822	DK BLUE	Chrysler Motors	C
1553	FAST BLUE	226.5	453.0
1501	LANDAU BLACK	360.9	721.8
1552	FAST RED	392.0	783.9
1554	TINTING WHITE	404.4	808.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1816	LT GRAY	Chrysler Motors	A3
1554	TINTING WHITE	342.2	684.4
1559	YELLOW OXIDE	392.6	785.3
1501	LANDAU BLACK	423.7	847.4
1550	RED OXIDE	431.5	863.0

1823	DK GREEN MET	Chrysler Motors	F
1556	FAST GREEN	215.9	431.9
1501	LANDAU BLACK	333.5	666.9
1508	SILVER	405.2	810.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1817	SILVER MET	Chrysler Motors	RA2
1508	SILVER	388.5	776.9
1501	LANDAU BLACK	408.7	817.4

1824	LT GREEN MET	Chrysler Motors	G
1508	SILVER	241.6	483.2
1553	FAST BLUE	335.0	669.9
1551	INDO YELLOW	382.5	764.9
1556	FAST GREEN	405.7	811.3

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1818	GREEN MET	Chrysler Motors	RF5
1508	SILVER	155.6	311.2
1553	FAST BLUE	274.0	548.0
1551	INDO YELLOW	388.6	777.1
1501	LANDAU BLACK	405.5	810.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1825	CHAMPAGNE	Chrysler Motors	G
1554	TINTING WHITE	383.1	766.3
1552	FAST RED	405.7	811.5
1551	INDO YELLOW	427.9	855.8
1556	FAST GREEN	433.2	866.4

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

1819	RED (PRINT)	Chrysler Motors	RR7
1552	FAST RED	225.5	451.1
1550	RED OXIDE	399.4	798.8
1501	LANDAU BLACK	407.1	814.2
1554	TINTING WHITE	408.4	816.8

1826	LT CREAM	Chrysler Motors	L
1554	TINTING WHITE	403.9	807.9
1559	YELLOW OXIDE	433.5	867.0
1550	RED OXIDE	434.5	869.1
1556	FAST GREEN	435.5	871.0

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 18

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

1827	DK RED	Chrysler Motors	R
1552	FAST RED	336.3	672.6
1551	INDO YELLOW	383.3	766.7
1554	TINTING WHITE	396.0	791.9
1501	LANDAU BLACK	405.0	810.0

1834	RED	Chrysler Motors	R4
1552	FAST RED	251.6	503.1
1559	YELLOW OXIDE	404.4	808.8
1554	TINTING WHITE	406.9	813.8
1501	LANDAU BLACK	407.6	815.1

1828	GRAY	Chrysler Motors	S
1554	TINTING WHITE	374.4	748.8
1559	YELLOW OXIDE	404.1	808.3
1501	LANDAU BLACK	426.9	853.9
1550	RED OXIDE	433.4	866.8

1835	CASHMERE	Chrysler Motors	T3
1559	YELLOW OXIDE	231.5	463.0
1554	TINTING WHITE	389.6	779.2
1550	RED OXIDE	415.0	829.9
1501	LANDAU BLACK	421.8	843.6

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

1829	PALE GRAY	Chrysler Motors	D
1554	TINTING WHITE	416.6	833.2
1559	YELLOW OXIDE	430.5	861.1
1501	LANDAU BLACK	435.3	870.6
1550	RED OXIDE	436.1	872.3

1836	LT BLUE MET	Chrysler Motors	B
1508	SILVER	294.3	588.6
1553	FAST BLUE	340.6	681.2
1501	LANDAU BLACK	385.2	770.5
1554	TINTING WHITE	397.3	794.6
1552	FAST RED	408.3	816.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1830	TAN MET	Chrysler Motors	U
1551	INDO YELLOW	243.3	486.6
1552	FAST RED	357.0	714.0
1508	SILVER	391.8	783.6
1501	LANDAU BLACK	404.4	808.8

1837	HEATHER	Chrysler Motors	D
1554	TINTING WHITE	352.5	705.1
1559	YELLOW OXIDE	402.7	805.4
1550	RED OXIDE	421.7	843.4
1501	LANDAU BLACK	432.5	865.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1831	CREAM	Chrysler Motors	Y
1554	TINTING WHITE	290.6	581.2
1559	YELLOW OXIDE	420.7	841.3
1550	RED OXIDE	426.3	852.5
1501	LANDAU BLACK	429.3	858.6

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

1838	DK GREEN MET	Chrysler Motors	F
1553	FAST BLUE	179.0	358.0
1501	LANDAU BLACK	270.8	541.7
1551	INDO YELLOW	356.6	713.3
1508	SILVER	404.0	808.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1832	MIDNIGHT BLUE	Chrysler Motors	C8
1553	FAST BLUE	252.9	505.8
1501	LANDAU BLACK	377.8	755.6
1554	TINTING WHITE	405.5	810.9

1839	CASHMERE	Chrysler Motors	K
1559	YELLOW OXIDE	224.2	448.4
1554	TINTING WHITE	390.2	780.3
1550	RED OXIDE	416.6	833.2
1501	LANDAU BLACK	422.3	844.6

1833	TEAL GREEN	Chrysler Motors	G5
1554	TINTING WHITE	152.1	304.2
1556	FAST GREEN	254.0	508.1
1559	YELLOW OXIDE	351.8	703.6
1501	LANDAU BLACK	417.8	835.6

1840	MED RED MET	Chrysler Motors	R
1552	FAST RED	339.7	679.4
1508	SILVER	371.2	742.3
1551	INDO YELLOW	388.1	776.2
1553	FAST BLUE	401.4	802.8
1554	TINTING WHITE	404.4	808.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 19

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

1841	BLACK WALNUT M	Chrysler Motors	U
1501	LANDAU BLACK	389.7	779.4
1508	SILVER	405.2	810.4

1848	PALE HEATHER	Chrysler Motors	D1
1554	TINTING WHITE	400.8	801.6
1559	YELLOW OXIDE	425.9	851.8
1550	RED OXIDE	431.7	863.4
1501	LANDAU BLACK	435.3	870.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1842	BLUE	Chrysler Motors	B2
1554	TINTING WHITE	327.9	655.9
1501	LANDAU BLACK	400.8	801.6
1553	FAST BLUE	421.8	843.6
1551	INDO YELLOW	429.1	858.2

1849	DK CASHMERE ME	Chrysler Motors	T8
1552	FAST RED	194.7	389.3
1551	INDO YELLOW	296.2	592.4
1501	LANDAU BLACK	371.3	742.5
1508	SILVER	404.5	809.0
	REQ. BASE COAT 150		

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

1843	HEATHER	Chrysler Motors	D3
1554	TINTING WHITE	255.2	510.3
1559	YELLOW OXIDE	362.0	724.1
1550	RED OXIDE	399.1	798.2
1501	LANDAU BLACK	426.7	853.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1850	CREAM	Chrysler Motors	Y1
1554	TINTING WHITE	411.4	822.9
1559	YELLOW OXIDE	434.8	869.6
1556	FAST GREEN	435.5	871.0
1550	RED OXIDE	436.0	871.9

1844	BEIGE	Chrysler Motors	L3
1554	TINTING WHITE	379.8	759.6
1552	FAST RED	405.7	811.5
1551	INDO YELLOW	427.1	854.2
1556	FAST GREEN	432.9	865.8

1851	SOFT YELLOW	Chrysler Motors	Y2
1554	TINTING WHITE	332.1	664.2
1559	YELLOW OXIDE	430.3	860.5
1556	FAST GREEN	431.6	863.2

1845	RED	Chrysler Motors	M6
1552	FAST RED	237.6	475.2
1550	RED OXIDE	351.1	702.2
1554	TINTING WHITE	385.4	770.8
1501	LANDAU BLACK	409.5	819.1

1852	DK AUBERGINE	Chrysler Motors	H9
1501	LANDAU BLACK	199.8	399.6
1550	RED OXIDE	340.9	681.7
1559	YELLOW OXIDE	397.5	795.0
1554	TINTING WHITE	410.2	820.4

1846	SEA SPRAY GREEN	Chrysler Motors	F5
1554	TINTING WHITE	231.9	463.8
1559	YELLOW OXIDE	369.6	739.3
1501	LANDAU BLACK	406.8	813.6
1556	FAST GREEN	424.9	849.9

1853	DK SILVER	Chrysler Motors	A7
1554	TINTING WHITE	248.9	497.8
1501	LANDAU BLACK	368.3	736.6
1551	INDO YELLOW	398.2	796.5
1552	FAST RED	423.3	846.6

1847	LT TAN	Chrysler Motors	T1
1554	TINTING WHITE	304.2	608.4
1559	YELLOW OXIDE	422.2	844.4
1550	RED OXIDE	427.1	854.2
1501	LANDAU BLACK	429.9	859.8

1854	MED BLUE	Chrysler Motors	B2
1554	TINTING WHITE	255.1	510.2
1550	RED OXIDE	340.2	680.4
1553	FAST BLUE	387.9	775.8
1559	YELLOW OXIDE	426.2	852.3

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 20

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

1855	DK BLUE	Chrysler Motors	C8
1553	FAST BLUE	258.6	517.2
1501	LANDAU BLACK	377.2	754.3
1554	TINTING WHITE	405.5	810.9

1862	DK MAHOGANY ME	Chrysler Motors	H9
1552	FAST RED	296.3	592.6
1501	LANDAU BLACK	392.6	785.3
1508	SILVER	401.9	803.9
1554	TINTING WHITE	404.5	809.0

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1856	SEA SPRAY GREEN	Chrysler Motors	F5
1554	TINTING WHITE	312.1	624.2
1501	LANDAU BLACK	365.9	731.9
1551	INDO YELLOW	415.5	831.1
1556	FAST GREEN	428.0	856.0

1863	MED SPICE MET	Chrysler Motors	K7
1552	FAST RED	233.9	467.8
1551	INDO YELLOW	374.7	749.4
1501	LANDAU BLACK	396.6	793.3
1508	SILVER	404.2	808.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1857	MED RED	Chrysler Motors	M6
1552	FAST RED	246.1	492.1
1302	LOW LUSTER CLEAR	380.9	761.7
1550	RED OXIDE	393.1	786.2
1554	TINTING WHITE	401.1	802.2
1501	LANDAU BLACK	404.1	808.3

1864	MED RED	Chrysler Motors	M8
1552	FAST RED	389.0	778.1
1554	TINTING WHITE	395.4	790.8
1553	FAST BLUE	400.0	799.9
1501	LANDAU BLACK	404.5	809.0

1858	LT TAN	Chrysler Motors	T4
1559	YELLOW OXIDE	235.5	471.0
1554	TINTING WHITE	386.7	773.5
1550	RED OXIDE	414.8	829.5
1501	LANDAU BLACK	421.5	843.0

1865	MANILA CREAM	Chrysler Motors	T2
1554	TINTING WHITE	416.8	833.5
1551	INDO YELLOW	432.1	864.1
1552	FAST RED	435.4	870.8
1556	FAST GREEN	435.9	871.7

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

1859	WHITE	Chrysler Motors	W1
1554	TINTING WHITE	406.7	813.4
1559	YELLOW OXIDE	433.9	867.7
1501	LANDAU BLACK	435.6	871.2

1866	WHITE	Chrysler Motors	W3
1554	TINTING WHITE	422.0	844.0
1559	YELLOW OXIDE	434.2	868.5
1501	LANDAU BLACK	436.0	871.9
1550	RED OXIDE	436.4	872.9

1860	DK CHARCOAL ME	Chrysler Motors	A9
1501	LANDAU BLACK	209.4	418.8
1508	SILVER	367.2	734.4
1553	FAST BLUE	401.7	803.3
1552	FAST RED	406.3	812.6

1900	MED BLUE MET	American Moto	P32
1554	TINTING WHITE	192.8	385.5
1508	SILVER	293.0	586.0
1553	FAST BLUE	356.4	712.9
1552	FAST RED	399.1	798.2
1501	LANDAU BLACK	417.7	835.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1861	LT GREEN MET	Chrysler Motors	F2
1508	SILVER	344.9	689.9
1501	LANDAU BLACK	368.2	736.4
1551	INDO YELLOW	389.8	779.6
1556	FAST GREEN	408.1	816.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1901	DK BLUE	American Moto	
1553	FAST BLUE	295.0	590.0
1501	LANDAU BLACK	371.1	742.1
1554	TINTING WHITE	391.5	783.0
1552	FAST RED	404.5	809.0

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 21

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	YELLOW	American Moto	
1554	TINTING WHITE	335.5	671.1
1551	INDO YELLOW	411.5	823.1
1552	FAST RED	427.2	854.4
1556	FAST GREEN	429.6	859.2

	MED RUSSET MET	American Moto	
1552	FAST RED	295.3	590.5
1551	INDO YELLOW	346.5	692.9
1508	SILVER	395.8	791.5
1554	TINTING WHITE	401.4	802.8
1501	LANDAU BLACK	405.1	810.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	MED BROWN MET	American Moto	
1508	SILVER	102.8	205.6
1554	TINTING WHITE	195.8	391.6
1552	FAST RED	288.8	577.6
1551	INDO YELLOW	374.4	748.8
1501	LANDAU BLACK	412.5	825.0

	RUSSET	American Moto		
1552	FAST RED	249.3	498.6	79R1
1551	INDO YELLOW	338.2	676.4	
1554	TINTING WHITE	390.5	781.1	
1501	LANDAU BLACK	408.0	816.1	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	DK BROWN MET	American Moto	
1552	FAST RED	210.4	420.9
1501	LANDAU BLACK	308.6	617.1
1508	SILVER	355.1	710.2
1551	INDO YELLOW	396.2	792.3
1554	TINTING WHITE	405.6	811.1

	BLUE	American Moto		
1554	TINTING WHITE	239.1	478.2	79R2
1553	FAST BLUE	318.5	637.1	
1501	LANDAU BLACK	385.2	770.5	
1552	FAST RED	419.5	839.0	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	SILVER MET	American Moto	
1554	TINTING WHITE	364.4	728.8
1501	LANDAU BLACK	414.7	829.4
1551	INDO YELLOW	424.9	849.9
1552	FAST RED	432.0	863.9

	BROWN	American Moto		
1559	YELLOW OXIDE	196.8	393.7	80P1
1550	RED OXIDE	299.6	599.3	
1501	LANDAU BLACK	370.9	741.8	
1554	TINTING WHITE	414.4	828.8	

	DK RUSSET MET	American Moto	
1552	FAST RED	293.2	586.3
1501	LANDAU BLACK	331.3	662.5
1551	INDO YELLOW	367.6	735.1
1508	SILVER	393.9	787.7
1554	TINTING WHITE	405.4	810.7

	BEIGE	American Moto		
1554	TINTING WHITE	268.7	537.3	80P3
1559	YELLOW OXIDE	402.2	804.5	
1550	RED OXIDE	424.4	848.7	
1501	LANDAU BLACK	428.1	856.1	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	BEIGE	American Moto		
1554	TINTING WHITE	248.5	497.0	80P35
1559	YELLOW OXIDE	398.9	797.8	
1550	RED OXIDE	420.1	840.2	
1501	LANDAU BLACK	426.8	853.7	

	RED	American Moto		
1550	RED OXIDE	204.9	409.8	80P2
1552	FAST RED	362.0	723.9	
1554	TINTING WHITE	395.3	790.6	
1559	YELLOW OXIDE	411.9	823.8	

	WHITE	American Moto		
1554	TINTING WHITE	424.5	848.9	80P92
1559	YELLOW OXIDE	433.0	866.0	
1550	RED OXIDE	435.7	871.3	
1556	FAST GREEN	436.6	873.2	

	WINE	American Moto		
1552	FAST RED	352.9	705.9	81P10
1551	INDO YELLOW	371.1	742.1	
1501	LANDAU BLACK	388.8	777.7	
1554	TINTING WHITE	405.3	810.5	

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 22

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

1916	MED BROWN	American Moto	81P8
1559	YELLOW OXIDE	158.3	316.5
1302	LOW LUSTER CLEAR	295.5	590.9
1550	RED OXIDE	346.8	693.7
1554	TINTING WHITE	395.8	791.5
1501	LANDAU BLACK	411.6	823.3

1923	SILVER MET	American Moto	82P21
1508	SILVER	358.7	717.4
1553	FAST BLUE	377.0	753.9
1554	TINTING WHITE	394.4	788.9
1501	LANDAU BLACK	408.5	817.0
1552	FAST RED	409.6	819.3

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1917	NUTMEG	American Moto	81P12
1559	YELLOW OXIDE	269.1	538.3
1550	RED OXIDE	395.3	790.6
1554	TINTING WHITE	404.5	809.0
1501	LANDAU BLACK	413.7	827.5

1924	MED BLUE MET	American Moto	82P22
1553	FAST BLUE	117.5	235.0
1508	SILVER	207.2	414.4
1501	LANDAU BLACK	287.7	575.3
1554	TINTING WHITE	355.8	711.6
1552	FAST RED	410.0	820.0

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1918	NUTMEG MET	American Moto	81P69
1551	INDO YELLOW	190.2	380.4
1552	FAST RED	373.6	747.3
1508	SILVER	402.2	804.5
1501	LANDAU BLACK	404.3	808.6

1925	DK BLUE	American Moto	82P23
1553	FAST BLUE	170.2	340.5
1552	FAST RED	299.0	597.9
1501	LANDAU BLACK	388.5	776.9
1554	TINTING WHITE	404.8	809.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1919	MED BROWN MET	American Moto	80P36
1552	FAST RED	150.3	300.6
1508	SILVER	273.8	547.6
1551	INDO YELLOW	367.9	735.9
1501	LANDAU BLACK	405.6	811.1

1926	BLUE GREEN MET	American Moto	82P24
1553	FAST BLUE	277.5	555.0
1551	INDO YELLOW	333.3	666.5
1508	SILVER	376.6	753.2
1501	LANDAU BLACK	403.5	806.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1920	DEEP MAROON ME	American Moto	81P68
1552	FAST RED	360.1	720.1
1501	LANDAU BLACK	388.6	777.1
1508	SILVER	401.4	802.8
1551	INDO YELLOW	404.2	808.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1927	DK GREEN MET	American Moto	82P25
1501	LANDAU BLACK	202.9	405.8
1551	INDO YELLOW	302.8	605.5
1556	FAST GREEN	358.0	715.9
1508	SILVER	405.1	810.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1921	VINTAGE RED MET	American Moto	81P67
1552	FAST RED	354.1	708.1
1551	INDO YELLOW	381.2	762.5
1508	SILVER	393.8	787.6
1501	LANDAU BLACK	404.1	808.3

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1928	BEIGE	American Moto	82P26
1554	TINTING WHITE	291.8	583.7
1559	YELLOW OXIDE	421.4	842.8
1550	RED OXIDE	426.9	853.9
1501	LANDAU BLACK	429.3	858.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

1922	DK BLUE	American Moto	81P66
1553	FAST BLUE	244.6	489.3
1501	LANDAU BLACK	393.2	786.4
1554	TINTING WHITE	404.2	808.5

1929	GOLD MET	American Moto	82P27
1508	SILVER	161.4	322.8
1551	INDO YELLOW	305.0	609.9
1552	FAST RED	400.0	799.9
1501	LANDAU BLACK	405.9	811.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 23

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	SILVER MET	American Moto	82P21
1508	SILVER	358.7	717.4
1553	FAST BLUE	377.0	753.9
1554	TINTING WHITE	394.4	788.9
1501	LANDAU BLACK	408.5	817.0
1552	FAST RED	409.6	819.3

	SLATE BLUE	American Moto	82P3
1501	LANDAU BLACK	208.9	417.8
1554	TINTING WHITE	348.7	697.3
1553	FAST BLUE	387.3	774.6
1556	FAST GREEN	415.2	830.3

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	MED BLUE MET	American Moto	82P22
1508	SILVER	200.8	401.7
1553	FAST BLUE	289.7	579.3
1501	LANDAU BLACK	344.0	688.0
1552	FAST RED	390.6	781.3
1554	TINTING WHITE	407.4	814.7

	WHITE	General Motors	11
1554	TINTING WHITE	433.1	866.2
1551	INDO YELLOW	435.8	871.5
1552	FAST RED	436.6	873.2
1501	LANDAU BLACK	437.1	874.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	DK BLUE	American Moto	82P23
1553	FAST BLUE	204.4	408.9
1501	LANDAU BLACK	305.7	611.4
1556	FAST GREEN	391.2	782.4
1554	TINTING WHITE	404.5	809.0

	WHITE	General Motors	11T
1554	TINTING WHITE	433.1	866.2
1551	INDO YELLOW	435.8	871.5
1552	FAST RED	436.6	873.2
1501	LANDAU BLACK	437.1	874.2

	BLUE GREEN MET	American Moto	82P24
1553	FAST BLUE	310.0	620.0
1551	INDO YELLOW	366.5	733.0
1508	SILVER	393.7	787.4
1501	LANDAU BLACK	403.2	806.4

	SILVER MET	General Motors	15
1508	SILVER	391.7	783.4
1501	LANDAU BLACK	408.7	817.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	DK GREEN	American Moto	82P25
1501	LANDAU BLACK	208.0	415.9
1551	INDO YELLOW	296.4	592.8
1508	SILVER	355.3	710.6
1556	FAST GREEN	405.2	810.4

	MED GRAY MET	General Motors	17
1508	SILVER	199.9	399.8
1501	LANDAU BLACK	299.5	599.1
1554	TINTING WHITE	379.6	759.2
1553	FAST BLUE	400.2	800.5
1552	FAST RED	412.7	825.4

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	BEIGE	American Moto	82P26
1554	TINTING WHITE	305.0	610.1
1559	YELLOW OXIDE	421.3	842.7
1550	RED OXIDE	428.7	857.5
1501	LANDAU BLACK	430.1	860.1

	MED WAXBERRY	General Motors	45
1559	YELLOW OXIDE	222.8	445.6
1554	TINTING WHITE	373.2	746.3
1550	RED OXIDE	407.5	814.9
1553	FAST BLUE	421.1	842.3

	GOLD MET	American Moto	82P27
1508	SILVER	149.7	299.4
1551	INDO YELLOW	289.0	578.0
1552	FAST RED	399.1	798.2
1501	LANDAU BLACK	405.7	811.5

	LT WAXBERRY	General Motors	46
1554	TINTING WHITE	384.8	769.7
1559	YELLOW OXIDE	431.1	862.2
1556	FAST GREEN	433.5	867.0
1552	FAST RED	434.4	868.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 24

		PINTS	QUARTS			PINTS	QUARTS		
		GRAMS				GRAMS			
2605	MED JADESTONE	General Motors		47	2611	MED DOESKIN	General Motors		64T
1554	TINTING WHITE	245.8	491.5		1554	TINTING WHITE	199.5	399.0	
1501	LANDAU BLACK	349.1	698.3		1552	FAST RED	309.8	619.6	
1551	INDO YELLOW	393.0	786.0		1551	INDO YELLOW	400.3	800.7	
1553	FAST BLUE	422.9	845.9		1556	FAST GREEN	419.2	838.5	
2606	LT SANDSTONE	General Motors		63	2612	DK GRAY	General Motors		15
1554	TINTING WHITE	292.6	585.2		1501	LANDAU BLACK	256.5	513.0	
1559	YELLOW OXIDE	400.4	800.9		1554	TINTING WHITE	345.1	690.3	
1550	RED OXIDE	418.9	837.7		1559	YELLOW OXIDE	412.9	825.7	
1501	LANDAU BLACK	429.2	858.4						
2607	MED RED	General Motors		75	2613	MED GRAY	General Motors		17
1552	FAST RED	318.9	637.8		1554	TINTING WHITE	251.8	503.7	
1551	INDO YELLOW	376.6	753.2		1501	LANDAU BLACK	382.4	764.8	
1554	TINTING WHITE	401.9	803.7		1559	YELLOW OXIDE	419.2	838.5	
1550	RED OXIDE	406.0	812.1		1553	FAST BLUE	424.4	848.7	
2608	Dark Maple	General Motors		75-77	2614	DK GRAY	General Motors		17
1552	FAST RED	140.2	280.4		1553	FAST BLUE	131.3	262.6	
1557	MAGENTA	240.4	480.8		1501	LANDAU BLACK	246.8	493.6	
1302	LOW LUSTER CLEAR	323.0	646.0		1550	RED OXIDE	356.3	712.5	
1551	INDO YELLOW	404.3	808.7		1554	TINTING WHITE	410.6	821.2	
1553	FAST BLUE	413.2	826.3						
2609	MED MAUVE	General Motors		99	2615	MIDNIGHT BLUE	General Motors		29
1554	TINTING WHITE	161.3	322.6		1556	FAST GREEN	255.3	510.5	
1552	FAST RED	289.1	578.2		1553	FAST BLUE	382.9	765.9	
1501	LANDAU BLACK	355.7	711.4		1501	LANDAU BLACK	400.2	800.5	
1551	INDO YELLOW	416.5	833.0		1554	TINTING WHITE	402.3	804.7	
2610	DK JADE	General Motors		44	2616	MED DK AQUA	General Motors		41
1501	LANDAU BLACK	169.2	338.4		1559	YELLOW OXIDE	163.8	327.6	
1556	FAST GREEN	312.7	625.5		1553	FAST BLUE	325.7	651.3	
1554	TINTING WHITE	382.0	764.0		1554	TINTING WHITE	383.0	766.1	
1553	FAST BLUE	409.6	819.3		1501	LANDAU BLACK	411.4	822.9	
2611	MED DOESKIN	General Motors		64	2617	MED DK GREEN	General Motors		42
1554	TINTING WHITE	199.5	399.0		1551	INDO YELLOW	247.1	494.2	
1552	FAST RED	309.8	619.6		1554	TINTING WHITE	325.0	650.0	
1551	INDO YELLOW	400.3	800.7		1501	LANDAU BLACK	368.2	736.4	
1556	FAST GREEN	419.2	838.5		1556	FAST GREEN	410.0	820.0	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 25

		PINTS	QUARTS			PINTS	QUARTS		
		GRAMS				GRAMS			
2618	DK WAXBERRY	General Motors		46	2625	PASTEL WAXBERR	General Motors		35T
1501	LANDAU BLACK	219.8	439.7		1554	TINTING WHITE	388.8	777.7	
1559	YELLOW OXIDE	339.5	679.1		1559	YELLOW OXIDE	430.1	860.1	
1550	RED OXIDE	380.4	760.8		1556	FAST GREEN	432.6	865.3	
1554	TINTING WHITE	410.5	821.0		1550	RED OXIDE	434.5	869.1	
2619	MED DK WAXBERR	General Motors		45	2626	LT WAXBERRY ME	General Motors		36T
1559	YELLOW OXIDE	276.5	553.1		1508	SILVER	297.8	595.7	
1501	LANDAU BLACK	377.9	755.8		1551	INDO YELLOW	364.7	729.4	
1550	RED OXIDE	406.0	812.1		1552	FAST RED	392.1	784.1	
1554	TINTING WHITE	411.4	822.9		1501	LANDAU BLACK	407.6	815.1	
2620	DK JADESTONE	General Motors		47	MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR				
1501	LANDAU BLACK	140.6	281.2		2627	PASTEL JADESTON	General Motors		44T
1302	LOW LUSTER CLEAR	277.7	555.4		1554	TINTING WHITE	413.5	827.1	
1554	TINTING WHITE	326.5	653.0		1553	FAST BLUE	422.2	844.4	
1551	INDO YELLOW	367.4	734.7		1501	LANDAU BLACK	429.9	859.8	
1553	FAST BLUE	407.1	814.2		1551	INDO YELLOW	435.6	871.2	
2621	DK DOESKIN	General Motors		63	MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				
1559	YELLOW OXIDE	211.8	423.5		2628	LT JADESTONE	General Motors		45T
1501	LANDAU BLACK	325.9	651.9		1508	SILVER	325.4	650.8	
1550	RED OXIDE	411.1	822.1		1553	FAST BLUE	362.6	725.2	
					1551	INDO YELLOW	383.0	766.1	
					1554	TINTING WHITE	398.9	797.8	
					1501	LANDAU BLACK	408.4	816.8	
2622	MED DK DOESKIN	General Motors		64	MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				
1559	YELLOW OXIDE	203.8	407.6		2629	DK DOESKIN MET	General Motors		1508 SILVER
1501	LANDAU BLACK	310.0	620.0		1551	INDO YELLOW	200.3	400.5	
1550	RED OXIDE	397.7	795.3		1552	FAST RED	328.4	656.8	
1554	TINTING WHITE	412.1	824.2		1508	SILVER	372.5	745.0	
					1501	LANDAU BLACK	404.5	809.0	
2623	MED DK MAUVE	General Motors		99	MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				
1559	YELLOW OXIDE	166.7	333.5		2630	PASTEL SANDSTON	General Motors		63T
1550	RED OXIDE	264.3	528.6		1554	TINTING WHITE	268.7	537.3	
1554	TINTING WHITE	348.3	696.5		1559	YELLOW OXIDE	391.5	783.0	
1501	LANDAU BLACK	416.6	833.2		1550	RED OXIDE	415.2	830.5	
					1501	LANDAU BLACK	427.8	855.6	
2624	SILVER MET	General Motors		16T	MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				
1508	SILVER	408.9	817.8		2631	DK SANDSTONE ME	General Motors		69T
					1552	FAST RED	202.3	404.5	
					1551	INDO YELLOW	315.5	631.0	
					1501	LANDAU BLACK	364.0	728.1	
					1508	SILVER	404.5	809.0	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 26

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	DK MAPLE MET	General Motors	77T
1552	FAST RED	359.1	718.2
1501	LANDAU BLACK	375.3	750.7
1551	INDO YELLOW	390.0	780.0
1508	SILVER	404.2	808.5

	DK AMBER TAN	General Motors	62
1559	YELLOW OXIDE	184.4	368.8
1550	RED OXIDE	340.3	680.6
1501	LANDAU BLACK	412.1	824.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	SAXONY RED	General Motors	78T
1552	FAST RED	298.2	596.4
1559	YELLOW OXIDE	377.2	754.3
1550	RED OXIDE	405.3	810.5
1554	TINTING WHITE	406.4	812.8

	DK GRAY BLUE	General Motors	24
1554	TINTING WHITE	142.9	285.8
1501	LANDAU BLACK	277.0	554.0
1553	FAST BLUE	362.8	725.6
1550	RED OXIDE	416.1	832.2

	MED SLATE MET	General Motors	85T
1508	SILVER	132.9	265.8
1552	FAST RED	238.2	476.3
1501	LANDAU BLACK	329.9	659.9
1553	FAST BLUE	405.5	810.9

	DK SPRUCE	General Motors	48
1501	LANDAU BLACK	174.9	349.8
1554	TINTING WHITE	345.7	691.4
1551	INDO YELLOW	392.6	785.3
1556	FAST GREEN	417.5	835.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	MED JADESTONE M	General Motors	96T
1508	SILVER	186.7	373.4
1553	FAST BLUE	301.0	601.9
1501	LANDAU BLACK	361.1	722.2
1551	INDO YELLOW	405.9	811.9

	MED SADDLE TAN	General Motors	61
1559	YELLOW OXIDE	208.1	416.1
1554	TINTING WHITE	381.5	763.0
1550	RED OXIDE	410.8	821.6
1501	LANDAU BLACK	422.6	845.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	DOESKIN MET	General Motors	97T
1508	SILVER	174.7	349.4
1551	INDO YELLOW	326.7	653.4
1552	FAST RED	406.0	812.1

	MED DK SADDLE T	General Motors	61
1559	YELLOW OXIDE	267.2	534.5
1550	RED OXIDE	350.4	700.7
1501	LANDAU BLACK	394.0	787.9
1554	TINTING WHITE	413.5	827.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	CHARCOAL	General Motors	18
1501	LANDAU BLACK	226.7	453.3
1554	TINTING WHITE	296.6	593.2
1552	FAST RED	353.3	706.6
1551	INDO YELLOW	410.0	820.0

	DK SADDLE TAN	General Motors	61
1559	YELLOW OXIDE	232.2	464.4
1550	RED OXIDE	327.2	654.4
1501	LANDAU BLACK	411.7	823.5

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	MED DK AMBER TA	General Motors	62
1559	YELLOW OXIDE	303.3	606.7
1550	RED OXIDE	393.0	786.0
1554	TINTING WHITE	409.9	819.9
1501	LANDAU BLACK	414.2	828.4

	DK SABLE	General Motors	67
1559	YELLOW OXIDE	141.5	282.9
1550	RED OXIDE	260.7	521.4
1501	LANDAU BLACK	352.4	704.7
1554	TINTING WHITE	415.2	830.3

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 27

		PINTS	QUARTS			PINTS	QUARTS		
		GRAMS				GRAMS			
2646	MED DK AUTUMN	General Motors		72	2653	SABLE MET	General Motors		64T
1552	FAST RED	319.6	639.2		1552	FAST RED	177.3	354.5	
1550	RED OXIDE	384.9	769.9		1508	SILVER	273.4	546.8	
1553	FAST BLUE	398.7	797.4		1501	LANDAU BLACK	354.2	708.3	
1554	TINTING WHITE	406.0	812.1		1551	INDO YELLOW	405.3	810.5	
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR									
2647	DK REDWOOD	General Motors		77	2654	AUTUMN MAPLE M	General Motors		74T
1552	FAST RED	295.6	591.3		1552	FAST RED	394.9	789.8	
1551	INDO YELLOW	378.7	757.3		1508	SILVER	401.0	802.0	
1501	LANDAU BLACK	392.7	785.5		1553	FAST BLUE	404.0	808.1	
1554	TINTING WHITE	404.9	809.8						
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR									
2648	MED SANDSTONE	General Motors		63	2655	DK REDWOOD MET	General Motors		77T
1559	YELLOW OXIDE	174.1	348.3		1552	FAST RED	304.0	608.0	
1554	TINTING WHITE	339.0	677.9		1551	INDO YELLOW	373.4	746.9	
1550	RED OXIDE	390.9	781.9		1501	LANDAU BLACK	389.4	778.8	
1501	LANDAU BLACK	421.8	843.6		1508	SILVER	404.1	808.3	
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR									
2649	DK BLUE	General Motors		28T	2656	SLATE GRAY	General Motors		80T
1553	FAST BLUE	291.3	582.5		1554	TINTING WHITE	393.7	787.4	
1501	LANDAU BLACK	392.4	784.7		1559	YELLOW OXIDE	416.3	832.6	
1554	TINTING WHITE	404.0	808.1		1501	LANDAU BLACK	434.2	868.3	
					1550	RED OXIDE	434.6	869.3	
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR									
2650	LT JADESTONE	General Motors		45T	2657	LT DOESKIN	General Motors		86T
1554	TINTING WHITE	341.1	682.1		1559	YELLOW OXIDE	204.8	409.6	
1501	LANDAU BLACK	399.8	799.5		1554	TINTING WHITE	375.6	751.3	
1556	FAST GREEN	416.7	833.3		1550	RED OXIDE	412.4	824.8	
1551	INDO YELLOW	430.2	860.3		1501	LANDAU BLACK	422.6	845.1	
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR									
2651	LT YELLOW	General Motors		54T	2658	DK REDWOOD	General Motors		87T
1554	TINTING WHITE	389.0	778.1		1550	RED OXIDE	172.2	344.5	
1551	INDO YELLOW	422.6	845.1		1552	FAST RED	328.2	656.5	
1552	FAST RED	431.7	863.4		1501	LANDAU BLACK	406.7	813.4	
1556	FAST GREEN	433.7	867.4		1554	TINTING WHITE	408.6	817.2	
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR									
2652	ALMOND	General Motors		61T	2659	MED SPRUCE MET	General Motors		91T
1554	TINTING WHITE	276.2	552.3		1508	SILVER	262.0	524.0	
1559	YELLOW OXIDE	414.0	828.0		1501	LANDAU BLACK	368.8	737.6	
1550	RED OXIDE	424.3	848.5		1556	FAST GREEN	407.5	814.9	
1501	LANDAU BLACK	428.3	856.5						
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR									

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 28

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

2660	LT SABLE MET	General Motors	96T
1508	SILVER	274.0	548.0
1552	FAST RED	353.5	707.0
1501	LANDAU BLACK	390.6	781.3
1551	INDO YELLOW	407.4	814.7

2704	DK SPRUCE MET	Ford Motor	M
1553	FAST BLUE	251.4	502.7
1551	INDO YELLOW	344.4	688.8
1508	SILVER	382.1	764.2
1501	LANDAU BLACK	403.5	806.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

2661	LT REDWOOD MET	General Motors	97T
1508	SILVER	192.5	384.9
1552	FAST RED	334.9	669.8
1551	INDO YELLOW	397.6	795.2
1501	LANDAU BLACK	406.3	812.6

2705	FAWN	Ford Motor	U
1554	TINTING WHITE	325.2	650.4
1559	YELLOW OXIDE	404.3	808.6
1550	RED OXIDE	423.1	846.3
1501	LANDAU BLACK	430.9	861.8

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

2662	ALMOND MET	General Motors	98T
1508	SILVER	190.1	380.2
1551	INDO YELLOW	313.8	627.6
1552	FAST RED	399.4	798.8
1501	LANDAU BLACK	406.2	812.4

2706	PASTEL CAMEL	Ford Motor	Y
1554	TINTING WHITE	299.8	599.6
1559	YELLOW OXIDE	426.9	853.9
1550	RED OXIDE	428.9	857.9
1553	FAST BLUE	429.7	859.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

2700	LT BLUE MET	Ford Motor	B
1508	SILVER	254.7	509.4
1553	FAST BLUE	365.8	731.7
1552	FAST RED	386.0	772.0
1554	TINTING WHITE	398.6	797.2
1551	INDO YELLOW	407.6	815.3

2707	MED DK NUTMEG	Ford Motor	Z
1552	FAST RED	221.4	442.7
1551	INDO YELLOW	364.1	728.3
1508	SILVER	393.7	787.4
1501	LANDAU BLACK	404.3	808.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

2701	MED BITTERSWEET	Ford Motor	C
1552	FAST RED	273.0	546.1
1551	INDO YELLOW	372.3	744.6
1508	SILVER	404.4	808.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

2708	DK BROWN MET	Ford Motor	Z
1552	FAST RED	228.4	456.8
1551	INDO YELLOW	366.6	733.2
1501	LANDAU BLACK	386.5	772.9
1508	SILVER	404.2	808.5

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

2702	BITTERSWEET ME	Ford Motor	C
1552	FAST RED	301.3	602.7
1551	INDO YELLOW	377.2	754.5
1508	SILVER	396.2	792.5
1501	LANDAU BLACK	404.2	808.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

2709	MED PEWTER MET	Ford Motor	3
1508	SILVER	266.9	533.7
1501	LANDAU BLACK	376.2	752.4
1552	FAST RED	394.8	789.6
1551	INDO YELLOW	407.5	814.9

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

2703	MED RED	Ford Motor	D
1552	FAST RED	395.7	791.4
1554	TINTING WHITE	401.3	802.6
1553	FAST BLUE	404.4	808.8

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

2710	LT PEWTER MET	Ford Motor	4
1508	SILVER	276.8	553.7
1501	LANDAU BLACK	342.0	684.0
1551	INDO YELLOW	383.9	767.8
1552	FAST RED	407.6	815.1

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 29

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

2711	LT GOLD MET	Ford Motor	7
1508	SILVER	219.5	439.1
1551	INDO YELLOW	354.2	708.3
1552	FAST RED	394.4	788.9
1501	LANDAU BLACK	406.6	813.2

2718	MIDNIGHT BLUE M	Ford Motor	B
1553	FAST BLUE	230.4	460.8
1501	LANDAU BLACK	320.5	641.1
1508	SILVER	369.6	739.1
1552	FAST RED	396.2	792.3
1554	TINTING WHITE	402.4	804.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

2712	LT FAWN MET	Ford Motor	H
1508	SILVER	194.8	389.7
1552	FAST RED	303.0	605.9
1551	INDO YELLOW	355.6	711.2
1501	LANDAU BLACK	406.5	813.0

2719	DK RED MET	Ford Motor	D
1552	FAST RED	370.4	740.8
1508	SILVER	399.9	799.7
1553	FAST BLUE	404.1	808.3

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

2713	DK CHAMPAGNE M	Ford Motor	J
1552	FAST RED	225.0	449.9
1551	INDO YELLOW	312.6	625.1
1501	LANDAU BLACK	391.8	783.6
1508	SILVER	404.4	808.8

2720	BITTERSWEET	Ford Motor	E
1552	FAST RED	197.8	395.6
1551	INDO YELLOW	353.6	707.2
1554	TINTING WHITE	405.9	811.9
1501	LANDAU BLACK	408.0	816.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

2714	DK RED MET	Ford Motor	N
1552	FAST RED	389.3	778.6
1554	TINTING WHITE	395.1	790.2
1508	SILVER	400.0	800.1
1553	FAST BLUE	404.4	808.8

2721	MULBERRY MET	Ford Motor	F
1552	FAST RED	278.2	556.3
1551	INDO YELLOW	338.8	677.5
1501	LANDAU BLACK	375.3	750.7
1508	SILVER	404.4	808.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

2715	SILVER MET	Ford Motor	P
1508	SILVER	393.2	786.4
1501	LANDAU BLACK	408.7	817.4

2722	VAQUERO	Ford Motor	F
1550	RED OXIDE	350.8	701.7
1559	YELLOW OXIDE	382.0	764.0
1501	LANDAU BLACK	406.4	812.8
1554	TINTING WHITE	414.1	828.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

2716	CREAM	Ford Motor	V
1554	TINTING WHITE	345.5	691.0
1559	YELLOW OXIDE	428.8	857.7
1556	FAST GREEN	430.9	861.8
1552	FAST RED	432.2	864.3

2723	TEAL MET	Ford Motor	K
1553	FAST BLUE	264.5	529.0
1551	INDO YELLOW	321.8	643.5
1501	LANDAU BLACK	363.9	727.7
1508	SILVER	403.5	806.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

2717	DK HARBOR BLUE	Ford Motor	B
1553	FAST BLUE	221.4	442.9
1508	SILVER	291.7	583.3
1501	LANDAU BLACK	348.9	697.9
1556	FAST GREEN	391.4	782.8
1554	TINTING WHITE	405.1	810.2

2724	DK TEAL MET	Ford Motor	K
1553	FAST BLUE	325.9	651.7
1551	INDO YELLOW	385.8	771.6
1508	SILVER	402.9	805.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 30

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
2725	FRENCH VANILLA	Ford Motor		L	2732	MED DK MULBERR	Ford Motor	F
1554	TINTING WHITE	341.4	682.9		1552	FAST RED	313.8	627.6
1559	YELLOW OXIDE	424.9	849.9		1551	INDO YELLOW	360.2	720.5
1550	RED OXIDE	430.1	860.1		1501	LANDAU BLACK	386.2	772.4
1501	LANDAU BLACK	432.0	863.9		1508	SILVER	404.2	808.5
				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				
2726	LT FRENCH VANIL	Ford Motor		L	2733	FRENCH VANILLA	Ford Motor	L
1554	TINTING WHITE	217.6	435.3		1554	TINTING WHITE	392.1	784.1
1559	YELLOW OXIDE	395.9	791.7		1559	YELLOW OXIDE	431.9	863.7
1550	RED OXIDE	417.9	835.8		1550	RED OXIDE	433.9	867.7
1501	LANDAU BLACK	425.1	850.3		1501	LANDAU BLACK	434.8	869.6
2727	MED VANILLA	Ford Motor		L	3000	DK CHARCOAL	General Motors	17
1559	YELLOW OXIDE	244.3	488.7		1501	LANDAU BLACK	168.6	337.3
1554	TINTING WHITE	372.8	745.6		1559	YELLOW OXIDE	304.2	608.4
1550	RED OXIDE	406.1	812.3		1550	RED OXIDE	360.8	721.6
1501	LANDAU BLACK	420.1	840.2		1554	TINTING WHITE	412.9	825.7
2728	MED FAWN	Ford Motor		U	3001	DK ROYAL BLUE	General Motors	22
1559	YELLOW OXIDE	202.9	405.8		1501	LANDAU BLACK	149.7	299.4
1554	TINTING WHITE	319.6	639.2		1554	TINTING WHITE	289.6	579.1
1550	RED OXIDE	389.8	779.6		1552	FAST RED	358.4	716.9
1501	LANDAU BLACK	419.2	838.5		1553	FAST BLUE	414.9	829.7
2729	OPAL	Ford Motor		W	3002	MED GRAY FERN	General Motors	42
1554	TINTING WHITE	399.3	798.6		1554	TINTING WHITE	216.4	432.8
1559	YELLOW OXIDE	429.3	858.6		1501	LANDAU BLACK	353.0	706.0
1501	LANDAU BLACK	432.6	865.3		1551	INDO YELLOW	418.6	837.1
1550	RED OXIDE	435.2	870.4		1552	FAST RED	420.9	841.9
				MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR				
2730	LT BLUE MET	Ford Motor		B	3003	DK GRAY FERN	General Motors	
1508	SILVER	308.8	617.7		1501	LANDAU BLACK	206.9	413.8
1553	FAST BLUE	364.8	729.6		1554	TINTING WHITE	304.6	609.1
1501	LANDAU BLACK	387.0	774.1		1551	INDO YELLOW	398.5	797.1
1554	TINTING WHITE	401.7	803.3		1550	RED OXIDE	412.3	824.6
1552	FAST RED	408.7	817.4					
2731	DK BROWN MET	Ford Motor		F	3004	MED BEECH	General Motors	58
1552	FAST RED	246.5	493.1		1559	YELLOW OXIDE	278.6	557.3
1551	INDO YELLOW	323.1	646.2		1550	RED OXIDE	358.6	717.3
1501	LANDAU BLACK	389.8	779.6		1554	TINTING WHITE	409.8	819.7
1508	SILVER	404.3	808.6		1501	LANDAU BLACK	416.1	832.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 31

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	DK BEECH	General Motors		
3005			58	
1559	YELLOW OXIDE	239.3	478.6	
1550	RED OXIDE	354.0	707.9	
1501	LANDAU BLACK	391.2	782.4	
1554	TINTING WHITE	414.0	828.0	

	MED DK RYL BLUE	General Motors		
3012			27T	
1552	FAST RED	140.2	280.4	
1553	FAST BLUE	279.6	559.2	
1508	SILVER	362.7	725.4	
1501	LANDAU BLACK	388.4	776.7	
1551	INDO YELLOW	404.5	809.0	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	LT SAND GRAY	General Motors		
3006			60	
1554	TINTING WHITE	342.5	685.0	
1559	YELLOW OXIDE	401.7	803.3	
1550	RED OXIDE	417.6	835.2	
1501	LANDAU BLACK	431.9	863.7	

	LT GRAY FERN ME	General Motors		
3013			42T	
1508	SILVER	347.7	695.4	
1501	LANDAU BLACK	381.5	763.0	
1551	INDO YELLOW	397.5	795.0	
1553	FAST BLUE	408.1	816.2	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	MED SAND GRAY	General Motors		
3007			60	
1554	TINTING WHITE	217.6	435.3	
1501	LANDAU BLACK	300.0	600.0	
1552	FAST RED	365.4	730.7	
1551	INDO YELLOW	411.4	822.7	

	DK GRAY FERN ME	General Motors		
3014			48T	
1501	LANDAU BLACK	276.5	553.1	
1508	SILVER	331.8	663.7	
1551	INDO YELLOW	385.5	771.0	
1556	FAST GREEN	405.5	810.9	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	DK BRIAR BROWN	General Motors		
3008			67	
1550	RED OXIDE	160.8	321.7	
1501	LANDAU BLACK	287.3	574.6	
1559	YELLOW OXIDE	394.8	789.6	
1554	TINTING WHITE	412.0	824.0	

	FLAX	General Motors		
3015			50T	
1554	TINTING WHITE	420.7	841.3	
1551	INDO YELLOW	434.6	869.3	
1550	RED OXIDE	435.5	871.0	
1501	LANDAU BLACK	436.1	872.3	

	DK MAPLE	General Motors		
3009			77	
1552	FAST RED	337.9	675.8	
1551	INDO YELLOW	382.5	764.9	
1501	LANDAU BLACK	394.4	788.9	
1554	TINTING WHITE	404.7	809.4	

	LT SAND GRAY	General Motors		
3016			60T	
1554	TINTING WHITE	343.5	687.0	
1559	YELLOW OXIDE	402.4	804.8	
1550	RED OXIDE	418.3	836.6	
1501	LANDAU BLACK	432.0	863.9	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	SILVER SAND MET	General Motors		
3010			15T	
1508	SILVER	297.4	594.9	
1501	LANDAU BLACK	374.9	749.7	
1552	FAST RED	396.7	793.4	
1551	INDO YELLOW	407.6	815.3	

	LT BRIAR BROWN	General Motors		
3017			62T	
1508	SILVER	286.0	572.1	
1552	FAST RED	349.5	699.0	
1501	LANDAU BLACK	388.7	777.5	
1551	INDO YELLOW	407.4	814.7	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	LT ROYAL BLUE M	General Motors		
3011			22T	
1508	SILVER	270.1	540.2	
1552	FAST RED	344.5	688.9	
1553	FAST BLUE	407.0	814.0	

	DK ROYAL BLUE M	General Motors		
3018			90T	
1553	FAST BLUE	243.0	486.0	
1556	FAST GREEN	342.2	684.4	
1501	LANDAU BLACK	394.7	789.5	
1508	SILVER	403.3	806.6	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 32

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	LT FLAX MET	General Motors	91T
1508	SILVER	226.5	453.0
1551	INDO YELLOW	320.1	640.1
1552	FAST RED	399.4	798.8
1556	FAST GREEN	406.7	813.4

	BEIGE MET	Chrysler Motors	L4
1508	SILVER	210.2	420.5
1551	INDO YELLOW	288.0	576.1
1552	FAST RED	361.5	723.0
1554	TINTING WHITE	387.0	774.1
1501	LANDAU BLACK	408.6	817.2

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	DK BEECH MET	General Motors	94T
1552	FAST RED	173.9	347.7
1551	INDO YELLOW	318.9	637.8
1508	SILVER	391.6	783.2
1501	LANDAU BLACK	404.9	809.8

	BEIGE	Chrysler Motors	L6
1554	TINTING WHITE	284.2	568.5
1559	YELLOW OXIDE	397.9	795.7
1550	RED OXIDE	419.7	839.4
1501	LANDAU BLACK	428.7	857.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	SILVER	Chrysler Motors	A2
1508	SILVER	270.6	541.1
1554	TINTING WHITE	386.0	772.0
1552	FAST RED	401.8	803.5
1551	INDO YELLOW	409.8	819.7
1553	FAST BLUE	416.0	832.0

	DK BROWN	Chrysler Motors	T8
1559	YELLOW OXIDE	157.4	314.8
1501	LANDAU BLACK	301.9	603.8
1550	RED OXIDE	401.2	802.4
1554	TINTING WHITE	411.2	822.3

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	MED BLUE	Chrysler Motors	B5
1554	TINTING WHITE	244.0	487.9
1553	FAST BLUE	320.2	640.3
1501	LANDAU BLACK	386.8	773.7
1552	FAST RED	422.6	845.1

	MIDNIGHT BLUE	Ford Motor	B
1553	FAST BLUE	222.1	444.2
1501	LANDAU BLACK	366.4	732.8
1554	TINTING WHITE	406.6	813.2

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	BEIGE	Chrysler Motors	L
1554	TINTING WHITE	264.7	529.3
1559	YELLOW OXIDE	391.3	782.6
1550	RED OXIDE	416.3	832.6
1501	LANDAU BLACK	427.6	855.2

	MED RED	Ford Motor	D
1552	FAST RED	309.9	619.8
1550	RED OXIDE	394.6	789.3
1554	TINTING WHITE	406.6	813.2
1501	LANDAU BLACK	407.1	814.2

	DK SADDLE	Chrysler Motors	K9
1559	YELLOW OXIDE	249.5	498.9
1550	RED OXIDE	404.3	808.6
1501	LANDAU BLACK	413.3	826.7

	DK RED	Ford Motor	D
1552	FAST RED	365.0	730.0
1551	INDO YELLOW	389.9	779.8
1554	TINTING WHITE	398.7	797.4
1553	FAST BLUE	404.6	809.2

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	DK BROWN	Chrysler Motors	T8
1559	YELLOW OXIDE	157.4	314.8
1501	LANDAU BLACK	301.9	603.8
1550	RED OXIDE	401.2	802.4
1554	TINTING WHITE	411.2	822.3

	MULBERRY	Ford Motor	F
1550	RED OXIDE	273.9	547.8
1501	LANDAU BLACK	379.5	759.1
1559	YELLOW OXIDE	399.3	798.6
1554	TINTING WHITE	412.5	825.0

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 33

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

3034	TEAL	Ford Motor	K
1553	FAST BLUE	272.5	544.9
1551	INDO YELLOW	344.9	689.9
1501	LANDAU BLACK	377.6	755.3
1554	TINTING WHITE	405.2	810.4

3041	WALNUT	Ford Motor	Z
1559	YELLOW OXIDE	169.0	338.0
1550	RED OXIDE	309.6	619.2
1501	LANDAU BLACK	397.4	794.8
1554	TINTING WHITE	412.7	825.4

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

3035	LT FRENCH VANIL	Ford Motor	L
1554	TINTING WHITE	343.0	686.1
1559	YELLOW OXIDE	424.2	848.4
1550	RED OXIDE	430.5	861.1
1501	LANDAU BLACK	432.2	864.3

3042	DK HARBOR BLUE	Ford Motor	B
1553	FAST BLUE	288.9	577.8
1554	TINTING WHITE	339.2	678.3
1501	LANDAU BLACK	382.2	764.4
1551	INDO YELLOW	406.7	813.4

3036	MED FRENCH VANI	Ford Motor	L
1554	TINTING WHITE	217.6	435.3
1559	YELLOW OXIDE	395.9	791.7
1550	RED OXIDE	417.9	835.8
1501	LANDAU BLACK	425.1	850.3

3042	DK. Harbor Blue	Ford Motor	B
1553	FAST BLUE	250.7	501.5
1554	TINTING WHITE	327.7	655.4
1501	LANDAU BLACK	394.5	789.0
1551	INDO YELLOW	419.1	838.2

3037	DK FRENCH VANIL	Ford Motor	L
1559	YELLOW OXIDE	241.3	482.6
1554	TINTING WHITE	371.6	743.3
1550	RED OXIDE	405.5	810.9
1501	LANDAU BLACK	420.2	840.4

3043	DK TEAL MET	Ford Motor	K
1553	FAST BLUE	289.8	579.5
1551	INDO YELLOW	355.7	711.4
1508	SILVER	394.7	789.5
1501	LANDAU BLACK	403.3	806.6

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

3038	CHARCOAL	Ford Motor	P
1501	LANDAU BLACK	170.1	340.1
1554	TINTING WHITE	297.4	594.7
1551	INDO YELLOW	356.5	713.1
1552	FAST RED	414.1	828.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

3044	FRENCH VANILLA	Ford Motor	L
1508	SILVER	207.2	414.4
1551	INDO YELLOW	304.9	609.7
1552	FAST RED	397.4	794.8
1501	LANDAU BLACK	406.5	813.0

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

3039	CADET BLUE	Ford Motor	S
1554	TINTING WHITE	233.4	466.8
1550	RED OXIDE	347.5	695.0
1553	FAST BLUE	401.8	803.5
1559	YELLOW OXIDE	424.9	849.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

3045	SILVER MET	Ford Motor	P
1508	SILVER	337.1	674.1
1554	TINTING WHITE	390.5	780.9
1501	LANDAU BLACK	412.1	824.2

3040	DESERT TAN	Ford Motor	U
1559	YELLOW OXIDE	210.0	420.1
1554	TINTING WHITE	352.7	705.5
1550	RED OXIDE	407.8	815.7
1501	LANDAU BLACK	420.9	841.7

3046	PASTEL CADET BL	Ford Motor	S
1508	SILVER	321.5	643.0
1553	FAST BLUE	367.8	735.7
1552	FAST RED	402.6	805.2
1501	LANDAU BLACK	407.6	815.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 34

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	MED WALNUT MET	Ford Motor	Z
1552	FAST RED	202.4	404.9
1501	LANDAU BLACK	293.6	587.3
1551	INDO YELLOW	373.1	746.1
1508	SILVER	404.6	809.2

	DK BRONZE MET	General Motors	76DN
1552	FAST RED	299.1	598.1
1551	INDO YELLOW	359.3	718.6
1501	LANDAU BLACK	385.6	771.2
1508	SILVER	404.2	808.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	SILVER MET	Ford Motor	P
1508	SILVER	381.0	762.1
1501	LANDAU BLACK	402.9	805.8
1553	FAST BLUE	408.5	817.0

	RED	Chrysler Motors	M5
1552	FAST RED	393.6	787.2
1553	FAST BLUE	399.0	798.0
1554	TINTING WHITE	404.4	808.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	DK CHARCOAL	General Motors	18DN
1501	LANDAU BLACK	253.6	507.1
1559	YELLOW OXIDE	349.7	699.4
1554	TINTING WHITE	400.0	800.1
1550	RED OXIDE	410.9	821.8

	SILVER	Chrysler Motors	A4
1508	SILVER	202.2	404.3
1554	TINTING WHITE	387.4	774.8
1501	LANDAU BLACK	408.1	816.2
1551	INDO YELLOW	420.7	841.3

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	MED DK CHARCOA	General Motors	18CN
1501	LANDAU BLACK	192.8	385.5
1554	TINTING WHITE	310.5	620.9
1559	YELLOW OXIDE	415.9	831.8

	MED TAN	Chrysler Motors	T6
1559	YELLOW OXIDE	269.7	539.4
1554	TINTING WHITE	347.7	695.4
1550	RED OXIDE	396.7	793.4
1501	LANDAU BLACK	417.1	834.3

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	MED DK ALMOND	General Motors	61CN
1559	YELLOW OXIDE	224.1	448.2
1302	LOW LUSTER CLEAR	306.2	612.4
1550	RED OXIDE	370.8	741.6
1501	LANDAU BLACK	405.1	810.2
1554	TINTING WHITE	410.5	821.0

	DK BRIAR BROWN	General Motors	67T
1552	FAST RED	205.0	410.0
1501	LANDAU BLACK	297.5	595.1
1551	INDO YELLOW	351.8	703.6
1508	SILVER	404.8	809.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	DK ALMOND	General Motors	61DN
1559	YELLOW OXIDE	212.6	425.2
1550	RED OXIDE	293.6	587.3
1501	LANDAU BLACK	365.1	730.2
1302	LOW LUSTER CLEAR	410.6	821.2

	DK AUTUMN MAPL	General Motors	78T
1552	FAST RED	342.3	684.6
1501	LANDAU BLACK	371.1	742.1
1551	INDO YELLOW	388.8	777.7
1508	SILVER	404.2	808.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	VERY DK CARMINE	General Motors	74DN
1552	FAST RED	326.9	653.8
1551	INDO YELLOW	361.3	722.6
1554	TINTING WHITE	387.8	775.6
1501	LANDAU BLACK	406.0	812.1

	MED BRIAR BROW	General Motors	92T
1508	SILVER	166.7	333.5
1552	FAST RED	293.7	587.5
1501	LANDAU BLACK	373.3	746.5
1551	INDO YELLOW	406.2	812.4

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 35

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

3061	DK CADET BLUE M	Ford Motor	S
1553	FAST BLUE	149.9	299.8
1552	FAST RED	278.8	557.7
1501	LANDAU BLACK	344.0	688.0
1508	SILVER	383.9	767.8
1554	TINTING WHITE	405.7	811.3

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

3062	MIDNT CADET BLU	Ford Motor	S
1553	FAST BLUE	210.8	421.6
1552	FAST RED	301.0	601.9
1501	LANDAU BLACK	383.2	766.5
1508	SILVER	403.6	807.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

3063	OYSTER WHITE	General Motors	12AN
1554	TINTING WHITE	419.6	839.2
1551	INDO YELLOW	426.6	853.1
1501	LANDAU BLACK	432.3	864.7
1552	FAST RED	436.0	871.9

3064	LT SLATE GRAY	General Motors	13AN
1554	TINTING WHITE	362.6	725.2
1559	YELLOW OXIDE	396.2	792.5
1501	LANDAU BLACK	423.0	846.1
1550	RED OXIDE	432.7	865.5

3065	MED DK SLATE GR	General Motors	13CN
1554	TINTING WHITE	251.8	503.5
1501	LANDAU BLACK	349.1	698.3
1559	YELLOW OXIDE	407.4	814.7
1550	RED OXIDE	425.2	850.4

3066	DK GRAY	General Motors	15DN
1501	LANDAU BLACK	285.2	570.4
1554	TINTING WHITE	397.7	795.3
1551	INDO YELLOW	413.4	826.9

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

3067	MED LT BLUE	General Motors	23BN
1554	TINTING WHITE	157.0	314.1
1553	FAST BLUE	297.4	594.9
1501	LANDAU BLACK	374.2	748.4
1550	RED OXIDE	416.7	833.3

3068	MED BLUE	General Motors	23CN
1553	FAST BLUE	200.6	401.3
1501	LANDAU BLACK	327.0	654.0
1554	TINTING WHITE	395.1	790.2
1556	FAST GREEN	408.7	817.4

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

3069	DK BLUE	General Motors	23DN
1553	FAST BLUE	161.4	322.8
1501	LANDAU BLACK	312.6	625.3
1554	TINTING WHITE	385.9	771.8
1550	RED OXIDE	409.9	819.9

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

3070	MED JADESTONE	General Motors	47DN
1554	TINTING WHITE	245.8	491.5
1501	LANDAU BLACK	349.1	698.3
1551	INDO YELLOW	393.0	786.0
1553	FAST BLUE	422.9	845.9

3071	MED DK JADESTON	General Motors	47CN
1302	LOW LUSTER CLEAR	136.6	273.2
1501	LANDAU BLACK	242.1	484.1
1554	TINTING WHITE	315.6	631.2
1559	YELLOW OXIDE	385.0	770.1
1553	FAST BLUE	410.4	820.8

3072	DK JADESTONE	General Motors	47DN
1501	LANDAU BLACK	194.5	388.9
1553	FAST BLUE	292.5	585.0
1551	INDO YELLOW	351.3	702.6
1554	TINTING WHITE	408.5	817.0

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

3073	MED ALMOND	General Motors	61BN
1554	TINTING WHITE	236.4	472.7
1552	FAST RED	323.2	646.4
1551	INDO YELLOW	403.5	806.9
1556	FAST GREEN	422.0	844.0

3074	DK CARMINE	General Motors	74CN
1552	FAST RED	329.0	658.0
1551	INDO YELLOW	385.3	770.6
1554	TINTING WHITE	401.1	802.2
1553	FAST BLUE	405.2	810.4

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 36

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	DK GRAY	General Motors	13DN
1501	LANDAU BLACK	171.9	343.7
1554	TINTING WHITE	343.2	686.5
1559	YELLOW OXIDE	406.7	813.4
1550	RED OXIDE	419.2	838.5

	DK GARNET	American Moto	83P96
1552	FAST RED	196.4	392.7
1550	RED OXIDE	297.0	593.9
1302	LOW LUSTER CLEAR	378.1	756.2
1501	LANDAU BLACK	398.2	796.5
1554	TINTING WHITE	406.7	813.4

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	WALNUT	Ford Motor	N
1559	YELLOW OXIDE	259.6	519.3
1302	LOW LUSTER CLEAR	341.9	683.8
1550	RED OXIDE	390.3	780.5
1554	TINTING WHITE	405.0	810.0
1501	LANDAU BLACK	411.4	822.9

	DK GRAY	American Moto	83P97
1554	TINTING WHITE	254.6	509.2
1501	LANDAU BLACK	381.2	762.5
1551	INDO YELLOW	405.0	810.0
1552	FAST RED	423.7	847.4

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	GRAY	American Moto	83P18
1554	TINTING WHITE	330.0	660.1
1501	LANDAU BLACK	385.0	770.1
1551	INDO YELLOW	407.4	814.7
1552	FAST RED	429.3	858.6

	DK NUTMEG	American Moto	83P98
1551	INDO YELLOW	166.2	332.3
1550	RED OXIDE	293.5	586.9
1302	LOW LUSTER CLEAR	375.2	750.3
1554	TINTING WHITE	399.7	799.3
1501	LANDAU BLACK	408.5	817.0

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	GARNET	American Moto	83P19
1552	FAST RED	164.9	329.8
1550	RED OXIDE	309.2	618.5
1302	LOW LUSTER CLEAR	390.6	781.3
1501	LANDAU BLACK	401.8	803.5
1554	TINTING WHITE	407.5	814.9

	DK SLATE BLUE	American Moto	83P120
1501	LANDAU BLACK	278.8	557.7
1554	TINTING WHITE	382.6	765.1
1553	FAST BLUE	409.9	819.9
1551	INDO YELLOW	412.5	825.0

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	ALMOND	American Moto	83P20
1554	TINTING WHITE	239.9	479.8
1559	YELLOW OXIDE	389.0	778.1
1550	RED OXIDE	414.4	828.8
1501	LANDAU BLACK	426.4	852.7

	WEDGEWOOD BLU	Ford Motor	B
1554	TINTING WHITE	196.4	392.7
1501	LANDAU BLACK	310.1	620.2
1553	FAST BLUE	409.0	818.0
1556	FAST GREEN	418.9	837.7

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	DK ALMOND	American Moto	83P21
1302	LOW LUSTER CLEAR	139.9	279.9
1559	YELLOW OXIDE	272.4	544.7
1554	TINTING WHITE	365.8	731.7
1550	RED OXIDE	400.8	801.6
1501	LANDAU BLACK	413.9	827.8

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	LT GRAY	General Motors	16AN
1554	TINTING WHITE	362.6	725.2
1501	LANDAU BLACK	395.6	791.2
1559	YELLOW OXIDE	428.2	856.3
1550	RED OXIDE	432.6	865.3

	DEEP DK ALMOND	American Moto	83P95
1559	YELLOW OXIDE	238.5	477.1
1550	RED OXIDE	321.7	643.3
1554	TINTING WHITE	390.5	781.1
1501	LANDAU BLACK	416.7	833.3

	MED GRAY	General Motors	16BN
1554	TINTING WHITE	254.0	508.1
1501	LANDAU BLACK	364.5	729.0
1551	INDO YELLOW	400.3	800.7
1552	FAST RED	423.7	847.4

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 37

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
3089	DK GRAY	General Motors	16CN	3096	MED SADDLE	Corvette	62BN
1501	LANDAU BLACK	201.4	402.8	1559	YELLOW OXIDE	167.8	335.5
1554	TINTING WHITE	347.3	694.6	1302	LOW LUSTER CLEAR	304.8	609.5
1551	INDO YELLOW	393.5	787.0	1550	RED OXIDE	350.6	701.3
1552	FAST RED	415.6	831.3	1554	TINTING WHITE	395.2	790.4
				1501	LANDAU BLACK	411.4	822.7
3090	GRAPHITE	Corvette	12DN	3097	DK BRONZE MET	Corvette	64CM
1501	LANDAU BLACK	213.3	426.6	1552	FAST RED	145.2	290.3
1554	TINTING WHITE	312.1	624.2	1501	LANDAU BLACK	267.0	533.9
1552	FAST RED	365.4	730.7	1551	INDO YELLOW	337.1	674.1
1551	INDO YELLOW	412.0	824.0	1508	SILVER	400.9	801.8
				1554	TINTING WHITE	405.4	810.7
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR			
3091	MED GRAY MET	Corvette	15BM	3098	DK BRONZE	Corvette	64CN
1508	SILVER	332.6	665.2	1559	YELLOW OXIDE	182.7	365.4
1501	LANDAU BLACK	394.1	788.1	1501	LANDAU BLACK	298.0	596.0
1553	FAST BLUE	402.4	804.8	1550	RED OXIDE	371.9	743.9
1551	INDO YELLOW	408.0	816.1	1554	TINTING WHITE	413.3	826.7
						0.0	0.0
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR			
3092	MED GRAY	Corvette	15BN	3099	DK CARMINE	Corvette	74CN
1554	TINTING WHITE	276.5	552.9	1552	FAST RED	310.0	620.0
1501	LANDAU BLACK	365.5	730.9	1551	INDO YELLOW	393.6	787.2
1551	INDO YELLOW	404.5	809.0	1554	TINTING WHITE	402.3	804.7
1552	FAST RED	425.3	850.6	1553	FAST BLUE	404.6	809.2
						0.0	0.0
3093	MED BLUE MET	Corvette	28BM	3903	Charcoal Trim Metalli		
1553	FAST BLUE	132.0	263.9	1501	LANDAU BLACK	266.6	533.2
1508	SILVER	263.9	527.8	1508	SILVER	350.3	700.6
1552	FAST RED	379.1	758.3	1553	FAST BLUE	375.9	751.8
1501	LANDAU BLACK	397.8	795.5	1302	LOW LUSTER CLEAR	395.7	791.3
1551	INDO YELLOW	405.2	810.4	1557	MAGENTA	415.3	830.5
MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR				MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR			
3094	MED BLUE	Corvette	28BN	3929	Honda Black	Honda	
1501	LANDAU BLACK	85.3	170.6	1302	LOW LUSTER CLEAR	128.9	257.7
1551	INDO YELLOW	96.9	193.8	1559	YELLOW OXIDE	233.1	466.1
1552	FAST RED	174.9	349.8	1557	MAGENTA	301.3	602.6
1553	FAST BLUE	256.5	513.0	1553	FAST BLUE	355.2	710.4
1554	TINTING WHITE	416.1	832.2	1501	LANDAU BLACK	405.0	810.1
				1552	FAST RED	415.2	830.4
3095	LT SADDLE	Corvette	62AN	4001	CHARCOAL	Ford Motor	P
1559	YELLOW OXIDE	229.1	458.3	1501	LANDAU BLACK	167.6	335.2
1554	TINTING WHITE	373.2	746.3	1554	TINTING WHITE	289.3	578.6
1550	RED OXIDE	410.2	820.4	1552	FAST RED	352.1	704.1
1501	LANDAU BLACK	420.9	841.9	1551	INDO YELLOW	408.3	816.6
				1553	FAST BLUE	413.7	827.5

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 38

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4002	CANYON RED	Ford Motor	D	4009	BLUE	Mercedes Benz	252
1552	FAST RED	305.3	610.7	1302	LOW LUSTER CLEAR	132.1	264.1
1551	INDO YELLOW	384.8	769.7	1553	FAST BLUE	230.7	461.3
1554	TINTING WHITE	398.5	797.1	1501	LANDAU BLACK	325.9	651.7
1501	LANDAU BLACK	405.1	810.2	1550	RED OXIDE	372.9	745.8
		0.0	0.0	1554	TINTING WHITE	406.7	813.4
4003	WHITE TEXTURE	American Moto	83J134	4010	DK BROWN	Mercedes Benz	253
1554	TINTING WHITE	423.6	847.2	1302	LOW LUSTER CLEAR	135.8	271.5
1559	YELLOW OXIDE	432.3	864.7	1501	LANDAU BLACK	254.3	508.6
1550	RED OXIDE	434.8	869.6	1559	YELLOW OXIDE	331.2	662.3
1556	FAST GREEN	436.5	873.1	1550	RED OXIDE	402.8	805.6
		0.0	0.0	1554	TINTING WHITE	407.3	814.5
4004	NUTMEG TEXTURE	American Moto	83J135	4011	PALOMINO	Mercedes Benz	254
1551	INDO YELLOW	159.4	318.8	1559	YELLOW OXIDE	191.3	382.7
1552	FAST RED	317.1	634.2	1302	LOW LUSTER CLEAR	328.6	657.2
1554	TINTING WHITE	390.6	781.3	1554	TINTING WHITE	373.1	746.1
1501	LANDAU BLACK	409.5	819.1	1550	RED OXIDE	404.9	809.8
		0.0	0.0	1501	LANDAU BLACK	411.4	822.9
4005	BLUE TEXTURE	American Moto	82J154	4012	BEIGE	Mercedes Benz	255
1554	TINTING WHITE	189.9	379.8	1302	LOW LUSTER CLEAR	138.5	277.0
1501	LANDAU BLACK	345.8	691.6	1554	TINTING WHITE	271.2	542.5
1553	FAST BLUE	408.6	817.2	1559	YELLOW OXIDE	399.3	798.6
1556	FAST GREEN	418.8	837.5	1501	LANDAU BLACK	407.8	815.7
		0.0	0.0	1550	RED OXIDE	416.2	832.4
4006	TOBACCO	Mercedes Benz	203	4013	DK GREEN	Mercedes Benz	256
1559	YELLOW OXIDE	160.6	321.3	1551	INDO YELLOW	202.7	405.5
1302	LOW LUSTER CLEAR	297.3	594.5	1501	LANDAU BLACK	347.4	694.8
1550	RED OXIDE	372.1	744.2	1554	TINTING WHITE	409.2	818.3
1501	LANDAU BLACK	393.4	786.8				
1554	TINTING WHITE	409.8	819.7				
4007	BAMBOO	Mercedes Benz	204	MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR			
1559	YELLOW OXIDE	215.4	430.7	4014	HENNA RED	Mercedes Benz	257
1302	LOW LUSTER CLEAR	352.1	704.1	1302	LOW LUSTER CLEAR	135.4	270.8
1550	RED OXIDE	386.9	773.9	1559	YELLOW OXIDE	262.4	524.8
1554	TINTING WHITE	404.9	809.8	1552	FAST RED	389.1	778.2
1501	LANDAU BLACK	410.0	820.0	1501	LANDAU BLACK	404.0	808.1
				1554	TINTING WHITE	406.2	812.4
4008	PARCHMENT	Mercedes Benz	205	4015	GREY	Mercedes Benz	258
1554	TINTING WHITE	263.7	527.4	1554	TINTING WHITE	267.0	533.9
1559	YELLOW OXIDE	405.3	810.5	1552	FAST RED	326.4	652.8
1501	LANDAU BLACK	418.1	836.2	1501	LANDAU BLACK	370.3	740.6
1550	RED OXIDE	427.5	855.0	1551	INDO YELLOW	406.1	812.3
		0.0	0.0	1553	FAST BLUE	424.4	848.7

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 39

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4016	MED BLUE	Chrysler Motors	B5	4023	SABLE MET	Chrysler Motors	T6
1554	TINTING WHITE	165.9	331.7	1552	FAST RED	171.4	342.8
1550	RED OXIDE	289.8	579.7	1501	LANDAU BLACK	276.5	552.9
1553	FAST BLUE	378.4	756.8	1551	INDO YELLOW	365.2	730.4
1559	YELLOW OXIDE	420.3	840.6	1508	SILVER	404.8	809.6
4017	DK BLUE	Chrysler Motors	C7	4024	DK BLUE MET	Ford Motor	B
1501	LANDAU BLACK	180.7	361.4	1553	FAST BLUE	227.1	454.3
1553	FAST BLUE	337.5	675.1	1552	FAST RED	313.3	626.6
1554	TINTING WHITE	382.8	765.5	1501	LANDAU BLACK	375.0	749.9
1550	RED OXIDE	407.8	815.7	1508	SILVER	395.9	791.7
				1551	INDO YELLOW	403.6	807.1
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR							
4018	SADDLE TAN	Chrysler Motors	K5	4025	MIDNITE CANYON	Ford Motor	D
1551	INDO YELLOW	193.7	387.4	1552	FAST RED	393.1	786.2
1550	RED OXIDE	352.9	705.9	1553	FAST BLUE	399.7	799.3
1554	TINTING WHITE	396.9	793.8	1554	TINTING WHITE	404.4	808.8
1501	LANDAU BLACK	411.3	822.5				
4019	RED	Chrysler Motors	M5	4026	MED SAGE MET	Ford Motor	G
1552	FAST RED	361.8	723.5	1501	LANDAU BLACK	235.0	470.1
1551	INDO YELLOW	391.9	783.8	1508	SILVER	329.1	658.2
1554	TINTING WHITE	400.5	801.0	1551	INDO YELLOW	397.8	795.5
1553	FAST BLUE	404.6	809.2	1556	FAST GREEN	405.7	811.5
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR							
4020	CHARCOAL	Chrysler Motors	S8	4027	LT WHEAT	Ford Motor	Y
1501	LANDAU BLACK	204.7	409.5	1554	TINTING WHITE	337.2	674.3
1554	TINTING WHITE	337.2	674.3	1559	YELLOW OXIDE	428.4	856.7
1551	INDO YELLOW	384.3	768.6	1550	RED OXIDE	430.5	861.1
1552	FAST RED	414.7	829.4	1501	LANDAU BLACK	431.9	863.7
4021	CHARCOAL	Chrysler Motors	A9	4028	DK WALNUT MET	Ford Motor	Z
1508	SILVER	179.0	358.0	1552	FAST RED	242.0	483.9
1501	LANDAU BLACK	337.6	675.3	1551	INDO YELLOW	325.3	650.6
1553	FAST BLUE	376.2	752.4	1501	LANDAU BLACK	391.9	783.8
1552	FAST RED	406.4	812.8	1508	SILVER	404.3	808.6
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR			
4022	SLATE BLUE MET	Chrysler Motors	C6	4029	LT SLATE GRAY	General Motors	13
1553	FAST BLUE	145.3	290.5	1554	TINTING WHITE	238.3	476.5
1501	LANDAU BLACK	275.1	550.2	1302	LOW LUSTER CLEAR	378.8	757.5
1508	SILVER	374.0	748.0	1501	LANDAU BLACK	399.0	798.0
1552	FAST RED	404.9	809.8	1559	YELLOW OXIDE	418.4	836.8
				1550	RED OXIDE	421.7	843.4
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR							

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 40

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4030	VERY DK ROYAL B	General Motors	22
1553	FAST BLUE	244.6	489.3
1501	LANDAU BLACK	393.2	786.4
1554	TINTING WHITE	404.2	808.5

4037	SILVER MET	General Motors	13T
1508	SILVER	408.9	817.8

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4031	MED WAXBERRY	General Motors	45
1554	TINTING WHITE	228.1	456.2
1552	FAST RED	313.7	627.4
1551	INDO YELLOW	394.7	789.5
1556	FAST GREEN	421.4	842.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4038	PASTEL SANDSTON	General Motors	63T
1554	TINTING WHITE	278.4	556.9
1559	YELLOW OXIDE	392.8	785.7
1550	RED OXIDE	416.0	832.0
1501	LANDAU BLACK	428.5	856.9

4032	MED DK DOESKIN	General Motors	64
1551	INDO YELLOW	189.1	378.1
1552	FAST RED	340.7	681.3
1501	LANDAU BLACK	378.6	757.2
1554	TINTING WHITE	406.2	812.4

4039	DK SANDSTONE ME	General Motors	68T
1552	FAST RED	153.0	306.1
1551	INDO YELLOW	274.5	548.9
1508	SILVER	346.8	693.7
1501	LANDAU BLACK	405.0	810.0

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4033	MED BEIGE	General Motors	69
1554	TINTING WHITE	185.0	369.9
1559	YELLOW OXIDE	355.5	711.0
1550	RED OXIDE	395.8	791.5
1501	LANDAU BLACK	422.9	845.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4040	GUNMETAL MET	General Motors	84T
1501	LANDAU BLACK	195.5	391.0
1508	SILVER	377.9	755.8
1553	FAST BLUE	402.2	804.5
1552	FAST RED	406.6	813.2

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4034	DK BEIGE	General Motors	69
1559	YELLOW OXIDE	195.4	390.8
1501	LANDAU BLACK	327.5	654.9
1550	RED OXIDE	400.2	800.5
1554	TINTING WHITE	411.4	822.7

4041	VERY LT GRAYFER	General Motors	97T
1508	SILVER	380.4	760.8
1501	LANDAU BLACK	396.1	792.1
1551	INDO YELLOW	405.1	810.2
1556	FAST GREEN	408.6	817.2

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4035	MED DK GRAY	General Motors	82
1554	TINTING WHITE	212.9	425.8
1501	LANDAU BLACK	337.4	674.9
1559	YELLOW OXIDE	421.1	842.3
1553	FAST BLUE	422.4	844.7

4042	MED DK WAXBERR	General Motors	45
1559	YELLOW OXIDE	261.3	522.7
1501	LANDAU BLACK	328.1	656.3
1554	TINTING WHITE	387.9	775.8
1550	RED OXIDE	415.2	830.5

4036	BLACK CHERRY	General Motors	99
1552	FAST RED	310.4	620.7
1553	FAST BLUE	375.0	749.9
1551	INDO YELLOW	400.6	801.2
1554	TINTING WHITE	403.9	807.9

4043	BLACK CHERRY M	General Motors	99T
1552	FAST RED	305.6	611.2
1553	FAST BLUE	369.6	739.3
1551	INDO YELLOW	395.3	790.6
1508	SILVER	403.8	807.7

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 41

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

		General Motors			General Motors	
4044	LT SANDSTONE ME		96T	4051	VERY DK MAPLE	77EN
1508	SILVER	213.8	427.5	1552	FAST RED	329.9 659.9
1552	FAST RED	299.5	599.1	1553	FAST BLUE	377.8 755.6
1551	INDO YELLOW	362.6	725.2	1551	INDO YELLOW	401.0 802.0
1501	LANDAU BLACK	406.8	813.6	1554	TINTING WHITE	404.0 808.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

		General Motors			General Motors	
4045	DK CRIMSON MAPL		98T	4052	MED DK GRAY	82CN
1552	FAST RED	305.8	611.6	1554	TINTING WHITE	211.1 422.2
1551	INDO YELLOW	342.4	684.8	1501	LANDAU BLACK	335.8 671.7
1508	SILVER	373.6	747.3	1559	YELLOW OXIDE	418.1 836.2
1501	LANDAU BLACK	404.4	808.8	1550	RED OXIDE	422.4 844.7

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

		General Motors			General Motors	
4046	LT SADDLE		62AN	4053	HONEY	84P5
1559	YELLOW OXIDE	195.2	390.5	1559	YELLOW OXIDE	285.9 571.7
1554	TINTING WHITE	346.9	693.9	1550	RED OXIDE	348.7 697.5
1550	RED OXIDE	411.5	823.1	1554	TINTING WHITE	405.4 810.7
1556	FAST GREEN	421.4	842.8	1501	LANDAU BLACK	416.2 832.4

		General Motors			American Moto	
4047	MED SADDLE		62BN	4054	ALMOND	83P24
1559	YELLOW OXIDE	167.8	335.5	1554	TINTING WHITE	255.2 510.3
1302	LOW LUSTER CLEAR	304.8	609.5	1559	YELLOW OXIDE	396.0 791.9
1550	RED OXIDE	350.6	701.3	1550	RED OXIDE	416.9 833.7
1554	TINTING WHITE	395.2	790.4	1501	LANDAU BLACK	427.1 854.2
1501	LANDAU BLACK	411.4	822.7			

		General Motors			American Moto	
4048	DK SADDLE			4055	DK BLUE	82P46
1551	INDO YELLOW	179.2	358.3	1553	FAST BLUE	179.9 359.9
1552	FAST RED	343.8	687.6	1501	LANDAU BLACK	326.7 653.4
1501	LANDAU BLACK	383.7	767.4	1550	RED OXIDE	378.8 757.5
1554	TINTING WHITE	405.7	811.5	1554	TINTING WHITE	407.2 814.3

		General Motors			American Moto	
4049	VERY DK SADDLE		62EN	4056	GARNET MET	84P60
1501	LANDAU BLACK	144.2	288.4	1552	FAST RED	348.2 696.4
1551	INDO YELLOW	282.4	564.9	1551	INDO YELLOW	375.3 750.5
1550	RED OXIDE	402.8	805.6	1508	SILVER	397.6 795.2
1554	TINTING WHITE	407.7	815.5	1553	FAST BLUE	404.2 808.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

		General Motors			American Moto	
4050	VERY DK BRONZE		76EN	4057	ALMOND	84P68
1501	LANDAU BLACK	249.6	499.1	1554	TINTING WHITE	330.1 660.3
1553	FAST BLUE	335.4	670.7	1559	YELLOW OXIDE	419.6 839.2
1550	RED OXIDE	405.5	810.9	1550	RED OXIDE	426.4 852.7
1554	TINTING WHITE	406.1	812.3	1501	LANDAU BLACK	431.4 862.8

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 42

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4058	SAGE GREEN	Ford Motor	G
1554	TINTING WHITE	210.6	421.2
1559	YELLOW OXIDE	373.4	746.7
1501	LANDAU BLACK	417.4	834.9
1556	FAST GREEN	423.8	847.6

4065	GRAPHITE	General Motors	82DN
1501	LANDAU BLACK	226.7	453.3
1554	TINTING WHITE	296.6	593.2
1551	INDO YELLOW	353.4	706.8
1552	FAST RED	409.9	819.9

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4059	WHITE	Ford Motor	W
1554	TINTING WHITE	432.3	864.5
1559	YELLOW OXIDE	434.9	869.8
1501	LANDAU BLACK	437.1	874.2

4066	HONEY	American Moto	84P69
1551	INDO YELLOW	197.4	394.8
1552	FAST RED	324.9	649.8
1508	SILVER	397.2	794.4
1501	LANDAU BLACK	405.0	810.0

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4060	OXFORD GRAY	Ford Motor	P
1554	TINTING WHITE	334.5	669.0
1501	LANDAU BLACK	377.0	753.9
1559	YELLOW OXIDE	418.5	837.0
1550	RED OXIDE	430.9	861.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4067	BLUE GREEN MET	American Moto	82P47
1553	FAST BLUE	170.1	340.3
1556	FAST GREEN	329.4	658.7
1501	LANDAU BLACK	370.6	741.2
1508	SILVER	403.8	807.7

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4061	WHEAT	Ford Motor	Y
1559	YELLOW OXIDE	148.9	297.7
1302	LOW LUSTER CLEAR	287.4	574.8
1554	TINTING WHITE	403.0	806.0
1550	RED OXIDE	411.1	822.1
1501	LANDAU BLACK	415.4	830.9

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4068	LT DESERT TAN	Ford Motor	U
1554	TINTING WHITE	264.6	529.2
1559	YELLOW OXIDE	400.9	801.8
1550	RED OXIDE	423.5	847.0
1501	LANDAU BLACK	427.8	855.6

4062	MED RED MET	Ford Motor	D
1552	FAST RED	352.3	704.5
1508	SILVER	378.2	756.4
1551	INDO YELLOW	400.2	800.5
1501	LANDAU BLACK	404.3	808.6

4069	DK HONEY	American Moto	84P9
1559	YELLOW OXIDE	197.0	394.1
1302	LOW LUSTER CLEAR	333.5	666.9
1550	RED OXIDE	385.0	770.1
1554	TINTING WHITE	399.2	798.4
1501	LANDAU BLACK	409.8	819.7

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4063	LT SAGE MET	Ford Motor	G
1508	SILVER	302.7	605.3
1501	LANDAU BLACK	357.4	714.8
1551	INDO YELLOW	400.7	801.4
1556	FAST GREEN	407.8	815.7

4070	SADDLE	Ford Motor	Z
1302	LOW LUSTER CLEAR	199.1	398.2
1551	INDO YELLOW	303.4	606.9
1552	FAST RED	383.6	767.2
1554	TINTING WHITE	394.1	788.1
1501	LANDAU BLACK	403.5	806.9

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4064	DESERT TAN MET	Ford Motor	U
1552	FAST RED	165.3	330.6
1551	INDO YELLOW	313.1	626.2
1508	SILVER	376.1	752.2
1501	LANDAU BLACK	398.0	795.9
1554	TINTING WHITE	405.3	810.5

4071	CHARCOAL MDNIT	Ford Motor	B
1553	FAST BLUE	222.1	444.2
1501	LANDAU BLACK	366.4	732.8
1554	TINTING WHITE	406.6	813.2

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 43

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4072	NUTMEG	American Moto	81P24
1551	INDO YELLOW	219.4	438.7
1552	FAST RED	345.8	691.6
1554	TINTING WHITE	396.8	793.6
1501	LANDAU BLACK	407.9	815.9

4079	CHAMOIS	General Motors	52AM
1554	TINTING WHITE	218.8	437.6
1559	YELLOW OXIDE	405.1	810.2
1550	RED OXIDE	419.3	838.7
1501	LANDAU BLACK	425.3	850.6

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4073	WHEAT MET	Ford Motor	Y
1508	SILVER	257.6	515.3
1551	INDO YELLOW	332.1	664.2
1552	FAST RED	402.7	805.4
1501	LANDAU BLACK	407.1	814.2

4080	LT CHAMOIS	General Motors	52BN
1559	YELLOW OXIDE	240.8	481.7
1554	TINTING WHITE	384.6	769.1
1550	RED OXIDE	411.9	823.8
1501	LANDAU BLACK	421.0	842.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4074	MED DK ROYAL BL	General Motors	22
1554	TINTING WHITE	235.3	470.6
1501	LANDAU BLACK	312.9	625.9
1552	FAST RED	378.2	756.4
1553	FAST BLUE	419.7	839.4

4081	DK CHAMOIS	General Motors	52CN
1559	YELLOW OXIDE	213.8	427.5
1550	RED OXIDE	299.9	599.8
1554	TINTING WHITE	357.7	715.4
1501	LANDAU BLACK	415.4	830.9

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4075	DK BLUE	General Motors	27CN
1501	LANDAU BLACK	212.2	424.5
1553	FAST BLUE	301.1	602.1
1554	TINTING WHITE	361.4	722.8
1556	FAST GREEN	408.9	817.8

4082	LT SADDLE	General Motors	62AN
1559	YELLOW OXIDE	217.6	435.3
1554	TINTING WHITE	374.4	748.8
1550	RED OXIDE	410.9	821.8
1501	LANDAU BLACK	421.7	843.4

4076	MED SAGE	General Motors	43BN
1554	TINTING WHITE	235.2	470.4
1501	LANDAU BLACK	349.8	699.6
1551	INDO YELLOW	422.3	844.6

4083	DK BEIGE	General Motors	69CN
1559	YELLOW OXIDE	160.8	321.7
1302	LOW LUSTER CLEAR	243.6	487.2
1554	TINTING WHITE	312.5	624.9
1550	RED OXIDE	366.0	732.1
1501	LANDAU BLACK	413.7	827.5

4077	DK SAGE	General Motors	43CN
1554	TINTING WHITE	196.5	392.9
1501	LANDAU BLACK	333.7	667.5
1551	INDO YELLOW	419.3	838.7

4084	DK SADDLE	General Motors	62CN
1552	FAST RED	143.1	286.1
1551	INDO YELLOW	279.2	558.4
1554	TINTING WHITE	369.6	739.3
1501	LANDAU BLACK	411.0	821.9

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4078	MIDNIGHT SAGE	General Motors	49CN
1501	LANDAU BLACK	206.6	413.3
1551	INDO YELLOW	345.8	691.6
1554	TINTING WHITE	387.4	774.8
1556	FAST GREEN	407.6	815.3

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4085	RUSSET	General Motors	68CN
1550	RED OXIDE	255.4	510.7
1551	INDO YELLOW	368.3	736.6
1554	TINTING WHITE	391.0	782.0
1501	LANDAU BLACK	412.0	824.0

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 44

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	CARMINE	General Motors	72CN
1552	FAST RED	347.5	695.0
1550	RED OXIDE	394.9	789.8
1554	TINTING WHITE	404.0	808.1
1501	LANDAU BLACK	405.8	811.7

	LT SAGE GREEN M	General Motors	43T
1508	SILVER	315.0	630.0
1501	LANDAU BLACK	363.6	727.1
1551	INDO YELLOW	397.5	795.0
1556	FAST GREEN	407.9	815.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	DK CLARET	General Motors	79CN
1552	FAST RED	274.6	549.3
1302	LOW LUSTER CLEAR	355.5	711.0
1501	LANDAU BLACK	388.2	776.3
1559	YELLOW OXIDE	397.8	795.5
1554	TINTING WHITE	404.2	808.5

	MED SAGE	General Motors	47T
1552	FAST RED	115.4	230.9
1553	FAST BLUE	215.7	431.3
1551	INDO YELLOW	306.8	613.5
1508	SILVER	372.1	744.2
1501	LANDAU BLACK	404.4	808.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	GRAY	General Motors	12T
1554	TINTING WHITE	240.6	481.3
1302	LOW LUSTER CLEAR	386.7	773.3
1501	LANDAU BLACK	411.2	822.3
1551	INDO YELLOW	416.7	833.3
1552	FAST RED	421.3	842.7

	YELLOW BEIGE	General Motors	54T
1554	TINTING WHITE	403.9	807.9
1551	INDO YELLOW	428.7	857.5
1552	FAST RED	434.0	867.9
1501	LANDAU BLACK	434.8	869.6

	DK BLUE	General Motors	28T
1501	LANDAU BLACK	150.5	301.0
1302	LOW LUSTER CLEAR	285.4	570.8
1556	FAST GREEN	338.2	676.4
1553	FAST BLUE	387.8	775.6
1554	TINTING WHITE	404.5	809.0

	VRY DK SANDSTON	General Motors	57T
1552	FAST RED	242.8	485.6
1501	LANDAU BLACK	324.4	648.9
1551	INDO YELLOW	384.8	769.7
1508	SILVER	404.4	808.8

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	DK GRAY	General Motors	82DN
1554	TINTING WHITE	192.8	385.5
1501	LANDAU BLACK	385.0	770.1
1551	INDO YELLOW	414.2	828.4
1552	FAST RED	419.2	838.5

	LT SADDLE	General Motors	58T
1554	TINTING WHITE	224.3	448.6
1552	FAST RED	314.8	629.7
1551	INDO YELLOW	400.7	801.4
1556	FAST GREEN	421.1	842.3

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	DK BLUE MET	General Motors	31T
1553	FAST BLUE	242.9	485.8
1501	LANDAU BLACK	306.8	613.5
1552	FAST RED	360.0	719.9
1551	INDO YELLOW	388.1	776.2
1508	SILVER	403.4	806.7

	DK RED MET	General Motors	79T
1552	FAST RED	314.6	629.3
1553	FAST BLUE	371.1	742.1
1551	INDO YELLOW	395.0	790.0
1508	SILVER	403.8	807.7

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	LT BLUE MET	General Motors	34T
1508	SILVER	264.3	528.6
1553	FAST BLUE	349.5	699.0
1552	FAST RED	386.9	773.9
1551	INDO YELLOW	397.3	794.6
1554	TINTING WHITE	407.6	815.3

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	DK RED	General Motors	79T
1302	LOW LUSTER CLEAR	135.2	270.4
1552	FAST RED	259.2	518.3
1501	LANDAU BLACK	332.5	665.0
1550	RED OXIDE	396.7	793.4
1554	TINTING WHITE	405.6	811.1

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 45

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4100	HEATHER MET	General Motors	91T
1508	SILVER	281.2	562.4
1552	FAST RED	354.0	707.9
1501	LANDAU BLACK	407.6	815.1

4107	SABLE	Ford Motor	Z
1559	YELLOW OXIDE	134.2	268.5
1501	LANDAU BLACK	242.0	483.9
1302	LOW LUSTER CLEAR	323.5	647.0
1550	RED OXIDE	404.3	808.6
1554	TINTING WHITE	409.1	818.1

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4101	CANYON RED MET	General Motors	92T
1552	FAST RED	361.3	722.6
1553	FAST BLUE	381.5	763.0
1508	SILVER	401.8	803.5
1551	INDO YELLOW	404.2	808.5

4108	CANYON RED	Ford Motor	D
1552	FAST RED	315.6	631.2
1559	YELLOW OXIDE	389.4	778.8
1501	LANDAU BLACK	405.7	811.3

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4102	MED BLUE MET	General Motors	94T
1553	FAST BLUE	168.5	337.1
1552	FAST RED	325.9	651.9
1508	SILVER	375.0	749.9
1551	INDO YELLOW	403.9	807.9

4109	CHARCOAL	Ford Motor	P
1501	LANDAU BLACK	245.8	491.5
1554	TINTING WHITE	339.3	678.7
1550	RED OXIDE	377.1	754.1
1559	YELLOW OXIDE	413.5	827.1

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4103	DK GRAY FIREMIS	General Motors	97T
1501	LANDAU BLACK	265.6	531.2
1556	FAST GREEN	332.9	665.8
1553	FAST BLUE	380.7	761.3
1508	SILVER	404.8	809.6

4112	MED BLUE	American Moto	85P1
1554	TINTING WHITE	140.1	280.3
1553	FAST BLUE	244.9	489.8
1550	RED OXIDE	339.9	679.8
1559	YELLOW OXIDE	418.3	836.6

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4104	MED SLATE	General Motors	82BN
1554	TINTING WHITE	346.2	692.4
1501	LANDAU BLACK	405.1	810.2
1551	INDO YELLOW	418.1	836.2
1552	FAST RED	430.6	861.3

4113	DK GRAY MET	American Moto	85P5
1501	LANDAU BLACK	232.8	465.7
1508	SILVER	404.4	808.8
1551	INDO YELLOW	406.6	813.2

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4105	MED BLUE	General Motors	26AN
1501	LANDAU BLACK	136.6	273.2
1554	TINTING WHITE	264.6	529.2
1553	FAST BLUE	380.1	760.2
1556	FAST GREEN	413.7	827.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4114	DK VALUE MED BL	American Moto	85P2
1554	TINTING WHITE	126.4	252.7
1553	FAST BLUE	245.4	490.8
1552	FAST RED	357.6	715.2
1551	INDO YELLOW	398.7	797.4
1501	LANDAU BLACK	413.3	826.5

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4106	MULBERRY	Ford Motor	F
1550	RED OXIDE	273.9	547.8
1501	LANDAU BLACK	379.5	759.1
1559	YELLOW OXIDE	399.3	798.6
1554	TINTING WHITE	412.5	825.0

4115	DK HONEY TEXTU	American Moto	85J6
1559	YELLOW OXIDE	301.9	603.8
1550	RED OXIDE	380.4	760.8
1501	LANDAU BLACK	399.2	798.4
1554	TINTING WHITE	413.9	827.8

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 46

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4116	DK SILVER	Chrysler Motors	A7
1554	TINTING WHITE	251.8	503.5
1501	LANDAU BLACK	365.3	730.6
1551	INDO YELLOW	398.0	795.9
1552	FAST RED	423.5	847.0

4123	LT BLUE MET	Chrysler Motors	B1
1508	SILVER	364.6	729.2
1553	FAST BLUE	394.4	788.9
1501	LANDAU BLACK	408.2	816.4

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4117	RED	Chrysler Motors	M4
1552	FAST RED	362.5	725.0
1551	INDO YELLOW	391.4	782.8
1554	TINTING WHITE	399.9	799.7
1553	FAST BLUE	404.7	809.4

4124	GUNMETAL MET	Chrysler Motors	C6
1501	LANDAU BLACK	138.5	277.0
1553	FAST BLUE	263.4	526.9
1508	SILVER	356.3	712.7
1552	FAST RED	404.9	809.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4118	CRIMSON	Chrysler Motors	M6
1552	FAST RED	239.6	479.2
1302	LOW LUSTER CLEAR	378.1	756.2
1551	INDO YELLOW	392.3	784.5
1554	TINTING WHITE	400.0	800.1
1553	FAST BLUE	403.7	807.3

4125	CRIMSON RED	Chrysler Motors	M6
1552	FAST RED	365.0	730.0
1551	INDO YELLOW	389.9	779.8
1554	TINTING WHITE	398.7	797.4
1553	FAST BLUE	404.6	809.2

4119	TAN PRINT	Chrysler Motors	T3
1559	YELLOW OXIDE	248.6	497.2
1554	TINTING WHITE	391.2	782.4
1550	RED OXIDE	419.0	837.9
1501	LANDAU BLACK	421.0	842.1

4126	CREAM TAN	Chrysler Motors	T2
1554	TINTING WHITE	388.1	776.2
1551	INDO YELLOW	421.8	843.6
1552	FAST RED	432.3	864.5
1501	LANDAU BLACK	433.7	867.4

4120	LT PALOMINO	Chrysler Motors	DT3
1559	YELLOW OXIDE	239.0	478.0
1554	TINTING WHITE	389.5	779.0
1550	RED OXIDE	419.4	838.9
1501	LANDAU BLACK	421.5	843.0

4127	TAN MET	Chrysler Motors	T4
1508	SILVER	216.6	433.2
1551	INDO YELLOW	309.1	618.3
1552	FAST RED	392.4	784.9
1554	TINTING WHITE	402.1	804.3
1501	LANDAU BLACK	407.3	814.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4121	DK TAN PRINT	Chrysler Motors	T5
1559	YELLOW OXIDE	297.1	594.1
1550	RED OXIDE	355.1	710.2
1554	TINTING WHITE	407.3	814.5
1501	LANDAU BLACK	416.0	832.0

4128	TAN	Chrysler Motors	T5
1559	YELLOW OXIDE	273.2	546.4
1554	TINTING WHITE	350.3	700.5
1550	RED OXIDE	407.2	814.3
1501	LANDAU BLACK	417.4	834.9

4122	DK PALOMINO	Chrysler Motors	T5
1559	YELLOW OXIDE	297.8	595.7
1554	TINTING WHITE	353.0	706.0
1550	RED OXIDE	407.4	814.7
1501	LANDAU BLACK	416.3	832.6

4129	TAN	Chrysler Motors	T3
1559	YELLOW OXIDE	239.0	478.0
1554	TINTING WHITE	389.5	779.0
1550	RED OXIDE	419.4	838.9
1501	LANDAU BLACK	421.5	843.0

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 47

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
4130	REGATTA BLUE	Ford Motor		B	4137	LT CHARCOAL PRI	Ford Motor	P
1554	TINTING WHITE	139.5	278.9		1554	TINTING WHITE	363.2	726.4
1553	FAST BLUE	242.7	485.5		1501	LANDAU BLACK	403.6	807.1
1501	LANDAU BLACK	335.8	671.7		1552	FAST RED	419.7	839.4
1550	RED OXIDE	416.4	832.8		1551	INDO YELLOW	431.8	863.6
				MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR				
4131	DK BLUE	Ford Motor		B	4138	DK CHARCOAL	Ford Motor	P
1553	FAST BLUE	186.3	372.6		1501	LANDAU BLACK	198.5	396.9
1501	LANDAU BLACK	338.3	676.6		1553	FAST BLUE	353.0	706.0
1550	RED OXIDE	377.5	755.1		1554	TINTING WHITE	385.6	771.2
1554	TINTING WHITE	407.0	814.0		1552	FAST RED	406.4	812.8
				MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR				
4132	PASTEL REGATTA	Ford Motor		5	4139	SAND BEIGE PRINT	Ford Motor	T
1554	TINTING WHITE	309.8	619.6		1554	TINTING WHITE	322.7	645.4
1501	LANDAU BLACK	398.8	797.6		1559	YELLOW OXIDE	408.1	816.2
1553	FAST BLUE	417.4	834.9		1550	RED OXIDE	423.0	846.1
1550	RED OXIDE	428.1	856.1		1501	LANDAU BLACK	430.9	861.8
				MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR				
4133	SAND BEIGE	Ford Motor		T	4140	MED SAND BEIGE P	Ford Motor	T
1554	TINTING WHITE	164.7	329.5		1559	YELLOW OXIDE	246.2	492.5
1559	YELLOW OXIDE	299.7	599.5		1550	RED OXIDE	321.6	643.2
1302	LOW LUSTER CLEAR	383.1	766.3		1554	TINTING WHITE	378.5	757.0
1550	RED OXIDE	405.0	810.0		1501	LANDAU BLACK	415.7	831.4
1501	LANDAU BLACK	419.7	839.4					
				MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR				
4134	CARMEL	Ford Motor		T	4141	MED CANYON RED	Ford Motor	D
1551	INDO YELLOW	231.5	463.0		1552	FAST RED	357.3	714.6
1554	TINTING WHITE	318.7	637.5		1508	SILVER	379.8	759.6
1552	FAST RED	400.9	801.8		1551	INDO YELLOW	401.9	803.7
1501	LANDAU BLACK	410.6	821.2		1553	FAST BLUE	404.2	808.5
				MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR				
4135	MED SAGE	Ford Motor		G	4142	DK ROSEWOOD	Ford Motor	F
1559	YELLOW OXIDE	176.6	353.2		1550	RED OXIDE	204.6	409.3
1501	LANDAU BLACK	343.4	686.9		1501	LANDAU BLACK	371.8	743.7
1302	LOW LUSTER CLEAR	380.5	761.0		1553	FAST BLUE	391.6	783.2
1556	FAST GREEN	402.0	804.1		1554	TINTING WHITE	410.9	821.8
1554	TINTING WHITE	408.6	817.2					
				MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR				
4136	DK SLATE PRINT	Ford Motor		K	4143	BLUE	Ford Motor	B
1501	LANDAU BLACK	199.4	398.8		1302	LOW LUSTER CLEAR	135.0	270.0
1553	FAST BLUE	301.8	603.6		1501	LANDAU BLACK	243.0	486.0
1551	INDO YELLOW	370.3	740.6		1553	FAST BLUE	348.6	697.1
1554	TINTING WHITE	406.9	813.8		1552	FAST RED	377.8	755.6
					1554	TINTING WHITE	405.1	810.2

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 48

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
4144	SAND BEIGE	Ford Motor		U	4151	DK TAN	American Moto	86P84
1302	LOW LUSTER CLEAR	138.0	276.1		1559	YELLOW OXIDE	257.5	515.1
1559	YELLOW OXIDE	271.0	542.1		1554	TINTING WHITE	355.0	710.0
1554	TINTING WHITE	366.4	732.8		1550	RED OXIDE	404.6	809.2
1550	RED OXIDE	400.6	801.2		1501	LANDAU BLACK	418.5	837.0
1501	LANDAU BLACK	414.1	828.2					
4145	MED TEAL BLUE	General Motors		26BN	4152	DK PEWTER	American Moto	86P147
1554	TINTING WHITE	156.0	312.0		1559	YELLOW OXIDE	175.6	351.1
1501	LANDAU BLACK	299.1	598.1		1501	LANDAU BLACK	344.9	689.7
1553	FAST BLUE	397.7	795.3		1554	TINTING WHITE	401.2	802.4
1551	INDO YELLOW	415.2	830.5		1550	RED OXIDE	413.0	825.9
4146	DK TEAL BLUE	General Motors		27CN	4153	BEIGE	American Moto	
1302	LOW LUSTER CLEAR	152.9	305.7		1554	TINTING WHITE	416.9	833.7
1553	FAST BLUE	259.0	517.9		1551	INDO YELLOW	430.7	861.5
1501	LANDAU BLACK	349.1	698.3		1552	FAST RED	434.0	867.9
1554	TINTING WHITE	395.3	790.6		1501	LANDAU BLACK	435.8	871.5
1556	FAST GREEN	406.3	812.6					
4147	TAN	American Moto		86P1/86P4	4154	MED BLUE MET	American Moto	V519
1559	YELLOW OXIDE	211.4	422.8		1553	FAST BLUE	200.5	401.1
1554	TINTING WHITE	295.7	591.5		1508	SILVER	314.2	628.3
1302	LOW LUSTER CLEAR	378.8	757.5		1552	FAST RED	386.1	772.2
1550	RED OXIDE	407.3	814.5		1551	INDO YELLOW	404.6	809.2
1501	LANDAU BLACK	415.4	830.9					
4148	PEWTER	American Moto		86P2/86P93	4155	DK BLUE MET	American Moto	V520
1501	LANDAU BLACK	178.3	356.6		1553	FAST BLUE	197.4	394.8
1554	TINTING WHITE	287.3	574.6		1501	LANDAU BLACK	369.1	738.2
1551	INDO YELLOW	368.7	737.4		1508	SILVER	392.9	785.8
1552	FAST RED	412.7	825.4		1551	INDO YELLOW	403.9	807.9
4149	DEEP DK TAN	American Moto		86P5	4156	DK SILVER	Chrysler Motors	A7
1559	YELLOW OXIDE	262.7	525.4		1554	TINTING WHITE	164.0	327.9
1554	TINTING WHITE	342.5	685.0		1302	LOW LUSTER CLEAR	303.3	606.7
1550	RED OXIDE	397.8	795.5		1501	LANDAU BLACK	377.8	755.6
1501	LANDAU BLACK	417.2	834.5		1551	INDO YELLOW	397.1	794.2
					1552	FAST RED	415.8	831.6
4150	DK TAN	American Moto		86P6	4157	Twilight Blue	Chrysler Motors	FC5
1559	YELLOW OXIDE	185.8	371.6		1550	RED OXIDE	127.8	255.6
1302	LOW LUSTER CLEAR	322.9	645.8		1553	FAST BLUE	216.6	433.2
1554	TINTING WHITE	370.2	740.4		1554	TINTING WHITE	295.7	591.4
1550	RED OXIDE	402.5	805.0		1302	LOW LUSTER CLEAR	367.0	734.1
1501	LANDAU BLACK	411.5	823.1		1559	YELLOW OXIDE	423.4	846.8
					0			

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 49

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4158	DK BLUE	Chrysler Motors		C9	4165	ALMOND	
1553	FAST BLUE	199.2	398.4	1559	YELLOW OXIDE	155.6	311.2
1501	LANDAU BLACK	325.9	651.7	1302	LOW LUSTER CLEAR	293.6	587.3
1552	FAST RED	369.7	739.5	1554	TINTING WHITE	388.1	776.2
1554	TINTING WHITE	406.3	812.6	1550	RED OXIDE	409.4	818.7
				1501	LANDAU BLACK	414.3	828.6
4159	CORDOVAN	Chrysler Motors		E8	4166	TAUPE	
1552	FAST RED	263.4	526.9	1554	TINTING WHITE	158.1	316.2
1302	LOW LUSTER CLEAR	335.7	671.5	1552	FAST RED	277.4	554.8
1550	RED OXIDE	382.6	765.1	1501	LANDAU BLACK	347.0	694.1
1501	LANDAU BLACK	404.6	809.2	1551	INDO YELLOW	416.3	832.6
4160	ALMOND	Chrysler Motors		K1	4167	SMOKE	
1559	YELLOW OXIDE	155.6	311.2	1554	TINTING WHITE	243.4	486.8
1302	LOW LUSTER CLEAR	293.6	587.3	1501	LANDAU BLACK	350.1	700.2
1554	TINTING WHITE	388.1	776.2	1551	INDO YELLOW	388.6	777.1
1550	RED OXIDE	409.4	818.7	1552	FAST RED	422.8	845.7
1501	LANDAU BLACK	414.3	828.6				
4161	MED ALMOND	Chrysler Motors		K3	4168	CHESTNUT	
1559	YELLOW OXIDE	288.7	577.4	1559	YELLOW OXIDE	188.4	376.8
1554	TINTING WHITE	356.6	713.3	1302	LOW LUSTER CLEAR	270.9	541.9
1550	RED OXIDE	405.5	810.9	1554	TINTING WHITE	332.7	665.4
1501	LANDAU BLACK	416.9	833.7	1550	RED OXIDE	390.9	781.9
				1501	LANDAU BLACK	413.8	827.6
4162	RED	Chrysler Motors		M6	4169	MED REGATTA BL	
1552	FAST RED	367.7	735.5	1554	TINTING WHITE	202.7	405.5
1551	INDO YELLOW	393.0	786.0	1552	FAST RED	280.1	560.1
1554	TINTING WHITE	401.1	802.2	1553	FAST BLUE	342.0	684.0
1553	FAST BLUE	404.5	809.0	1501	LANDAU BLACK	403.9	807.9
				1551	INDO YELLOW	419.4	838.9
4163	CREAM	Chrysler Motors		Y1	MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR		
1554	TINTING WHITE	398.1	796.1	4170	DK TAUPE		F
1551	INDO YELLOW	420.6	841.1	1501	LANDAU BLACK	182.9	365.8
1552	FAST RED	432.3	864.5	1550	RED OXIDE	303.5	607.1
1501	LANDAU BLACK	434.4	868.9	1552	FAST RED	394.0	787.9
				1554	TINTING WHITE	408.6	817.2
4164	IVORY CREAM	Chrysler Motors		T1	4171	SMOKE	
1554	TINTING WHITE	422.6	845.1	1554	TINTING WHITE	244.4	488.9
1551	INDO YELLOW	432.6	865.3	1501	LANDAU BLACK	349.9	699.8
1552	FAST RED	436.2	872.5	1551	INDO YELLOW	388.6	777.1
				1552	FAST RED	423.0	846.1

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 50

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
4172	DK SABLE	Ford Motor		Z	4179	MED DRIFTWOOD	General Motors	60BN
1559	YELLOW OXIDE	165.7	331.4		1559	YELLOW OXIDE	223.6	447.3
1501	LANDAU BLACK	301.6	603.3		1554	TINTING WHITE	361.8	723.5
1550	RED OXIDE	395.7	791.4		1550	RED OXIDE	397.5	795.0
1554	TINTING WHITE	411.5	823.1		1501	LANDAU BLACK	420.5	840.9
4173	SILVER TEXTURE	American Moto		82J53	4180	DK DRIFTWOOD	General Motors	60CN
1554	TINTING WHITE	320.2	640.3		1559	YELLOW OXIDE	241.9	483.7
1501	LANDAU BLACK	385.7	771.4		1554	TINTING WHITE	317.0	634.0
1559	YELLOW OXIDE	416.2	832.4		1550	RED OXIDE	372.9	745.8
1550	RED OXIDE	429.6	859.2		1501	LANDAU BLACK	416.6	833.2
4174	MED EMERALD	General Motors		48BN	4181	MED LT SADDLE	General Motors	62BN
1554	TINTING WHITE	229.2	458.5		1559	YELLOW OXIDE	274.7	549.5
1501	LANDAU BLACK	305.2	610.5		1554	TINTING WHITE	339.9	679.8
1553	FAST BLUE	356.4	712.9		1550	RED OXIDE	397.0	794.0
1551	INDO YELLOW	401.2	802.4		1501	LANDAU BLACK	416.6	833.2
1552	FAST RED	421.5	843.0					
4175	DK EMERALD	General Motors		48DN	4182	DK SADDLE	General Motors	INSTRUMENT PANEL
1554	TINTING WHITE	162.5	324.9		1551	INDO YELLOW	143.5	286.9
1501	LANDAU BLACK	248.3	496.7		1552	FAST RED	277.2	554.4
1553	FAST BLUE	315.7	631.4		1554	TINTING WHITE	370.6	741.2
1551	INDO YELLOW	369.3	738.5		1501	LANDAU BLACK	411.3	822.5
1552	FAST RED	416.4	832.8					
MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR					MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR			
4176	DK YELLOW	General Motors		50BN	4183	VERY DK CARMINE	General Motors	INSTRUMENT PANEL
1554	TINTING WHITE	179.1	358.2		1552	FAST RED	248.8	497.6
1551	INDO YELLOW	301.4	602.9		1302	LOW LUSTER CLEAR	379.8	759.6
1552	FAST RED	394.3	788.5		1551	INDO YELLOW	391.1	782.2
1556	FAST GREEN	417.7	835.4		1553	FAST BLUE	399.3	798.6
					1554	TINTING WHITE	403.4	806.7
4177	VERY DK YELLOW	General Motors		50CN	4184	GARNET RED	General Motors	INSTRUMENT PANEL
1559	YELLOW OXIDE	255.5	510.9		1302	LOW LUSTER CLEAR	200.6	401.3
1302	LOW LUSTER CLEAR	337.7	675.5		1552	FAST RED	393.9	787.7
1550	RED OXIDE	373.3	746.5		1553	FAST BLUE	399.1	798.2
1501	LANDAU BLACK	401.1	802.2		1554	TINTING WHITE	402.9	805.8
1554	TINTING WHITE	410.7	821.4					
MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR					MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR			
4178	LT DRIFTWOOD	General Motors		60AN	4185	LT QUARTZ	General Motors	94BN
1554	TINTING WHITE	271.7	543.4		1554	TINTING WHITE	202.5	405.1
1559	YELLOW OXIDE	407.7	815.5		1550	RED OXIDE	308.8	617.5
1550	RED OXIDE	421.1	842.3		1559	YELLOW OXIDE	404.3	808.6
1501	LANDAU BLACK	428.1	856.1		1501	LANDAU BLACK	424.3	848.5

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 51

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4186	DK QUARTZ	General Motors	PANEL ONLY
1552	FAST RED	204.9	409.8
1302	LOW LUSTER CLEAR	330.4	660.8
1551	INDO YELLOW	363.6	727.1
1554	TINTING WHITE	386.6	773.1
1501	LANDAU BLACK	404.9	809.8

4193	HONEY	American Moto
1551	INDO YELLOW	207.7 415.3
1552	FAST RED	341.7 683.4
1508	SILVER	397.5 795.0
1556	FAST GREEN	404.3 808.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4187	MIDNITE WINE	Ford Motor	J
1552	FAST RED	321.8	643.5
1553	FAST BLUE	373.8	747.7
1551	INDO YELLOW	393.2	786.4
1554	TINTING WHITE	399.7	799.3
1501	LANDAU BLACK	404.3	808.6

4194	WARM GRAY	Chrysler Motors	A3
1554	TINTING WHITE	274.4	548.7
1302	LOW LUSTER CLEAR	359.0	718.0
1559	YELLOW OXIDE	401.0	802.0
1501	LANDAU BLACK	422.4	844.7
1550	RED OXIDE	425.4	850.8

4188	DEEP SHADOW BLU	Ford Motor	B
1501	LANDAU BLACK	249.6	499.1
1553	FAST BLUE	357.4	714.8
1554	TINTING WHITE	392.4	784.7
1556	FAST GREEN	406.9	813.8

4195	CORDOVAN	Chrysler Motors	E8
1552	FAST RED	263.4	526.9
1302	LOW LUSTER CLEAR	335.7	671.5
1550	RED OXIDE	382.6	765.1
1501	LANDAU BLACK	404.6	809.2

4189	GRAPHITE	Ford Motor	P
1501	LANDAU BLACK	311.3	622.6
1551	INDO YELLOW	355.8	711.6
1554	TINTING WHITE	388.6	777.1
1552	FAST RED	407.3	814.5

4196	ALMOND	Chrysler Motors	K1
1559	YELLOW OXIDE	155.6	311.2
1302	LOW LUSTER CLEAR	293.6	587.3
1554	TINTING WHITE	388.1	776.2
1550	RED OXIDE	409.4	818.7
1501	LANDAU BLACK	414.3	828.6

4190	MED SAND BEIGE	Ford Motor	T
1559	YELLOW OXIDE	191.9	383.8
1554	TINTING WHITE	382.9	765.9
1550	RED OXIDE	411.5	823.1
1501	LANDAU BLACK	423.5	847.0

4197	DK CORDOVAN	Chrysler Motors	E9
1552	FAST RED	377.3	754.7
1553	FAST BLUE	395.7	791.4
1508	SILVER	404.0	808.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4191	PASTEL CORDOVA	Chrysler Motors	E2
1508	SILVER	319.0	638.0
1552	FAST RED	378.6	757.2
1551	INDO YELLOW	399.9	799.7
1501	LANDAU BLACK	407.8	815.7

4198	BRONZE MET	Chrysler Motors	T5
1552	FAST RED	157.8	315.6
1551	INDO YELLOW	267.5	535.0
1501	LANDAU BLACK	336.5	673.0
1508	SILVER	405.0	810.0

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4192	GARNET	American Moto
1552	FAST RED	344.4 688.8
1551	INDO YELLOW	383.5 767.0
1508	SILVER	395.4 790.8
1553	FAST BLUE	404.1 808.3

4199	BUCKSKIN	Ford Motor	T
1559	YELLOW OXIDE	179.7	359.5
1302	LOW LUSTER CLEAR	262.4	524.8
1554	TINTING WHITE	323.2	646.4
1550	RED OXIDE	375.2	750.3
1501	LANDAU BLACK	413.4	826.9

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 52

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
4200	SHADOW BLUE	Ford Motor		B	4207	SUN GOLD	General Motors	38T
1553	FAST BLUE	241.2	482.4		1554	TINTING WHITE	405.8	811.7
1501	LANDAU BLACK	360.3	720.7		1551	INDO YELLOW	433.7	867.4
1554	TINTING WHITE	386.7	773.5		1501	LANDAU BLACK	435.0	870.0
1556	FAST GREEN	405.5	810.9					
4201	LT TAUPE	Ford Motor		F	4208	BLACK EMERALD	General Motors	87s ELK/TUX GR
1554	TINTING WHITE	190.0	380.0		1553	FAST BLUE	215.4	430.7
1559	YELLOW OXIDE	303.4	606.9		1501	LANDAU BLACK	308.2	616.4
1550	RED OXIDE	386.4	772.7		1551	INDO YELLOW	386.7	773.3
1501	LANDAU BLACK	423.2	846.5		1508	SILVER	403.6	807.1
MUST BE TOP COATED WITH 1301 SATIN GLOSS CLEAR								
4202	AEGEAN	Ford Motor		K	4209	CHAMOIS	General Motors	55T
1559	YELLOW OXIDE	140.9	281.8		1554	TINTING WHITE	362.6	725.2
1501	LANDAU BLACK	273.0	546.1		1551	INDO YELLOW	407.6	815.1
1554	TINTING WHITE	395.6	791.2		1552	FAST RED	427.4	854.8
1553	FAST BLUE	416.9	833.7		1501	LANDAU BLACK	431.7	863.4
MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR								
4203	DEEP SANDALWOO	Ford Motor		T	4210	LT CHESTNUT	General Motors	58T
1559	YELLOW OXIDE	176.6	353.2		1508	SILVER	263.0	525.9
1501	LANDAU BLACK	280.3	560.7		1552	FAST RED	321.7	643.3
1550	RED OXIDE	335.9	671.8		1551	INDO YELLOW	376.1	752.2
1554	TINTING WHITE	374.7	749.4		1554	TINTING WHITE	399.7	799.3
1302	LOW LUSTER CLEAR	412.3	824.6		1501	LANDAU BLACK	409.0	818.0
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR								
4204	DK DESERT TAN	Ford Motor		U	4211	LT DRIFTWOOD	General Motors	63T
1551	INDO YELLOW	148.9	297.7		1554	TINTING WHITE	306.6	613.1
1552	FAST RED	287.2	574.4		1559	YELLOW OXIDE	415.2	830.3
1554	TINTING WHITE	369.4	738.7		1550	RED OXIDE	422.8	845.7
1501	LANDAU BLACK	410.4	820.8		1501	LANDAU BLACK	430.0	859.9
4205	VERY DK EMERAL	General Motors		INSTRUMENT PANEL	4212	MED DRIFTWOOD	General Motors	65T
1501	LANDAU BLACK	175.0	350.0		1501	LANDAU BLACK	128.8	257.6
1556	FAST GREEN	319.8	639.5		1552	FAST RED	251.7	503.3
1554	TINTING WHITE	407.5	814.9		1508	SILVER	341.2	682.5
1551	INDO YELLOW	411.3	822.5		1551	INDO YELLOW	405.5	810.9
MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR								
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR								
4206	WHITE	General Motors		11T	4213	FLAME RED MET	General Motors	74T
1554	TINTING WHITE	423.7	847.4		1552	FAST RED	335.2	670.3
1559	YELLOW OXIDE	432.5	865.1		1551	INDO YELLOW	393.2	786.4
1550	RED OXIDE	435.6	871.2		1508	SILVER	400.0	800.1
1556	FAST GREEN	436.7	873.4		1501	LANDAU BLACK	404.0	808.1
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR								

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 53

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	DK CARMINE MET	General Motors	78T
1552	FAST RED	291.1	582.2
1501	LANDAU BLACK	362.0	724.1
1508	SILVER	384.9	769.9
1551	INDO YELLOW	404.3	808.6

	BRIGHT BLUE MET	Corvette	21CM
1508	SILVER	188.5	377.0
1553	FAST BLUE	364.4	728.8
1556	FAST GREEN	391.8	783.6
1501	LANDAU BLACK	405.5	810.9

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	MED QUARTZ	General Motors	86T
1552	FAST RED	323.2	646.4
1553	FAST BLUE	365.3	730.6
1551	INDO YELLOW	394.0	787.9
1508	SILVER	403.9	807.9

	FLAME RED	Corvette	73BN
1552	FAST RED	231.9	463.8
1302	LOW LUSTER CLEAR	312.8	625.7
1551	INDO YELLOW	386.9	773.9
1554	TINTING WHITE	399.3	798.6
1550	RED OXIDE	404.6	809.2

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	MED EMERALD	General Motors	92T
1553	FAST BLUE	277.0	554.0
1551	INDO YELLOW	356.0	711.9
1508	SILVER	393.9	787.7
1501	LANDAU BLACK	403.4	806.7

	SANDALWOOD	Ford Motor	T
1559	YELLOW OXIDE	186.8	373.5
1501	LANDAU BLACK	316.6	633.3
1550	RED OXIDE	381.1	762.3
1554	TINTING WHITE	412.4	824.8

	Med Emerald	General Motors	92T
1556	FAST GREEN	169.5	339.1
1508	SILVER	263.1	526.2
1501	LANDAU BLACK	344.4	688.7
1553	FAST BLUE	414.8	829.7

	CREAM BEIGE	Mercedes Benz	275
1554	TINTING WHITE	217.5	434.9
1559	YELLOW OXIDE	389.0	778.1
1550	RED OXIDE	410.8	821.6
1501	LANDAU BLACK	424.9	849.9

	SUNGOLD MET	General Motors	95T
1508	SILVER	232.3	464.6
1551	INDO YELLOW	324.9	649.8
1552	FAST RED	397.7	795.3
1556	FAST GREEN	406.7	813.4

	DK GREEN	Mercedes Benz	276
1551	INDO YELLOW	231.2	462.5
1501	LANDAU BLACK	347.9	695.8
1554	TINTING WHITE	381.0	762.1
1552	FAST RED	407.0	814.0

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	LT QUARTZ FIREM	General Motors	97T
1508	SILVER	215.2	430.4
1552	FAST RED	358.1	716.1
1501	LANDAU BLACK	390.3	780.5
1551	INDO YELLOW	406.6	813.2

	BURGUNDY	Mercedes Benz	277
1552	FAST RED	272.4	544.7
1559	YELLOW OXIDE	390.7	781.5
1553	FAST BLUE	404.1	808.3
1554	TINTING WHITE	406.8	813.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	CHAMOIS MET	General Motors	98T
1508	SILVER	250.2	500.5
1552	FAST RED	323.6	647.1
1551	INDO YELLOW	394.2	788.3
1556	FAST GREEN	407.0	814.0

	VRY DK CHESTNUT	General Motors	57T
1552	FAST RED	199.4	398.8
1551	INDO YELLOW	287.8	575.5
1501	LANDAU BLACK	373.4	746.9
1508	SILVER	404.6	809.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 54

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	DK CHESTNUT MET	General Motors	62T
1552	FAST RED	174.1	348.3
1551	INDO YELLOW	285.4	570.8
1508	SILVER	364.9	729.8
1501	LANDAU BLACK	405.0	810.0

	LT SAPPHIRE BLUE	General Motors	22T
1508	SILVER	266.4	532.8
1553	FAST BLUE	350.2	700.3
1552	FAST RED	381.0	761.9
1501	LANDAU BLACK	406.9	813.8

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	PEARL GRAY	General Motors	17T
1554	TINTING WHITE	358.8	717.6
1559	YELLOW OXIDE	404.2	808.5
1501	LANDAU BLACK	431.1	862.2
1553	FAST BLUE	432.4	864.9

	LT SAPPHIRE BLUE	General Motors	22T
1508	SILVER	318.3	636.7
1553	FAST BLUE	374.3	748.6
1552	FAST RED	401.7	803.3
1501	LANDAU BLACK	407.6	815.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	DK DRIFTWOOD M	General Motors	96T
1552	FAST RED	153.9	307.8
1501	LANDAU BLACK	266.1	532.2
1551	INDO YELLOW	369.4	738.7
1508	SILVER	404.8	809.6

	LT SAPPHIRE BLUE	General Motors	22T
1508	SILVER	308.7	617.3
1553	FAST BLUE	373.2	746.3
1552	FAST RED	402.6	805.2
1501	LANDAU BLACK	407.4	814.7

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	BLACK	General Motors	18T
1501	LANDAU BLACK	302.2	604.4
1553	FAST BLUE	404.3	808.6
		0.0	0.0

	BLACK SAPPHIRE	General Motors	28T
1553	FAST BLUE	207.7	415.3
1556	FAST GREEN	323.5	647.0
1501	LANDAU BLACK	395.4	790.8
1508	SILVER	403.4	806.7

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	MED GARNET RED	General Motors	72T
1552	FAST RED	387.5	775.0
1554	TINTING WHITE	394.2	788.3
1553	FAST BLUE	399.6	799.1
1501	LANDAU BLACK	404.5	809.0

	BLACK SAPPHIRE	General Motors	28T
1553	FAST BLUE	189.6	379.2
1556	FAST GREEN	326.8	653.6
1501	LANDAU BLACK	399.4	798.8
1508	SILVER	403.4	806.7

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	MED GARNET RED	General Motors	72T
1552	FAST RED	390.3	780.5
1508	SILVER	398.6	797.2
1553	FAST BLUE	404.0	808.1

	BLACK SAPPHIRE	General Motors	28T
1553	FAST BLUE	207.7	415.3
1556	FAST GREEN	323.5	647.0
1501	LANDAU BLACK	395.4	790.8
1508	SILVER	403.4	806.7

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	MED GARNET RED	General Motors	72T
1552	FAST RED	390.3	780.5
1508	SILVER	398.6	797.2
1553	FAST BLUE	404.0	808.1

	MED ROSEWOOD M	General Motors	82T
1552	FAST RED	242.3	484.7
1501	LANDAU BLACK	329.9	659.9
1508	SILVER	369.4	738.7
1551	INDO YELLOW	404.8	809.6

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 55

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	DK AMETHYST ME	General Motors	99T
1501	LANDAU BLACK	295.2	590.3
1552	FAST RED	356.6	713.3
1553	FAST BLUE	400.5	801.0
1554	TINTING WHITE	404.9	809.8

	DK GARNET RED M	General Motors	76T
1552	FAST RED	372.9	745.8
1553	FAST BLUE	397.7	795.3
1508	SILVER	403.8	807.7

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	DK AMETHYST ME	General Motors	99T
1501	LANDAU BLACK	329.9	659.9
1552	FAST RED	379.1	758.1
1554	TINTING WHITE	394.0	787.9
1551	INDO YELLOW	405.9	811.9

	DK GARNET RED M	General Motors	76T
1552	FAST RED	362.5	725.0
1553	FAST BLUE	396.7	793.4
1508	SILVER	403.9	807.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	LT DRIFTWOOD M	General Motors	33T
1508	SILVER	299.2	598.3
1552	FAST RED	348.9	697.9
1551	INDO YELLOW	392.2	784.3
1501	LANDAU BLACK	407.6	815.1

	MD SAPPHIRE BLU	General Motors	83T
1553	FAST BLUE	288.1	576.3
1501	LANDAU BLACK	357.0	714.0
1508	SILVER	403.6	807.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	LT DRIFTWOOD M	General Motors	33T
1508	SILVER	275.0	550.1
1552	FAST RED	343.2	686.5
1551	INDO YELLOW	391.6	783.2
1501	LANDAU BLACK	407.4	814.7

	MD SAPPHIRE BLU	General Motors	83T
1553	FAST BLUE	287.0	574.0
1501	LANDAU BLACK	348.4	696.7
1508	SILVER	403.7	807.3

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	LT AMETHYST ME	General Motors	91T
1552	FAST RED	159.9	319.8
1508	SILVER	286.4	572.9
1553	FAST BLUE	360.7	721.4
1501	LANDAU BLACK	405.4	810.7

	VERY DK DRIFTWO	General Motors	60DN
1552	FAST RED	130.9	261.8
1551	INDO YELLOW	244.8	489.6
1554	TINTING WHITE	328.1	656.3
1501	LANDAU BLACK	410.6	821.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	LT AMETHYST ME	General Motors	91T
1552	FAST RED	147.4	294.9
1508	SILVER	276.9	553.9
1553	FAST BLUE	343.8	687.6
1501	LANDAU BLACK	405.4	810.7

	VERY DK GARNET	General Motors	78DN
1552	FAST RED	363.1	726.2
1501	LANDAU BLACK	381.1	762.3
1553	FAST BLUE	397.6	795.2
1554	TINTING WHITE	404.5	809.0

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	DK GARNET RED M	General Motors	76T
1552	FAST RED	372.9	745.8
1553	FAST BLUE	397.7	795.3
1508	SILVER	403.8	807.7

	MED AMETHYST	General Motors	83BN
1554	TINTING WHITE	261.7	523.5
1501	LANDAU BLACK	357.0	714.0
1552	FAST RED	415.2	830.3
1553	FAST BLUE	424.1	848.2

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 56

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	DK AMETHYST	General Motors	83CN
1554	TINTING WHITE	165.8	331.6
1552	FAST RED	284.7	569.4
1501	LANDAU BLACK	384.3	768.6
1553	FAST BLUE	416.8	833.5

	DK SIENNA	General Motors	61CN
1552	FAST RED	158.1	316.2
1551	INDO YELLOW	315.7	631.4
1554	TINTING WHITE	379.0	757.9
1501	LANDAU BLACK	408.9	817.8

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	VERY DK SAPPHIR	General Motors	20DN
1501	LANDAU BLACK	197.6	395.2
1553	FAST BLUE	296.0	592.0
1554	TINTING WHITE	385.8	771.6
1552	FAST RED	411.0	821.9

	VERY DK COPPER	General Motors	67DN
1550	RED OXIDE	187.6	375.3
1501	LANDAU BLACK	343.0	686.1
1559	YELLOW OXIDE	396.4	792.9
1554	TINTING WHITE	411.4	822.7

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	MED SAPPHIRE	General Motors	20BN
1554	TINTING WHITE	156.2	312.4
1552	FAST RED	287.8	575.5
1553	FAST BLUE	376.9	753.7
1551	INDO YELLOW	415.5	831.1

	TAN PRINT	Chrysler Motors	T3
1554	TINTING WHITE	244.8	489.6
1551	INDO YELLOW	363.5	726.9
1552	FAST RED	416.3	832.6
1501	LANDAU BLACK	422.8	845.7

	DK ROSEWOOD	General Motors	75CN
1552	FAST RED	179.8	359.7
1554	TINTING WHITE	283.3	566.6
1501	LANDAU BLACK	352.3	704.5
1551	INDO YELLOW	412.1	824.2

	DK TAN	Chrysler Motors	T5
1551	INDO YELLOW	167.2	334.4
1554	TINTING WHITE	302.2	604.4
1552	FAST RED	397.9	795.7
1501	LANDAU BLACK	414.3	828.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	VERY DK ROSEWO	General Motors	75DN
1501	LANDAU BLACK	158.7	317.3
1550	RED OXIDE	313.3	626.6
1554	TINTING WHITE	380.6	761.1
1559	YELLOW OXIDE	414.1	828.2

	LT YELLOW	General Motors	50AN
1554	TINTING WHITE	344.3	688.6
1559	YELLOW OXIDE	428.0	856.0
1551	INDO YELLOW	430.5	861.1
1556	FAST GREEN	432.1	864.1

	LT PEARL GRAY	General Motors	13AN
1554	TINTING WHITE	408.3	816.6
1501	LANDAU BLACK	429.1	858.2
1551	INDO YELLOW	435.2	870.4

	TWILIGHT BLUE	Chrysler Motors	C7
1553	FAST BLUE	210.9	421.8
1552	FAST RED	292.8	585.6
1501	LANDAU BLACK	369.4	738.7
1508	SILVER	403.8	807.7

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	MED PEARL GRAY	General Motors	13BN
1554	TINTING WHITE	343.4	686.9
1501	LANDAU BLACK	415.2	830.5
1551	INDO YELLOW	427.3	854.6
1552	FAST RED	430.4	860.7

	CHARCOAL MET	Chrysler Motors	S8
1501	LANDAU BLACK	261.0	521.9
1508	SILVER	363.8	727.5
1553	FAST BLUE	405.7	811.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 57

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4272	TAN MET	Chrysler Motors	T4
1508	SILVER	229.2	458.5
1551	INDO YELLOW	327.5	654.9
1552	FAST RED	406.7	813.4

4279	FLASH RED	Chrysler Motors	R3
1552	FAST RED	252.1	504.3
1551	INDO YELLOW	380.3	760.6
1554	TINTING WHITE	405.5	810.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4273	MINK MET	Chrysler Motors	T6
1552	FAST RED	179.4	358.7
1551	INDO YELLOW	280.0	559.9
1501	LANDAU BLACK	374.5	749.0
1508	SILVER	404.6	809.2

4280	CORAL MET	Chrysler Motors	V7
1552	FAST RED	285.4	570.8
1501	LANDAU BLACK	336.7	673.4
1551	INDO YELLOW	382.6	765.1
1508	SILVER	404.3	808.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4274	TWILIGHT BLUE	Chrysler Motors	C4
1553	FAST BLUE	240.9	481.8
1501	LANDAU BLACK	363.2	726.4
1556	FAST GREEN	393.3	786.6
1554	TINTING WHITE	404.1	808.3

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4281	DK TAUPE	Ford Motor	F
1501	LANDAU BLACK	206.2	412.5
1550	RED OXIDE	371.6	743.3
1559	YELLOW OXIDE	399.4	798.8
1554	TINTING WHITE	410.0	820.0

4275	DK CORDOVAN	Chrysler Motors	E7
1552	FAST RED	383.6	767.2
1501	LANDAU BLACK	395.8	791.5
1553	FAST BLUE	400.2	800.5
1554	TINTING WHITE	404.3	808.6

4282	DRIFTWOOD	Ford Motor	T
1559	YELLOW OXIDE	191.8	383.6
1554	TINTING WHITE	356.4	712.9
1550	RED OXIDE	396.6	793.3
1501	LANDAU BLACK	421.9	843.8

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4276	SILVER	Chrysler Motors	A2
1508	SILVER	408.5	817.0
		0.0	0.0
	VERY CLOSE MATCH	0.0	0.0

4283	DK SHADOW BLUE	Ford Motor	B
1501	LANDAU BLACK	206.7	413.4
1553	FAST BLUE	389.9	779.8
1554	TINTING WHITE	404.9	809.8

4277	ICE BLUE MET	Chrysler Motors	B1
1508	SILVER	365.4	730.7
1553	FAST BLUE	392.7	785.5
1501	LANDAU BLACK	408.2	816.4

4284	MIDNITE CABERNE	Ford Motor	D
1552	FAST RED	331.7	663.5
1501	LANDAU BLACK	370.7	741.4
1559	YELLOW OXIDE	394.0	787.9
1554	TINTING WHITE	405.5	810.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4278	DK CORDOVAN	Chrysler Motors	E9
1552	FAST RED	382.0	764.0
1501	LANDAU BLACK	394.2	788.3
1553	FAST BLUE	401.0	802.0
1554	TINTING WHITE	404.2	808.5

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4285	MED SHADOW BLU	Ford Motor	B
1501	LANDAU BLACK	219.8	439.7
1553	FAST BLUE	329.7	659.5
1554	TINTING WHITE	373.0	745.9
1550	RED OXIDE	408.3	816.6

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 58

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
4286	CRYSTAL	Ford Motor		P	4293	CABERNET	Ford Motor	H
1554	TINTING WHITE	258.7	517.4		1552	FAST RED	343.0	685.9
1559	YELLOW OXIDE	353.0	706.0		1551	INDO YELLOW	371.0	742.0
1501	LANDAU BLACK	406.4	812.8		1553	FAST BLUE	396.6	793.3
1550	RED OXIDE	426.5	852.9		1554	TINTING WHITE	404.5	809.0
4287	LT SANDALWOOD	Ford Motor		Z	4294	LT ROSEWOOD ME	General Motors	85T
1554	TINTING WHITE	280.2	560.3		1552	FAST RED	220.0	440.0
1559	YELLOW OXIDE	386.7	773.5		1508	SILVER	313.0	626.1
1501	LANDAU BLACK	409.1	818.1		1551	INDO YELLOW	360.3	720.7
1550	RED OXIDE	428.3	856.5		1553	FAST BLUE	404.8	809.6
4288	WHITE	American Moto		87J63	4295	DK GRAY	Chrysler Motors	A7
1554	TINTING WHITE	430.7	861.5		1501	LANDAU BLACK	192.0	384.0
1552	FAST RED	433.4	866.8		1554	TINTING WHITE	305.6	611.2
1551	INDO YELLOW	435.6	871.2		1559	YELLOW OXIDE	402.4	804.8
1556	FAST GREEN	436.9	873.8		1550	RED OXIDE	415.5	831.1
4289	CORDOVAN	American Moto		87P1	4296	MED GRAY	Chrysler Motors	S7
1550	RED OXIDE	226.0	452.0		1501	LANDAU BLACK	163.1	326.2
1302	LOW LUSTER CLEAR	307.5	615.0		1559	YELLOW OXIDE	291.1	582.2
1553	FAST BLUE	377.4	754.9		1554	TINTING WHITE	397.7	795.3
1501	LANDAU BLACK	405.5	810.9		1552	FAST RED	415.4	830.9
1554	TINTING WHITE	409.1	818.1					
4290	SHADOW BLUE	Ford Motor		B	4297	SILVER	Chrysler Motors	A3
1553	FAST BLUE	204.5	409.1		1554	TINTING WHITE	348.9	697.9
1501	LANDAU BLACK	344.6	689.1		1559	YELLOW OXIDE	397.3	794.6
1556	FAST GREEN	384.8	769.7		1501	LANDAU BLACK	428.8	857.7
1554	TINTING WHITE	405.0	810.0		1550	RED OXIDE	431.9	863.7
4291	SCARLET	Ford Motor		D	4298	MED PRAIRIE MIST	Ford Motor	G
1552	FAST RED	341.1	682.1		1559	YELLOW OXIDE	191.9	383.8
1551	INDO YELLOW	389.3	778.6		1501	LANDAU BLACK	310.5	620.9
1554	TINTING WHITE	401.9	803.9		1554	TINTING WHITE	368.0	736.1
1553	FAST BLUE	404.9	809.8		1550	RED OXIDE	414.0	828.0
4292	Lt. Sandlewood	Ford Motor		Z(int)	4299	OYSTER WHITE	General Motors	12AN
1302	LOW LUSTER CLEAR	174.4	348.8		1554	TINTING WHITE	419.6	839.2
1554	TINTING WHITE	283.6	567.2		1551	INDO YELLOW	426.6	853.1
1559	YELLOW OXIDE	375.8	751.6		1501	LANDAU BLACK	432.3	864.7
1550	RED OXIDE	404.9	809.8		1552	FAST RED	436.0	871.9
1501	LANDAU BLACK	424.1	848.1					

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

No

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 59

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4300	DK COPPER	General Motors	67CN	4307	DK SMOKE	Ford Motor	P
1552	FAST RED	200.3	400.5	1501	LANDAU BLACK	145.8	291.7
1551	INDO YELLOW	367.8	735.7	1559	YELLOW OXIDE	265.3	530.7
1554	TINTING WHITE	395.0	790.0	1554	TINTING WHITE	381.0	762.1
1501	LANDAU BLACK	406.0	812.1	1550	RED OXIDE	416.7	833.3
4301	DK SMOKE	Ford Motor	P	4308	DK SHADOW BLUE	Ford Motor	B
1501	LANDAU BLACK	224.2	448.4	1553	FAST BLUE	208.4	416.9
1554	TINTING WHITE	300.6	601.2	1556	FAST GREEN	324.5	649.0
1551	INDO YELLOW	371.5	743.1	1501	LANDAU BLACK	396.5	793.1
1552	FAST RED	410.4	820.8	1508	SILVER	403.4	806.7
MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR			
4302	DK SCARLET	Ford Motor	D	4309	ISUZU BUMPER GR		
1552	FAST RED	227.9	455.8	1302	LOW LUSTER CLEAR	136.2	272.5
1302	LOW LUSTER CLEAR	362.1	724.3	1501	LANDAU BLACK	270.4	540.7
1551	INDO YELLOW	390.6	781.3	1554	TINTING WHITE	338.8	677.5
1501	LANDAU BLACK	398.7	797.4	1552	FAST RED	376.7	753.4
1554	TINTING WHITE	403.5	806.9	1551	INDO YELLOW	408.7	817.4
4303	DK TAUPE	Ford Motor	F	4310	MED BEECHWOOD	General Motors	66BN
1501	LANDAU BLACK	169.1	338.2	1559	YELLOW OXIDE	250.5	501.0
1550	RED OXIDE	293.6	587.3	1550	RED OXIDE	331.3	662.5
1302	LOW LUSTER CLEAR	348.0	696.0	1554	TINTING WHITE	402.7	805.4
1559	YELLOW OXIDE	398.0	795.9	1501	LANDAU BLACK	417.1	834.3
1554	TINTING WHITE	409.2	818.3				
4304	WHITE	Ford Motor	W	4311	VERY DK SIENNA	General Motors	61DN
1554	TINTING WHITE	432.4	864.9	1559	YELLOW OXIDE	148.7	297.4
1551	INDO YELLOW	435.5	871.0	1550	RED OXIDE	267.4	534.9
1552	FAST RED	436.3	872.7	1501	LANDAU BLACK	365.4	730.7
1501	LANDAU BLACK	437.0	874.0	1302	LOW LUSTER CLEAR	405.7	811.5
				1554	TINTING WHITE	410.5	821.0
4305	MED SMOKE	Ford Motor	P	4312	MED SMOKE GRAY	General Motors	90BN
1501	LANDAU BLACK	232.8	465.5	1554	TINTING WHITE	187.2	374.3
1559	YELLOW OXIDE	319.1	638.2	1559	YELLOW OXIDE	294.5	589.0
1554	TINTING WHITE	378.7	757.3	1501	LANDAU BLACK	359.9	719.7
1550	RED OXIDE	411.9	823.8	1550	RED OXIDE	422.4	844.7
4306	DK WALNUT MET	Ford Motor	Z	4313	MED COGNAC	General Motors	60BN
1552	FAST RED	231.5	463.0	1559	YELLOW OXIDE	304.4	608.8
1501	LANDAU BLACK	307.0	614.1	1550	RED OXIDE	371.2	742.3
1551	INDO YELLOW	376.2	752.4	1554	TINTING WHITE	404.2	808.5
1508	SILVER	404.5	809.0	1501	LANDAU BLACK	415.0	829.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 60

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4314	MED ANTELOPE	General Motors	65BN	4321	DK FOREST GREEN	Chrysler Motors	G7
1554	TINTING WHITE	205.0	410.0	1553	FAST BLUE	179.4	358.7
1559	YELLOW OXIDE	340.0	680.0	1556	FAST GREEN	297.6	595.3
1550	RED OXIDE	396.4	792.9	1501	LANDAU BLACK	386.7	773.5
1501	LANDAU BLACK	424.0	848.0	1508	SILVER	403.7	807.3
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR							
4315	DK ANTELOPE	General Motors	65CN	4322	BLACK CHERRY	Chrysler Motors	M9
1554	TINTING WHITE	126.6	253.3	1552	FAST RED	330.7	661.4
1552	FAST RED	251.4	502.7	1553	FAST BLUE	378.6	757.2
1551	INDO YELLOW	351.7	703.4	1551	INDO YELLOW	401.6	803.1
1501	LANDAU BLACK	413.8	827.6	1554	TINTING WHITE	403.9	807.9
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR							
4316	DK BROWNSTONE	American Moto	88P4	4323	WHITE	Chrysler Motors	W7
1559	YELLOW OXIDE	142.7	285.4	1554	TINTING WHITE	432.4	864.9
1302	LOW LUSTER CLEAR	225.4	450.9	1501	LANDAU BLACK	435.3	870.6
1554	TINTING WHITE	301.7	603.4	1559	YELLOW OXIDE	437.1	874.2
1501	LANDAU BLACK	365.8	731.5				
1550	RED OXIDE	413.7	827.5				
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR							
4317	NAVY	American Moto	88P5	4324	SILVER PENNY	Chrysler Motors	L2
1302	LOW LUSTER CLEAR	136.2	272.5	1508	SILVER	240.8	481.7
1501	LANDAU BLACK	260.5	521.0	1552	FAST RED	326.5	653.0
1554	TINTING WHITE	319.7	639.4	1501	LANDAU BLACK	364.6	729.2
1553	FAST BLUE	375.9	751.8	1551	INDO YELLOW	387.4	774.8
1550	RED OXIDE	408.4	816.8	1553	FAST BLUE	406.9	813.8
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR							
4318	WHITE TEXTURE			4325	WHITE	Chrysler Motors	W7
1554	TINTING WHITE	431.8	863.6	1554	TINTING WHITE	434.8	869.6
1559	YELLOW OXIDE	435.0	870.0	1501	LANDAU BLACK	436.4	872.9
1501	LANDAU BLACK	436.4	872.9	1559	YELLOW OXIDE	437.2	874.4
1552	FAST RED	437.0	874.0				
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR							
4319	GLAMOR RED	Chrysler Motors	M4	4326	TAUPE	Chrysler Motors	L5
1552	FAST RED	369.4	738.7	1501	LANDAU BLACK	115.2	230.5
1551	INDO YELLOW	390.4	780.7	1559	YELLOW OXIDE	217.3	434.5
1554	TINTING WHITE	398.6	797.2	1302	LOW LUSTER CLEAR	312.6	625.3
1553	FAST BLUE	404.7	809.4	1550	RED OXIDE	374.8	749.6
				1554	TINTING WHITE	410.2	820.4
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR							
4320	DK ANTIQUE PENN	Chrysler Motors	L8	4327	BLACK CHERRY	Chrysler Motors	M9
1501	LANDAU BLACK	182.8	365.6	1552	FAST RED	352.6	705.3
1552	FAST RED	341.4	682.9	1553	FAST BLUE	391.2	782.4
1508	SILVER	382.5	764.9	1501	LANDAU BLACK	401.5	802.9
1551	INDO YELLOW	405.0	810.0	1554	TINTING WHITE	404.0	808.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 61

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
4328	BRIGHT WHITE	Chrysler Motors		W7	4335	LT BEECHWOOD M	General Motors	62T
1554	TINTING WHITE	431.3	862.6		1552	FAST RED	146.2	292.4
1559	YELLOW OXIDE	434.8	869.6		1508	SILVER	275.1	550.2
1501	LANDAU BLACK	437.0	874.0		1551	INDO YELLOW	371.4	742.7
					1501	LANDAU BLACK	405.7	811.3
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR								
4329	BORDEAUX RED	Chrysler Motors		R9	4336	LT BEECHWOOD M	General Motors	62T
1552	FAST RED	386.3	772.5		1552	FAST RED	149.1	298.1
1553	FAST BLUE	398.5	797.1		1508	SILVER	280.4	560.9
1554	TINTING WHITE	404.4	808.8		1551	INDO YELLOW	378.5	757.0
					1501	LANDAU BLACK	405.6	811.1
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR								
4330	TAUPE	Chrysler Motors		L9	4337	ANTELOPE BEIGE	General Motors	86T
1559	YELLOW OXIDE	170.6	341.2		1554	TINTING WHITE	303.1	606.3
1302	LOW LUSTER CLEAR	253.1	506.2		1559	YELLOW OXIDE	378.0	756.0
1550	RED OXIDE	332.5	665.0		1550	RED OXIDE	415.2	830.3
1554	TINTING WHITE	379.0	757.9		1501	LANDAU BLACK	429.8	859.6
1501	LANDAU BLACK	413.0	825.9					
4331	CINNABAR	Ford Motor		F	4338	ANTELOPE BEIGE	General Motors	86T
1501	LANDAU BLACK	156.7	313.3		1554	TINTING WHITE	306.1	612.2
1550	RED OXIDE	289.2	578.4		1559	YELLOW OXIDE	378.6	757.2
1551	INDO YELLOW	384.4	768.7		1550	RED OXIDE	414.1	828.2
1554	TINTING WHITE	409.5	819.1		1501	LANDAU BLACK	429.9	859.8
4332	DK CABERNET	Ford Motor		D	4339	ANTELOPE BEIGE	General Motors	86T
1552	FAST RED	327.1	654.2		1554	TINTING WHITE	307.9	615.8
1551	INDO YELLOW	363.2	726.4		1559	YELLOW OXIDE	380.6	761.1
1501	LANDAU BLACK	398.0	795.9		1550	RED OXIDE	414.6	829.2
1554	TINTING WHITE	404.6	809.2		1501	LANDAU BLACK	430.1	860.1
4333	TWILIGHT BLUE	Ford Motor		B	4340	LT BEECHWOOD M	General Motors	57T
1553	FAST BLUE	170.2	340.5		1552	FAST RED	150.1	300.2
1552	FAST RED	298.8	597.6		1508	SILVER	279.0	558.0
1501	LANDAU BLACK	388.5	776.9		1551	INDO YELLOW	367.6	735.1
1554	TINTING WHITE	404.8	809.6		1501	LANDAU BLACK	405.7	811.3
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR								
4334	DK TITANIUM	Ford Motor		P	4342	DK SAPPHIRE BLUE	General Motors	29T
1559	YELLOW OXIDE	168.0	335.9		1553	FAST BLUE	302.2	604.4
1501	LANDAU BLACK	320.1	640.1		1501	LANDAU BLACK	374.6	749.2
1550	RED OXIDE	368.1	736.3		1508	SILVER	403.4	806.7
1554	TINTING WHITE	412.7	825.4					
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR								

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 62

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4343	LT ANTELOPE MET	General Motors	95T	4350	VERY DK COGNAC	General Motors	60DN
1508	SILVER	259.5	519.1	1559	YELLOW OXIDE	177.7	355.3
1552	FAST RED	355.3	710.6	1550	RED OXIDE	305.6	611.2
1551	INDO YELLOW	385.8	771.6	1501	LANDAU BLACK	405.6	811.1
1553	FAST BLUE	406.9	813.8	1554	TINTING WHITE	411.8	823.7

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4344	DK ANTELOPE MET	General Motors	67T	4351	VERY DK BLUE	General Motors	24DN
1552	FAST RED	239.3	478.6	1501	LANDAU BLACK	154.6	309.1
1551	INDO YELLOW	361.1	722.2	1553	FAST BLUE	294.8	589.6
1501	LANDAU BLACK	404.0	808.1	1556	FAST GREEN	366.2	732.5
				1554	TINTING WHITE	406.9	813.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4345	MED BEECHWOOD	General Motors	69T	4352	DK BLUE	General Motors	24CN
1552	FAST RED	204.9	409.8	1501	LANDAU BLACK	166.9	333.8
1551	INDO YELLOW	343.8	687.6	1553	FAST BLUE	277.8	555.6
1501	LANDAU BLACK	381.8	763.6	1554	TINTING WHITE	378.7	757.3
1508	SILVER	404.4	808.8	1556	FAST GREEN	411.7	823.5

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4346	COPPER BEIGE	General Motors	56T	4353	MED BEIGE	General Motors	69BN
1554	TINTING WHITE	344.0	688.0	1559	YELLOW OXIDE	179.7	359.5
1559	YELLOW OXIDE	420.8	841.5	1554	TINTING WHITE	351.4	702.8
1550	RED OXIDE	431.3	862.6	1550	RED OXIDE	394.7	789.5
1501	LANDAU BLACK	432.3	864.5	1501	LANDAU BLACK	422.2	844.4

4347	Titanium	Ford Motor	56T	4354	MED DK BEIGE	General Motors	69CN
1554	TINTING WHITE	166.1	332.3	1559	YELLOW OXIDE	207.5	415.0
1302	LOW LUSTER CLEAR	262.6	525.3	1554	TINTING WHITE	288.2	576.5
1559	YELLOW OXIDE	358.1	716.2	1550	RED OXIDE	355.8	711.6
1501	LANDAU BLACK	396.6	793.2	1501	LANDAU BLACK	416.7	833.3
1557	MAGENTA	418.2	836.4				

4348	SANDALWOOD	Ford Motor	Z	4355	DK ENGLISH SADD	General Motors	64CN
1559	YELLOW OXIDE	143.0	286.0	1551	INDO YELLOW	167.7	335.4
1501	LANDAU BLACK	257.0	514.0	1552	FAST RED	309.7	619.4
1302	LOW LUSTER CLEAR	332.2	664.4	1554	TINTING WHITE	370.7	741.4
1550	RED OXIDE	393.2	786.4	1501	LANDAU BLACK	408.7	817.4
1554	TINTING WHITE	409.7	819.5				

4349	DK COGNAC	General Motors	60CN	4356	MIDNIGHT BLUE	General Motors	23EN
1551	INDO YELLOW	208.6	417.2	1501	LANDAU BLACK	192.9	385.9
1552	FAST RED	337.9	675.8	1553	FAST BLUE	385.9	771.8
1554	TINTING WHITE	386.3	772.5	1554	TINTING WHITE	405.1	810.2
1501	LANDAU BLACK	407.7	815.5				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 63

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4357	MED ROSEWOOD M	General Motors	78T
1552	FAST RED	242.4	484.9
1501	LANDAU BLACK	329.7	659.5
1508	SILVER	369.4	738.7
1551	INDO YELLOW	404.7	809.4

4364	MED SANDALWOO	Ford Motor	Z
1559	YELLOW OXIDE	237.5	475.0
1501	LANDAU BLACK	309.4	618.8
1550	RED OXIDE	372.3	744.6
1554	TINTING WHITE	414.2	828.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4358	LT SAPPHIRE BLUE	General Motors	26T
1508	SILVER	259.9	519.8
1553	FAST BLUE	358.7	717.4
1552	FAST RED	395.8	791.5
1501	LANDAU BLACK	406.7	813.4

4365	MED TITANIUM BU	Ford Motor	P
1508	SILVER	289.4	578.7
1501	LANDAU BLACK	378.5	757.0
1552	FAST RED	391.2	782.4
1551	INDO YELLOW	401.6	803.1
1554	TINTING WHITE	408.1	816.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4359	CHARCOAL	American Moto	88P6
1554	TINTING WHITE	184.7	369.4
1302	LOW LUSTER CLEAR	268.3	536.6
1559	YELLOW OXIDE	339.6	679.3
1501	LANDAU BLACK	398.0	795.9
1550	RED OXIDE	419.8	839.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4366	DEEP SANDALWOO	Ford Motor	Z
1501	LANDAU BLACK	189.2	378.5
1559	YELLOW OXIDE	327.7	655.3
1550	RED OXIDE	393.4	786.8
1554	TINTING WHITE	410.5	821.0

4360	DK CHARCOAL	American Moto	88P7
1501	LANDAU BLACK	165.5	331.0
1554	TINTING WHITE	296.7	593.4
1559	YELLOW OXIDE	404.1	808.3
1550	RED OXIDE	417.2	834.5

4367	LT SANDALWOOD	Ford Motor	Z
1554	TINTING WHITE	210.7	421.4
1551	INDO YELLOW	302.2	604.4
1552	FAST RED	367.7	735.3
1501	LANDAU BLACK	420.1	840.2

4361	CINNABAR	Ford Motor	F
1550	RED OXIDE	128.9	257.8
1559	YELLOW OXIDE	226.4	452.8
1302	LOW LUSTER CLEAR	308.2	616.4
1501	LANDAU BLACK	367.3	734.5
1554	TINTING WHITE	412.4	824.8

4368	DK REGATTA BLUE	Ford Motor	B
1553	FAST BLUE	190.8	381.5
1501	LANDAU BLACK	340.9	681.7
1554	TINTING WHITE	381.1	762.3
1552	FAST RED	406.8	813.6

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4362	DK CINNABAR	Ford Motor	F
1550	RED OXIDE	120.1	240.2
1501	LANDAU BLACK	221.6	443.3
1559	YELLOW OXIDE	303.8	607.6
1302	LOW LUSTER CLEAR	386.0	772.0
1554	TINTING WHITE	410.3	820.6

4369	BRIGHT BLUE MET	Corvette	21CM
1508	SILVER	188.5	377.0
1553	FAST BLUE	364.4	728.8
1556	FAST GREEN	391.8	783.6
1501	LANDAU BLACK	405.5	810.9

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4363	DK TITANIUM	Ford Motor	P
1559	YELLOW OXIDE	106.0	212.0
1501	LANDAU BLACK	208.1	416.3
1302	LOW LUSTER CLEAR	290.6	581.2
1554	TINTING WHITE	369.9	739.9
1550	RED OXIDE	413.2	826.3

4370	TOAST	Chrysler Motors	K2
1559	YELLOW OXIDE	194.4	388.7
1554	TINTING WHITE	373.4	746.9
1550	RED OXIDE	409.4	818.7
1501	LANDAU BLACK	422.9	845.9

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 64

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4371	BUCKSKIN	Chrysler Motors	V6	4378	DK TAUPE	Chrysler Motors	V8
1554	TINTING WHITE	230.9	461.9	1559	YELLOW OXIDE	127.3	254.6
1559	YELLOW OXIDE	370.9	741.8	1501	LANDAU BLACK	224.1	448.2
1550	RED OXIDE	401.6	803.1	1302	LOW LUSTER CLEAR	306.2	612.4
1501	LANDAU BLACK	425.5	851.0	1550	RED OXIDE	378.7	757.3
				1554	TINTING WHITE	410.8	821.6
4372	LT BUCKSKIN	Chrysler Motors	K3	4379	NEUTRAL DK GRAY	Chrysler Motors	S5
1554	TINTING WHITE	196.4	392.7	1501	LANDAU BLACK	165.7	331.4
1559	YELLOW OXIDE	391.5	783.0	1559	YELLOW OXIDE	281.4	562.8
1550	RED OXIDE	411.3	822.5	1554	TINTING WHITE	359.5	719.0
1501	LANDAU BLACK	423.9	847.8	1550	RED OXIDE	414.3	828.6
4373	MED CURRANT RE	Ford Motor	A	4380	OXFORD WHITE	Ford Motor	P
1552	FAST RED	386.3	772.5	1554	TINTING WHITE	411.4	822.9
1553	FAST BLUE	398.5	797.1	1559	YELLOW OXIDE	429.8	859.6
1554	TINTING WHITE	404.4	808.8	1501	LANDAU BLACK	434.2	868.3
				1550	RED OXIDE	435.9	871.7
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR							
4374	PASTEL ADOBE PRI	Ford Motor	A	4381	TAURUS/SABLE BL	Ford Motor	FACIA
1554	TINTING WHITE	389.3	778.6	1508	SILVER	224.5	449.0
1559	YELLOW OXIDE	431.0	862.0	1553	FAST BLUE	302.9	605.7
1501	LANDAU BLACK	433.2	866.4	1501	LANDAU BLACK	367.4	734.7
1550	RED OXIDE	434.7	869.4	1552	FAST RED	405.9	811.9
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR							
4375	TWILIGHT BLUE	Ford Motor	B	4382	MIDNIGHT BLUE	Chrysler Motors	B9
1501	LANDAU BLACK	204.8	409.6	1553	FAST BLUE	219.7	439.5
1553	FAST BLUE	388.2	776.3	1501	LANDAU BLACK	370.3	740.6
1554	TINTING WHITE	405.1	810.2	1554	TINTING WHITE	392.1	784.1
				1556	FAST GREEN	405.1	810.2
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR							
4376	LT TITANIUM	Ford Motor	A	4383	MED QUARTZ	Chrysler Motors	D5
1554	TINTING WHITE	208.5	417.1	1554	TINTING WHITE	164.6	329.3
1559	YELLOW OXIDE	308.9	617.9	1501	LANDAU BLACK	266.7	533.3
1501	LANDAU BLACK	380.6	761.1	1559	YELLOW OXIDE	357.4	714.8
1550	RED OXIDE	423.4	846.8	1550	RED OXIDE	420.5	840.9
MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR							
4377	MIDNITE CURRANT	Ford Motor	A	4384	MED QUARTZ I.P.	Chrysler Motors	D5
1552	FAST RED	380.9	761.7	1302	LOW LUSTER CLEAR	138.2	276.5
1553	FAST BLUE	391.7	783.4	1554	TINTING WHITE	262.1	524.2
1501	LANDAU BLACK	400.9	801.8	1501	LANDAU BLACK	328.4	656.8
1554	TINTING WHITE	404.1	808.3	1559	YELLOW OXIDE	377.5	755.1
				1550	RED OXIDE	414.8	829.5
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR							

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 65

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4386	MAHOGANY	Chrysler Motors	H7
1501	LANDAU BLACK	210.7	421.4
1550	RED OXIDE	350.8	701.7
1553	FAST BLUE	394.0	787.9
1554	TINTING WHITE	409.0	818.0

4393	MIDNIGHT BLUE M	Chrysler Motors	B9
1553	FAST BLUE	227.5	455.1
1552	FAST RED	321.2	642.4
1501	LANDAU BLACK	391.3	782.6
1508	SILVER	403.5	806.9

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4387	GINGER PRINT	Chrysler Motors	T5
1559	YELLOW OXIDE	346.3	692.6
1550	RED OXIDE	397.2	794.4
1554	TINTING WHITE	407.6	815.1
1501	LANDAU BLACK	413.7	827.5

4394	DIAMOND BLUE M	Chrysler Motors	C1
1508	SILVER	321.6	643.2
1553	FAST BLUE	368.0	736.1
1552	FAST RED	402.7	805.4
1501	LANDAU BLACK	407.6	815.1

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4388	TUNDRA	Chrysler Motors	T7
1559	YELLOW OXIDE	239.8	479.6
1554	TINTING WHITE	345.8	691.6
1550	RED OXIDE	386.4	772.7
1501	LANDAU BLACK	418.4	836.8

4395	LT MAHOGANY ME	Chrysler Motors	H6
1552	FAST RED	247.0	494.0
1553	FAST BLUE	316.5	633.1
1551	INDO YELLOW	362.6	725.2
1508	SILVER	404.2	808.5

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4389	LT CHAMPAGNE	Chrysler Motors	V4
1302	LOW LUSTER CLEAR	138.9	277.8
1554	TINTING WHITE	274.5	548.9
1559	YELLOW OXIDE	396.4	792.9
1550	RED OXIDE	408.7	817.4
1501	LANDAU BLACK	416.5	833.0

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4396	MED MAHOGANY	Chrysler Motors	H8
1552	FAST RED	256.1	512.2
1553	FAST BLUE	353.0	706.0
1551	INDO YELLOW	399.7	799.3
1508	SILVER	403.6	807.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4390	MED CHAMPAGNE	General Motors	V8
1559	YELLOW OXIDE	213.8	427.5
1554	TINTING WHITE	361.4	722.8
1550	RED OXIDE	394.4	788.9
1501	LANDAU BLACK	420.9	841.9

4397	LT TAUPE MET	Chrysler Motors	L3
1508	SILVER	227.5	455.1
1552	FAST RED	318.5	637.1
1551	INDO YELLOW	374.9	749.7
1501	LANDAU BLACK	406.7	813.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4391	LT QUARTZ	Chrysler Motors	W8
1554	TINTING WHITE	332.0	664.1
1559	YELLOW OXIDE	378.4	756.8
1501	LANDAU BLACK	404.9	809.8
1550	RED OXIDE	431.0	862.0

4398	MED TAUPE MET	Chrysler Motors	L6
1552	FAST RED	157.4	314.8
1508	SILVER	255.2	510.3
1501	LANDAU BLACK	339.4	678.9
1551	INDO YELLOW	405.4	810.7

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4392	BLUE GRAY MET	Chrysler Motors	B5
1553	FAST BLUE	115.6	231.2
1501	LANDAU BLACK	224.9	449.7
1552	FAST RED	319.1	638.2
1508	SILVER	404.8	809.6

4400	WHITE	Chrysler Motors	W5
1554	TINTING WHITE	391.0	782.0
1559	YELLOW OXIDE	417.1	834.3
1550	RED OXIDE	431.1	862.2
1553	FAST BLUE	434.8	869.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 66

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
4401	SILVER	Chrysler Motors		A3	4408	DK CHARCOAL	Chrysler Motors	A8
1554	TINTING WHITE	195.2	390.5		1501	LANDAU BLACK	170.1	340.1
1302	LOW LUSTER CLEAR	335.3	670.5		1554	TINTING WHITE	295.1	590.1
1559	YELLOW OXIDE	377.0	753.9		1559	YELLOW OXIDE	407.2	814.3
1550	RED OXIDE	407.9	815.9		1550	RED OXIDE	416.8	833.5
1553	FAST BLUE	419.6	839.2					
4402	SAND	American Moto		89P1	4409	LT BROWNSTONE	Chrysler Motors	F3
1554	TINTING WHITE	210.3	420.7		1554	TINTING WHITE	267.6	535.2
1302	LOW LUSTER CLEAR	350.9	701.9		1559	YELLOW OXIDE	378.1	756.2
1559	YELLOW OXIDE	410.0	820.0		1550	RED OXIDE	408.1	816.2
1550	RED OXIDE	418.8	837.5		1501	LANDAU BLACK	427.6	855.2
1553	FAST BLUE	420.6	841.1					
4403	DK SAND	American Moto		89P2	4410	DK TUNDRA	Chrysler Motors	J9
1302	LOW LUSTER CLEAR	138.3	276.6		1559	YELLOW OXIDE	251.6	503.1
1554	TINTING WHITE	270.6	541.1		1501	LANDAU BLACK	310.4	620.7
1559	YELLOW OXIDE	383.4	766.8		1550	RED OXIDE	365.5	730.9
1550	RED OXIDE	405.3	810.5		1554	TINTING WHITE	414.8	829.5
1501	LANDAU BLACK	416.3	832.6					
4404	GRANITE	Ford Motor		E	4411	MED CABERNET	Ford Motor	D
1302	LOW LUSTER CLEAR	137.1	274.2		1552	FAST RED	352.9	705.9
1501	LANDAU BLACK	244.1	488.1		1559	YELLOW OXIDE	387.4	774.8
1559	YELLOW OXIDE	323.6	647.1		1553	FAST BLUE	397.3	794.6
1554	TINTING WHITE	396.0	791.9		1554	TINTING WHITE	405.4	810.7
1550	RED OXIDE	411.0	821.9					
4405	CRYSTAL BLUE	Ford Motor		A	4412	CRYSTAL BLUE PRI	Ford Motor	A
1501	LANDAU BLACK	208.3	416.7		1554	TINTING WHITE	342.5	685.0
1554	TINTING WHITE	376.5	753.0		1501	LANDAU BLACK	416.5	833.0
1553	FAST BLUE	417.2	834.5		1559	YELLOW OXIDE	430.6	861.3

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4406	CURRANT	Ford Motor		A	4414	WHITE	General Motors	11T
1552	FAST RED	261.5	523.1		1554	TINTING WHITE	423.7	847.4
1302	LOW LUSTER CLEAR	392.0	783.9		1559	YELLOW OXIDE	432.5	865.1
1553	FAST BLUE	398.9	797.8		1550	RED OXIDE	435.6	871.2
1554	TINTING WHITE	403.5	806.9		1556	FAST GREEN	436.7	873.4

4407	MED QUARTZ	Chrysler Motors		D4	4415	MED BLUE MET	General Motors	21EN
1302	LOW LUSTER CLEAR	204.8	409.6		1508	SILVER	195.4	390.8
1554	TINTING WHITE	270.9	541.9		1553	FAST BLUE	349.4	698.8
1501	LANDAU BLACK	333.6	667.3		1556	FAST GREEN	370.4	740.8
1559	YELLOW OXIDE	378.9	757.7		1554	TINTING WHITE	389.3	778.6
1550	RED OXIDE	409.5	819.1		1501	LANDAU BLACK	407.2	814.3

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 67

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
4416	MED SANDALWOO	Ford Motor		Z	4423	BLUE	Mercedes Benz	172
1302	LOW LUSTER CLEAR	135.9	271.9		1553	FAST BLUE	180.7	361.4
1559	YELLOW OXIDE	265.9	531.8		1501	LANDAU BLACK	349.9	699.8
1501	LANDAU BLACK	328.1	656.3		1554	TINTING WHITE	391.4	782.8
1550	RED OXIDE	373.7	747.5		1556	FAST GREEN	406.9	813.8
1554	TINTING WHITE	410.0	820.0					
4417	MED CANYON RED	Ford Motor		D	4424	BURGUNDY	Mercedes Benz	177
1552	FAST RED	316.6	633.3		1552	FAST RED	310.1	620.2
1559	YELLOW OXIDE	401.6	803.1		1551	INDO YELLOW	363.9	727.9
1553	FAST BLUE	405.9	811.9		1501	LANDAU BLACK	386.0	772.0
					1554	TINTING WHITE	405.6	811.1
4418	GARNET RED	General Motors		75T	4425	CREME BEIGE	Mercedes Benz	175
1552	FAST RED	370.4	740.8		1554	TINTING WHITE	217.9	435.9
1508	SILVER	389.3	778.6		1559	YELLOW OXIDE	388.3	776.5
1553	FAST BLUE	400.6	801.2		1550	RED OXIDE	408.1	816.2
1554	TINTING WHITE	404.4	808.8		1501	LANDAU BLACK	425.0	850.1
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR								
4419	DK BLUE	Ford Motor		B	4426	DK SAND	Chrysler Motors	Y6
1553	FAST BLUE	252.9	505.8		1554	TINTING WHITE	207.1	414.2
1501	LANDAU BLACK	377.8	755.6		1559	YELLOW OXIDE	379.0	757.9
1554	TINTING WHITE	405.5	810.9		1550	RED OXIDE	408.7	817.4
					1501	LANDAU BLACK	424.4	848.7
MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR								
4420	RAVEN BLACK	Ford Motor		A	4427	MULBERRY	Jaguar	
1501	LANDAU BLACK	193.8	387.6		1550	RED OXIDE	150.8	301.5
1302	LOW LUSTER CLEAR	329.6	659.1		1302	LOW LUSTER CLEAR	289.2	578.4
1554	TINTING WHITE	367.7	735.3		1552	FAST RED	348.7	697.3
1559	YELLOW OXIDE	400.7	801.4		1554	TINTING WHITE	384.1	768.2
1550	RED OXIDE	407.4	814.7		1501	LANDAU BLACK	409.6	819.3
4421	BEIGE	Ford Motor		Y	4428	SAVILE GRAY	Jaguar	
1302	LOW LUSTER CLEAR	139.6	279.1		1554	TINTING WHITE	241.7	483.4
1554	TINTING WHITE	270.8	541.5		1501	LANDAU BLACK	336.5	673.0
1559	YELLOW OXIDE	384.1	768.2		1559	YELLOW OXIDE	388.2	776.3
1550	RED OXIDE	403.5	806.9		1550	RED OXIDE	424.7	849.5
1501	LANDAU BLACK	416.0	832.0					
MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR								
4422	STONE PINE GREE	Mercedes Benz		176	4429	BARLEY	Jaguar	
1501	LANDAU BLACK	160.2	320.3		1554	TINTING WHITE	181.8	363.7
1551	INDO YELLOW	272.9	545.9		1552	FAST RED	304.3	608.6
1556	FAST GREEN	358.3	716.7		1551	INDO YELLOW	394.3	788.7
1554	TINTING WHITE	408.2	816.4		1556	FAST GREEN	417.9	835.8

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 68

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4430	BLACK	Jaguar	
1501	LANDAU BLACK	311.3	622.6
1551	INDO YELLOW	355.8	711.6
1554	TINTING WHITE	388.6	777.1
1552	FAST RED	407.3	814.5

4437	RUSSET	MG	
1552	FAST RED	280.2	560.3
1551	INDO YELLOW	367.8	735.7
1554	TINTING WHITE	386.8	773.7
1550	RED OXIDE	405.8	811.7

4431	BUCKSKIN	Jaguar	
1559	YELLOW OXIDE	191.3	382.7
1550	RED OXIDE	282.4	564.9
1554	TINTING WHITE	366.8	733.6
1501	LANDAU BLACK	417.1	834.3

4438	LT BLUE	MG	
1554	TINTING WHITE	197.3	394.6
1501	LANDAU BLACK	286.3	572.7
1302	LOW LUSTER CLEAR	343.1	686.3
1559	YELLOW OXIDE	388.6	777.1
1550	RED OXIDE	420.8	841.5

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4432	DOESKIN	Jaguar	
1554	TINTING WHITE	195.2	390.5
1559	YELLOW OXIDE	366.9	733.8
1550	RED OXIDE	399.1	798.2
1501	LANDAU BLACK	423.5	847.0

4439	CINNAMON	MG	
1559	YELLOW OXIDE	197.9	395.8
1302	LOW LUSTER CLEAR	280.3	560.7
1550	RED OXIDE	343.2	686.5
1554	TINTING WHITE	405.5	810.9
1501	LANDAU BLACK	414.1	828.2

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4433	ISIS BLUE	Jaguar	
1501	LANDAU BLACK	225.2	450.5
1553	FAST BLUE	291.6	583.1
1554	TINTING WHITE	357.3	714.6
1552	FAST RED	409.4	818.7

4440	LT BEIGE	MG	
1554	TINTING WHITE	225.5	451.1
1559	YELLOW OXIDE	392.5	785.1
1550	RED OXIDE	413.1	826.1
1501	LANDAU BLACK	425.4	850.8

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4434	MAGNOLIA	Jaguar	
1554	TINTING WHITE	322.3	644.7
1559	YELLOW OXIDE	420.7	841.3
1550	RED OXIDE	429.3	858.6
1501	LANDAU BLACK	430.9	861.8

4441	LT TAN	MG	
1551	INDO YELLOW	156.5	312.9
1550	RED OXIDE	274.4	548.7
1302	LOW LUSTER CLEAR	357.4	714.8
1554	TINTING WHITE	402.5	805.0
1501	LANDAU BLACK	409.8	819.7

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4435	GRAY	MG	
1302	LOW LUSTER CLEAR	138.9	277.8
1554	TINTING WHITE	262.2	524.4
1559	YELLOW OXIDE	369.4	738.7
1501	LANDAU BLACK	405.5	810.9
1550	RED OXIDE	415.2	830.3

4442	DK TAN	MG	
1551	INDO YELLOW	157.2	314.5
1550	RED OXIDE	304.8	609.5
1302	LOW LUSTER CLEAR	386.7	773.3
1554	TINTING WHITE	399.3	798.6
1501	LANDAU BLACK	408.0	816.1

4436	RED	MG	
1552	FAST RED	339.7	679.4
1551	INDO YELLOW	390.8	781.7
1554	TINTING WHITE	404.2	808.5
1501	LANDAU BLACK	405.1	810.2

4443	BLUE	Mercedes Benz	245
1501	LANDAU BLACK	172.4	344.9
1553	FAST BLUE	297.6	595.3
1554	TINTING WHITE	384.7	769.3
1556	FAST GREEN	410.5	821.0

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 69

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4444	RED	Mercedes Benz	243
1552	FAST RED	294.2	588.4
1551	INDO YELLOW	384.4	768.7
1554	TINTING WHITE	403.6	807.1
1553	FAST BLUE	405.5	810.9

4451	BLACK	BMW	
1501	LANDAU BLACK	405.1	810.2

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4445	BLUE	Mercedes Benz	245
1501	LANDAU BLACK	159.9	319.8
1553	FAST BLUE	313.2	626.4
1554	TINTING WHITE	385.2	770.5
1551	INDO YELLOW	409.4	818.7

4452	NATUR	BMW	
1302	LOW LUSTER CLEAR	137.8	275.5
1559	YELLOW OXIDE	257.5	514.9
1554	TINTING WHITE	370.3	740.6
1550	RED OXIDE	402.5	805.0
1501	LANDAU BLACK	415.1	830.1

4446	BAMBOO	Mercedes Benz	249
1551	INDO YELLOW	187.2	374.3
1554	TINTING WHITE	306.5	612.9
1552	FAST RED	395.7	791.4
1501	LANDAU BLACK	413.2	826.3

4453	INDIGO	BMW	
1501	LANDAU BLACK	183.5	367.1
1302	LOW LUSTER CLEAR	320.7	641.4
1554	TINTING WHITE	373.3	746.5
1551	INDO YELLOW	407.6	815.1

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4447	COGNAC PRINT	Mercedes Benz	250
1551	INDO YELLOW	205.4	410.8
1552	FAST RED	313.2	626.4
1554	TINTING WHITE	395.2	790.4
1501	LANDAU BLACK	410.3	820.6

4454	SILVER	BMW	
1302	LOW LUSTER CLEAR	137.9	275.9
1554	TINTING WHITE	248.6	497.2
1559	YELLOW OXIDE	324.5	649.0
1501	LANDAU BLACK	389.9	779.8
1550	RED OXIDE	413.9	827.8

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4448	PARCHMENT	Mercedes Benz	254
1554	TINTING WHITE	269.4	538.8
1559	YELLOW OXIDE	402.3	804.7
1501	LANDAU BLACK	415.5	831.1
1550	RED OXIDE	427.9	855.8

4455	LAMA	BMW	
1559	YELLOW OXIDE	190.3	380.6
1302	LOW LUSTER CLEAR	327.0	654.0
1550	RED OXIDE	373.2	746.3
1554	TINTING WHITE	395.7	791.4
1501	LANDAU BLACK	410.2	820.4

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4449	BAMBOO PRINT	Mercedes Benz	267
1551	INDO YELLOW	199.0	398.1
1554	TINTING WHITE	303.2	606.5
1552	FAST RED	392.3	784.5
1501	LANDAU BLACK	412.0	824.0

4456	PEARL BEIGE	BMW	
1302	LOW LUSTER CLEAR	138.5	277.0
1554	TINTING WHITE	267.6	535.2
1559	YELLOW OXIDE	387.0	774.1
1501	LANDAU BLACK	406.1	812.3
1550	RED OXIDE	415.8	831.6

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4450	CARDINAL RED	BMW	
1302	LOW LUSTER CLEAR	166.1	332.1
1552	FAST RED	325.1	650.2
1551	INDO YELLOW	378.2	756.4
1554	TINTING WHITE	396.9	793.8
1501	LANDAU BLACK	404.4	808.8

4457	LOTUS WHITE	BMW	
1554	TINTING WHITE	357.4	714.8
1559	YELLOW OXIDE	413.3	826.7
1501	LANDAU BLACK	423.2	846.5
1550	RED OXIDE	432.7	865.5

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 70

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	MED SLATE GRAY	General Motors	15BN
1554	TINTING WHITE	339.2	678.5
1501	LANDAU BLACK	395.6	791.2
1559	YELLOW OXIDE	417.1	834.1
1550	RED OXIDE	430.9	861.8

	TAN	Rolls Royce / Be	A-846
1559	YELLOW OXIDE	241.1	482.2
1554	TINTING WHITE	348.1	696.2
1550	RED OXIDE	410.8	821.6
1501	LANDAU BLACK	419.1	838.3

	ROVER GRAY	Rolls Royce / Be	A-5032
1554	TINTING WHITE	241.7	483.4
1501	LANDAU BLACK	336.5	673.0
1559	YELLOW OXIDE	388.2	776.3
1550	RED OXIDE	424.7	849.5

	PARCHMENT	Rolls Royce / Be	A-3672
1554	TINTING WHITE	224.9	449.7
1302	LOW LUSTER CLEAR	365.2	730.4
1559	YELLOW OXIDE	414.7	829.4
1550	RED OXIDE	419.0	837.9
1501	LANDAU BLACK	421.5	843.0

	COFFEE BEIGE	Rolls Royce / Be	A-4184
1559	YELLOW OXIDE	208.1	416.1
1554	TINTING WHITE	342.2	684.4
1550	RED OXIDE	401.5	802.9
1501	LANDAU BLACK	420.4	840.8

	BISCUIT	Rolls Royce / Be	A-4103
1559	YELLOW OXIDE	230.7	461.3
1554	TINTING WHITE	373.2	746.3
1550	RED OXIDE	417.2	834.5
1501	LANDAU BLACK	421.0	842.1

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	ROSSO RED	Rolls Royce / Be	A-8300
1552	FAST RED	228.2	456.4
1551	INDO YELLOW	385.8	771.6
1554	TINTING WHITE	404.6	809.2
1501	LANDAU BLACK	405.0	810.0

	BEIGE	Rolls Royce / Be	A-3234
1554	TINTING WHITE	144.4	288.8
1302	LOW LUSTER CLEAR	283.3	566.6
1559	YELLOW OXIDE	397.8	795.5
1550	RED OXIDE	409.9	819.9
1501	LANDAU BLACK	416.9	833.7

	RR RED	Rolls Royce / Be	A-3086
1302	LOW LUSTER CLEAR	198.6	397.3
1552	FAST RED	369.3	738.5
1551	INDO YELLOW	394.3	788.5
1554	TINTING WHITE	401.4	802.8
1553	FAST BLUE	403.2	806.4

	BLACK	Rolls Royce / Be	A-8500
1501	LANDAU BLACK	405.1	810.2

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	BURGUNDY	Rolls Royce / Be	A-893
1302	LOW LUSTER CLEAR	219.3	438.5
1552	FAST RED	387.8	775.6
1551	INDO YELLOW	394.6	789.3
1554	TINTING WHITE	399.6	799.1
1553	FAST BLUE	402.9	805.8

	WHITE	Rolls Royce / Be	A-4169
1554	TINTING WHITE	437.4	874.8

	LT NAVY	Rolls Royce / Be	A-3282
1553	FAST BLUE	288.0	576.1
1501	LANDAU BLACK	387.9	775.8
1554	TINTING WHITE	404.2	808.5

	BLUEGRAY	Rolls Royce / Be	A-3244
1554	TINTING WHITE	191.9	383.8
1501	LANDAU BLACK	343.6	687.2
1551	INDO YELLOW	416.4	832.8
1552	FAST RED	419.0	838.1

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 71

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4472	RED	Rolls Royce / Be	A-3171
1552	FAST RED	315.1	630.2
1551	INDO YELLOW	390.8	781.7
1554	TINTING WHITE	403.8	807.5
1501	LANDAU BLACK	405.0	810.0

4479	MAGNOLIA	Rolls Royce / Be	A-3997
1554	TINTING WHITE	350.7	701.5
1559	YELLOW OXIDE	426.6	853.1
1550	RED OXIDE	431.0	862.0
1556	FAST GREEN	432.6	865.3

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4473	LAKE BLUE	Rolls Royce / Be	A-3015
1554	TINTING WHITE	191.0	382.1
1501	LANDAU BLACK	375.3	750.5
1556	FAST GREEN	408.8	817.6
1553	FAST BLUE	419.0	837.9

4480	CREAM	Rolls Royce / Be	A-3099
1554	TINTING WHITE	260.4	520.8
1559	YELLOW OXIDE	413.1	826.1
1550	RED OXIDE	425.9	851.8
1501	LANDAU BLACK	427.6	855.2

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4474	LT BLUE	Rolls Royce / Be	A-4135
1554	TINTING WHITE	312.6	625.3
1501	LANDAU BLACK	388.6	777.3
1553	FAST BLUE	424.7	849.3
1556	FAST GREEN	427.9	855.8

4481	RR TAN	Rolls Royce / Be	A-4134
1559	YELLOW OXIDE	299.3	598.7
1550	RED OXIDE	363.4	726.8
1554	TINTING WHITE	404.5	809.0
1501	LANDAU BLACK	415.3	830.7

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4475	RR BLUE	Rolls Royce / Be	A-4133
1501	LANDAU BLACK	209.0	418.0
1554	TINTING WHITE	323.8	647.5
1553	FAST BLUE	400.0	799.9
1556	FAST GREEN	413.0	825.9

4482	SADDLE	Rolls Royce / Be	A-3128
1554	TINTING WHITE	240.2	480.3
1551	INDO YELLOW	358.8	717.6
1552	FAST RED	416.3	832.6
1501	LANDAU BLACK	422.4	844.7

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4476	CHOCOLATE	Rolls Royce / Be	A-890
1559	YELLOW OXIDE	123.3	246.6
1501	LANDAU BLACK	217.1	434.2
1550	RED OXIDE	303.0	605.9
1302	LOW LUSTER CLEAR	384.9	769.9
1554	TINTING WHITE	410.5	821.0

4483	CINNAMON	Rolls Royce / Be	A-3243
1559	YELLOW OXIDE	249.9	499.7
1554	TINTING WHITE	378.6	757.2
1550	RED OXIDE	415.5	831.1
1501	LANDAU BLACK	420.4	840.8

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4477	MINK	Rolls Royce / Be	A-4186
1302	LOW LUSTER CLEAR	138.6	277.2
1554	TINTING WHITE	262.4	524.8
1552	FAST RED	325.5	650.9
1551	INDO YELLOW	377.3	754.7
1501	LANDAU BLACK	412.6	825.2

4484	FAWN	Rolls Royce / Be	A-847
1559	YELLOW OXIDE	237.5	475.0
1554	TINTING WHITE	381.8	763.6
1550	RED OXIDE	408.0	816.1
1501	LANDAU BLACK	420.9	841.9

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4478	CHESTNUT	Rolls Royce / Be	A-891
1550	RED OXIDE	138.2	276.5
1302	LOW LUSTER CLEAR	274.6	549.1
1559	YELLOW OXIDE	366.1	732.3
1501	LANDAU BLACK	401.9	803.9
1554	TINTING WHITE	409.3	818.5

4485	RR GREY	Rolls Royce / Be	A-3393
1554	TINTING WHITE	221.9	443.8
1559	YELLOW OXIDE	364.8	729.6
1501	LANDAU BLACK	406.0	812.1
1550	RED OXIDE	424.7	849.3

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 72

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4486	RR GREEN	Rolls Royce / Be	A-3655
1551	INDO YELLOW	159.9	319.8
1501	LANDAU BLACK	278.8	557.7
1554	TINTING WHITE	350.1	700.2
1556	FAST GREEN	409.7	819.5

4493	BROWN	Ford Motor	
1559	YELLOW OXIDE	182.7	365.4
1550	RED OXIDE	343.6	687.2
1554	TINTING WHITE	392.5	785.1
1501	LANDAU BLACK	415.8	831.6

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4487	LT GREEN	Ford Motor	
1554	TINTING WHITE	390.5	780.9
1556	FAST GREEN	426.5	852.9
1551	INDO YELLOW	431.2	862.4
1501	LANDAU BLACK	433.8	867.5

4494	RED	Ford Motor	
1552	FAST RED	189.3	378.7
1302	LOW LUSTER CLEAR	270.9	541.9
1551	INDO YELLOW	346.0	692.0
1554	TINTING WHITE	404.7	809.4
1550	RED OXIDE	407.9	815.9

4488	RED	Ford Motor	
1552	FAST RED	303.3	606.7
1551	INDO YELLOW	382.9	765.9
1554	TINTING WHITE	405.7	811.3

4495	RED	Ford Motor	
1552	FAST RED	220.2	440.4
1302	LOW LUSTER CLEAR	302.1	604.2
1551	INDO YELLOW	355.8	711.6
1554	TINTING WHITE	382.2	764.4
1550	RED OXIDE	406.0	812.1

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4489	DK GREEN	Ford Motor	
1556	FAST GREEN	229.7	459.4
1554	TINTING WHITE	304.3	608.6
1501	LANDAU BLACK	356.9	713.8
1553	FAST BLUE	409.5	819.1

4496	CHARCOAL	General Motors		17
1501	LANDAU BLACK	351.4	702.8	
1554	TINTING WHITE	377.5	755.1	
1551	INDO YELLOW	399.5	799.0	
1556	FAST GREEN	407.0	814.0	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4490	WHITE	Ford Motor	
1554	TINTING WHITE	432.4	864.9
1551	INDO YELLOW	435.5	871.0
1552	FAST RED	436.3	872.7
1501	LANDAU BLACK	437.0	874.0

4497	MAROON	General Motors		71
1552	FAST RED	340.9	681.7	
1551	INDO YELLOW	381.4	762.9	
1554	TINTING WHITE	395.7	791.4	
1553	FAST BLUE	405.0	810.0	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4491	LT BLUE	Ford Motor	
1554	TINTING WHITE	183.2	366.3
1553	FAST BLUE	346.8	693.5
1556	FAST GREEN	393.1	786.2
1551	INDO YELLOW	417.3	834.7

4498	SADDLE	General Motors		63
1559	YELLOW OXIDE	273.8	547.6	
1550	RED OXIDE	339.2	678.3	
1554	TINTING WHITE	399.6	799.1	
1501	LANDAU BLACK	416.4	832.8	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4492	LT GREEN	Ford Motor	
1554	TINTING WHITE	263.4	526.9
1551	INDO YELLOW	376.7	753.4
1556	FAST GREEN	401.9	803.7
1501	LANDAU BLACK	424.1	848.2

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4499	LT SAND	Chrysler Motors		Y1
1554	TINTING WHITE	331.8	663.7	
1559	YELLOW OXIDE	421.8	843.6	
1550	RED OXIDE	427.3	854.6	
1501	LANDAU BLACK	431.5	863.0	

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 73

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	LT CHARCOAL	Chrysler Motors		
4500				51
1554	TINTING WHITE	152.2	304.4	
1302	LOW LUSTER CLEAR	290.8	581.6	
1501	LANDAU BLACK	348.2	696.4	
1559	YELLOW OXIDE	401.4	802.8	
1550	RED OXIDE	416.4	832.8	

	DK TUNDRA	Chrysler Motors		
4507				J9
1559	YELLOW OXIDE	259.1	518.1	
1501	LANDAU BLACK	314.2	628.3	
1550	RED OXIDE	367.6	735.1	
1554	TINTING WHITE	414.9	829.7	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	NAVY	Chrysler Motors		
4501				Q8
1302	LOW LUSTER CLEAR	136.2	272.5	
1501	LANDAU BLACK	260.5	521.0	
1554	TINTING WHITE	319.7	639.4	
1553	FAST BLUE	375.9	751.8	
1550	RED OXIDE	408.4	816.8	

	DK BLUE	Chrysler Motors		
4508				B9
1501	LANDAU BLACK	192.9	385.9	
1553	FAST BLUE	385.9	771.8	
1554	TINTING WHITE	405.1	810.2	

	CORDOVAN	Chrysler Motors		
4502				H9
1550	RED OXIDE	278.4	556.7	
1501	LANDAU BLACK	349.4	698.8	
1553	FAST BLUE	392.3	784.5	
1554	TINTING WHITE	412.4	824.8	

	DK BLUE	Chrysler Motors		
4509				B9
1553	FAST BLUE	219.7	439.5	
1501	LANDAU BLACK	370.3	740.6	
1554	TINTING WHITE	392.1	784.1	
1556	FAST GREEN	405.1	810.2	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	DK MAHOGANY	Chrysler Motors		
4503				H7
1501	LANDAU BLACK	158.7	317.3	
1302	LOW LUSTER CLEAR	294.5	589.0	
1550	RED OXIDE	387.5	775.0	
1554	TINTING WHITE	401.3	802.6	
1559	YELLOW OXIDE	407.0	814.0	

	DK BLUE	Chrysler Motors		
4510				B7
1501	LANDAU BLACK	192.9	385.9	
1553	FAST BLUE	385.9	771.8	
1554	TINTING WHITE	405.1	810.2	

	DK AUBURN	General Motors		
4504				68
1550	RED OXIDE	233.0	466.1	
1559	YELLOW OXIDE	370.7	741.4	
1501	LANDAU BLACK	411.0	821.9	
1554	TINTING WHITE	413.1	826.1	

	BORDEAUX	Chrysler Motors		
4511				R7
1552	FAST RED	382.9	765.9	
1501	LANDAU BLACK	393.9	787.7	
1553	FAST BLUE	400.3	800.7	
1554	TINTING WHITE	404.3	808.6	

	DK SABLE MET	General Motors		
4505				65T
1552	FAST RED	183.9	367.8	
1508	SILVER	279.3	558.6	
1501	LANDAU BLACK	359.5	719.0	
1551	INDO YELLOW	405.4	810.7	

	LT BUCKSKIN	Chrysler Motors		
4512				V2
1554	TINTING WHITE	196.4	392.7	
1559	YELLOW OXIDE	391.5	783.0	
1550	RED OXIDE	411.3	822.5	
1501	LANDAU BLACK	423.9	847.8	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	MIDNIGHT BLUE	General Motors		
4506				24EN
1501	LANDAU BLACK	157.1	314.3	
1553	FAST BLUE	303.1	606.3	
1556	FAST GREEN	372.5	745.0	
1554	TINTING WHITE	406.4	812.8	

	SLATE GRAY	General Motors		
4513				18T
1554	TINTING WHITE	371.2	742.3	
1501	LANDAU BLACK	407.5	814.9	
1559	YELLOW OXIDE	423.4	846.8	
1550	RED OXIDE	432.9	865.8	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 74

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4514	LT AUBURN MET	General Motors	64T
1552	FAST RED	176.8	353.6
1508	SILVER	298.0	596.0
1551	INDO YELLOW	370.0	740.1
1501	LANDAU BLACK	405.6	811.1

4521	GRAPHITE	Ford Motor	P
1501	LANDAU BLACK	229.1	458.3
1553	FAST BLUE	289.5	578.9
1508	SILVER	349.4	698.8
1552	FAST RED	405.1	810.2

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4515	DK AUBURN MET	General Motors	66T
1552	FAST RED	304.7	609.3
1501	LANDAU BLACK	352.4	704.7
1551	INDO YELLOW	395.2	790.4
1508	SILVER	404.2	808.5

4522	DK RED	General Motors	47CN
1552	FAST RED	351.4	702.8
1550	RED OXIDE	394.7	789.5
1553	FAST BLUE	402.0	804.1
1554	TINTING WHITE	405.3	810.5

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4516	MED SLATE GRAY	General Motors	85T
1508	SILVER	170.5	341.1
1501	LANDAU BLACK	258.2	516.4
1552	FAST RED	344.9	689.7
1553	FAST BLUE	406.0	812.1

4523	LT TITANIUM	Ford Motor	A
1554	TINTING WHITE	216.5	433.0
1302	LOW LUSTER CLEAR	355.1	710.2
1559	YELLOW OXIDE	389.8	779.6
1501	LANDAU BLACK	405.6	811.1
1550	RED OXIDE	420.8	841.5

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4517	OXFORD WHITE	Ford Motor	W
1554	TINTING WHITE	429.9	859.8
1559	YELLOW OXIDE	433.8	867.5
1501	LANDAU BLACK	436.8	873.6

4524	DK BISQUE	Ford Motor	A
1559	YELLOW OXIDE	137.5	274.9
1302	LOW LUSTER CLEAR	274.9	549.9
1554	TINTING WHITE	354.4	708.9
1550	RED OXIDE	386.7	773.3
1501	LANDAU BLACK	413.0	825.9

4518	VERY DK RED	General Motors	47DN
1552	FAST RED	303.8	607.6
1550	RED OXIDE	353.0	706.0
1501	LANDAU BLACK	395.2	790.4
1554	TINTING WHITE	406.1	812.3

4525	BISQUE	Ford Motor	A
1554	TINTING WHITE	211.6	423.1
1302	LOW LUSTER CLEAR	351.7	703.4
1559	YELLOW OXIDE	412.2	824.4
1550	RED OXIDE	417.0	833.9
1501	LANDAU BLACK	420.6	841.1

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4519	DK RED	General Motors	47CN
1552	FAST RED	238.7	477.5
1302	LOW LUSTER CLEAR	373.4	746.9
1550	RED OXIDE	392.4	784.7
1554	TINTING WHITE	398.6	797.2
1501	LANDAU BLACK	404.1	808.3

4526	DK QUARTZ MET	Chrysler Motors	D8
1501	LANDAU BLACK	186.4	372.8
1508	SILVER	314.3	628.5
1552	FAST RED	381.6	763.2
1553	FAST BLUE	405.8	811.7

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4520	SANDALWOOD	Ford Motor	T
1501	LANDAU BLACK	134.1	268.3
1508	SILVER	253.8	507.7
1552	FAST RED	353.2	706.4
1551	INDO YELLOW	405.7	811.3

4527	PASTEL ALABASTE	Ford Motor	H
1554	TINTING WHITE	399.2	798.4
1559	YELLOW OXIDE	428.7	857.5
1550	RED OXIDE	433.1	866.2
1501	LANDAU BLACK	435.3	870.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 75

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4528	MED CURRANT RE	Ford Motor		A	4535	WHITE	Ford Motor
1552	FAST RED	395.2	790.4		1554	TINTING WHITE	396.0
1554	TINTING WHITE	400.8	801.6		1552	FAST RED	414.2
1553	FAST BLUE	404.4	808.8		1551	INDO YELLOW	428.2
					1556	FAST GREEN	434.2
							828.4
							856.3
							868.5
4529	LT BUCKSKIN MET	Chrysler Motors		V3	4536	LT RED MET	Ford Motor
1508	SILVER	332.6	665.2		1552	FAST RED	196.1
1551	INDO YELLOW	362.4	724.9		1508	SILVER	288.4
1552	FAST RED	389.2	778.4		1554	TINTING WHITE	350.3
1501	LANDAU BLACK	407.9	815.9		1551	INDO YELLOW	399.8
					1501	LANDAU BLACK	409.8
							392.2
							576.8
							700.5
							799.5
							819.7
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR			
4530	DUSTY ROSE MET	Chrysler Motors		M7	4537	LT GREEN	Ford Motor
1552	FAST RED	353.7	707.4		1559	YELLOW OXIDE	226.0
1553	FAST BLUE	387.6	775.2		1554	TINTING WHITE	395.7
1508	SILVER	404.1	808.3		1553	FAST BLUE	417.7
					1501	LANDAU BLACK	422.0
							452.0
							791.4
							835.4
							844.0
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR			
4531	DK SAPPHIRE BLUE	General Motors			4538	DK GREEN	Ford Motor
1553	FAST BLUE	179.2	358.3		1554	TINTING WHITE	193.4
1501	LANDAU BLACK	304.4	608.8		1551	INDO YELLOW	310.7
1556	FAST GREEN	367.0	734.0		1553	FAST BLUE	373.8
1554	TINTING WHITE	406.6	813.2		1501	LANDAU BLACK	418.6
							386.8
							621.3
							747.7
							837.1
4532	LT QUARTZ MET	Chrysler Motors		D1	4539	LT BLUE	Ford Motor
1508	SILVER	381.3	762.7		1554	TINTING WHITE	300.1
1552	FAST RED	399.5	799.0		1302	LOW LUSTER CLEAR	384.8
1501	LANDAU BLACK	405.7	811.3		1501	LANDAU BLACK	401.8
1553	FAST BLUE	408.5	817.0		1553	FAST BLUE	414.7
					1559	YELLOW OXIDE	426.6
							600.2
							769.7
							803.5
							829.4
							853.1
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR			
4533	DK TITANIUM	Ford Motor		J	4540	DK BLUE	Ford Motor
1501	LANDAU BLACK	247.3	494.6		1554	TINTING WHITE	150.3
1508	SILVER	381.0	761.9		1302	LOW LUSTER CLEAR	288.4
1552	FAST RED	400.1	800.3		1501	LANDAU BLACK	344.3
1551	INDO YELLOW	406.3	812.6		1553	FAST BLUE	399.6
					1556	FAST GREEN	414.5
							300.6
							576.8
							688.6
							799.1
							829.0
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR			
4534	DK SLATE GRAY M	General Motors		99T	4541	LT BEECHWOOD	General Motors
1501	LANDAU BLACK	119.1	238.3		1559	YELLOW OXIDE	234.6
1508	SILVER	223.6	447.3		1550	RED OXIDE	366.9
1553	FAST BLUE	316.4	632.9		1553	FAST BLUE	396.2
1552	FAST RED	405.2	810.4		1554	TINTING WHITE	413.7
							469.1
							733.8
							792.5
							827.5
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR				MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR			

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 76

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4542	WHITE	General Motors	
1554	TINTING WHITE	427.1	854.2
1559	YELLOW OXIDE	435.0	870.0
1501	LANDAU BLACK	436.7	873.4

4549	SLATE BLUE	Chrysler Motors		B7
1302	LOW LUSTER CLEAR	136.6	273.2	
1553	FAST BLUE	223.8	447.6	
1550	RED OXIDE	301.5	603.1	
1554	TINTING WHITE	371.7	743.5	
1501	LANDAU BLACK	410.0	820.0	

4543	DK SILVER MET	Chrysler Motors		S7
1508	SILVER	179.1	358.2	
1501	LANDAU BLACK	337.7	675.5	
1553	FAST BLUE	376.3	752.6	
1552	FAST RED	406.5	813.0	

4550	CRIMSON	Chrysler Motors		MA
1552	FAST RED	246.1	492.1	
1302	LOW LUSTER CLEAR	380.9	761.7	
1550	RED OXIDE	393.1	786.2	
1554	TINTING WHITE	401.1	802.2	
1501	LANDAU BLACK	404.1	808.3	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4544	LT BLUE SATIN GL	Chrysler Motors		BD
1552	FAST RED	131.3	262.6	
1553	FAST BLUE	259.7	519.5	
1508	SILVER	358.5	717.1	
1554	TINTING WHITE	408.4	816.8	

4551	SLATE BLUE	Chrysler Motors		BE
1302	LOW LUSTER CLEAR	133.6	267.1	
1553	FAST BLUE	237.1	474.2	
1550	RED OXIDE	322.5	645.1	
1554	TINTING WHITE	375.2	750.3	
1501	LANDAU BLACK	408.9	817.8	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4545	MED WATER BLUE	Chrysler Motors		BF
1553	FAST BLUE	196.9	393.9	
1552	FAST RED	322.3	644.7	
1501	LANDAU BLACK	359.6	719.2	
1508	SILVER	388.3	776.5	
1554	TINTING WHITE	405.0	810.0	

4552	GINGER	Chrysler Motors		T5
1559	YELLOW OXIDE	215.2	430.4	
1302	LOW LUSTER CLEAR	351.6	703.2	
1550	RED OXIDE	387.8	775.6	
1554	TINTING WHITE	404.2	808.5	
1501	LANDAU BLACK	410.0	820.0	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4546	RADIANT FIRE	Chrysler Motors		RB
1552	FAST RED	314.4	628.7	
1551	INDO YELLOW	394.9	789.8	
1554	TINTING WHITE	404.7	809.4	

4553	GRAY MET	General Motors	
1501	LANDAU BLACK	299.8	599.6
1508	SILVER	392.1	784.1
1551	INDO YELLOW	405.9	811.9

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4547	FROST WHITE	Chrysler Motors		WC
1554	TINTING WHITE	422.8	845.7	
1559	YELLOW OXIDE	429.9	859.8	
1501	LANDAU BLACK	436.1	872.1	
1550	RED OXIDE	436.5	873.1	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4554	BLUE	Acura	
1501	LANDAU BLACK	223.3	446.5
1554	TINTING WHITE	321.9	643.7
1302	LOW LUSTER CLEAR	397.9	795.7
1559	YELLOW OXIDE	411.9	823.8

4548	RADIANT RED	Chrysler Motors		RC
1552	FAST RED	211.5	422.9	
1302	LOW LUSTER CLEAR	345.3	690.7	
1551	INDO YELLOW	386.3	772.5	
1550	RED OXIDE	395.2	790.4	
1554	TINTING WHITE	404.0	808.1	

4555	CHARCOAL BLACK	Acura	
1501	LANDAU BLACK	210.2	420.5
1554	TINTING WHITE	295.0	590.0
1551	INDO YELLOW	361.5	723.0
1552	FAST RED	411.0	821.9

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 77

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4556	IVORY	Acura	
1554	TINTING WHITE	183.4	366.9
1559	YELLOW OXIDE	300.9	601.7
1302	LOW LUSTER CLEAR	384.9	769.9
1550	RED OXIDE	403.4	806.7
1501	LANDAU BLACK	420.4	840.8

4562	GRAPHITE	Ford Motor	P
1501	LANDAU BLACK	229.1	458.3
1553	FAST BLUE	289.5	578.9
1508	SILVER	349.4	698.8
1552	FAST RED	405.1	810.2

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4557	BURGUNDY	Acura	
1550	RED OXIDE	198.2	396.3
1501	LANDAU BLACK	379.3	758.7
1554	TINTING WHITE	406.2	812.4
1559	YELLOW OXIDE	411.6	823.3

4563	LT TITANIUM	Ford Motor	A
1508	SILVER	340.6	681.2
1501	LANDAU BLACK	377.3	754.7
1552	FAST RED	400.3	800.7
1551	INDO YELLOW	408.1	816.2

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4558	MED WOODROSE	Ford Motor	C
1550	RED OXIDE	175.5	350.9
1501	LANDAU BLACK	343.2	686.5
1559	YELLOW OXIDE	405.9	811.9
1554	TINTING WHITE	410.4	820.8

4564	LT SANDALWOOD	Ford Motor	Z
1508	SILVER	290.0	580.1
1552	FAST RED	342.4	684.8
1551	INDO YELLOW	377.4	754.9
1501	LANDAU BLACK	407.6	815.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4559	EBONY	Ford Motor	ZHEA
1501	LANDAU BLACK	225.9	451.8
1302	LOW LUSTER CLEAR	360.9	721.8
1559	YELLOW OXIDE	381.8	763.6
1553	FAST BLUE	394.2	788.3
1554	TINTING WHITE	404.9	809.8

4565	DK MAPLE RED	General Motors	70CN
1552	FAST RED	180.1	360.2
1550	RED OXIDE	285.6	571.1
1302	LOW LUSTER CLEAR	366.8	733.6
1501	LANDAU BLACK	398.0	795.9
1554	TINTING WHITE	406.8	813.6

4559	EBONY	Ford Motor	H
1501	LANDAU BLACK	225.9	451.8
1302	LOW LUSTER CLEAR	360.9	721.8
1559	YELLOW OXIDE	381.8	763.6
1553	FAST BLUE	394.2	788.3
1554	TINTING WHITE	404.9	809.8

4566	DK SLATE	General Motors	15C
1302	LOW LUSTER CLEAR	137.1	274.2
1554	TINTING WHITE	261.3	522.5
1501	LANDAU BLACK	377.3	754.7
1559	YELLOW OXIDE	398.9	797.8
1550	RED OXIDE	413.7	827.5

4560	TWILIGHT BLUE	Ford Motor	B
1553	FAST BLUE	223.8	447.6
1556	FAST GREEN	350.1	700.2
1501	LANDAU BLACK	398.4	796.9
1508	SILVER	403.4	806.7

4567	DK AUBURN	General Motors	68
1559	YELLOW OXIDE	174.4	348.8
1552	FAST RED	311.4	622.8
1302	LOW LUSTER CLEAR	393.1	786.2
1501	LANDAU BLACK	407.4	814.7

4561	SILVER	Ford Motor	P
1508	SILVER	399.6	799.1
1501	LANDAU BLACK	405.9	811.9
1551	INDO YELLOW	407.6	815.1
1552	FAST RED	408.8	817.6

4568	MED WEDGEWOOD	Ford Motor	B
1554	TINTING WHITE	206.2	412.5
1501	LANDAU BLACK	312.5	624.9
1553	FAST BLUE	398.8	797.6
1556	FAST GREEN	417.2	834.5

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 78

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4569	BLACK	Volvo		4576	GREY	Volvo	
1501	LANDAU BLACK	405.1	810.2	1302	LOW LUSTER CLEAR	136.7	273.4
				1501	LANDAU BLACK	242.0	483.9
				1559	YELLOW OXIDE	326.3	652.7
				1554	TINTING WHITE	381.8	763.6
				1550	RED OXIDE	410.1	820.2
MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR							
4570	BLACK	Volvo		4577	BEIGE	Volvo	
1501	LANDAU BLACK	405.1	810.2	1559	YELLOW OXIDE	195.7	391.4
				1302	LOW LUSTER CLEAR	333.0	666.0
				1554	TINTING WHITE	381.7	763.4
				1550	RED OXIDE	405.7	811.3
				1501	LANDAU BLACK	411.7	823.5
4571	BLUE	Volvo		4578	BEIGE	Volvo	
1553	FAST BLUE	195.5	391.0	1302	LOW LUSTER CLEAR	136.2	272.5
1501	LANDAU BLACK	349.0	698.1	1554	TINTING WHITE	251.5	502.9
1554	TINTING WHITE	391.8	783.6	1551	INDO YELLOW	339.0	677.9
1552	FAST RED	406.9	813.8	1552	FAST RED	390.7	781.5
				1501	LANDAU BLACK	412.0	824.0
4572	BLUE	Volvo		4579	BEIGE	Volvo	
1302	LOW LUSTER CLEAR	134.6	269.2	1559	YELLOW OXIDE	207.3	414.6
1501	LANDAU BLACK	244.3	488.7	1554	TINTING WHITE	301.2	602.3
1553	FAST BLUE	348.8	697.7	1302	LOW LUSTER CLEAR	384.2	768.4
1554	TINTING WHITE	400.0	800.1	1550	RED OXIDE	411.2	822.3
1550	RED OXIDE	407.1	814.2	1501	LANDAU BLACK	415.9	831.8
4573	RED	Volvo		4580	BEIGE	Volvo	
1550	RED OXIDE	229.8	459.6	1559	YELLOW OXIDE	170.9	341.8
1302	LOW LUSTER CLEAR	366.3	732.6	1302	LOW LUSTER CLEAR	308.6	617.1
1552	FAST RED	387.9	775.8	1554	TINTING WHITE	372.7	745.4
1501	LANDAU BLACK	400.7	801.4	1550	RED OXIDE	406.8	813.6
1554	TINTING WHITE	409.5	818.9	1501	LANDAU BLACK	412.6	825.2
4574	RED	Volvo		4581	GRAPHITE	Audi	
1552	FAST RED	199.4	398.8	1501	LANDAU BLACK	157.5	315.0
1302	LOW LUSTER CLEAR	333.9	667.9	1302	LOW LUSTER CLEAR	293.5	586.9
1551	INDO YELLOW	379.4	758.9	1559	YELLOW OXIDE	360.1	720.3
1501	LANDAU BLACK	393.1	786.2	1554	TINTING WHITE	393.8	787.6
1554	TINTING WHITE	403.8	807.7	1550	RED OXIDE	407.8	815.7
4575	TAUPE	Volvo		4582	PLATINUM GREY	Audi	
1559	YELLOW OXIDE	175.4	350.7	1302	LOW LUSTER CLEAR	137.9	275.9
1554	TINTING WHITE	267.1	534.3	1554	TINTING WHITE	245.3	490.6
1501	LANDAU BLACK	347.6	695.2	1559	YELLOW OXIDE	333.0	666.0
1550	RED OXIDE	416.8	833.5	1501	LANDAU BLACK	389.6	779.2
				1550	RED OXIDE	414.0	828.0

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 79

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4583	NAUTICAL BLUE	Audi	
1501	LANDAU BLACK	278.1	556.1
1554	TINTING WHITE	361.5	723.0
1553	FAST BLUE	391.9	783.8
1551	INDO YELLOW	411.0	821.9

4590	LEXUS GRAY	Lexus	
1501	LANDAU BLACK	144.1	288.2
1554	TINTING WHITE	272.9	545.9
1559	YELLOW OXIDE	385.5	771.0
1550	RED OXIDE	417.5	835.1

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4584	RED	Saab	
1550	RED OXIDE	203.6	407.2
1302	LOW LUSTER CLEAR	339.8	679.6
1501	LANDAU BLACK	373.9	747.8
1553	FAST BLUE	404.3	808.6
1554	TINTING WHITE	408.3	816.6

4591	BERYL GREEN MET	Chrysler Motors		G6
1553	FAST BLUE	128.8	257.6	
1556	FAST GREEN	228.0	456.0	
1508	SILVER	320.0	639.9	
1501	LANDAU BLACK	404.8	809.6	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4585	TAN	Saab	
1559	YELLOW OXIDE	159.0	318.1
1302	LOW LUSTER CLEAR	296.6	593.2
1554	TINTING WHITE	357.1	714.2
1550	RED OXIDE	401.9	803.9
1501	LANDAU BLACK	412.4	824.8

4592	KHAKI	Chrysler Motors		J7
1554	TINTING WHITE	153.5	307.0	
1302	LOW LUSTER CLEAR	292.5	585.0	
1559	YELLOW OXIDE	389.2	778.4	
1550	RED OXIDE	405.9	811.9	
1501	LANDAU BLACK	417.3	834.7	

4586	GREY	Saab	
1302	LOW LUSTER CLEAR	135.1	270.2
1501	LANDAU BLACK	261.0	521.9
1559	YELLOW OXIDE	337.4	674.9
1550	RED OXIDE	375.3	750.7
1554	TINTING WHITE	408.7	817.4

4593	TEAL	Chrysler Motors		P5
1553	FAST BLUE	237.8	475.6	
1508	SILVER	335.0	669.9	
1501	LANDAU BLACK	388.9	777.9	
1556	FAST GREEN	404.3	808.6	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4587	TAN	General Motors	
1559	YELLOW OXIDE	269.0	538.1
1550	RED OXIDE	385.2	770.5
1501	LANDAU BLACK	412.9	825.7

4594	SPICE	Chrysler Motors		TB
1559	YELLOW OXIDE	204.7	409.5	
1302	LOW LUSTER CLEAR	341.1	682.1	
1550	RED OXIDE	380.9	761.7	
1554	TINTING WHITE	397.9	795.7	
1501	LANDAU BLACK	409.9	819.9	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4588	DK STEEL BLUE	General Motors		22CN
1501	LANDAU BLACK	208.9	417.8	
1554	TINTING WHITE	409.0	818.0	
1550	RED OXIDE	420.1	840.2	

4595	FROST WHITE	Chrysler Motors		WC
1554	TINTING WHITE	273.4	546.8	
1302	LOW LUSTER CLEAR	414.6	829.2	
1501	LANDAU BLACK	420.0	840.0	
1559	YELLOW OXIDE	423.4	846.8	
1550	RED OXIDE	424.0	848.0	

4589	LT BERYL MET	Ford Motor		K
1508	SILVER	332.7	665.4	
1556	FAST GREEN	376.9	753.7	
1553	FAST BLUE	407.8	815.7	

4596	DK SAND	Chrysler Motors		YC
1554	TINTING WHITE	160.9	321.9	
1302	LOW LUSTER CLEAR	290.9	581.8	
1559	YELLOW OXIDE	389.6	779.2	
1550	RED OXIDE	406.8	813.6	
1501	LANDAU BLACK	418.0	836.0	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 80

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4597	LT BLUE MET	Chrysler Motors	BD
1552	FAST RED	115.0	230.1
1508	SILVER	225.2	450.5
1553	FAST BLUE	332.5	665.0
1554	TINTING WHITE	410.8	821.6

4604	DK ANTELOPE MET	General Motors	51T
1552	FAST RED	242.9	485.8
1501	LANDAU BLACK	366.6	733.2
1551	INDO YELLOW	396.2	792.5
1508	SILVER	404.4	808.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4598	MED WATER BLUE	Chrysler Motors	BF
1553	FAST BLUE	186.9	373.7
1552	FAST RED	294.4	588.8
1501	LANDAU BLACK	340.4	680.8
1508	SILVER	385.2	770.5
1554	TINTING WHITE	405.4	810.7

4605	LT CAMEL	General Motors	67AN
1554	TINTING WHITE	196.5	392.9
1559	YELLOW OXIDE	386.2	772.4
1550	RED OXIDE	415.4	830.9
1501	LANDAU BLACK	423.9	847.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4599	BLUE	Lexus	
1501	LANDAU BLACK	272.6	545.1
1554	TINTING WHITE	415.7	831.4

4606	ALABASTER	General Motors	56T
1554	TINTING WHITE	343.5	687.0
1559	YELLOW OXIDE	413.3	826.5
1550	RED OXIDE	424.0	848.0
1501	LANDAU BLACK	432.2	864.3

4600	AQUA	Chrysler Motors	QE
1508	SILVER	196.4	392.7
1553	FAST BLUE	304.0	608.0
1556	FAST GREEN	382.4	764.8
1552	FAST RED	405.9	811.9

4607	MED CAMEL	General Motors	67BN
1559	YELLOW OXIDE	198.3	396.5
1302	LOW LUSTER CLEAR	280.6	561.3
1554	TINTING WHITE	356.2	712.3
1550	RED OXIDE	397.0	794.0
1501	LANDAU BLACK	414.7	829.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4601	BURGUNDY	Lexus	
1550	RED OXIDE	183.8	367.7
1501	LANDAU BLACK	347.0	694.1
1554	TINTING WHITE	394.8	789.6
1559	YELLOW OXIDE	413.0	825.9

4608	AGATE	Chrysler Motors	AZ
1501	LANDAU BLACK	155.4	310.8
1302	LOW LUSTER CLEAR	291.3	582.5
1559	YELLOW OXIDE	334.6	669.2
1550	RED OXIDE	374.5	749.0
1554	TINTING WHITE	408.0	816.1

4602	IVORY	Lexus	
1554	TINTING WHITE	209.8	419.5
1559	YELLOW OXIDE	381.0	761.9
1550	RED OXIDE	410.2	820.4
1501	LANDAU BLACK	424.6	849.1

4609	DK CHARCOAL	Chrysler Motors	A8
1501	LANDAU BLACK	161.5	323.0
1554	TINTING WHITE	283.6	567.2
1559	YELLOW OXIDE	405.7	811.3
1550	RED OXIDE	416.7	833.3

4603	FIESTA RED	General Motors	74T
1552	FAST RED	328.7	657.4
1551	INDO YELLOW	371.9	743.9
1508	SILVER	396.2	792.5
1553	FAST BLUE	404.2	808.5

4610	LT BROWNSTONE	Chrysler Motors	F3
1554	TINTING WHITE	269.2	538.5
1559	YELLOW OXIDE	380.4	760.8
1550	RED OXIDE	408.1	816.2
1501	LANDAU BLACK	427.7	855.4

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 81

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4611	LT DRIFTWOOD	Chrysler Motors	F4	4618	DK POLO GREEN	General Motors	91T
1554	TINTING WHITE	159.4	318.8	1556	FAST GREEN	211.8	423.5
1302	LOW LUSTER CLEAR	298.6	597.2	1501	LANDAU BLACK	333.5	666.9
1559	YELLOW OXIDE	378.5	757.0	1553	FAST BLUE	375.9	751.8
1550	RED OXIDE	400.7	801.4	1508	SILVER	404.5	809.0
1501	LANDAU BLACK	417.6	835.2				
4612	DK DRIFTWOOD	Chrysler Motors	F8	MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR			
1302	LOW LUSTER CLEAR	136.6	273.2	4619	LT GRAY	General Motors	13AN
1559	YELLOW OXIDE	261.7	523.5	1554	TINTING WHITE	200.5	400.9
1554	TINTING WHITE	321.5	643.0	1302	LOW LUSTER CLEAR	340.1	680.2
1501	LANDAU BLACK	374.4	748.8	1559	YELLOW OXIDE	376.4	752.8
1550	RED OXIDE	411.4	822.9	1501	LANDAU BLACK	405.7	811.3
				1550	RED OXIDE	419.5	839.0
4613	DK GREEN	Chrysler Motors	G8	4620	MED GRAY	General Motors	13BN
1302	LOW LUSTER CLEAR	135.9	271.7	1554	TINTING WHITE	149.5	299.1
1559	YELLOW OXIDE	233.4	466.8	1302	LOW LUSTER CLEAR	287.9	575.9
1501	LANDAU BLACK	325.5	650.9	1559	YELLOW OXIDE	347.8	695.6
1556	FAST GREEN	384.2	768.4	1501	LANDAU BLACK	395.8	791.5
1554	TINTING WHITE	407.3	814.5	1550	RED OXIDE	416.5	833.0
4614	SPICE	Chrysler Motors	TB	4621	DK GRAY	General Motors	13CN
1559	YELLOW OXIDE	206.6	413.3	1554	TINTING WHITE	176.9	353.8
1302	LOW LUSTER CLEAR	343.5	687.0	1559	YELLOW OXIDE	287.6	575.1
1550	RED OXIDE	383.8	767.6	1501	LANDAU BLACK	381.9	763.8
1554	TINTING WHITE	403.9	807.9	1550	RED OXIDE	421.1	842.3
1501	LANDAU BLACK	410.3	820.6				
4615	DK CAMEL	General Motors	67DN	4622	CRANBERRY	Ford Motor	R
1559	YELLOW OXIDE	179.1	358.2	1552	FAST RED	299.5	599.1
1302	LOW LUSTER CLEAR	263.7	527.4	1302	LOW LUSTER CLEAR	380.4	760.8
1550	RED OXIDE	322.4	644.9	1554	TINTING WHITE	394.9	789.8
1554	TINTING WHITE	372.6	745.2	1553	FAST BLUE	404.5	809.0
1501	LANDAU BLACK	412.8	825.6				
4616	CINDER	Chrysler Motors	XA	4623	MED MOCHA	Ford Motor	A
1501	LANDAU BLACK	179.6	359.3	1302	LOW LUSTER CLEAR	137.8	275.7
1302	LOW LUSTER CLEAR	265.3	530.7	1559	YELLOW OXIDE	236.6	473.1
1559	YELLOW OXIDE	350.3	700.5	1554	TINTING WHITE	325.3	650.6
1554	TINTING WHITE	392.4	784.7	1550	RED OXIDE	379.8	759.6
1550	RED OXIDE	409.5	818.9	1501	LANDAU BLACK	413.4	826.9
4617	MED CAMEL	General Motors	67BN	4624	MOCHA	Ford Motor	A
1559	YELLOW OXIDE	264.4	528.8	1554	TINTING WHITE	142.5	285.0
1554	TINTING WHITE	340.5	681.0	1302	LOW LUSTER CLEAR	281.4	562.8
1550	RED OXIDE	395.8	791.5	1559	YELLOW OXIDE	358.0	715.9
1501	LANDAU BLACK	417.1	834.1	1550	RED OXIDE	398.6	797.2
				1501	LANDAU BLACK	416.7	833.3

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 82

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4625	GRAPHITE MET	Ford Motor	P
1501	LANDAU BLACK	222.9	445.7
1508	SILVER	292.5	585.0
1553	FAST BLUE	351.1	702.2
1552	FAST RED	405.2	810.4

4632	FLINT	Honda	
1302	LOW LUSTER CLEAR	136.7	273.4
1559	YELLOW OXIDE	241.6	483.2
1501	LANDAU BLACK	318.5	637.1
1554	TINTING WHITE	365.9	731.9
1550	RED OXIDE	410.3	820.6

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4626	MED PLATINUM	Ford Motor	P
1501	LANDAU BLACK	216.3	432.6
1508	SILVER	401.0	802.0
1553	FAST BLUE	406.7	813.4

4633	MINK	Honda	
1302	LOW LUSTER CLEAR	138.1	276.3
1554	TINTING WHITE	239.4	478.8
1559	YELLOW OXIDE	340.7	681.3
1550	RED OXIDE	387.4	774.8
1501	LANDAU BLACK	414.3	828.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4627	DK TITANIUM	Ford Motor	P
1501	LANDAU BLACK	242.3	484.7
1508	SILVER	373.4	746.7
1552	FAST RED	392.2	784.3
1551	INDO YELLOW	406.2	812.4

4634	YELLOW	Ford Motor	
1554	TINTING WHITE	283.6	567.2
1551	INDO YELLOW	416.6	833.2
1550	RED OXIDE	423.7	847.4
1556	FAST GREEN	425.8	851.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4628	BRIGHT TITANIUM	Ford Motor	K
1508	SILVER	253.7	507.3
1302	LOW LUSTER CLEAR	387.1	774.3
1552	FAST RED	400.5	801.0
1551	INDO YELLOW	406.1	812.3

4635	HONDA BUMPER G	Honda	
1501	LANDAU BLACK	259.1	518.1
1559	YELLOW OXIDE	332.7	665.4
1554	TINTING WHITE	390.3	780.5
1550	RED OXIDE	411.3	822.5

4629	STONE BEIGE	Honda	
1554	TINTING WHITE	272.9	545.9
1559	YELLOW OXIDE	399.9	799.7
1550	RED OXIDE	417.7	835.4
1501	LANDAU BLACK	428.2	856.3

4636	DK MAPLE MET	General Motors	78T
1552	FAST RED	351.0	702.1
1551	INDO YELLOW	373.8	747.7
1553	FAST BLUE	390.1	780.1
1508	SILVER	404.1	808.3

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4630	AZURE BLUE	Honda	
1302	LOW LUSTER CLEAR	134.9	269.8
1501	LANDAU BLACK	237.3	474.6
1552	FAST RED	310.5	620.9
1553	FAST BLUE	378.8	757.5
1554	TINTING WHITE	405.1	810.2

4637	BLACK SAPPHIRE	General Motors	28T
1553	FAST BLUE	336.2	672.4
1551	INDO YELLOW	397.2	794.4
1508	SILVER	402.7	805.4

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4631	COFFEE BEIGE	Honda	
1302	LOW LUSTER CLEAR	137.9	275.9
1559	YELLOW OXIDE	275.6	551.2
1554	TINTING WHITE	360.1	720.1
1550	RED OXIDE	399.8	799.5
1501	LANDAU BLACK	413.5	827.1

4638	LT SAPPHIRE BLUE	General Motors	22T
1508	SILVER	242.5	485.1
1553	FAST BLUE	331.9	663.9
1552	FAST RED	384.0	768.0
1554	TINTING WHITE	400.8	801.6
1551	INDO YELLOW	407.9	815.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 83

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	TAUPE	General Motors	54BN
1302	LOW LUSTER CLEAR	137.7	275.3
1554	TINTING WHITE	237.4	474.8
1559	YELLOW OXIDE	306.1	612.2
1501	LANDAU BLACK	364.5	729.0
1550	RED OXIDE	413.5	827.1

	L-2287 BLUE	Ford Motor	
1508	SILVER	265.3	530.7
1553	FAST BLUE	315.4	630.8
1552	FAST RED	358.1	716.1
1556	FAST GREEN	391.8	783.6
1554	TINTING WHITE	408.1	816.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	LT NEUTRAL	General Motors	52AM
1554	TINTING WHITE	189.0	377.9
1302	LOW LUSTER CLEAR	329.6	659.1
1559	YELLOW OXIDE	393.3	786.6
1550	RED OXIDE	408.2	816.4
1501	LANDAU BLACK	419.3	838.7

	L-2288 PALOMINO	Ford Motor	
1559	YELLOW OXIDE	188.9	377.7
1554	TINTING WHITE	345.8	691.6
1550	RED OXIDE	404.9	809.8
1501	LANDAU BLACK	421.7	843.4

	LT NEUTRAL	General Motors	WA9772
1554	TINTING WHITE	189.0	377.9
1302	LOW LUSTER CLEAR	329.6	659.1
1559	YELLOW OXIDE	393.3	786.6
1550	RED OXIDE	408.2	816.4
1501	LANDAU BLACK	419.3	838.7

	L-2290 WHITE	Ford Motor	
1554	TINTING WHITE	414.6	829.2
1551	INDO YELLOW	425.9	851.8
1550	RED OXIDE	431.5	863.0
1501	LANDAU BLACK	435.9	871.7

	L-957 RED	Ford Motor	
1552	FAST RED	312.6	625.3
1551	INDO YELLOW	393.5	787.0
1554	TINTING WHITE	404.4	808.8
1553	FAST BLUE	404.8	809.6

	L-2505 DK BLUE	Ford Motor	
1553	FAST BLUE	176.1	352.3
1501	LANDAU BLACK	324.6	649.2
1554	TINTING WHITE	384.4	768.7
1551	INDO YELLOW	408.2	816.4

	L-958 BLACK	Ford Motor	
1501	LANDAU BLACK	374.1	748.2
1554	TINTING WHITE	393.9	787.7
1551	INDO YELLOW	406.5	813.0

	L-2613 PARCHMEN	Ford Motor	
1554	TINTING WHITE	265.2	530.5
1559	YELLOW OXIDE	398.5	797.1
1550	RED OXIDE	417.7	835.4
1501	LANDAU BLACK	427.7	855.4

	L-2095 BLUE	Ford Motor	
1508	SILVER	158.3	316.5
1553	FAST BLUE	295.8	591.7
1501	LANDAU BLACK	351.9	703.8
1552	FAST RED	405.5	810.9

	L-2920 RED	Ford Motor	
1552	FAST RED	366.6	733.2
1508	SILVER	397.0	794.0
1551	INDO YELLOW	404.4	808.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	L-2286 DK IVY GOL	Ford Motor	
1508	SILVER	166.8	333.6
1501	LANDAU BLACK	297.7	595.5
1551	INDO YELLOW	385.1	770.3
1554	TINTING WHITE	408.0	816.1

	L-2921 EMBERGLO	Ford Motor	
1552	FAST RED	285.0	570.0
1551	INDO YELLOW	353.5	707.0
1508	SILVER	397.5	795.0
1556	FAST GREEN	404.5	809.0

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 84

PINTS	QUARTS
GRAMS	

4653	L-2929 TURQUOISE	Ford Motor	
1508	SILVER	203.8	407.6
1556	FAST GREEN	303.2	606.5
1553	FAST BLUE	360.4	720.9
1501	LANDAU BLACK	389.4	778.8
1554	TINTING WHITE	407.6	815.3

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4654	L-3096 PARCHMEN	Ford Motor	
1554	TINTING WHITE	345.8	691.6
1559	YELLOW OXIDE	417.5	835.1
1550	RED OXIDE	427.5	855.0
1501	LANDAU BLACK	432.3	864.5

4655	L-3097 DK TURQUOI	Ford Motor	
1553	FAST BLUE	151.8	303.6
1556	FAST GREEN	268.5	536.9
1508	SILVER	345.0	690.1
1501	LANDAU BLACK	404.4	808.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4656	L-3099 SADDLE	Ford Motor	
1559	YELLOW OXIDE	241.9	483.7
1550	RED OXIDE	323.8	647.5
1554	TINTING WHITE	401.5	802.9
1501	LANDAU BLACK	417.3	834.7

4657	L-3116 MAROON	Ford Motor	
1552	FAST RED	360.0	719.9
1508	SILVER	382.9	765.9
1551	INDO YELLOW	394.3	788.5
1501	LANDAU BLACK	404.3	808.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4658	L-3448 NUGGET GO	Ford Motor	
1508	SILVER	299.5	599.1
1552	FAST RED	354.2	708.3
1551	INDO YELLOW	404.7	809.4
1556	FAST GREEN	407.6	815.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4659	L-3625 NUGGET GO	Ford Motor	
1508	SILVER	255.4	510.7
1551	INDO YELLOW	322.3	644.7
1552	FAST RED	368.1	736.3
1554	TINTING WHITE	404.9	809.8
1501	LANDAU BLACK	409.8	819.7

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

PINTS	QUARTS
GRAMS	

4660	L-3627 LT BLUE	Ford Motor	
1508	SILVER	231.0	462.1
1554	TINTING WHITE	314.5	629.1
1553	FAST BLUE	368.9	737.8
1501	LANDAU BLACK	413.1	826.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4661	L-3628 DK IVY GOL	Ford Motor	
1501	LANDAU BLACK	185.5	371.1
1508	SILVER	302.8	605.5
1551	INDO YELLOW	371.9	743.9
1554	TINTING WHITE	393.4	786.8
1556	FAST GREEN	407.6	815.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4662	L-3722 BLACK	Ford Motor	
1501	LANDAU BLACK	374.1	748.2
1554	TINTING WHITE	393.9	787.7
1551	INDO YELLOW	406.5	813.0

4663	L-3724 DK RED	Ford Motor	
1552	FAST RED	339.7	679.4
1508	SILVER	371.2	742.3
1551	INDO YELLOW	388.1	776.2
1553	FAST BLUE	401.4	802.8
1554	TINTING WHITE	404.4	808.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4664	L-3788 MED BLUE	Ford Motor	
1508	SILVER	161.5	323.0
1553	FAST BLUE	308.8	617.7
1501	LANDAU BLACK	386.7	773.3
1552	FAST RED	405.5	810.9

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4665	L-4060 MED IVY GO	Ford Motor	
1508	SILVER	163.3	326.6
1501	LANDAU BLACK	315.8	631.6
1551	INDO YELLOW	394.7	789.5
1556	FAST GREEN	406.3	812.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4666	L-4061 GINGER	Ford Motor	
1559	YELLOW OXIDE	299.2	598.3
1550	RED OXIDE	371.4	742.7
1554	TINTING WHITE	397.4	794.8
1501	LANDAU BLACK	414.4	828.8

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 85

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4667	L-4062 WHITE	Ford Motor	
1554	TINTING WHITE	402.7	805.4
1559	YELLOW OXIDE	432.4	864.9
1501	LANDAU BLACK	434.2	868.3
1550	RED OXIDE	435.5	871.0

4674	LT DRIFTWOOD M	General Motors		33T
1508	SILVER	304.5	609.0	
1552	FAST RED	358.2	716.5	
1551	INDO YELLOW	397.0	794.0	
1501	LANDAU BLACK	407.6	815.3	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4668	L-4063 VERMILLIO	Ford Motor	
1552	FAST RED	243.7	487.4
1551	INDO YELLOW	379.1	758.1
1554	TINTING WHITE	406.1	812.3

4675	DK GREEN GRAY M	General Motors		18T
1501	LANDAU BLACK	170.9	341.8	
1553	FAST BLUE	311.3	622.6	
1556	FAST GREEN	363.9	727.9	
1508	SILVER	404.3	808.6	

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4669	L-4234 GREEN	Ford Motor	
1508	SILVER	136.4	272.8
1501	LANDAU BLACK	246.3	492.7
1551	INDO YELLOW	338.8	677.5
1556	FAST GREEN	405.8	811.7

4676	DK GREEN MET	General Motors		18T
1501	LANDAU BLACK	159.8	319.6	
1553	FAST BLUE	317.4	634.8	
1556	FAST GREEN	366.5	733.0	
1508	SILVER	404.2	808.5	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4670	BUMPER GRAY	Honda	
1501	LANDAU BLACK	185.2	370.3
1302	LOW LUSTER CLEAR	267.4	534.9
1559	YELLOW OXIDE	340.7	681.3
1554	TINTING WHITE	391.3	782.6
1550	RED OXIDE	409.8	819.7

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4677	MED TAUPE MET	General Motors		63T
1552	FAST RED	193.5	387.0	
1508	SILVER	285.0	570.0	
1553	FAST BLUE	353.2	706.4	
1551	INDO YELLOW	404.9	809.8	

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4671	LT CAMEL MET	General Motors		67T
1508	SILVER	259.6	519.3	
1552	FAST RED	320.6	641.3	
1551	INDO YELLOW	374.4	748.8	
1554	TINTING WHITE	401.5	802.9	
1501	LANDAU BLACK	409.1	818.1	

4678	DK PLUM MET	General Motors		88T
1552	FAST RED	194.5	388.9	
1501	LANDAU BLACK	298.5	597.0	
1553	FAST BLUE	377.9	755.8	
1508	SILVER	404.3	808.6	

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4672	LT BEIGE MET	General Motors		57T
1508	SILVER	295.7	591.5	
1552	FAST RED	343.2	686.5	
1501	LANDAU BLACK	370.6	741.2	
1551	INDO YELLOW	396.3	792.7	
1554	TINTING WHITE	408.4	816.8	

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4679	LT CANYON YELLO	General Motors		55T
1554	TINTING WHITE	348.0	696.0	
1559	YELLOW OXIDE	427.4	854.8	
1550	RED OXIDE	430.9	861.8	
1556	FAST GREEN	432.4	864.9	

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4673	Lt. Beige Met	General Motors	
1508	SILVER	234.9	469.8
1552	FAST RED	316.8	633.5
1501	LANDAU BLACK	367.7	735.5
1551	INDO YELLOW	428.2	856.3

4680	SILVER BUMPER	Ford Motor		J
1300	HIGH GLOSS CLEAR	236.6	473.3	
2024	SILVER BASE	417.3	834.7	
1554	TINTING WHITE	418.9	837.7	

Yes(see 5979)

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 86

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
4681	MED QUARTZ	Chrysler Motors		D6	4688	CINDER	Chrysler Motors	XA
1302	LOW LUSTER CLEAR	138.7	277.4		1501	LANDAU BLACK	157.5	315.0
1554	TINTING WHITE	252.2	504.5		1302	LOW LUSTER CLEAR	293.5	586.9
1501	LANDAU BLACK	322.2	644.5		1559	YELLOW OXIDE	360.1	720.3
1559	YELLOW OXIDE	379.8	759.6		1554	TINTING WHITE	393.8	787.6
1550	RED OXIDE	414.0	828.0		1550	RED OXIDE	407.8	815.7
4682	MED DRIFTWOOD	Chrysler Motors		F6	4689	DK CRANBERRY	Ford Motor	R
1302	LOW LUSTER CLEAR	138.4	276.8		1552	FAST RED	323.9	647.7
1554	TINTING WHITE	262.8	525.5		1553	FAST BLUE	403.7	807.3
1559	YELLOW OXIDE	355.2	710.4					
1501	LANDAU BLACK	387.1	774.3					
1550	RED OXIDE	415.3	830.7					
4683	DK BROWNSTONE	Chrysler Motors		F7	4690	ARCTIC WHITE	General Motors	9N
1302	LOW LUSTER CLEAR	136.5	273.0		1554	TINTING WHITE	282.8	565.6
1559	YELLOW OXIDE	259.3	518.5		1302	LOW LUSTER CLEAR	424.3	848.5
1554	TINTING WHITE	318.3	636.7		1553	FAST BLUE	424.5	848.9
1501	LANDAU BLACK	374.1	748.2		1559	YELLOW OXIDE	424.7	849.3
1550	RED OXIDE	411.3	822.5					
4684	CORDOVAN	General Motors		H9	4691	MED DK NEUTRAL	General Motors	52CN
1550	RED OXIDE	158.0	316.0		1559	YELLOW OXIDE	167.0	334.0
1302	LOW LUSTER CLEAR	294.5	589.0		1554	TINTING WHITE	289.9	579.9
1501	LANDAU BLACK	391.1	782.2		1501	LANDAU BLACK	355.4	710.8
1554	TINTING WHITE	408.6	817.2		1550	RED OXIDE	418.8	837.5
4685	CORDOVAN	General Motors		H9	4692	MED NEUTRAL	General Motors	52BN
1550	RED OXIDE	199.4	398.8		1554	TINTING WHITE	176.9	353.8
1302	LOW LUSTER CLEAR	335.6	671.3		1559	YELLOW OXIDE	322.4	644.9
1553	FAST BLUE	384.4	768.7		1550	RED OXIDE	375.4	750.9
1501	LANDAU BLACK	401.6	803.1		1501	LANDAU BLACK	422.1	844.2
1554	TINTING WHITE	408.4	816.8					
4686	MED BEIGE	General Motors		64BN	4693	LT BEIGE	General Motors	64AN
1302	LOW LUSTER CLEAR	137.3	274.6		1302	LOW LUSTER CLEAR	138.7	277.4
1559	YELLOW OXIDE	270.3	540.6		1554	TINTING WHITE	265.5	531.1
1554	TINTING WHITE	344.4	688.8		1559	YELLOW OXIDE	370.7	741.4
1550	RED OXIDE	389.9	779.8		1550	RED OXIDE	403.9	807.9
1501	LANDAU BLACK	412.9	825.7		1501	LANDAU BLACK	415.9	831.8
4687	DK SPICE	Chrysler Motors		TC	4694	MED BEIGE	General Motors	64BN
1559	YELLOW OXIDE	196.3	392.5		1302	LOW LUSTER CLEAR	137.4	274.7
1302	LOW LUSTER CLEAR	332.5	665.0		1559	YELLOW OXIDE	265.3	530.7
1550	RED OXIDE	389.6	779.2		1554	TINTING WHITE	342.9	685.7
1501	LANDAU BLACK	408.9	817.8		1550	RED OXIDE	389.2	778.4
					1501	LANDAU BLACK	413.1	826.1

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 87

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4695	DK BEIGE	General Motors	64DN	4700	BLACK	Ford Motor	A
1302	LOW LUSTER CLEAR	137.4	274.7	1501	LANDAU BLACK	266.1	532.2
1559	YELLOW OXIDE	274.5	548.9	1302	LOW LUSTER CLEAR	347.6	695.2
1550	RED OXIDE	330.6	661.2	1559	YELLOW OXIDE	372.3	744.6
1554	TINTING WHITE	375.8	751.6	1554	TINTING WHITE	391.5	783.0
1501	LANDAU BLACK	411.0	821.9	1553	FAST BLUE	406.1	812.3
4696	MED GRAY	General Motors	14BN	4701	CLR CRSTL BLUE F	Ford Motor	A
1554	TINTING WHITE	205.4	410.8	1554	TINTING WHITE	315.0	630.0
1559	YELLOW OXIDE	281.1	562.2	1501	LANDAU BLACK	384.1	768.2
1501	LANDAU BLACK	338.5	677.0	1550	RED OXIDE	408.0	816.1
1302	LOW LUSTER CLEAR	390.9	781.9	1553	FAST BLUE	428.7	857.5
1550	RED OXIDE	421.9	843.8				
4697	DK GRAY	General Motors	14CN	4702	DK TITANIUM	Ford Motor	P
1554	TINTING WHITE	140.5	281.0	1501	LANDAU BLACK	181.5	363.1
1559	YELLOW OXIDE	223.9	447.8	1559	YELLOW OXIDE	332.7	665.4
1302	LOW LUSTER CLEAR	306.3	612.6	1550	RED OXIDE	373.8	747.7
1501	LANDAU BLACK	382.9	765.9	1554	TINTING WHITE	411.7	823.5
1550	RED OXIDE	417.1	834.1				
4698	LT GRAY	General Motors	14AN	4703	OXFORD WHITE	General Motors	W
1554	TINTING WHITE	255.7	511.5	1554	TINTING WHITE	434.2	868.5
1559	YELLOW OXIDE	316.4	632.9	1501	LANDAU BLACK	436.7	873.4
1302	LOW LUSTER CLEAR	369.2	738.3	1559	YELLOW OXIDE	437.1	874.2
1501	LANDAU BLACK	406.4	812.8	1553	FAST BLUE	437.2	874.4
1550	RED OXIDE	425.0	850.1				
4698	LT GRAY	General Motors	WA9781	4704	DK CRYSTAL BLUE	Ford Motor	A
1554	TINTING WHITE	255.7	511.5	1501	LANDAU BLACK	211.6	423.1
1559	YELLOW OXIDE	316.4	632.9	1554	TINTING WHITE	369.0	738.0
1302	LOW LUSTER CLEAR	369.2	738.3	1553	FAST BLUE	413.3	826.7
1501	LANDAU BLACK	406.4	812.8	1552	FAST RED	416.5	833.0
1550	RED OXIDE	425.0	850.1				
4699	VERY DK GRAY	General Motors	14DN	4705	Medium Opal	Ford Motor	M4221H/YCCA
1501	LANDAU BLACK	123.8	247.6	1554	TINTING WHITE	127.5	255.0
1559	YELLOW OXIDE	216.4	432.8	1302	LOW LUSTER CLEAR	249.0	498.1
1302	LOW LUSTER CLEAR	300.0	600.0	1550	RED OXIDE	355.2	710.5
1554	TINTING WHITE	382.0	764.0	1553	FAST BLUE	400.3	800.6
1550	RED OXIDE	412.8	825.6	1551	INDO YELLOW	425.3	850.6
4706	DK OPAL	General Motors	WA9902	4706	DK OPAL	Ford Motor	C
1501	LANDAU BLACK	123.8	247.6	1302	LOW LUSTER CLEAR	137.6	275.1
1559	YELLOW OXIDE	216.4	432.8	1550	RED OXIDE	235.7	471.4
1302	LOW LUSTER CLEAR	300.0	600.0	1554	TINTING WHITE	310.4	620.7
1554	TINTING WHITE	382.0	764.0	1559	YELLOW OXIDE	369.4	738.7
1550	RED OXIDE	412.8	825.6	1553	FAST BLUE	412.4	824.8

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 88

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4707	CHARCOAL ARGEN	Ford Motor	F
1508	SILVER	211.8	423.5
2024	SILVER BASE	320.6	641.3
1552	FAST RED	374.3	748.6
1553	FAST BLUE	395.2	790.4
1551	INDO YELLOW	416.1	832.2

4714	LT MOCHA	Ford Motor	A
1554	TINTING WHITE	388.8	777.7
1559	YELLOW OXIDE	424.8	849.7
1550	RED OXIDE	433.2	866.4
1501	LANDAU BLACK	434.7	869.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4708	MED MOCHA	Ford Motor	A
1552	FAST RED	143.3	286.5
1508	SILVER	283.7	567.3
1501	LANDAU BLACK	353.1	706.2
1551	INDO YELLOW	405.8	811.7

4715	MED PLATINUM	Ford Motor	B
1501	LANDAU BLACK	280.9	561.8
1508	SILVER	406.2	812.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4709	ULTRA RED	Ford Motor	WU
1552	FAST RED	383.6	767.2
1551	INDO YELLOW	397.6	795.2
1554	TINTING WHITE	404.5	809.0

4716	PASTEL ALABASTE	Ford Motor	H
1554	TINTING WHITE	398.1	796.1
1559	YELLOW OXIDE	428.2	856.3
1550	RED OXIDE	432.4	864.9
1501	LANDAU BLACK	435.1	870.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4710	MED GRAY	Ford Motor	D
1508	SILVER	286.8	573.6
1501	LANDAU BLACK	371.2	742.3
1554	TINTING WHITE	403.7	807.3
1556	FAST GREEN	410.1	820.2

4717	PARCHMENT	BMW	356
1554	TINTING WHITE	159.9	319.8
1302	LOW LUSTER CLEAR	299.2	598.3
1551	INDO YELLOW	342.2	684.4
1552	FAST RED	383.4	766.8
1501	LANDAU BLACK	415.2	830.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4711	LT GRAY	Ford Motor	D
1554	TINTING WHITE	181.5	362.9
1501	LANDAU BLACK	293.8	587.7
1559	YELLOW OXIDE	394.9	789.8
1550	RED OXIDE	421.0	842.1

4718	ULTRAMARINE	BMW	355
1501	LANDAU BLACK	141.4	282.7
1302	LOW LUSTER CLEAR	280.6	561.3
1554	TINTING WHITE	344.6	689.1
1552	FAST RED	383.8	767.6
1553	FAST BLUE	408.2	816.4

4712	MOCHA FROST ME	Ford Motor	A
1508	SILVER	275.6	551.2
1552	FAST RED	363.8	727.5
1551	INDO YELLOW	401.8	803.5
1501	LANDAU BLACK	407.3	814.5

4719	MED GRAY MET BU	Ford Motor	P
1508	SILVER	212.7	425.4
2024	SILVER BASE	329.0	658.0
1501	LANDAU BLACK	395.1	790.2
1554	TINTING WHITE	407.7	815.5
1551	INDO YELLOW	418.0	836.0

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4713	MED REGATTA BL	Ford Motor	B
1508	SILVER	152.6	305.1
2024	SILVER BASE	286.2	572.5
1553	FAST BLUE	347.3	694.6
1501	LANDAU BLACK	393.1	786.2
1552	FAST RED	417.5	835.1

4720	MED TITANIUM ME	Ford Motor	C
1508	SILVER	260.1	520.2
1501	LANDAU BLACK	333.7	667.5
1552	FAST RED	370.1	740.2
2024	SILVER BASE	393.8	787.6
1551	INDO YELLOW	409.4	818.7

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 89

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4721	MED TITANIUM BU	Ford Motor		C	4728	BROWN	Mazda
1508	SILVER	188.3	376.6		1302	LOW LUSTER CLEAR	137.0
1501	LANDAU BLACK	290.2	580.5		1559	YELLOW OXIDE	257.5
2024	SILVER BASE	353.0	706.0		1501	LANDAU BLACK	310.9
1552	FAST RED	396.6	793.3		1550	RED OXIDE	361.5
1551	INDO YELLOW	412.0	824.0		1554	TINTING WHITE	410.9
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR							
4722	MED LT TITANIUM	Ford Motor		P	4729	BLUE	Mazda
1554	TINTING WHITE	250.9	501.8		1302	LOW LUSTER CLEAR	135.9
1559	YELLOW OXIDE	327.9	655.9		1501	LANDAU BLACK	255.3
1501	LANDAU BLACK	381.1	762.3		1553	FAST BLUE	316.7
1550	RED OXIDE	426.2	852.3		1550	RED OXIDE	362.4
					1554	TINTING WHITE	407.8
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR							
4723	DK CRYSTAL BLUE	Ford Motor		A	4730	THOMAS BUS GREE	
1501	LANDAU BLACK	172.1	344.3		1501	LANDAU BLACK	135.1
1553	FAST BLUE	299.7	599.5		1556	FAST GREEN	240.0
1554	TINTING WHITE	387.1	774.3		1551	INDO YELLOW	332.4
1550	RED OXIDE	411.2	822.3		1554	TINTING WHITE	410.2
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR							
4724	TITANIUM	Ford Motor		C	4731	BLUEBIRD GREEN	
1554	TINTING WHITE	141.4	282.7		1556	FAST GREEN	120.0
1559	YELLOW OXIDE	256.7	513.4		1551	INDO YELLOW	235.8
1501	LANDAU BLACK	359.5	719.0		1501	LANDAU BLACK	334.5
1550	RED OXIDE	419.0	838.1		1554	TINTING WHITE	410.0
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR							
4725	DK BRONZE	General Motors	76DM		4732	BUMPER GRAY	BMW
1550	RED OXIDE	249.2	498.4		1501	LANDAU BLACK	207.4
1501	LANDAU BLACK	364.9	729.8		1559	YELLOW OXIDE	301.9
1552	FAST RED	407.6	815.3		1554	TINTING WHITE	383.7
1554	TINTING WHITE	410.8	821.6		1550	RED OXIDE	413.6
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR							
4726	BEIGE	Acura			4733	DK SILVER GLOSS	General Motors
1554	TINTING WHITE	157.6	315.2		1501	LANDAU BLACK	177.3
1302	LOW LUSTER CLEAR	296.9	593.8		1508	SILVER	329.3
1559	YELLOW OXIDE	401.7	803.3		2024	SILVER BASE	373.5
1550	RED OXIDE	412.0	824.0		1553	FAST BLUE	396.9
1501	LANDAU BLACK	417.7	835.4		1552	FAST RED	410.1
MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR							
4727	TAUPE	Mazda			4734	PORTOLA RED	
1554	TINTING WHITE	176.1	352.3		1552	FAST RED	302.9
1302	LOW LUSTER CLEAR	319.7	639.4		1551	INDO YELLOW	386.7
1552	FAST RED	358.6	717.3		1554	TINTING WHITE	405.4
1551	INDO YELLOW	393.4	786.8				
1501	LANDAU BLACK	416.6	833.2				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 90

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4735	Palomino		
1559	YELLOW OXIDE	259.7	519.4
1554	TINTING WHITE	390.1	780.2
1550	RED OXIDE	422.1	844.2
1558	BRITE RED	428.6	857.2
1501	LANDAU BLACK	430.7	861.4

4743	RED	Corvette	
1552	FAST RED		262.5
1551	INDO YELLOW		343.8
1550	RED OXIDE		382.6
1554	TINTING WHITE		406.7
			813.4

4737	BRIGHT BLUE	Corvette	414-415
1553	FAST BLUE	185.5	371.1
1508	SILVER	345.3	690.7
1501	LANDAU BLACK	376.4	752.8
1556	FAST GREEN	397.8	795.5
1554	TINTING WHITE	405.8	811.7

4744	BRONZE BUMPER	Ford Motor	
1508	SILVER		162.6
1501	LANDAU BLACK		261.4
1552	FAST RED		340.4
1551	INDO YELLOW		406.2
			812.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4738	BRIGHT BLUE	Corvette	411-412
1553	FAST BLUE	193.9	387.8
1508	SILVER	370.2	740.4
1501	LANDAU BLACK	394.2	788.3
1556	FAST GREEN	405.3	810.5

4745	BROWN	Honda	
1302	LOW LUSTER CLEAR		136.0
1559	YELLOW OXIDE		267.5
1501	LANDAU BLACK		344.4
1550	RED OXIDE		395.2
1554	TINTING WHITE		408.5
			817.0

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4739	RED	Corvette	72-722
1552	FAST RED	312.6	625.3
1551	INDO YELLOW	393.5	787.0
1554	TINTING WHITE	404.4	808.8
1553	FAST BLUE	404.8	809.6

4746	VIGOR BEIGE	Acura	
1302	LOW LUSTER CLEAR		137.9
1554	TINTING WHITE		275.6
1552	FAST RED		333.9
1551	INDO YELLOW		375.7
1501	LANDAU BLACK		413.5
			827.1

4740	OXBLOOD	Corvette	425
1552	FAST RED	305.2	610.5
1550	RED OXIDE	389.7	779.4
1554	TINTING WHITE	401.5	802.9
1553	FAST BLUE	407.0	814.0

4748	LT SADDLE	General Motors	58T
1559	YELLOW OXIDE		139.9
1302	LOW LUSTER CLEAR		278.2
1554	TINTING WHITE		386.7
1550	RED OXIDE		406.8
1501	LANDAU BLACK		415.0
			829.9

4741	BLUE	Corvette	418-419
1501	LANDAU BLACK	216.2	432.4
1553	FAST BLUE	346.1	692.2
1556	FAST GREEN	385.1	770.3
1554	TINTING WHITE	405.7	811.3

4749	PROTEGE BROWN	Mazda	
1559	YELLOW OXIDE		139.6
1302	LOW LUSTER CLEAR		220.3
1501	LANDAU BLACK		299.0
1554	TINTING WHITE		363.7
1550	RED OXIDE		413.0
			825.9

4742	ROMAN RED	Corvette	
1552	FAST RED	260.7	521.4
1551	INDO YELLOW	385.2	770.5
1554	TINTING WHITE	405.5	810.9

4750	LT SILVER GRAY	BMW	0394-0451
1554	TINTING WHITE		248.9
1302	LOW LUSTER CLEAR		389.6
1559	YELLOW OXIDE		406.0
1501	LANDAU BLACK		418.2
1550	RED OXIDE		422.6
			845.1

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 91

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	AQUA	Ford Motor	
1508	SILVER	234.8	469.7
1556	FAST GREEN	304.6	609.1
1553	FAST BLUE	351.1	702.2
1554	TINTING WHITE	395.5	791.0
1501	LANDAU BLACK	410.0	820.0

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	LT BLUE MET	Ford Motor	
1508	SILVER	321.1	642.2
1553	FAST BLUE	351.4	702.8
1501	LANDAU BLACK	377.5	755.1
1554	TINTING WHITE	400.2	800.5
1551	INDO YELLOW	409.4	818.7

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	MED BLUE MET	Ford Motor	
1508	SILVER	264.3	528.6
1553	FAST BLUE	349.5	699.0
1552	FAST RED	386.9	773.9
1551	INDO YELLOW	397.3	794.6
1554	TINTING WHITE	407.6	815.3

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	GOLD	Ford Motor	
1508	SILVER	262.5	525.0
1551	INDO YELLOW	316.8	633.7
1552	FAST RED	370.8	741.6
1554	TINTING WHITE	394.3	788.5
1501	LANDAU BLACK	408.9	817.8

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	EMBERGLO	Ford Motor	
1552	FAST RED	366.6	733.2
1508	SILVER	397.0	794.0
1551	INDO YELLOW	404.4	808.8

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	TURQUOISE MET	Ford Motor	
1508	SILVER	140.9	281.8
1556	FAST GREEN	259.8	519.7
1553	FAST BLUE	337.7	675.5
1501	LANDAU BLACK	405.6	811.1

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	LT IVY GOLD	Ford Motor	
1508	SILVER	298.9	597.7
1551	INDO YELLOW	342.3	684.6
1552	FAST RED	376.6	753.2
1501	LANDAU BLACK	407.6	815.3

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	DK QUARTZ	Chrysler Motors	S6
1302	LOW LUSTER CLEAR	136.6	273.2
1501	LANDAU BLACK	250.5	501.0
1559	YELLOW OXIDE	314.9	629.9
1550	RED OXIDE	364.4	728.8
1554	TINTING WHITE	409.5	818.9

	PEARL WHITE	Ford Motor	
1554	TINTING WHITE	394.4	788.9
1559	YELLOW OXIDE	429.0	858.0
1501	LANDAU BLACK	433.8	867.5
1550	RED OXIDE	434.8	869.6

	OPAL FROST	Ford Motor	C
1554	TINTING WHITE	355.5	711.0
1501	LANDAU BLACK	423.6	847.2
1552	FAST RED	427.7	855.4
1553	FAST BLUE	431.4	862.8

	SEAMIST GREEN	Ford Motor	
1508	SILVER	338.7	677.4
1551	INDO YELLOW	382.9	765.9
1501	LANDAU BLACK	408.1	816.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	TAN	Chrysler Motors	KA
1559	YELLOW OXIDE	167.6	335.2
1302	LOW LUSTER CLEAR	304.7	609.3
1550	RED OXIDE	361.1	722.2
1554	TINTING WHITE	400.1	800.3
1501	LANDAU BLACK	411.3	822.5

	DK BLUE MET	Ford Motor	
1553	FAST BLUE	217.2	434.3
1501	LANDAU BLACK	349.3	698.6
1508	SILVER	402.3	804.7

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

	LT DRIFTWOOD M	Chrysler Motors	FA
1508	SILVER	385.7	771.4
1552	FAST RED	396.2	792.5
1551	INDO YELLOW	404.8	809.6
1554	TINTING WHITE	408.9	817.8

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 92

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	EMERALD GREEN	Chrysler Motors	GF
4765			
1556	FAST GREEN	227.3	454.7
1553	FAST BLUE	372.2	744.4
1501	LANDAU BLACK	391.1	782.2
1508	SILVER	403.6	807.1

	MED AQUAMARINE	Ford Motor	D
4772			
1501	LANDAU BLACK	138.5	277.0
1554	TINTING WHITE	263.0	525.9
1553	FAST BLUE	367.4	734.7
1556	FAST GREEN	413.5	827.1

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	MED BEIGE	General Motors	63BN
4766			
1559	YELLOW OXIDE	141.1	282.2
1302	LOW LUSTER CLEAR	278.6	557.3
1554	TINTING WHITE	347.0	694.1
1550	RED OXIDE	389.1	778.2
1501	LANDAU BLACK	412.5	825.0

	MED AQUAMARINE	Ford Motor	D
4773			
1553	FAST BLUE	219.8	439.7
1501	LANDAU BLACK	314.3	628.5
1556	FAST GREEN	381.8	763.6
1554	TINTING WHITE	405.2	810.4

	DK BEIGE	General Motors	63DN
4767			
1302	LOW LUSTER CLEAR	137.1	274.2
1559	YELLOW OXIDE	267.2	534.5
1550	RED OXIDE	325.7	651.3
1554	TINTING WHITE	373.1	746.1
1501	LANDAU BLACK	411.2	822.3

	LT SILVER GLOSS	General Motors	
4774			
1508	SILVER	399.6	799.1
1501	LANDAU BLACK	405.9	811.9
1551	INDO YELLOW	407.6	815.1
1552	FAST RED	408.8	817.6

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	LT BEIGE	General Motors	64AN
4768			
1302	LOW LUSTER CLEAR	138.7	277.4
1554	TINTING WHITE	265.5	531.1
1559	YELLOW OXIDE	370.7	741.4
1550	RED OXIDE	403.9	807.9
1501	LANDAU BLACK	415.9	831.8

	DK SILVER GLOSS	General Motors	
4775			
1508	SILVER	285.4	570.8
1501	LANDAU BLACK	407.6	815.3
		0.0	0.0

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	MOCHA FROST	Ford Motor	A
4769			
1554	TINTING WHITE	192.9	385.9
1559	YELLOW OXIDE	326.4	652.8
1550	RED OXIDE	390.2	780.3
1501	LANDAU BLACK	423.3	846.6

	SILVER	Ford Motor	J
4776			
1554	TINTING WHITE	339.7	679.4
1501	LANDAU BLACK	386.5	772.9
1559	YELLOW OXIDE	419.8	839.6
1550	RED OXIDE	431.0	862.0

	LAPIS BLUE	Ford Motor	V
4770			
1553	FAST BLUE	174.4	348.8
1554	TINTING WHITE	276.5	552.9
1501	LANDAU BLACK	357.1	714.2
1552	FAST RED	411.4	822.7

	AQUAMARINE	Ford Motor	D
4778			
1554	TINTING WHITE	154.5	308.9
1501	LANDAU BLACK	291.7	583.5
1553	FAST BLUE	378.2	756.4
1556	FAST GREEN	415.8	831.6

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	RUBY	Ford Motor	Y
4771			
1552	FAST RED	384.1	768.2
1554	TINTING WHITE	395.1	790.2
1553	FAST BLUE	404.8	809.6

	DELTA GREY	Ford Motor	D
4779			
1302	LOW LUSTER CLEAR	137.9	275.9
1554	TINTING WHITE	241.9	483.7
1501	LANDAU BLACK	326.7	653.4
1559	YELLOW OXIDE	411.1	822.1
1550	RED OXIDE	413.3	826.5

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 93

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	GRAPHITE	Ford Motor	P
1501	LANDAU BLACK	280.6	561.3
1508	SILVER	343.6	687.2
1553	FAST BLUE	375.3	750.5
1552	FAST RED	405.4	810.7

	DK CHERRY MET	General Motors	77T
1552	FAST RED	299.3	598.7
1553	FAST BLUE	361.6	723.1
1551	INDO YELLOW	394.3	788.7
1508	SILVER	403.9	807.9

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	MED DK GRAY	Ford Motor	R
1554	TINTING WHITE	227.7	455.4
1501	LANDAU BLACK	358.9	717.8
1559	YELLOW OXIDE	399.1	798.2
1550	RED OXIDE	423.2	846.5

	DK GRAY	Ford Motor	R
1501	LANDAU BLACK	290.9	581.8
1559	YELLOW OXIDE	352.4	704.7
1554	TINTING WHITE	410.5	821.0

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	MED DK GRAY	Ford Motor	R
1554	TINTING WHITE	148.2	296.4
1300	HIGH GLOSS CLEAR	286.9	573.8
1501	LANDAU BLACK	375.8	751.6
1559	YELLOW OXIDE	399.7	799.3
1550	RED OXIDE	415.8	831.6

	WILDBERRY	Chrysler Motors	MB
1552	FAST RED	311.3	622.6
1553	FAST BLUE	366.6	733.2
1551	INDO YELLOW	394.3	788.5
1508	SILVER	403.9	807.9

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	DK OPAL	Ford Motor	C
1501	LANDAU BLACK	188.7	377.3
1300	HIGH GLOSS CLEAR	323.3	646.6
1554	TINTING WHITE	387.5	775.0
1552	FAST RED	402.3	804.7

	RUBY RED	General Motors	79
1552	FAST RED	376.4	752.8
1501	LANDAU BLACK	387.8	775.6
1553	FAST BLUE	396.6	793.3
1554	TINTING WHITE	404.5	809.0

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	MED GRAY	Ford Motor	R
1554	TINTING WHITE	298.6	597.2
1501	LANDAU BLACK	375.5	751.1
1559	YELLOW OXIDE	415.3	830.7
1550	RED OXIDE	428.2	856.3

	BORDEAUX RED	General Motors	75
1552	FAST RED	346.7	693.3
1553	FAST BLUE	398.1	796.1
1554	TINTING WHITE	404.2	808.5

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	OXFORD WHITE	Ford Motor	W
1554	TINTING WHITE	432.9	865.8
1559	YELLOW OXIDE	435.0	870.0
1501	LANDAU BLACK	436.9	873.8
1553	FAST BLUE	437.1	874.2

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	TORCH RED	General Motors	70
1552	FAST RED	250.0	500.1
1551	INDO YELLOW	375.1	750.1
1554	TINTING WHITE	406.3	812.6

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

	BRONZE MET	General Motors	59T
1501	LANDAU BLACK	205.8	411.5
1508	SILVER	287.9	575.9
1552	FAST RED	353.4	706.8
1551	INDO YELLOW	405.6	811.1

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	ARCTIC WHITE	General Motors	10N
1554	TINTING WHITE	282.6	565.3
1302	LOW LUSTER CLEAR	424.2	848.4
1553	FAST BLUE	424.5	848.9
1559	YELLOW OXIDE	424.6	849.1
1501	LANDAU BLACK	424.7	849.3

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 94

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4795	TRAVERTINE	Audi		4802	BLACK	Mazda	
1559	YELLOW OXIDE	154.9	309.9	1302	LOW LUSTER CLEAR	135.3	270.6
1302	LOW LUSTER CLEAR	291.1	582.2	1501	LANDAU BLACK	256.3	512.6
1554	TINTING WHITE	348.8	697.7	1552	FAST RED	320.4	640.9
1550	RED OXIDE	390.5	781.1	1551	INDO YELLOW	368.5	737.0
1501	LANDAU BLACK	412.0	824.0	1554	TINTING WHITE	406.2	812.4
4796	ECRU	Audi		4803	TAN	Mazda	
1554	TINTING WHITE	188.6	377.2	1302	LOW LUSTER CLEAR	139.3	278.5
1302	LOW LUSTER CLEAR	328.3	656.6	1559	YELLOW OXIDE	277.4	554.8
1559	YELLOW OXIDE	391.3	782.6	1554	TINTING WHITE	389.4	778.8
1501	LANDAU BLACK	406.3	812.6	1550	RED OXIDE	410.6	821.2
1550	RED OXIDE	419.2	838.5	1501	LANDAU BLACK	415.2	830.3
4797	TAN	Mazda		4804	RED	Mazda	
1559	YELLOW OXIDE	203.6	407.2	1552	FAST RED	241.1	482.2
1302	LOW LUSTER CLEAR	340.5	681.0	1302	LOW LUSTER CLEAR	322.3	644.7
1550	RED OXIDE	373.2	746.3	1550	RED OXIDE	380.8	761.5
1554	TINTING WHITE	405.3	810.5	1554	TINTING WHITE	402.9	805.8
1501	LANDAU BLACK	411.0	821.9	1501	LANDAU BLACK	406.5	813.0
4798	SLATE	Mazda		4805	SMOKE GRAY	Mazda	
1554	TINTING WHITE	161.0	322.1	1554	TINTING WHITE	165.3	330.6
1302	LOW LUSTER CLEAR	299.8	599.6	1302	LOW LUSTER CLEAR	303.8	607.6
1501	LANDAU BLACK	358.7	717.4	1501	LANDAU BLACK	369.2	738.3
1559	YELLOW OXIDE	413.7	827.5	1551	INDO YELLOW	393.8	787.6
1553	FAST BLUE	416.8	833.5	1552	FAST RED	415.7	831.4
4799	GRAY	Mazda		4806	BEIGE	Mazda	
1554	TINTING WHITE	196.7	393.3	1559	YELLOW OXIDE	208.4	416.9
1501	LANDAU BLACK	283.1	566.2	1554	TINTING WHITE	317.1	634.2
1302	LOW LUSTER CLEAR	366.4	732.8	1550	RED OXIDE	382.6	765.1
1550	RED OXIDE	408.2	816.4	1501	LANDAU BLACK	418.7	837.3
1559	YELLOW OXIDE	419.9	839.8				
4800	TAUPE	Mazda		4807	GRAY	Mazda	
1554	TINTING WHITE	155.1	310.3	1554	TINTING WHITE	210.2	420.5
1302	LOW LUSTER CLEAR	294.2	588.4	1559	YELLOW OXIDE	321.1	642.2
1559	YELLOW OXIDE	367.7	735.5	1501	LANDAU BLACK	393.0	786.0
1550	RED OXIDE	393.9	787.7	1550	RED OXIDE	423.5	847.0
1501	LANDAU BLACK	417.1	834.3				
4801	GRAY	Mazda		4808	TAUPE	Mazda	
1554	TINTING WHITE	156.5	312.9	1302	LOW LUSTER CLEAR	137.0	274.0
1302	LOW LUSTER CLEAR	240.3	480.5	1559	YELLOW OXIDE	257.5	514.9
1501	LANDAU BLACK	312.3	624.5	1501	LANDAU BLACK	310.9	621.9
1559	YELLOW OXIDE	382.4	764.8	1550	RED OXIDE	361.5	723.0
1550	RED OXIDE	418.0	836.0	1554	TINTING WHITE	410.9	821.8

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 95

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
4809	LT TAUPE	Mazda		4816	DK MONTANA BLU	General Motors		21
1554	TINTING WHITE	178.6	357.2	1501	LANDAU BLACK	104.5	209.0	
1302	LOW LUSTER CLEAR	314.0	628.0	1552	FAST RED	199.8	399.6	
1551	INDO YELLOW	352.8	705.7	1553	FAST BLUE	286.2	572.5	
1552	FAST RED	390.8	781.7	1302	LOW LUSTER CLEAR	354.4	708.7	
1501	LANDAU BLACK	416.8	833.5	1554	TINTING WHITE	406.8	813.6	
4810	CAMRY GRAY	Toyota		4817	DK MOCHA	General Motors		34
1302	LOW LUSTER CLEAR	136.7	273.4	1501	LANDAU BLACK	183.9	367.8	
1501	LANDAU BLACK	241.5	483.0	1550	RED OXIDE	298.3	596.6	
1554	TINTING WHITE	327.3	654.6	1302	LOW LUSTER CLEAR	366.3	732.6	
1552	FAST RED	373.9	747.8	1554	TINTING WHITE	400.0	799.9	
1551	INDO YELLOW	409.9	819.9	1553	FAST BLUE	409.4	818.7	
4811	CAMRY BLUE	Toyota		4818	MOCHA	General Motors		34
1501	LANDAU BLACK	201.5	403.0	1559	YELLOW OXIDE	97.8	195.5	
1302	LOW LUSTER CLEAR	337.3	674.7	1550	RED OXIDE	191.0	382.1	
1554	TINTING WHITE	390.4	780.7	1501	LANDAU BLACK	271.2	542.5	
1553	FAST BLUE	404.1	808.3	1554	TINTING WHITE	344.9	689.9	
1552	FAST RED	407.8	815.7	1302	LOW LUSTER CLEAR	413.8	827.6	
4812	CAMRY LT BROWN	Toyota		4819	MED DK TEAL	General Motors		37
1559	YELLOW OXIDE	137.1	274.2	1501	LANDAU BLACK	147.3	294.7	
1302	LOW LUSTER CLEAR	219.7	439.5	1554	TINTING WHITE	261.1	522.1	
1554	TINTING WHITE	293.1	586.2	1556	FAST GREEN	341.8	683.6	
1501	LANDAU BLACK	354.2	708.3	1302	LOW LUSTER CLEAR	412.0	824.0	
1550	RED OXIDE	413.6	827.3					
4813	CAMRY BROWN	Toyota		4820	MED DK ADRIATIC	General Motors		30
1501	LANDAU BLACK	155.6	311.2	1302	LOW LUSTER CLEAR	137.7	275.3	
1302	LOW LUSTER CLEAR	236.9	473.9	1554	TINTING WHITE	254.1	508.3	
1550	RED OXIDE	315.2	630.4	1501	LANDAU BLACK	326.8	653.6	
1559	YELLOW OXIDE	375.0	749.9	1550	RED OXIDE	371.5	742.9	
1554	TINTING WHITE	409.8	819.7	1553	FAST BLUE	413.1	826.1	
4814	TAUPE	Lexus		4821	BRIGHT AQUA	General Motors		44
1559	YELLOW OXIDE	125.7	251.4	1556	FAST GREEN	157.3	314.6	
1550	RED OXIDE	211.9	423.9	1553	FAST BLUE	238.6	477.3	
1302	LOW LUSTER CLEAR	294.6	589.2	1554	TINTING WHITE	311.2	622.4	
1501	LANDAU BLACK	358.3	716.7	1302	LOW LUSTER CLEAR	379.6	759.2	
1554	TINTING WHITE	412.7	825.4	1552	FAST RED	407.7	815.5	
4815	LT ROYAL BLUE M	Chrysler Motors		4822	MOCHA PEARL	General Motors		34
1508	SILVER	156.0	312.0	1552	FAST RED	127.7	255.4	
1552	FAST RED	259.8	519.7	1554	TINTING WHITE	208.5	417.1	
1553	FAST BLUE	344.1	688.2	1501	LANDAU BLACK	282.6	565.3	
1554	TINTING WHITE	409.4	818.7	1551	INDO YELLOW	341.0	681.9	
				3521	RED PEARL	395.0	790.0	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 96

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
4823	NEUTRAL GRAY	Saturn		16	4830	EVERGREEN	Ford Motor	E
1554	TINTING WHITE	164.3	328.5		1302	LOW LUSTER CLEAR	135.3	270.6
1501	LANDAU BLACK	251.5	502.9		1556	FAST GREEN	268.0	536.0
1302	LOW LUSTER CLEAR	321.2	642.4		1501	LANDAU BLACK	334.7	669.4
1559	YELLOW OXIDE	389.9	779.8		1559	YELLOW OXIDE	386.0	772.0
1550	RED OXIDE	418.5	837.0		1554	TINTING WHITE	405.8	811.7
4824	LT BISCUIT	Saturn		61	4831	BRITE RED	Ford Motor	C
1554	TINTING WHITE	170.7	341.4		1552	FAST RED	303.1	606.1
1302	LOW LUSTER CLEAR	310.2	620.4		1559	YELLOW OXIDE	400.1	800.3
1559	YELLOW OXIDE	393.5	787.0		1554	TINTING WHITE	406.7	813.4
1550	RED OXIDE	408.7	817.4					
1501	LANDAU BLACK	418.4	836.8					
4825	DK BISCUIT	Saturn		61	4832	SADDLE	Ford Motor	C
1559	YELLOW OXIDE	135.3	270.6		1559	YELLOW OXIDE	147.5	295.1
1554	TINTING WHITE	261.3	522.7		1302	LOW LUSTER CLEAR	285.1	570.2
1302	LOW LUSTER CLEAR	330.0	660.1		1554	TINTING WHITE	350.5	700.9
1501	LANDAU BLACK	374.2	748.4		1550	RED OXIDE	399.2	798.4
1550	RED OXIDE	417.3	834.7		1501	LANDAU BLACK	412.6	825.2
4826	VERY DK BISCUIT	Saturn		61	4833	MED MOCHA	Ford Motor	A
1302	LOW LUSTER CLEAR	136.8	273.6		1554	TINTING WHITE	253.1	506.2
1559	YELLOW OXIDE	268.1	536.2		1559	YELLOW OXIDE	370.9	741.8
1501	LANDAU BLACK	319.5	639.0		1550	RED OXIDE	414.5	829.0
1554	TINTING WHITE	369.8	739.7		1501	LANDAU BLACK	427.1	854.2
1550	RED OXIDE	410.9	821.8					
4827	DK MOCHA	General Motors		34	4834	TAURUS SILVER BU	Ford Motor	
1501	LANDAU BLACK	185.3	370.5		1508	SILVER	199.8	399.6
1550	RED OXIDE	303.5	607.1		2024	SILVER BASE	308.8	617.5
1302	LOW LUSTER CLEAR	371.9	743.9		1501	LANDAU BLACK	389.0	778.1
1554	TINTING WHITE	393.4	786.8		1554	TINTING WHITE	400.9	801.8
1553	FAST BLUE	408.6	817.2		1551	INDO YELLOW	410.6	821.2
					1552	FAST RED	417.1	834.3
4828	DK MONTANA BLU	General Motors		21	MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR			
1302	LOW LUSTER CLEAR	128.9	257.8		4835	RED	Corvette	
1552	FAST RED	220.4	440.8		1552	FAST RED	260.5	521.0
1501	LANDAU BLACK	303.1	606.3		1551	INDO YELLOW	384.9	769.9
1553	FAST BLUE	371.4	742.7		1554	TINTING WHITE	405.2	810.4
1554	TINTING WHITE	405.7	811.3					
4829	PORTOFINO	Ford Motor		E	4836	DK BLUE	Corvette	
1552	FAST RED	147.2	294.3		1501	LANDAU BLACK	240.5	481.1
1553	FAST BLUE	287.1	574.2		1553	FAST BLUE	351.5	703.0
1501	LANDAU BLACK	362.4	724.9		1556	FAST GREEN	384.8	769.5
1554	TINTING WHITE	405.4	810.7		1554	TINTING WHITE	404.7	809.4

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 97

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4837	SADDLE	Corvette	
1559	YELLOW OXIDE	269.8	539.6
1550	RED OXIDE	365.9	731.9
1554	TINTING WHITE	397.9	795.7
1501	LANDAU BLACK	414.9	829.7

4843	TEAL	Corvette	
1508	SILVER	213.9	427.9
1501	LANDAU BLACK	301.6	603.3
1553	FAST BLUE	388.6	777.1
1556	FAST GREEN	405.7	811.3

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4838	LT SADDLE	Corvette	
1559	YELLOW OXIDE	233.1	466.3
1554	TINTING WHITE	361.7	723.3
1550	RED OXIDE	397.2	794.4
1501	LANDAU BLACK	419.9	839.8

4844	DK SADDLE	Corvette	
1559	YELLOW OXIDE	187.1	374.1
1302	LOW LUSTER CLEAR	323.3	646.6
1550	RED OXIDE	380.9	761.7
1501	LANDAU BLACK	400.5	801.0
1554	TINTING WHITE	409.3	818.5

4839	BRIGHT BLUE MET	Corvette	
1553	FAST BLUE	215.1	430.2
1508	SILVER	348.7	697.3
1501	LANDAU BLACK	373.3	746.5
1556	FAST GREEN	389.3	778.6
1554	TINTING WHITE	403.9	807.9

4844	DK SADDLE	Corvette	
1559	YELLOW OXIDE	187.1	374.1
1302	LOW LUSTER CLEAR	323.3	646.6
1550	RED OXIDE	380.9	761.7
1501	LANDAU BLACK	400.5	801.0
1554	TINTING WHITE	409.3	818.5

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4840	DK GREEN	Corvette	
1551	INDO YELLOW	133.3	266.6
1553	FAST BLUE	266.1	532.2
1501	LANDAU BLACK	377.1	754.1
1554	TINTING WHITE	404.4	808.8

4845	SADDLE	Corvette	
1559	YELLOW OXIDE	291.5	582.9
1550	RED OXIDE	360.2	720.5
1501	LANDAU BLACK	388.1	776.2
1554	TINTING WHITE	414.2	828.4

4841	RED	Corvette	
1552	FAST RED	316.8	633.7
1551	INDO YELLOW	380.9	761.7
1554	TINTING WHITE	405.7	811.3

4846	BRIGHT BLUE MET	Corvette	
1553	FAST BLUE	228.6	457.1
1508	SILVER	342.7	685.3
1556	FAST GREEN	392.4	784.7
1554	TINTING WHITE	398.6	797.2
1552	FAST RED	404.9	809.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4842	SILVER	Corvette	
1508	SILVER	238.1	476.1
2024	SILVER BASE	362.3	724.7
1552	FAST RED	390.5	781.1
1551	INDO YELLOW	404.9	809.8
1553	FAST BLUE	417.8	835.6

4847	DK GREEN MET	Corvette	
1501	LANDAU BLACK	166.4	332.9
1508	SILVER	248.1	496.3
1556	FAST GREEN	327.8	655.5
1551	INDO YELLOW	405.2	810.4

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4842	SILVER	Corvette	
1508	SILVER	238.1	476.1
2024	SILVER BASE	362.3	724.7
1552	FAST RED	390.5	781.1
1551	INDO YELLOW	404.9	809.8
1553	FAST BLUE	417.8	835.6
		0.0	0.0

4848	DK BLUE	Corvette	
1553	FAST BLUE	220.9	441.8
1501	LANDAU BLACK	364.4	728.8
1554	TINTING WHITE	404.4	808.8

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 98

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4849	OXBLOOD	Corvette		4856	DK BROWN	Corvette	
1552	FAST RED	305.2	610.5	1559	YELLOW OXIDE	219.8	439.7
1550	RED OXIDE	389.7	779.4	1501	LANDAU BLACK	319.5	639.0
1554	TINTING WHITE	401.5	802.9	1550	RED OXIDE	408.5	817.0
1553	FAST BLUE	407.0	814.0	1554	TINTING WHITE	411.7	823.5
4850	MED SADDLE	Corvette		4857	INDIGO BLUE	Corvette	
1559	YELLOW OXIDE	195.2	390.5	1553	FAST BLUE	163.8	327.6
1302	LOW LUSTER CLEAR	278.3	556.5	1552	FAST RED	303.2	606.5
1554	TINTING WHITE	354.9	709.8	1554	TINTING WHITE	355.9	711.7
1550	RED OXIDE	401.2	802.4	1501	LANDAU BLACK	405.7	811.5
1501	LANDAU BLACK	414.8	829.5				
4851	BLUE GREEN	Corvette		4858	DK GREEN	Corvette	
1556	FAST GREEN	313.6	627.2	1556	FAST GREEN	185.3	370.5
1501	LANDAU BLACK	371.0	742.0	1501	LANDAU BLACK	351.0	702.1
1508	SILVER	391.6	783.2	1508	SILVER	404.9	809.8
1554	TINTING WHITE	404.8	809.6				
4852	FIRETHORN	Corvette		4859	DOESKIN	Corvette	
1552	FAST RED	200.5	400.9	1554	TINTING WHITE	313.2	626.4
1550	RED OXIDE	397.8	795.5	1551	INDO YELLOW	370.9	741.8
1554	TINTING WHITE	405.9	811.9	1552	FAST RED	416.4	832.8
1501	LANDAU BLACK	409.5	818.9	1556	FAST GREEN	425.3	850.6
4853	WHITE	Corvette		4860	OYSTER	Corvette	
1554	TINTING WHITE	425.9	851.8	1554	TINTING WHITE	381.6	763.2
1559	YELLOW OXIDE	433.1	866.2	1559	YELLOW OXIDE	425.0	850.1
1550	RED OXIDE	436.0	871.9	1501	LANDAU BLACK	433.3	866.6
1556	FAST GREEN	436.7	873.4	1550	RED OXIDE	434.2	868.3
4854	DOVE GREY	Corvette		4861	DK BLUE	Corvette	
1554	TINTING WHITE	272.7	545.5	1553	FAST BLUE	203.5	407.0
1302	LOW LUSTER CLEAR	357.9	715.7	1501	LANDAU BLACK	304.3	608.6
1559	YELLOW OXIDE	399.4	798.8	1556	FAST GREEN	389.4	778.8
1501	LANDAU BLACK	421.9	843.8	1554	TINTING WHITE	402.6	805.2
1550	RED OXIDE	425.3	850.6				
4855	BUCKSKIN	Corvette		4862	SILVER	Corvette	
1559	YELLOW OXIDE	178.7	357.4	1508	SILVER	385.7	771.4
1302	LOW LUSTER CLEAR	316.2	632.3	1501	LANDAU BLACK	407.8	815.7
1554	TINTING WHITE	377.9	755.8	1551	INDO YELLOW	408.6	817.2
1550	RED OXIDE	404.6	809.2				
1501	LANDAU BLACK	412.4	824.8				

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 99

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4863	MED RED	Corvette	
1552	FAST RED	317.6	635.2
1551	INDO YELLOW	389.0	778.1
1554	TINTING WHITE	404.9	809.8

4870	MED TITANIUM	Ford Motor	R
1559	YELLOW OXIDE	140.1	280.3
1554	TINTING WHITE	261.9	523.8
1501	LANDAU BLACK	365.4	730.7
1550	RED OXIDE	417.9	835.8

4864	CINNABAR	Corvette	
1550	RED OXIDE	332.0	664.1
1559	YELLOW OXIDE	388.1	776.2
1501	LANDAU BLACK	405.3	810.5
1554	TINTING WHITE	414.1	828.2

4871	LT CRYSTAL BLUE	Ford Motor	A310N
2024	SILVER BASE	156.7	313.3
1553	FAST BLUE	275.1	550.2
1508	SILVER	332.3	664.6
1552	FAST RED	387.5	775.0
1501	LANDAU BLACK	418.2	836.4

4865	CHARCOAL	Corvette	
1501	LANDAU BLACK	210.0	420.1
1554	TINTING WHITE	294.7	589.4
1551	INDO YELLOW	361.1	722.2
1552	FAST RED	410.2	820.4

4872	GLACIER WHITE	Ford Motor	B
1554	TINTING WHITE	436.9	873.8
1553	FAST BLUE	437.2	874.4
1552	FAST RED	437.4	874.8

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4866	CARMINE	Corvette	
1552	FAST RED	309.8	619.6
1551	INDO YELLOW	393.4	786.8
1554	TINTING WHITE	402.1	804.3
1553	FAST BLUE	404.4	808.8

4873	MED DRIFTWOOD	Chrysler Motors	FD
1501	LANDAU BLACK	159.4	318.8
2024	SILVER BASE	281.2	562.4
1508	SILVER	392.4	784.7
1552	FAST RED	406.5	813.0
1551	INDO YELLOW	416.5	833.0

4867	SILVER GREEN	Corvette	
1508	SILVER	325.4	650.8
1553	FAST BLUE	362.6	725.2
1551	INDO YELLOW	383.0	766.1
1554	TINTING WHITE	398.9	797.8
1501	LANDAU BLACK	408.4	816.8

4874	PURPLE PEARL	General Motors	91T
1552	FAST RED	152.5	305.0
1501	LANDAU BLACK	292.3	584.6
1508	SILVER	342.0	684.0
1553	FAST BLUE	381.5	763.0
2024	SILVER BASE	407.1	814.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4868	BLUE	Corvette	
1501	LANDAU BLACK	176.3	352.6
1553	FAST BLUE	311.6	623.2
1554	TINTING WHITE	374.0	748.0
1551	INDO YELLOW	407.1	814.2

4875	DK QUARTZ GREY	Chrysler Motors	DL
1501	LANDAU BLACK	185.3	370.5
2024	SILVER BASE	278.9	557.8
1508	SILVER	345.0	690.1
1552	FAST RED	396.6	793.3
1553	FAST BLUE	413.5	827.1

4869	SILVER BEIGE	Corvette	
1508	SILVER	327.4	654.7
1551	INDO YELLOW	353.0	706.0
1554	TINTING WHITE	375.3	750.5
1501	LANDAU BLACK	394.2	788.3
1552	FAST RED	409.4	818.7

4876	MED GRAY MET	Ford Motor	ADLAMP/DOOR
1508	SILVER	199.0	398.1
1501	LANDAU BLACK	358.7	717.4
1551	INDO YELLOW	386.7	773.3
1552	FAST RED	406.8	813.6

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 100

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
4877	MED QUARTZ MET	Chrysler Motors		DM	4884	BRIGHT WHITE	General Motors	16T
1508	SILVER	139.7	279.5		1554	TINTING WHITE	435.8	871.5
2024	SILVER BASE	247.2	494.4		1501	LANDAU BLACK	436.4	872.9
1501	LANDAU BLACK	350.2	700.3		1559	YELLOW OXIDE	437.1	874.2
1551	INDO YELLOW	399.5	799.0		1553	FAST BLUE	437.3	874.6
1553	FAST BLUE	415.3	830.7					
				MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR				
4878	LT SANTA FE	Ford Motor		X	4885	MED ADRIATIC ME	General Motors	30T
1559	YELLOW OXIDE	157.4	314.8		1552	FAST RED	173.9	347.9
1554	TINTING WHITE	299.4	598.9		1553	FAST BLUE	318.9	637.8
1550	RED OXIDE	403.0	806.0		1508	SILVER	363.7	727.3
1501	LANDAU BLACK	420.9	841.9		1501	LANDAU BLACK	402.9	805.8
				MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR				
4879	SPRUCE	Chrysler Motors		P8	4886	DK ADRIATIC MET	General Motors	39T
1302	LOW LUSTER CLEAR	211.3	422.6		1553	FAST BLUE	281.4	562.8
1501	LANDAU BLACK	311.7	623.4		1556	FAST GREEN	383.3	766.7
1554	TINTING WHITE	378.7	757.3		1551	INDO YELLOW	401.6	803.1
1556	FAST GREEN	408.5	817.0		2024	SILVER BASE	403.0	806.0
				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				
4880	MED CAMEL TAN	Chrysler Motors		K5	4887	LT ADRIATIC MET	General Motors	36T
1302	LOW LUSTER CLEAR	138.0	276.1		1508	SILVER	292.8	585.6
1559	YELLOW OXIDE	274.6	549.3		1552	FAST RED	331.5	662.9
1554	TINTING WHITE	369.1	738.2		1553	FAST BLUE	368.9	737.8
1550	RED OXIDE	398.9	797.8		1501	LANDAU BLACK	396.1	792.1
1501	LANDAU BLACK	414.1	828.2		1554	TINTING WHITE	407.8	815.7
				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				
4881	LT NEUTRAL	Chrysler Motors		F1	4888	BLUE	Corvette	
1554	TINTING WHITE	194.6	389.1		1553	FAST BLUE	234.9	469.9
1302	LOW LUSTER CLEAR	334.6	669.2		1556	FAST GREEN	315.8	631.6
1559	YELLOW OXIDE	388.0	776.0		1554	TINTING WHITE	362.2	724.5
1550	RED OXIDE	405.9	811.9		1501	LANDAU BLACK	404.3	808.6
1501	LANDAU BLACK	419.4	838.9					
				MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR				
4882	DK FERN GREY ME	Chrysler Motors		F9	4889	LT DOESKIN	Corvette	
1501	LANDAU BLACK	225.1	450.1		1554	TINTING WHITE	243.9	487.7
2024	SILVER BASE	327.7	655.3		1559	YELLOW OXIDE	407.2	814.3
1508	SILVER	385.6	771.2		1550	RED OXIDE	421.7	843.4
1552	FAST RED	401.3	802.6		1501	LANDAU BLACK	426.6	853.3
1551	INDO YELLOW	414.4	828.8					
				MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR				
4883	LT GRAY MET	General Motors		14T	4890	SADDLE	Corvette	
1508	SILVER	265.1	530.3		1559	YELLOW OXIDE	254.3	508.6
1501	LANDAU BLACK	380.5	761.0		1554	TINTING WHITE	376.8	753.5
1553	FAST BLUE	401.9	803.9		1550	RED OXIDE	409.0	818.0
1551	INDO YELLOW	407.2	814.3		1501	LANDAU BLACK	419.7	839.4

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 101

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4891	DK BRIGHT BLUE	Corvette	
1553	FAST BLUE	321.6	643.2
1501	LANDAU BLACK	366.3	732.6
1508	SILVER	400.6	801.2

4898	NEUTRAL	Corvette	
1554	TINTING WHITE	291.0	582.0
1559	YELLOW OXIDE	416.1	832.2
1501	LANDAU BLACK	427.8	855.6
1550	RED OXIDE	429.0	858.0

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

4892	AQUA	Corvette	
1508	SILVER	206.4	412.9
1553	FAST BLUE	319.6	639.2
1556	FAST GREEN	401.9	803.9
1552	FAST RED	404.9	809.8

4899	IVORY		
1554	TINTING WHITE	391.8	783.6
1559	YELLOW OXIDE	433.1	866.2
1501	LANDAU BLACK	434.2	868.3
1550	RED OXIDE	434.8	869.6

4893	BLUE	Mazda	
1302	LOW LUSTER CLEAR	199.1	398.2
1501	LANDAU BLACK	297.1	594.1
1553	FAST BLUE	363.3	726.6
1554	TINTING WHITE	394.2	788.3
1552	FAST RED	405.3	810.5

4900	VANILLA		
1554	TINTING WHITE	308.7	617.3
1559	YELLOW OXIDE	426.6	853.3
1550	RED OXIDE	430.3	860.5

4894	LT YELLOW	General Motors	50
1554	TINTING WHITE	400.5	801.0
1551	INDO YELLOW	426.3	852.5
1552	FAST RED	430.5	861.1
1556	FAST GREEN	431.3	862.6

4901	SAFFRON		
1559	YELLOW OXIDE	220.8	441.6
1554	TINTING WHITE	420.4	840.8
1552	FAST RED	423.8	847.6
1501	LANDAU BLACK	424.2	848.4

4895	MED QUARTZ	Chrysler Motors	
1550	RED OXIDE	170.5	341.1
1508	SILVER	268.6	537.1
1559	YELLOW OXIDE	348.7	697.3
1553	FAST BLUE	410.9	821.8

4902	PARFAIT		
1554	TINTING WHITE	266.9	533.7
1559	YELLOW OXIDE	397.3	794.6
1550	RED OXIDE	427.6	855.2
1501	LANDAU BLACK	428.1	856.1

MUST TOPCOAT WITH 1300

4896	WHITE	Corvette	
1554	TINTING WHITE	431.2	862.4
1551	INDO YELLOW	434.0	867.9
1501	LANDAU BLACK	435.6	871.2
1550	RED OXIDE	436.9	873.8

4903	SHELL		
1554	TINTING WHITE	251.1	502.2
1559	YELLOW OXIDE	381.1	762.3
1550	RED OXIDE	426.1	852.2
1501	LANDAU BLACK	427.1	854.2

4897	GRAY MET	Chrysler Motors	MFE
1508	SILVER	354.4	708.9
1501	LANDAU BLACK	372.8	745.6
1552	FAST RED	390.7	781.5
3526	ORANGE PEARL	403.0	806.0
1551	INDO YELLOW	411.5	823.1

4904	TAN		
1559	YELLOW OXIDE	239.7	479.4
1554	TINTING WHITE	364.4	728.8
1550	RED OXIDE	410.8	821.6
1501	LANDAU BLACK	420.1	840.2

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 102

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4905	YELLOW BROWN						
1559	YELLOW OXIDE	223.8	447.6	1554	TINTING WHITE	348.4	696.7
1550	RED OXIDE	329.8	659.7	1553	FAST BLUE	419.7	839.4
1302	LOW LUSTER CLEAR	398.4	796.9	1550	RED OXIDE	429.0	858.0
1501	LANDAU BLACK	411.2	822.3	1559	YELLOW OXIDE	430.5	861.1
4906	PERSIMMON			4913	LT BLUE		
1550	RED OXIDE	150.9	301.7	1554	TINTING WHITE	330.0	660.1
1302	LOW LUSTER CLEAR	287.4	574.8	1553	FAST BLUE	403.9	807.9
1559	YELLOW OXIDE	398.3	796.7	1556	FAST GREEN	422.9	845.9
1501	LANDAU BLACK	409.3	818.5	1501	LANDAU BLACK	425.6	851.2
4907	WHITE			4914	REGATTA		
1554	TINTING WHITE	435.1	870.2	1554	TINTING WHITE	328.4	656.8
1559	YELLOW OXIDE	436.5	873.1	1553	FAST BLUE	397.2	794.4
1550	RED OXIDE	437.0	874.0	1501	LANDAU BLACK	420.9	841.9
1553	FAST BLUE	437.2	874.4	1559	YELLOW OXIDE	429.0	858.0
4908	GRAY	Lexus		4915	BOAT BLUE		
1554	TINTING WHITE	192.0	384.0	1554	TINTING WHITE	231.3	462.7
1501	LANDAU BLACK	362.6	725.2	1553	FAST BLUE	317.0	634.0
1559	YELLOW OXIDE	404.2	808.5	1559	YELLOW OXIDE	373.2	746.3
1553	FAST BLUE	419.9	839.8	1556	FAST GREEN	422.6	845.1
4909	PALE BLUE			4916	BLUE		
1554	TINTING WHITE	395.7	791.4	1554	TINTING WHITE	283.8	567.5
1553	FAST BLUE	417.4	834.9	1553	FAST BLUE	370.5	741.0
1552	FAST RED	424.9	849.9	1556	FAST GREEN	400.4	800.9
1556	FAST GREEN	430.7	861.5	1501	LANDAU BLACK	422.3	844.6
4910	LT BLUE	General Motors		4917	MED BLUE		
1554	TINTING WHITE	384.4	768.7	1554	TINTING WHITE	202.6	405.3
1559	YELLOW OXIDE	408.0	816.1	1553	FAST BLUE	395.1	790.2
1553	FAST BLUE	426.6	853.3	1501	LANDAU BLACK	405.8	811.7
1550	RED OXIDE	434.0	867.9	1556	FAST GREEN	415.4	830.9
4911	M-420 REGAL BLUE			4918	DK BLUE		
1554	TINTING WHITE	362.6	725.2	1553	FAST BLUE	181.2	362.3
1553	FAST BLUE	410.6	821.2	1556	FAST GREEN	286.4	572.9
1556	FAST GREEN	425.6	851.2	1554	TINTING WHITE	376.8	753.5
1501	LANDAU BLACK	428.2	856.3	1501	LANDAU BLACK	407.8	815.7

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 103

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4919	MARINE BLUE			4926	GREEN		
1553	FAST BLUE	335.5	671.1	1556	FAST GREEN	294.6	589.2
1554	TINTING WHITE	389.7	779.4	1554	TINTING WHITE	403.8	807.5
1556	FAST GREEN	401.8	803.5	1559	YELLOW OXIDE	408.1	816.2
1559	YELLOW OXIDE	407.0	814.0	1553	FAST BLUE	412.5	825.0
4920	VERY DK BLUE			4927	CHINA GREEN		
1553	FAST BLUE	193.9	387.8	1556	FAST GREEN	265.6	531.2
1552	FAST RED	344.0	688.0	1554	TINTING WHITE	381.0	762.1
1554	TINTING WHITE	397.4	794.8	1559	YELLOW OXIDE	405.5	810.9
1501	LANDAU BLACK	407.5	814.9	1501	LANDAU BLACK	413.3	826.7
4921	BRIGHT BLUE MET	Corvette	41	4928	MED GREEN		
1553	FAST BLUE	199.9	399.8	1559	YELLOW OXIDE	175.8	351.5
1508	SILVER	332.2	664.4	1556	FAST GREEN	328.8	657.6
1556	FAST GREEN	384.9	769.9	1554	TINTING WHITE	403.3	806.6
1501	LANDAU BLACK	403.2	806.4	1501	LANDAU BLACK	413.6	827.3
MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR							
4922	VERY LT GREEN	General Motors		4929	MED DK GREEN		
1554	TINTING WHITE	406.0	812.1	1556	FAST GREEN	249.6	499.1
1559	YELLOW OXIDE	425.9	851.8	1551	INDO YELLOW	336.1	672.2
1553	FAST BLUE	431.1	862.2	1554	TINTING WHITE	409.5	819.1
1556	FAST GREEN	435.5	871.0				
4923	LT GREEN			4930	BOAT GREEN		
1554	TINTING WHITE	280.3	560.7	1556	FAST GREEN	159.5	319.0
1556	FAST GREEN	361.3	722.6	1554	TINTING WHITE	276.8	553.7
1559	YELLOW OXIDE	410.7	821.4	1553	FAST BLUE	367.4	734.7
1501	LANDAU BLACK	426.5	852.9	1559	YELLOW OXIDE	413.6	827.3
4924	AQUA	Ford Motor	PF	4931	MINT GREEN		
1554	TINTING WHITE	222.0	444.0	1556	FAST GREEN	282.5	565.1
1556	FAST GREEN	376.4	752.8	1551	INDO YELLOW	352.8	705.7
1553	FAST BLUE	419.7	839.4	1554	TINTING WHITE	407.3	814.5
1559	YELLOW OXIDE	420.8	841.5				
4925	TURQUOISE			4932	OPAL		
1554	TINTING WHITE	235.4	470.8	1556	FAST GREEN	365.1	730.2
1556	FAST GREEN	367.3	734.5	1554	TINTING WHITE	400.0	800.1
1553	FAST BLUE	403.2	806.4	1501	LANDAU BLACK	406.6	813.2
1501	LANDAU BLACK	419.4	838.9				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 104

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4933	BLUE GREEN						
1559	YELLOW OXIDE	164.7	329.5	1501	LANDAU BLACK	248.0	496.1
1553	FAST BLUE	294.1	588.2	1559	YELLOW OXIDE	366.4	732.8
1556	FAST GREEN	394.4	788.9	1554	TINTING WHITE	388.9	777.9
1554	TINTING WHITE	408.2	816.4	1550	RED OXIDE	409.5	819.1
4934	GUNMETAL	Corvette		4940	MIST GRAY	Chrysler Motors	C3
1300	HIGH GLOSS CLEAR	202.1	404.1	1302	LOW LUSTER CLEAR	138.5	277.0
1501	LANDAU BLACK	310.8	621.7	1554	TINTING WHITE	275.9	551.8
1508	SILVER	389.0	778.1	1501	LANDAU BLACK	356.0	711.9
1556	FAST GREEN	404.1	808.3	1550	RED OXIDE	395.3	790.6
				1559	YELLOW OXIDE	415.2	830.5
4935	ANNIVERSARY WHI	Corvette		4941	MED ROSEWOOD	Chrysler Motors	EC
1554	TINTING WHITE	436.3	872.7	1302	LOW LUSTER CLEAR	137.6	275.1
1553	FAST BLUE	436.8	873.6	1559	YELLOW OXIDE	243.5	487.0
1551	INDO YELLOW	437.1	874.2	1554	TINTING WHITE	319.7	639.4
1501	LANDAU BLACK	437.3	874.6	1550	RED OXIDE	378.7	757.3
				1501	LANDAU BLACK	412.7	825.4
4936	MAHOGANY SAFFR	Corvette		4942	SHALE	General Motors	WA149B
1550	RED OXIDE	256.7	513.4	1554	TINTING WHITE	249.9	499.9
1552	FAST RED	375.3	750.5	1559	YELLOW OXIDE	332.0	663.9
1501	LANDAU BLACK	398.4	796.9	1302	LOW LUSTER CLEAR	413.9	827.7
1554	TINTING WHITE	411.3	822.5	1501	LANDAU BLACK	432.5	865.0
				1550	RED OXIDE	446.0	892.0
				0			
4937	DK RED CARMINE	Corvette		4943	CAPPUCCINO CREA	General Motors	TC16
1552	FAST RED	345.5	691.0	1554	TINTING WHITE	210.4	420.9
1550	RED OXIDE	396.6	793.3	1302	LOW LUSTER CLEAR	350.6	701.1
1553	FAST BLUE	401.3	802.6	1559	YELLOW OXIDE	409.6	819.3
1554	TINTING WHITE	405.6	811.1	1550	RED OXIDE	418.6	837.1
				1553	FAST BLUE	420.6	841.1
4938	MED SILVERFERN	Chrysler Motors	JK	4944	MOSS GREEN	Chrysler Motors	J4
1302	LOW LUSTER CLEAR	138.1	276.3	1302	LOW LUSTER CLEAR	135.7	271.3
1554	TINTING WHITE	258.9	517.8	1559	YELLOW OXIDE	270.8	541.5
1559	YELLOW OXIDE	358.8	717.6	1501	LANDAU BLACK	337.3	674.7
1501	LANDAU BLACK	413.8	827.6	1556	FAST GREEN	395.7	791.4
1550	RED OXIDE	414.7	829.4	1554	TINTING WHITE	407.3	814.5
4939	EBONY	General Motors	WA167A	4945	STEEL BLUE	Corvette	
1501	LANDAU BLACK	248.0	496.1	1501	LANDAU BLACK	207.4	414.8
1559	YELLOW OXIDE	366.4	732.8	1554	TINTING WHITE	379.8	759.6
1554	TINTING WHITE	388.9	777.9	1551	INDO YELLOW	399.5	799.0
1550	RED OXIDE	409.5	819.1	1550	RED OXIDE	418.1	836.2

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 105

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4946	TOBACCO	Corvette	
1559	YELLOW OXIDE	136.9	273.8
1550	RED OXIDE	268.7	537.3
1501	LANDAU BLACK	392.9	785.8
1554	TINTING WHITE	412.1	824.2

4953	MED MARBLEHEA	General Motors		3T
1508	SILVER	263.2	526.3	
1501	LANDAU BLACK	365.8	731.7	
1552	FAST RED	396.6	793.3	
1551	INDO YELLOW	407.5	814.9	

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4947	FAWN BEIGE	Corvette	
1508	SILVER	243.3	486.6
1554	TINTING WHITE	291.9	583.9
1551	INDO YELLOW	340.1	680.2
1552	FAST RED	379.1	758.1
1501	LANDAU BLACK	410.7	821.4

4954	DK CALYspo GREE	General Motors		92T
1556	FAST GREEN	224.7	449.4	
1553	FAST BLUE	334.1	668.2	
1501	LANDAU BLACK	376.1	752.2	
1508	SILVER	403.9	807.9	

MUST TOPCOAT WITH 1301 SATIN GLOSS CLEAR

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4948	DK NAVY BLUE	General Motors		30 & 26
1553	FAST BLUE	219.7	439.5	
1501	LANDAU BLACK	353.1	706.2	
1554	TINTING WHITE	389.7	779.4	
1552	FAST RED	406.3	812.6	

4955	CREAM	Ferrari		VM-3997
1554	TINTING WHITE	266.5	533.0	
1302	LOW LUSTER CLEAR	407.6	815.3	
1551	INDO YELLOW	418.7	837.3	
1552	FAST RED	422.8	845.7	
1556	FAST GREEN	423.4	846.8	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4949	MED GRAY	General Motors		13
1554	TINTING WHITE	143.2	286.3	
1302	LOW LUSTER CLEAR	280.1	560.1	
1559	YELLOW OXIDE	343.6	687.2	
1501	LANDAU BLACK	391.5	783.0	
1550	RED OXIDE	416.1	832.2	

4956	BEIGE	Ferrari		VM-4208
1554	TINTING WHITE	150.1	300.2	
1302	LOW LUSTER CLEAR	288.5	577.0	
1551	INDO YELLOW	373.9	747.8	
1550	RED OXIDE	415.0	829.9	
1501	LANDAU BLACK	415.5	831.1	

4950	MED NEUTRAL	General Motors		52
1554	TINTING WHITE	167.6	335.2	
1559	YELLOW OXIDE	325.8	651.5	
1550	RED OXIDE	380.5	761.0	
1501	LANDAU BLACK	421.7	843.4	

4957	GRIEGO	Ferrari		VM-3393
1302	LOW LUSTER CLEAR	138.8	277.6	
1554	TINTING WHITE	276.5	552.9	
1559	YELLOW OXIDE	377.5	755.1	
1501	LANDAU BLACK	406.3	812.6	
1550	RED OXIDE	416.1	832.2	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4951	MED LT MUSHROO	General Motors		55
1554	TINTING WHITE	220.0	440.0	
1559	YELLOW OXIDE	333.8	667.7	
1550	RED OXIDE	392.1	784.1	
1501	LANDAU BLACK	424.7	849.5	

4958	ROSSO	Ferrari		VM-3171
1552	FAST RED	194.8	389.5	
1302	LOW LUSTER CLEAR	329.7	659.3	
1551	INDO YELLOW	365.4	730.7	
1550	RED OXIDE	391.0	782.0	
1554	TINTING WHITE	404.8	809.6	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

4952	MED DK MUSHROO	General Motors		55
1554	TINTING WHITE	133.1	266.2	
1559	YELLOW OXIDE	262.0	524.0	
1550	RED OXIDE	352.2	704.3	
1501	LANDAU BLACK	419.3	838.7	

4959	BLUE	Ferrari		VM-3282
1501	LANDAU BLACK	201.4	402.8	
1302	LOW LUSTER CLEAR	337.2	674.3	
1554	TINTING WHITE	390.1	780.1	
1553	FAST BLUE	403.8	807.7	
1552	FAST RED	407.6	815.1	

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 106

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	NERO	Ferrari	VM-8500
1501	LANDAU BLACK	269.2	538.5
1302	LOW LUSTER CLEAR	403.8	807.7

	LT GRAPHITE	Ford Motor	B
1554	TINTING WHITE	324.2	648.5
1559	YELLOW OXIDE	373.7	747.5
1501	LANDAU BLACK	407.7	815.5
1550	RED OXIDE	430.5	861.1

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

	TAUPE	Lexus	
1302	LOW LUSTER CLEAR	137.8	275.7
1501	LANDAU BLACK	227.8	455.6
1550	RED OXIDE	291.5	582.9
1554	TINTING WHITE	352.1	704.1
1559	YELLOW OXIDE	410.8	821.6

	BLUE	Lexus	85L/80L
1302	LOW LUSTER CLEAR	134.0	268.1
1552	FAST RED	242.0	483.9
1554	TINTING WHITE	310.4	620.7
1553	FAST BLUE	370.8	741.6
1551	INDO YELLOW	408.1	816.2

	DK PORTOFINO	Ford Motor	
1553	FAST BLUE	312.7	625.5
1556	FAST GREEN	402.0	804.1
1508	SILVER	402.8	805.6

	GRAY	Lexus	15L/10L
1302	LOW LUSTER CLEAR	137.7	275.3
1554	TINTING WHITE	235.3	470.6
1501	LANDAU BLACK	309.5	619.0
1559	YELLOW OXIDE	378.9	757.7
1550	RED OXIDE	413.1	826.1

	MED GRAPHITE BU	Ford Motor	T
1552	FAST RED	131.5	263.0
1501	LANDAU BLACK	230.0	460.0
2024	SILVER BASE	301.1	602.1
1508	SILVER	367.7	735.5
1553	FAST BLUE	411.2	822.3

	BURGUNDY	Lexus	35L/
1552	FAST RED	293.2	586.3
1551	INDO YELLOW	344.1	688.2
1554	TINTING WHITE	378.4	756.8
1501	LANDAU BLACK	406.6	813.2

	MED GRAY MET	Ford Motor	C
2024	SILVER BASE	173.9	347.7
1301	SATIN GLOSS CLEAR	272.0	544.0
1508	SILVER	369.2	738.3
1501	LANDAU BLACK	415.8	831.6
1553	FAST BLUE	420.6	841.1

	MAUVE	Lexus	45L/
1302	LOW LUSTER CLEAR	136.0	272.1
1559	YELLOW OXIDE	229.1	458.3
1550	RED OXIDE	302.1	604.2
1554	TINTING WHITE	362.0	723.9
1501	LANDAU BLACK	411.6	823.3

	DK TITANIUM BUM	Ford Motor	T
1501	LANDAU BLACK	158.6	317.1
1508	SILVER	294.7	589.4
2024	SILVER BASE	407.2	814.3
1551	INDO YELLOW	416.0	832.0

	WILLOW	Ford Motor	D
1302	LOW LUSTER CLEAR	137.0	274.0
1559	YELLOW OXIDE	234.7	469.3
1554	TINTING WHITE	308.3	616.6
1501	LANDAU BLACK	378.0	756.0
1553	FAST BLUE	411.0	821.9

	IVORY	Ford Motor	A
1554	TINTING WHITE	380.0	760.0
1559	YELLOW OXIDE	426.8	853.7
1550	RED OXIDE	431.6	863.2
1501	LANDAU BLACK	434.2	868.3

	NIGHTMIST	Ford Motor	
1550	RED OXIDE	138.8	277.6
1302	LOW LUSTER CLEAR	276.0	552.0
1554	TINTING WHITE	341.2	682.5
1501	LANDAU BLACK	390.1	780.1
1553	FAST BLUE	411.4	822.9

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 107

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

4974	PUMICE	Ford Motor	
1554	TINTING WHITE	175.9	351.9
1559	YELLOW OXIDE	306.3	612.6
1550	RED OXIDE	366.5	733.0
1501	LANDAU BLACK	422.0	844.0

4981	CYPRESS	Ford Motor		A
1554	TINTING WHITE	198.3	396.5	
1302	LOW LUSTER CLEAR	339.1	678.1	
1559	YELLOW OXIDE	395.7	791.4	
1501	LANDAU BLACK	409.9	819.9	
1550	RED OXIDE	419.8	839.6	

MUST TOPCOAT WITH 1300 HIGH GLOSS CLEAR

4975	MED CAMEL TAN	Chrysler Motors		K5
1554	TINTING WHITE	171.7	343.3	
1302	LOW LUSTER CLEAR	311.1	622.3	
1559	YELLOW OXIDE	396.4	792.9	
1550	RED OXIDE	409.4	818.7	
1501	LANDAU BLACK	418.4	836.8	

4982	OPEL GRAY	General Motors		WA104D
1554	TINTING WHITE	215.6	431.1	
1302	LOW LUSTER CLEAR	356.5	713.1	
1559	YELLOW OXIDE	397.8	795.5	
1501	LANDAU BLACK	411.9	823.8	
1550	RED OXIDE	420.7	841.3	

4976	SADDLE TAN	Chrysler Motors		T6
1559	YELLOW OXIDE	180.7	361.4	
1302	LOW LUSTER CLEAR	318.0	635.9	
1554	TINTING WHITE	371.0	742.0	
1550	RED OXIDE	404.2	808.5	
1501	LANDAU BLACK	411.9	823.8	

4983	VERY DK TEAL	General Motors		37
1302	LOW LUSTER CLEAR	135.9	271.7	
1501	LANDAU BLACK	266.1	532.2	
1559	YELLOW OXIDE	330.2	660.4	
1553	FAST BLUE	370.3	740.6	
1554	TINTING WHITE	407.6	815.1	

4977	STONE WHITE	Chrysler Motors		W1
1554	TINTING WHITE	274.9	549.9	
1302	LOW LUSTER CLEAR	416.5	833.0	
1559	YELLOW OXIDE	422.7	845.3	
1501	LANDAU BLACK	424.1	848.2	

4984	MED CRYSTAL GRE	General Motors		42
1554	TINTING WHITE	138.3	276.6	
1302	LOW LUSTER CLEAR	276.6	553.3	
1559	YELLOW OXIDE	369.4	738.7	
1501	LANDAU BLACK	409.5	818.9	
1556	FAST GREEN	415.7	831.4	

4978	CAMEL TAN	Chrysler Motors		KC
1559	YELLOW OXIDE	154.7	309.3	
1302	LOW LUSTER CLEAR	292.6	585.2	
1554	TINTING WHITE	385.2	770.5	
1550	RED OXIDE	402.8	805.6	
1501	LANDAU BLACK	414.0	828.0	

4985	MED DK CRYSTAL	General Motors		42
1302	LOW LUSTER CLEAR	137.2	274.4	
1559	YELLOW OXIDE	252.7	505.4	
1501	LANDAU BLACK	330.4	660.8	
1554	TINTING WHITE	407.3	814.5	
1556	FAST GREEN	411.7	823.5	

4979	CORDOVAN	Ford Motor		E
1552	FAST RED	161.9	323.8	
1302	LOW LUSTER CLEAR	297.0	593.9	
1550	RED OXIDE	370.2	740.4	
1501	LANDAU BLACK	399.0	798.0	
1554	TINTING WHITE	405.6	811.1	

4986	VERY DK NEUTRAL	General Motors		52
1302	LOW LUSTER CLEAR	136.7	273.4	
1559	YELLOW OXIDE	241.6	483.2	
1501	LANDAU BLACK	318.5	637.1	
1554	TINTING WHITE	365.9	731.9	
1550	RED OXIDE	410.3	820.6	

4980	MED GRAPHITE	Ford Motor		C
1554	TINTING WHITE	141.6	283.3	
1302	LOW LUSTER CLEAR	280.3	560.7	
1559	YELLOW OXIDE	343.1	686.3	
1501	LANDAU BLACK	391.6	783.2	
1550	RED OXIDE	416.0	832.0	

4987	DK SMOKE GRAY	General Motors		55
1302	LOW LUSTER CLEAR	135.7	271.3	
1501	LANDAU BLACK	258.1	516.2	
1559	YELLOW OXIDE	332.5	665.0	
1550	RED OXIDE	373.9	747.8	
1554	TINTING WHITE	408.8	817.6	

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 108

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
4988	VERY DK RUBY RE	General Motors		79	4995	PACIFIC BLUE	
1552	FAST RED	237.1	474.2	1553	FAST BLUE	188.3	376.6
1302	LOW LUSTER CLEAR	371.6	743.3	1552	FAST RED	323.0	646.0
1501	LANDAU BLACK	399.1	798.2	1554	TINTING WHITE	398.2	796.5
1554	TINTING WHITE	403.6	807.1	1556	FAST GREEN	408.9	817.8
4989	DK GRAY	General Motors		4996	BLUEBIRD BROWN		
1302	LOW LUSTER CLEAR	137.1	274.2	1559	YELLOW OXIDE	249.5	498.9
1501	LANDAU BLACK	231.7	463.4	1550	RED OXIDE	341.0	681.9
1554	TINTING WHITE	307.1	614.3	1501	LANDAU BLACK	394.4	788.9
1559	YELLOW OXIDE	377.1	754.1	1554	TINTING WHITE	413.4	826.9
1550	RED OXIDE	411.6	823.3				
4990	DK CRYSTAL GREE	General Motors		4997	GRAPHITE PEARL	General Motors	12P
1302	LOW LUSTER CLEAR	136.7	273.4	1300	HIGH GLOSS CLEAR	191.2	382.5
1559	YELLOW OXIDE	270.1	540.2	1501	LANDAU BLACK	316.6	633.3
1501	LANDAU BLACK	350.7	701.5	1552	FAST RED	367.7	735.3
1554	TINTING WHITE	398.3	796.7	1551	INDO YELLOW	395.3	790.6
1553	FAST BLUE	409.8	819.7	3520	PLATINUM PEARL	406.3	812.6
4991	SAILCLOTH WHITE			4998	DENIM	Ford Motor	KYD
1554	TINTING WHITE	436.7	873.4	1550	RED OXIDE	113.3	226.7
1501	LANDAU BLACK	437.1	874.2	1554	TINTING WHITE	214.6	429.2
1551	INDO YELLOW	437.4	874.8	1553	FAST BLUE	300.9	601.7
				1302	LOW LUSTER CLEAR	377.6	755.3
				1559	YELLOW OXIDE	414.5	829.0
4992	SPINNAKER BLUE			4999	LT PRAIRIE TAN	Ford Motor	AYB
1554	TINTING WHITE	361.6	723.1	1554	TINTING WHITE	149.9	299.8
1553	FAST BLUE	406.0	812.1	1559	YELLOW OXIDE	292.2	584.4
1556	FAST GREEN	421.5	843.0	1302	LOW LUSTER CLEAR	376.1	752.2
1501	LANDAU BLACK	431.4	862.8	1550	RED OXIDE	408.5	817.0
				1501	LANDAU BLACK	419.0	837.9
4993	PORTSMOUTH GRA			5000	PRAIRIE TAN	Ford Motor	AYC
1554	TINTING WHITE	405.4	810.7	1559	YELLOW OXIDE	143.0	286.0
1550	RED OXIDE	416.7	833.3	1554	TINTING WHITE	263.7	527.4
1501	LANDAU BLACK	426.3	852.5	1302	LOW LUSTER CLEAR	347.1	694.3
1559	YELLOW OXIDE	435.4	870.8	1550	RED OXIDE	391.7	783.4
				1501	LANDAU BLACK	417.0	833.9
4994	AQUA			5001	DK PRAIRIE TAN	Ford Motor	AY5
1554	TINTING WHITE	332.8	665.6	1559	YELLOW OXIDE	138.2	276.5
1556	FAST GREEN	380.9	761.7	1302	LOW LUSTER CLEAR	274.8	549.7
1553	FAST BLUE	425.4	850.8	1550	RED OXIDE	325.7	651.3
1551	INDO YELLOW	429.3	858.6	1501	LANDAU BLACK	376.2	752.4
				1554	TINTING WHITE	410.1	820.2

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 109

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5002	WHEAT/DATE	Mercedes Benz		5009	MED DK GRAPHITE	Ford Motor	ZU4
1559	YELLOW OXIDE	288.7	577.4	1302	LOW LUSTER CLEAR	139.3	278.5
1554	TINTING WHITE	356.6	713.3	1554	TINTING WHITE	245.7	491.3
1550	RED OXIDE	405.5	810.9	1501	LANDAU BLACK	320.6	641.3
1501	LANDAU BLACK	416.9	833.7	1559	YELLOW OXIDE	381.2	762.5
				1550	RED OXIDE	413.5	827.1
5003	VERY DK BISCUIT	Saturn		5010	MIDNIGHT SADDLE	Ford Motor	DE5
1559	YELLOW OXIDE	194.7	389.3	1501	LANDAU BLACK	131.9	263.7
1554	TINTING WHITE	274.0	548.0	1559	YELLOW OXIDE	244.2	488.3
1501	LANDAU BLACK	353.3	706.6	1302	LOW LUSTER CLEAR	326.2	652.5
1550	RED OXIDE	416.1	832.2	1550	RED OXIDE	370.7	741.4
				1554	TINTING WHITE	410.5	821.0
5004	DK BISCUIT II	Saturn		5011	DK WILLOW	Ford Motor	SGE
1559	YELLOW OXIDE	202.4	404.9	1553	FAST BLUE	194.5	388.9
1554	TINTING WHITE	281.0	562.0	1559	YELLOW OXIDE	364.5	729.0
1550	RED OXIDE	353.8	707.6	1501	LANDAU BLACK	407.1	814.2
1501	LANDAU BLACK	416.4	832.8				
5005	DK ANTELOPE	Saturn		5012	DK CYPRESS	Ford Motor	BG5
1559	YELLOW OXIDE	185.3	370.5	1302	LOW LUSTER CLEAR	204.1	408.1
1550	RED OXIDE	284.4	568.9	1559	YELLOW OXIDE	292.4	584.8
1554	TINTING WHITE	358.1	716.1	1501	LANDAU BLACK	344.5	688.9
1501	LANDAU BLACK	416.3	832.6	1554	TINTING WHITE	379.5	759.1
				1550	RED OXIDE	408.1	816.2
5006	MED ANTELOPE	Saturn		5013	DK GRAPHITE	Ford Motor	ZU5
1554	TINTING WHITE	192.9	385.7	1501	LANDAU BLACK	164.4	328.7
1559	YELLOW OXIDE	332.9	665.8	1559	YELLOW OXIDE	265.0	529.9
1550	RED OXIDE	395.6	791.2	1554	TINTING WHITE	357.0	714.0
1501	LANDAU BLACK	423.5	847.0	1550	RED OXIDE	415.2	830.5
5007	GRAY MET	Chrysler Motors		5014	MED IVORY	Ford Motor	AUB
1508	SILVER	232.2	464.4	1554	TINTING WHITE	223.5	447.1
1501	LANDAU BLACK	373.5	747.1	1559	YELLOW OXIDE	371.9	743.9
1552	FAST RED	404.3	808.6	1550	RED OXIDE	404.2	808.5
1553	FAST BLUE	407.1	814.2	1501	LANDAU BLACK	425.2	850.4
5008	LT QUARTZ	Chrysler Motors		5015	CHEROKEE GRAY	Chrysler Motors	
1554	TINTING WHITE	327.5	654.9	1501	LANDAU BLACK	138.7	277.4
1559	YELLOW OXIDE	376.5	753.0	1559	YELLOW OXIDE	222.6	445.2
1501	LANDAU BLACK	405.7	811.5	1302	LOW LUSTER CLEAR	305.5	611.0
1550	RED OXIDE	430.7	861.5	1554	TINTING WHITE	365.5	730.9
				1550	RED OXIDE	411.4	822.7

MUST TOPCOAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 110

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5016	DARK DENIM	Ford Motor	KY5	5023	MED TRUFFLE	Ford Motor	
1302	LOW LUSTER CLEAR	204.3	408.7	1302	LOW LUSTER CLEAR	138.5	277.0
1501	LANDAU BLACK	285.0	570.0	1554	TINTING WHITE	274.6	549.1
1554	TINTING WHITE	352.5	704.9	1559	YELLOW OXIDE	356.8	713.6
1550	RED OXIDE	383.7	767.4	1501	LANDAU BLACK	397.7	795.3
1553	FAST BLUE	408.7	817.4	1550	RED OXIDE	415.9	831.8
5017	VERY DK CAMEL T	Chrysler Motors	JK3	5024	LT WARM GRAY	Saturn	11
1302	LOW LUSTER CLEAR	136.0	272.1	1554	TINTING WHITE	268.5	536.9
1501	LANDAU BLACK	251.6	503.1	1559	YELLOW OXIDE	337.9	675.8
1559	YELLOW OXIDE	341.0	681.9	1302	LOW LUSTER CLEAR	377.4	754.9
1550	RED OXIDE	388.8	777.7	1501	LANDAU BLACK	404.7	809.4
1554	TINTING WHITE	408.0	816.1	1550	RED OXIDE	426.5	852.9
5018	BEIGE	General Motors	171B	5025	MED WARM GRAY	Saturn	11
1554	TINTING WHITE	162.5	324.9	1554	TINTING WHITE	203.1	406.2
1559	YELLOW OXIDE	322.7	645.4	1559	YELLOW OXIDE	304.9	609.7
1550	RED OXIDE	381.4	762.9	1501	LANDAU BLACK	346.7	693.3
1501	LANDAU BLACK	421.5	843.0	1302	LOW LUSTER CLEAR	385.0	770.1
				1550	RED OXIDE	422.7	845.3
5019	GRAY	General Motors		5026	DK WARM GRAY	Saturn	11
1302	LOW LUSTER CLEAR	136.3	272.7	1559	YELLOW OXIDE	135.0	270.0
1501	LANDAU BLACK	257.4	514.7	1554	TINTING WHITE	230.7	461.3
1559	YELLOW OXIDE	330.2	660.4	1501	LANDAU BLACK	324.4	648.9
1554	TINTING WHITE	371.3	742.5	1550	RED OXIDE	378.1	756.2
1550	RED OXIDE	409.1	818.1	1302	LOW LUSTER CLEAR	415.6	831.3
5020	MED CAMEL TAN	Chrysler Motors	K5	5027	MED BISCUIT II	Saturn	61
1302	LOW LUSTER CLEAR	137.8	275.5	1554	TINTING WHITE	191.8	383.6
1559	YELLOW OXIDE	267.2	534.5	1559	YELLOW OXIDE	324.7	649.4
1554	TINTING WHITE	363.7	727.3	1302	LOW LUSTER CLEAR	362.7	725.4
1550	RED OXIDE	396.2	792.3	1550	RED OXIDE	399.6	799.1
1501	LANDAU BLACK	414.1	828.2	1501	LANDAU BLACK	422.4	844.7
5021	ALCHEMY NAPLES	Ford Motor		5028	ATLANTIS BLUE	Ford Motor	KZE
1302	LOW LUSTER CLEAR	135.3	270.6	1302	LOW LUSTER CLEAR	112.0	224.0
1501	LANDAU BLACK	236.9	473.9	1553	FAST BLUE	224.0	448.0
1553	FAST BLUE	327.0	654.0	1501	LANDAU BLACK	303.1	606.1
1550	RED OXIDE	390.0	780.0	1550	RED OXIDE	364.5	729.0
1554	TINTING WHITE	405.8	811.7	1554	TINTING WHITE	407.7	815.5
5022	GRAY MET	General Motors		5029	PUMICE	Ford Motor	DCC
1501	LANDAU BLACK	331.6	663.3	1554	TINTING WHITE	116.9	233.7
1552	FAST RED	379.1	758.1	1302	LOW LUSTER CLEAR	224.8	449.5
1508	SILVER	401.2	802.4	1559	YELLOW OXIDE	330.9	661.8
3522	GOLD PEARL	406.7	813.4	1550	RED OXIDE	377.7	755.4
				1501	LANDAU BLACK	415.8	831.6

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 111

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5030	MED DK PUMICE	Ford Motor	BA3	5037	MED PEWTER	General Motors	92
1302	LOW LUSTER CLEAR	156.4	312.7	1554	TINTING WHITE	185.7	371.5
1559	YELLOW OXIDE	263.2	526.5	1559	YELLOW OXIDE	289.2	578.4
1554	TINTING WHITE	323.2	646.4	1302	LOW LUSTER CLEAR	343.8	687.6
1550	RED OXIDE	368.0	736.1	1501	LANDAU BLACK	390.5	780.9
1501	LANDAU BLACK	411.1	822.1	1550	RED OXIDE	421.0	842.1
5031	MEDICI	General Motors	77	5038	DK TRUFFLE	Ford Motor	
1552	FAST RED	226.8	453.5	1559	YELLOW OXIDE	156.6	313.1
1302	LOW LUSTER CLEAR	381.5	763.0	1554	TINTING WHITE	271.1	542.3
1553	FAST BLUE	390.2	780.3	1501	LANDAU BLACK	379.3	758.7
1559	YELLOW OXIDE	397.4	794.8	1550	RED OXIDE	417.5	835.1
1554	TINTING WHITE	403.5	806.9				
5032	CRYSTAL GREEN	General Motors	42	5039	CORK PRINT	Porsche	
1554	TINTING WHITE	145.6	291.3	1559	YELLOW OXIDE	259.7	519.5
1302	LOW LUSTER CLEAR	269.6	539.2	1302	LOW LUSTER CLEAR	366.3	732.6
1559	YELLOW OXIDE	368.8	737.6	1550	RED OXIDE	408.7	817.4
1501	LANDAU BLACK	411.0	821.9	1501	LANDAU BLACK	410.0	820.0
1556	FAST GREEN	416.6	833.2				
5033	MED DK PEWTER	General Motors	92	5040	BUCKSKIN	BMW	
1554	TINTING WHITE	141.3	282.5	1559	YELLOW OXIDE	202.4	404.9
1559	YELLOW OXIDE	242.6	485.3	1302	LOW LUSTER CLEAR	291.3	582.5
1302	LOW LUSTER CLEAR	328.8	657.6	1554	TINTING WHITE	377.8	755.6
1501	LANDAU BLACK	386.4	772.7	1550	RED OXIDE	408.5	817.0
1550	RED OXIDE	417.4	834.9	1501	LANDAU BLACK	415.2	830.5
5034	DK TOREADOR RE	General Motors		5041	PEARL BEIGE	BMW	
1550	RED OXIDE	132.7	265.4	1554	TINTING WHITE	192.4	384.8
1552	FAST RED	246.2	492.5	1302	LOW LUSTER CLEAR	291.8	583.7
1302	LOW LUSTER CLEAR	344.6	689.1	1559	YELLOW OXIDE	388.0	776.0
1501	LANDAU BLACK	392.5	785.1	1501	LANDAU BLACK	405.6	811.1
1554	TINTING WHITE	408.0	816.1	1550	RED OXIDE	420.5	840.9
5035	FIRETHORN	General Motors		5042	BEIGE	Porsche	
1552	FAST RED	192.1	384.2	1302	LOW LUSTER CLEAR	132.7	265.4
1302	LOW LUSTER CLEAR	324.1	648.3	1559	YELLOW OXIDE	257.5	514.9
1551	INDO YELLOW	382.7	765.3	1554	TINTING WHITE	350.4	700.7
1554	TINTING WHITE	399.1	798.2	1550	RED OXIDE	393.1	786.2
1501	LANDAU BLACK	404.4	808.8	1501	LANDAU BLACK	414.1	828.2
5036	MED DK FIRETHOR	General Motors		5043	CARDINAL	BMW	
1552	FAST RED	225.1	450.1	1552	FAST RED	262.6	525.2
1559	YELLOW OXIDE	323.4	646.8	1302	LOW LUSTER CLEAR	354.7	709.5
1302	LOW LUSTER CLEAR	394.1	788.1	1550	RED OXIDE	394.8	789.6
1553	FAST BLUE	405.0	810.0	1554	TINTING WHITE	402.2	804.5
1554	TINTING WHITE	405.7	811.3	1553	FAST BLUE	405.0	810.0

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 112

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5044	LT CREME	Jaguar		5051	STEIN	Mercedes Benz	
1554	TINTING WHITE	251.5	502.9	1559	YELLOW OXIDE	144.3	288.6
1551	INDO YELLOW	326.5	653.0	1302	LOW LUSTER CLEAR	249.5	498.9
1302	LOW LUSTER CLEAR	393.2	786.4	1554	TINTING WHITE	349.2	698.4
1552	FAST RED	420.3	840.6	1550	RED OXIDE	386.2	772.4
1501	LANDAU BLACK	422.8	845.5	1501	LANDAU BLACK	415.1	830.1
5045	SADDLE	Jaguar		5052	PARCHMENT	Mercedes Benz	
1559	YELLOW OXIDE	199.0	398.1	1554	TINTING WHITE	262.8	525.5
1554	TINTING WHITE	291.9	583.9	1302	LOW LUSTER CLEAR	344.5	688.9
1302	LOW LUSTER CLEAR	368.5	737.0	1559	YELLOW OXIDE	413.1	826.1
1550	RED OXIDE	405.3	810.5	1501	LANDAU BLACK	420.6	841.1
1551	INDO YELLOW	416.0	832.0	1550	RED OXIDE	425.1	850.3
5046	GREY	Mercedes Benz		5053	BAMBOO	Mercedes Benz	
1554	TINTING WHITE	176.3	352.6	1559	YELLOW OXIDE	260.3	520.6
1302	LOW LUSTER CLEAR	284.6	569.2	1302	LOW LUSTER CLEAR	348.0	696.0
1559	YELLOW OXIDE	344.4	688.8	1550	RED OXIDE	397.1	794.2
1501	LANDAU BLACK	403.2	806.4	1554	TINTING WHITE	407.1	814.2
1550	RED OXIDE	418.7	837.3	1501	LANDAU BLACK	411.2	822.3
5047	CHAMPAGNE PRIN	Mercedes Benz		5054	GREEN	Honda	G
1554	TINTING WHITE	188.8	377.5	1554	TINTING WHITE	149.3	298.7
1559	YELLOW OXIDE	301.3	602.7	1302	LOW LUSTER CLEAR	253.8	507.7
1302	LOW LUSTER CLEAR	384.2	768.4	1501	LANDAU BLACK	333.0	666.0
1550	RED OXIDE	407.4	814.7	1559	YELLOW OXIDE	412.1	824.2
1501	LANDAU BLACK	420.9	841.9	1553	FAST BLUE	416.6	833.2
5048	CREME BEIGE PRI	Mercedes Benz		5055	BROWN	Honda	H
1554	TINTING WHITE	169.2	338.4	1302	LOW LUSTER CLEAR	103.8	207.7
1559	YELLOW OXIDE	314.9	629.9	1559	YELLOW OXIDE	204.7	409.5
1302	LOW LUSTER CLEAR	393.3	786.6	1554	TINTING WHITE	296.7	593.4
1550	RED OXIDE	408.3	816.6	1501	LANDAU BLACK	355.7	711.4
1501	LANDAU BLACK	420.1	840.2	1550	RED OXIDE	414.1	828.2
5049	SAFFRIN PRINT	Mercedes Benz		5056	BROWN	Honda	G
1559	YELLOW OXIDE	238.7	477.5	1559	YELLOW OXIDE	165.7	331.4
1302	LOW LUSTER CLEAR	337.1	674.1	1302	LOW LUSTER CLEAR	284.1	568.1
1550	RED OXIDE	391.8	783.6	1550	RED OXIDE	331.4	662.7
1554	TINTING WHITE	403.0	806.0	1501	LANDAU BLACK	374.3	748.6
1501	LANDAU BLACK	410.9	821.8	1554	TINTING WHITE	411.0	821.9
5050	MED GREY	Mercedes Benz		5057	GREY	Honda	
1501	LANDAU BLACK	120.2	240.4	1559	YELLOW OXIDE	114.0	228.0
1302	LOW LUSTER CLEAR	226.7	453.3	1302	LOW LUSTER CLEAR	224.9	449.7
1559	YELLOW OXIDE	321.6	643.2	1554	TINTING WHITE	308.8	617.5
1554	TINTING WHITE	395.5	791.0	1501	LANDAU BLACK	391.1	782.2
1550	RED OXIDE	411.6	823.3	1550	RED OXIDE	413.0	825.9

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 113

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
5058	BEIGE	Honda		H	5065	DK GREY	Honda	K
1554	TINTING WHITE	206.2	412.5		1501	LANDAU BLACK	182.3	364.6
1302	LOW LUSTER CLEAR	317.3	634.6		1302	LOW LUSTER CLEAR	282.0	563.9
1559	YELLOW OXIDE	382.0	764.0		1559	YELLOW OXIDE	339.0	677.9
1550	RED OXIDE	402.3	804.7		1554	TINTING WHITE	393.1	786.2
1501	LANDAU BLACK	421.0	842.1		1550	RED OXIDE	409.6	819.3
5059	BEIGE	Honda		F	5066	TAUPE	Chrysler Motors	L5
1554	TINTING WHITE	128.6	257.3		1554	TINTING WHITE	121.7	243.4
1559	YELLOW OXIDE	246.4	492.9		1559	YELLOW OXIDE	235.3	470.6
1302	LOW LUSTER CLEAR	354.9	709.8		1302	LOW LUSTER CLEAR	331.4	662.7
1550	RED OXIDE	392.4	784.9		1501	LANDAU BLACK	379.7	759.4
1501	LANDAU BLACK	416.7	833.3		1550	RED OXIDE	416.2	832.4
5060	BEIGE	Honda		F	5067	DK TAUPE	Chrysler Motors	L8
1554	TINTING WHITE	203.8	407.6		1559	YELLOW OXIDE	122.8	245.7
1302	LOW LUSTER CLEAR	315.2	630.4		1302	LOW LUSTER CLEAR	232.2	464.4
1559	YELLOW OXIDE	407.6	815.1		1501	LANDAU BLACK	309.4	618.8
1501	LANDAU BLACK	415.5	831.1		1554	TINTING WHITE	365.7	731.3
1550	RED OXIDE	420.9	841.9		1550	RED OXIDE	411.6	823.3
5061	BEIGE	Honda		F	5068	LT OAK	General Motors	
1554	TINTING WHITE	176.9	353.8		1559	YELLOW OXIDE	165.9	331.7
1302	LOW LUSTER CLEAR	286.0	572.1		1554	TINTING WHITE	290.8	581.6
1559	YELLOW OXIDE	395.2	790.4		1302	LOW LUSTER CLEAR	375.4	750.9
1550	RED OXIDE	407.6	815.3		1550	RED OXIDE	404.9	809.8
1501	LANDAU BLACK	419.5	839.0		1501	LANDAU BLACK	417.4	834.9
5062	MED BROWN	Honda		F	5069	MED DK OAK	General Motors	
1559	YELLOW OXIDE	170.0	339.9		1559	YELLOW OXIDE	201.3	402.6
1302	LOW LUSTER CLEAR	278.1	556.1		1302	LOW LUSTER CLEAR	285.1	570.2
1550	RED OXIDE	325.0	650.0		1550	RED OXIDE	339.3	678.7
1554	TINTING WHITE	371.4	742.7		1554	TINTING WHITE	388.3	776.5
1501	LANDAU BLACK	411.8	823.7		1501	LANDAU BLACK	413.1	826.1
5063	TAN	Honda			5070	DK OAK	General Motors	
1559	YELLOW OXIDE	129.6	259.2		1559	YELLOW OXIDE	198.6	397.1
1302	LOW LUSTER CLEAR	239.1	478.2		1302	LOW LUSTER CLEAR	280.3	560.7
1501	LANDAU BLACK	325.2	650.4		1501	LANDAU BLACK	346.8	693.5
1554	TINTING WHITE	375.9	751.8		1550	RED OXIDE	405.7	811.3
1550	RED OXIDE	411.2	822.3		1554	TINTING WHITE	409.9	819.9
5064	DK GREEN	Honda		G	5071	DK REGAL BLUE	General Motors	
1501	LANDAU BLACK	153.4	306.9		1501	LANDAU BLACK	131.0	262.0
1302	LOW LUSTER CLEAR	256.7	513.4		1554	TINTING WHITE	224.3	448.6
1559	YELLOW OXIDE	312.7	625.5		1302	LOW LUSTER CLEAR	306.9	613.9
1554	TINTING WHITE	365.8	731.7		1553	FAST BLUE	366.8	733.6
1556	FAST GREEN	409.0	818.0		1550	RED OXIDE	411.7	823.5

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 114

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
5072	MED DK PEWTER	General Motors		92	5079	CREME BEIGH PRI	Mercedes Benz	175
1554	TINTING WHITE	141.3	282.5		1554	TINTING WHITE	172.8	345.6
1559	YELLOW OXIDE	242.6	485.3		1559	YELLOW OXIDE	298.7	597.4
1302	LOW LUSTER CLEAR	328.8	657.6		1302	LOW LUSTER CLEAR	394.5	789.1
1501	LANDAU BLACK	386.4	772.7		1550	RED OXIDE	407.3	814.5
1550	RED OXIDE	417.4	834.9		1501	LANDAU BLACK	419.7	839.4
5073	DK HIGHLAND GRE	General Motors			5080	STONE PINE GREE	Mercedes Benz	176
1559	YELLOW OXIDE	171.1	342.2		1501	LANDAU BLACK	106.8	213.6
1501	LANDAU BLACK	292.8	585.6		1302	LOW LUSTER CLEAR	197.0	394.1
1302	LOW LUSTER CLEAR	374.6	749.2		1551	INDO YELLOW	287.0	574.0
1554	TINTING WHITE	393.2	786.4		1556	FAST GREEN	374.2	748.4
1556	FAST GREEN	408.9	817.8		1554	TINTING WHITE	406.1	812.3
5074	ACCENT OAK	General Motors			5081	BURGUNDY PRINT	Mercedes Benz	177
1559	YELLOW OXIDE	188.9	377.7		1552	FAST RED	224.3	448.6
1302	LOW LUSTER CLEAR	270.7	541.3		1302	LOW LUSTER CLEAR	330.2	660.4
1550	RED OXIDE	341.3	682.7		1551	INDO YELLOW	382.9	765.7
1501	LANDAU BLACK	386.8	773.7		1501	LANDAU BLACK	393.8	787.6
1554	TINTING WHITE	411.4	822.7		1554	TINTING WHITE	404.0	808.1
5075	BLACK PRINT	Mercedes Benz		171	5082	GREY PRINT	Mercedes Benz	178
1501	LANDAU BLACK	279.3	558.6		1554	TINTING WHITE	188.5	377.0
1302	LOW LUSTER CLEAR	375.1	750.1		1302	LOW LUSTER CLEAR	285.3	570.6
1559	YELLOW OXIDE	394.3	788.5		1501	LANDAU BLACK	349.8	699.6
1550	RED OXIDE	401.2	802.4		1559	YELLOW OXIDE	406.6	813.2
1554	TINTING WHITE	405.0	810.0		1550	RED OXIDE	419.5	839.0
5076	BLUE PRINT	Mercedes Benz		172	5083	BLACK	Mercedes Benz	
1553	FAST BLUE	188.1	376.2		1501	LANDAU BLACK	344.6	689.1
1501	LANDAU BLACK	290.6	581.2		1302	LOW LUSTER CLEAR	389.5	779.0
1302	LOW LUSTER CLEAR	380.5	761.0		1551	INDO YELLOW	398.5	797.1
1554	TINTING WHITE	404.7	809.4		1550	RED OXIDE	404.5	809.0
					1554	TINTING WHITE	404.8	809.6
5077	DK BROWN PRINT	Mercedes Benz		173	5084	GREY	Mercedes Benz	
1501	LANDAU BLACK	133.7	267.3		1554	TINTING WHITE	186.8	373.5
1550	RED OXIDE	242.8	485.6		1501	LANDAU BLACK	279.5	559.0
1302	LOW LUSTER CLEAR	333.7	667.5		1559	YELLOW OXIDE	357.5	715.0
1559	YELLOW OXIDE	404.0	808.1		1302	LOW LUSTER CLEAR	408.8	817.6
1554	TINTING WHITE	408.3	816.6		1550	RED OXIDE	420.1	840.2
5078	PALOMINO PRINT	Mercedes Benz		174	5085	PARCHMENT	Mercedes Benz	
1559	YELLOW OXIDE	213.6	427.1		1554	TINTING WHITE	162.6	325.3
1302	LOW LUSTER CLEAR	309.2	618.5		1559	YELLOW OXIDE	320.2	640.3
1554	TINTING WHITE	366.3	732.6		1302	LOW LUSTER CLEAR	375.2	750.3
1550	RED OXIDE	406.5	813.0		1550	RED OXIDE	403.4	806.7
1501	LANDAU BLACK	413.5	827.1		1501	LANDAU BLACK	420.2	840.4

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 115

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5086	BLUE	Mercedes Benz		5093	RUBY	General Motors 9933	
1501	LANDAU BLACK	155.4	310.8	1552	FAST RED	262.4	524.8
1553	FAST BLUE	304.9	609.7	1302	LOW LUSTER CLEAR	388.6	777.1
1302	LOW LUSTER CLEAR	364.6	729.2	1501	LANDAU BLACK	394.1	788.1
1554	TINTING WHITE	396.5	793.1	1553	FAST BLUE	398.8	797.6
1550	RED OXIDE	406.1	812.3	1554	TINTING WHITE	403.4	806.7
5087	SADDLE	Mercedes Benz		5094	MED SMOKE GARY	General Motors M18	
1559	YELLOW OXIDE	248.5	497.0	1554	TINTING WHITE	160.2	320.3
1550	RED OXIDE	317.9	635.7	1559	YELLOW OXIDE	259.5	519.1
1302	LOW LUSTER CLEAR	371.5	743.1	1501	LANDAU BLACK	315.8	631.6
1554	TINTING WHITE	398.7	797.4	1550	RED OXIDE	371.6	743.3
1501	LANDAU BLACK	413.1	826.1	1302	LOW LUSTER CLEAR	419.8	839.6
5088	TRUFFLE	Ford Motor	YEC	5095	MED BEIGE	General Motors UK	
1554	TINTING WHITE	140.9	281.8	1559	YELLOW OXIDE	217.3	434.5
1302	LOW LUSTER CLEAR	279.0	558.0	1554	TINTING WHITE	318.2	636.3
1559	YELLOW OXIDE	361.0	722.0	1550	RED OXIDE	387.2	774.4
1501	LANDAU BLACK	397.5	795.0	1501	LANDAU BLACK	418.3	836.6
1550	RED OXIDE	416.3	832.6				
5089	NAPLES	Ford Motor	YZ5A	5096	DARK REGAL BLUE	General Motors 104E	
1302	LOW LUSTER CLEAR	151.7	303.4	1302	LOW LUSTER CLEAR	144.1	288.2
1553	FAST BLUE	242.6	485.3	1501	LANDAU BLACK	227.1	454.3
1550	RED OXIDE	317.6	635.2	1554	TINTING WHITE	303.5	607.1
1501	LANDAU BLACK	390.0	780.0	1553	FAST BLUE	369.8	739.7
1554	TINTING WHITE	405.7	811.5	1550	RED OXIDE	409.9	819.9
5090	MIDNIGHT BLACK	Ford Motor	ZUEA	5097	LT WHEAT	General Motors 503F	
1501	LANDAU BLACK	135.9	271.7	1554	TINTING WHITE	377.9	755.8
1302	LOW LUSTER CLEAR	270.3	540.6	1559	YELLOW OXIDE	421.3	842.7
1559	YELLOW OXIDE	349.0	698.1	1550	RED OXIDE	430.8	861.7
1554	TINTING WHITE	380.0	760.0	1553	FAST BLUE	434.0	867.9
1550	RED OXIDE	408.2	816.4				
5091	BRIGHT AQUA	General Motors	147A	5098	MD WHEAT	General Motors 504F	
1556	FAST GREEN	141.2	282.3	1302	LOW LUSTER CLEAR	149.5	299.1
1302	LOW LUSTER CLEAR	231.1	462.3	1554	TINTING WHITE	271.6	543.2
1553	FAST BLUE	308.6	617.1	1559	YELLOW OXIDE	363.5	726.9
1554	TINTING WHITE	381.6	763.2	1501	LANDAU BLACK	395.5	791.0
1552	FAST RED	408.6	817.2	1550	RED OXIDE	415.0	829.9
5092	DK SIENNA	General Motors	M25	5099	MD DK WHEAT	General Motors 564F	
1559	YELLOW OXIDE	233.9	467.8	1302	LOW LUSTER CLEAR	142.9	285.8
1550	RED OXIDE	336.4	672.8	1559	YELLOW OXIDE	263.2	526.3
1302	LOW LUSTER CLEAR	373.4	746.9	1554	TINTING WHITE	344.6	689.1
1501	LANDAU BLACK	398.6	797.2	1501	LANDAU BLACK	386.3	772.5
1554	TINTING WHITE	412.7	825.4	1552	FAST RED	412.0	824.0

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 116

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
5100	DK GRAY	General Motors		8595	5107	OXFORD WHITE	Ford Motor	4PA
1501	LANDAU BLACK	173.3	346.6		1554	TINTING WHITE	415.4	830.9
1554	TINTING WHITE	323.2	646.4		1559	YELLOW OXIDE	431.2	862.4
1559	YELLOW OXIDE	414.2	828.4		1501	LANDAU BLACK	435.6	871.2
1550	RED OXIDE	418.0	836.0		1550	RED OXIDE	436.1	872.1
5101	PEWTER	General Motors		109D	5108	COGNAC	Chrysler Motors	UC
1554	TINTING WHITE	175.6	351.1		1302	LOW LUSTER CLEAR	214.4	428.8
1559	YELLOW OXIDE	273.7	547.4		1559	YELLOW OXIDE	344.5	688.9
1302	LOW LUSTER CLEAR	349.2	698.4		1550	RED OXIDE	403.1	806.2
1501	LANDAU BLACK	394.2	788.3		1556	FAST GREEN	406.8	813.6
1550	RED OXIDE	419.8	839.6					
5102	DARK GRAPHITE	Ford Motor		ZU5	5109	MED OPAL MET		
1302	LOW LUSTER CLEAR	135.6	271.1		1501	LANDAU BLACK	167.3	334.6
1501	LANDAU BLACK	231.6	463.2		1300	HIGH GLOSS CLEAR	331.3	662.5
1554	TINTING WHITE	308.5	616.9		3520	PLATINUM PEARL	396.9	793.8
1559	YELLOW OXIDE	379.6	759.2		1552	FAST RED	409.7	819.5
1550	RED OXIDE	411.5	823.1		1553	FAST BLUE	421.2	842.5
5103	FLANNEL GRAY	Ford Motor		YCB	5110	CAMEL	Chrysler Motors	K9
1554	TINTING WHITE	258.6	517.2		1302	LOW LUSTER CLEAR	176.0	352.1
1302	LOW LUSTER CLEAR	331.1	662.2		1559	YELLOW OXIDE	313.1	626.2
1501	LANDAU BLACK	373.8	747.7		1550	RED OXIDE	350.0	700.0
1559	YELLOW OXIDE	409.0	818.0		1554	TINTING WHITE	384.0	768.0
1550	RED OXIDE	424.6	849.1		1501	LANDAU BLACK	409.4	818.7
5104	MED DK TRUFFLE	Ford Motor		YE4	5111	FAWN	Chrysler Motors	T5
1302	LOW LUSTER CLEAR	138.0	276.1		1302	LOW LUSTER CLEAR	191.8	383.6
1559	YELLOW OXIDE	240.2	480.3		1559	YELLOW OXIDE	286.7	573.4
1501	LANDAU BLACK	313.9	627.8		1554	TINTING WHITE	363.5	726.9
1554	TINTING WHITE	386.5	772.9		1550	RED OXIDE	391.5	783.0
1550	RED OXIDE	411.5	823.1		1501	LANDAU BLACK	411.4	822.7
5105	MED PARCHMENT	Ford Motor		BJC	5111	TAN	Chrysler Motors	GT5
1554	TINTING WHITE	192.1	384.2		1302	LOW LUSTER CLEAR	191.8	383.6
1559	YELLOW OXIDE	361.9	723.7		1559	YELLOW OXIDE	286.7	573.4
1552	FAST RED	396.6	793.3		1554	TINTING WHITE	363.5	726.9
1501	LANDAU BLACK	422.5	844.9		1550	RED OXIDE	391.5	783.0
					1501	LANDAU BLACK	411.4	822.7
5106	LT PARCHMENT	Ford Motor		BJA	5112	EURO MET		
1554	TINTING WHITE	333.5	667.1		1501	LANDAU BLACK	234.9	469.9
1559	YELLOW OXIDE	412.2	824.4		1508	SILVER	366.1	732.3
1552	FAST RED	421.9	843.8		1553	FAST BLUE	403.3	806.6
1501	LANDAU BLACK	431.2	862.4		1552	FAST RED	406.0	812.1

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 117

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

5113	CHRYSLER GRAY G	Chrysler Motors	
1559	YELLOW OXIDE	190.7	381.3
1501	LANDAU BLACK	344.0	688.0
1554	TINTING WHITE	393.7	787.4
1553	FAST BLUE	412.3	824.6

5120	HOUSE WHITE		
1554	TINTING WHITE	435.8	871.5
1501	LANDAU BLACK	436.4	872.9
1559	YELLOW OXIDE	437.1	874.2
1553	FAST BLUE	437.3	874.6

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

5114	GLOSS CABERNET		
1552	FAST RED	334.7	669.4
1550	RED OXIDE	395.9	791.7
1553	FAST BLUE	402.5	805.0
1554	TINTING WHITE	405.7	811.3

5121	SHARK WHITE		
1554	TINTING WHITE	433.7	867.4
1501	LANDAU BLACK	435.4	870.8
1559	YELLOW OXIDE	436.7	873.4
1553	FAST BLUE	437.2	874.4

MUST BE TOP COATED WITH 1300 HIGH GLOSS CLEAR

5115	HATTERAS GREEN		
1556	FAST GREEN	275.6	551.2
1554	TINTING WHITE	396.6	793.3
1553	FAST BLUE	408.2	816.4
1551	INDO YELLOW	413.2	826.3

5122	GRAY WHITE		
1554	TINTING WHITE	434.7	869.4
1501	LANDAU BLACK	436.3	872.7
1559	YELLOW OXIDE	437.0	874.0
1553	FAST BLUE	437.2	874.4

5116	LT SLATE	Chrysler Motors	DB
1554	TINTING WHITE	151.9	303.8
1302	LOW LUSTER CLEAR	294.9	589.8
1559	YELLOW OXIDE	351.7	703.4
1501	LANDAU BLACK	401.9	803.7
1550	RED OXIDE	416.4	832.8

5123	PINE WHITE		
1554	TINTING WHITE	282.2	564.5
1302	LOW LUSTER CLEAR	424.1	848.2
1556	FAST GREEN	424.5	848.9
1550	RED OXIDE	424.6	849.1

5117	SUPREME WHITE		
1554	TINTING WHITE	282.4	564.9
1302	LOW LUSTER CLEAR	424.4	848.7
1501	LANDAU BLACK	424.5	848.9
1553	FAST BLUE	424.6	849.1

5124	SKY WHITE		
1554	TINTING WHITE	436.7	873.4
1553	FAST BLUE	437.4	874.8

5118	POLAR WHITE		
1554	TINTING WHITE	436.7	873.4
1553	FAST BLUE	437.1	874.2
1552	FAST RED	437.3	874.6

5125	FRESH VANILLA		
1554	TINTING WHITE	340.6	681.2
1559	YELLOW OXIDE	425.5	851.0
1550	RED OXIDE	429.9	859.8
1501	LANDAU BLACK	432.1	864.1

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

5119	BABY WHITE		
1554	TINTING WHITE	282.2	564.3
1302	LOW LUSTER CLEAR	423.9	847.8
1553	FAST BLUE	424.5	848.9
1501	LANDAU BLACK	424.6	849.1

5126	VANILLA CREAM		
1554	TINTING WHITE	344.7	689.3
1559	YELLOW OXIDE	425.4	850.8
1550	RED OXIDE	430.4	860.7
1501	LANDAU BLACK	432.3	864.5

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 118

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

5127	PASTEL BEIGE			
1554	TINTING WHITE	399.2	798.4	
1559	YELLOW OXIDE	428.7	857.5	
1550	RED OXIDE	433.1	866.2	
1501	LANDAU BLACK	435.3	870.6	

5134	NATURAL WHITE			
1554	TINTING WHITE	431.5	863.0	
1559	YELLOW OXIDE	435.3	870.6	
1552	FAST RED	436.7	873.4	
1553	FAST BLUE	437.0	874.0	

5128	VERY LIGHT MOC			
1554	TINTING WHITE	378.5	757.0	
1559	YELLOW OXIDE	423.7	847.4	
1550	RED OXIDE	432.3	864.7	
1501	LANDAU BLACK	434.1	868.1	

5135	CAROLINA WHITE			
1554	TINTING WHITE	430.8	861.7	
1559	YELLOW OXIDE	435.3	870.6	
1501	LANDAU BLACK	437.1	874.2	

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

5129	LIGHT CARAMEL			
1554	TINTING WHITE	389.9	779.8	
1559	YELLOW OXIDE	424.2	848.4	
1550	RED OXIDE	433.0	866.0	
1501	LANDAU BLACK	434.8	869.6	

5136	DARK NATURAL W			
1554	TINTING WHITE	420.3	840.6	
1559	YELLOW OXIDE	434.2	868.5	
1501	LANDAU BLACK	436.0	871.9	
1550	RED OXIDE	436.4	872.9	

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

5130	DARK PASTEL			
1554	TINTING WHITE	392.5	785.1	
1559	YELLOW OXIDE	426.4	852.7	
1550	RED OXIDE	431.4	862.8	
1501	LANDAU BLACK	434.9	869.8	

5137	OXFORD WHITE			
1554	TINTING WHITE	415.4	830.9	
1559	YELLOW OXIDE	431.2	862.4	
1501	LANDAU BLACK	435.6	871.2	
1550	RED OXIDE	436.1	872.1	

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

5131	GRAY IVORY			
1554	TINTING WHITE	380.4	760.8	
1559	YELLOW OXIDE	427.2	854.4	
1550	RED OXIDE	431.1	862.2	
1501	LANDAU BLACK	434.2	868.3	

5138	HEATHER BEIGE			
1554	TINTING WHITE	402.3	804.7	
1559	YELLOW OXIDE	426.7	853.5	
1550	RED OXIDE	432.4	864.9	
1501	LANDAU BLACK	435.5	871.0	

MUST TOP COAT WITH 1302 LOW LUSTER CLEAR

5132	BETTER BEIGE			
1554	TINTING WHITE	412.3	824.6	
1559	YELLOW OXIDE	430.6	861.3	
1550	RED OXIDE	433.5	867.0	
1501	LANDAU BLACK	436.1	872.1	

5139	MED PEARL WHITE			
1554	TINTING WHITE	391.3	782.6	
1559	YELLOW OXIDE	428.3	856.5	
1501	LANDAU BLACK	433.0	866.0	
1550	RED OXIDE	434.7	869.4	

5133	PASTEL WHITE			
1554	TINTING WHITE	431.8	863.6	
1551	INDO YELLOW	434.4	868.9	
1550	RED OXIDE	435.8	871.5	
1501	LANDAU BLACK	437.1	874.2	

5140	OYSTER WHITE			
1554	TINTING WHITE	405.6	811.1	
1559	YELLOW OXIDE	426.8	853.7	
1550	RED OXIDE	433.8	867.5	
1556	FAST GREEN	435.5	871.0	

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 119

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

5141	DARK OYSTER WHI		
1554	TINTING WHITE	289.9	579.9
1302	LOW LUSTER CLEAR	396.5	793.1
1559	YELLOW OXIDE	421.8	843.6
1550	RED OXIDE	424.3	848.5
1501	LANDAU BLACK	426.1	852.2

5148	ROCK BEIGE		
1554	TINTING WHITE	220.8	441.6
1559	YELLOW OXIDE	324.4	648.9
1302	LOW LUSTER CLEAR	408.8	817.6
1550	RED OXIDE	416.6	833.2
1501	LANDAU BLACK	422.8	845.5

5142	LIGHT PASTEL		
1554	TINTING WHITE	399.7	799.3
1559	YELLOW OXIDE	428.1	856.1
1550	RED OXIDE	432.3	864.7
1501	LANDAU BLACK	435.3	870.6

5149	KHAKI		
1554	TINTING WHITE	172.4	344.9
1559	YELLOW OXIDE	298.0	596.0
1302	LOW LUSTER CLEAR	393.6	787.2
1550	RED OXIDE	407.6	815.3
1501	LANDAU BLACK	419.7	839.4

5143	BAMBI		
1554	TINTING WHITE	265.1	530.1
1302	LOW LUSTER CLEAR	405.9	811.9
1559	YELLOW OXIDE	419.7	839.4
1550	RED OXIDE	422.6	845.1
1501	LANDAU BLACK	423.7	847.4

5150	DIRTY BEIGE		
1302	LOW LUSTER CLEAR	138.7	277.4
1554	TINTING WHITE	272.1	544.2
1559	YELLOW OXIDE	400.5	801.0
1501	LANDAU BLACK	408.5	817.0
1550	RED OXIDE	416.2	832.4

5144	DEER		
1554	TINTING WHITE	386.3	772.5
1559	YELLOW OXIDE	422.3	844.6
1550	RED OXIDE	430.5	861.1
1501	LANDAU BLACK	434.4	868.9

5151	HONEY BEIGE		
1554	TINTING WHITE	176.7	353.4
1559	YELLOW OXIDE	312.6	625.3
1302	LOW LUSTER CLEAR	396.7	793.4
1550	RED OXIDE	409.5	819.1
1501	LANDAU BLACK	420.3	840.6

5145	ELK		
1554	TINTING WHITE	267.8	535.6
1302	LOW LUSTER CLEAR	378.1	756.2
1559	YELLOW OXIDE	412.8	825.6
1550	RED OXIDE	421.3	842.7
1501	LANDAU BLACK	424.7	849.5

5152	PHANTOM BEIGE		
1554	TINTING WHITE	263.7	527.4
1559	YELLOW OXIDE	405.3	810.5
1501	LANDAU BLACK	418.1	836.2
1550	RED OXIDE	427.5	855.0

5146	CHAMPAGNE		
1554	TINTING WHITE	390.9	781.9
1559	YELLOW OXIDE	432.2	864.3
1550	RED OXIDE	433.5	867.0
1501	LANDAU BLACK	434.8	869.6

5153	WALNUT BEIGE		
1554	TINTING WHITE	357.4	714.8
1559	YELLOW OXIDE	413.3	826.7
1501	LANDAU BLACK	423.2	846.5
1550	RED OXIDE	432.7	865.5

5147	LIGHT PHANTOM		
1554	TINTING WHITE	404.3	808.6
1559	YELLOW OXIDE	431.3	862.6
1550	RED OXIDE	433.5	867.0
1501	LANDAU BLACK	435.5	871.0

5154	CASTLE BEIGE		
1554	TINTING WHITE	200.6	401.3
1302	LOW LUSTER CLEAR	341.6	683.2
1559	YELLOW OXIDE	397.3	794.6
1501	LANDAU BLACK	412.1	824.2
1550	RED OXIDE	419.8	839.6

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 120

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

5155	DUSTY BEIGE		
1554	TINTING WHITE	194.8	389.7
1302	LOW LUSTER CLEAR	334.8	669.6
1559	YELLOW OXIDE	393.8	787.6
1501	LANDAU BLACK	407.6	815.1
1550	RED OXIDE	419.5	839.0

5162	SAND BEIGE		
1554	TINTING WHITE	248.5	497.0
1551	INDO YELLOW	328.9	657.8
1302	LOW LUSTER CLEAR	391.0	782.0
1552	FAST RED	417.9	835.8
1501	LANDAU BLACK	422.6	845.1

5156	AUTUMN BEIGE		
1554	TINTING WHITE	250.5	501.0
1551	INDO YELLOW	329.4	658.7
1302	LOW LUSTER CLEAR	390.0	780.0
1552	FAST RED	419.9	839.8
1501	LANDAU BLACK	422.8	845.5

5163	CLAYTON TAN		
1554	TINTING WHITE	300.9	601.7
1559	YELLOW OXIDE	422.5	844.9
1550	RED OXIDE	427.2	854.4
1501	LANDAU BLACK	429.8	859.6

5157	APRICOT		
1554	TINTING WHITE	313.8	627.6
1559	YELLOW OXIDE	427.1	854.2
1550	RED OXIDE	430.5	861.1

5164	LIGHT BEIGE		
1554	TINTING WHITE	271.4	542.8
1559	YELLOW OXIDE	416.1	832.2
1550	RED OXIDE	422.6	845.1
1501	LANDAU BLACK	428.2	856.3

5158	COTTAGE BEIGE		
1554	TINTING WHITE	339.8	679.6
1559	YELLOW OXIDE	420.2	840.4
1550	RED OXIDE	431.1	862.2
1501	LANDAU BLACK	432.1	864.1

5165	SUPREME BEIGE		
1554	TINTING WHITE	173.8	347.5
1559	YELLOW OXIDE	320.0	639.9
1302	LOW LUSTER CLEAR	404.0	808.1
1550	RED OXIDE	414.1	828.2
1501	LANDAU BLACK	420.2	840.4

5159	CREAM WHEAT		
1554	TINTING WHITE	339.0	677.9
1559	YELLOW OXIDE	430.6	861.3
1501	LANDAU BLACK	432.0	863.9

5166	PECAN BEIGE		
1554	TINTING WHITE	256.5	513.0
1559	YELLOW OXIDE	389.8	779.6
1550	RED OXIDE	414.2	828.4
1501	LANDAU BLACK	427.3	854.6

5160	WHEAT		
1559	YELLOW OXIDE	148.9	297.7
1302	LOW LUSTER CLEAR	287.4	574.8
1554	TINTING WHITE	403.0	806.0
1550	RED OXIDE	411.1	822.1
1501	LANDAU BLACK	415.4	830.9

5167	SADDLE BEIGE		
1554	TINTING WHITE	153.5	307.0
1302	LOW LUSTER CLEAR	292.5	585.0
1559	YELLOW OXIDE	389.2	778.4
1550	RED OXIDE	405.9	811.9
1501	LANDAU BLACK	417.3	834.7

5161	ROCKY BEIGE		
1559	YELLOW OXIDE	300.4	600.8
1554	TINTING WHITE	405.1	810.2
1550	RED OXIDE	415.6	831.3
1501	LANDAU BLACK	418.9	837.7

5168	CLASSIC CARAMEL		
1554	TINTING WHITE	265.2	530.5
1559	YELLOW OXIDE	398.5	797.1
1550	RED OXIDE	417.7	835.4
1501	LANDAU BLACK	427.7	855.4

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 121

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

5169	DARK KAHLUA		
1554	TINTING WHITE	202.3	404.5
1559	YELLOW OXIDE	384.9	769.9
1550	RED OXIDE	412.8	825.6
1501	LANDAU BLACK	424.2	848.4

5176	Elk Grain		
1554	TINTING WHITE	232.1	464.1
1302	LOW LUSTER CLEAR	358.9	717.8
1559	YELLOW OXIDE	411.2	822.5
1550	RED OXIDE	431.8	863.5
1501	LANDAU BLACK	443.8	887.6

5170	KAHLUA		
1559	YELLOW OXIDE	200.1	400.1
1554	TINTING WHITE	387.0	774.1
1550	RED OXIDE	415.3	830.7
1501	LANDAU BLACK	423.4	846.8

5177	SWEET MOCHA		
1554	TINTING WHITE	253.4	506.7
1559	YELLOW OXIDE	371.5	742.9
1550	RED OXIDE	415.1	830.1
1501	LANDAU BLACK	427.0	854.1

5171	CHESTNUT		
1559	YELLOW OXIDE	207.3	414.6
1554	TINTING WHITE	301.2	602.3
1302	LOW LUSTER CLEAR	384.2	768.4
1550	RED OXIDE	411.2	822.3
1501	LANDAU BLACK	415.9	831.8

5178	ANTELOPE BEIGE		
1554	TINTING WHITE	303.3	606.7
1559	YELLOW OXIDE	381.6	763.2
1550	RED OXIDE	416.0	832.0
1501	LANDAU BLACK	429.8	859.6

5172	COPPER MET.		
1508	SILVER	199.9	399.8
1552	FAST RED	332.5	665.0
1551	INDO YELLOW	381.4	762.9
1556	FAST GREEN	401.4	802.8
1554	TINTING WHITE	406.7	813.4

5179	SIERRA NEUTRAL		
1554	TINTING WHITE	185.9	371.8
1302	LOW LUSTER CLEAR	326.2	652.5
1559	YELLOW OXIDE	391.8	783.6
1550	RED OXIDE	406.7	813.4
1501	LANDAU BLACK	419.0	838.1

MUST TOP COAT WITH 1301 SATIN GLOSS CLEAR

5173	LIGHT SADDLE		
1559	YELLOW OXIDE	216.9	433.8
1554	TINTING WHITE	373.2	746.3
1550	RED OXIDE	410.4	820.8
1501	LANDAU BLACK	421.6	843.2

5180	DARK SADDLE		
1559	YELLOW OXIDE	217.6	435.3
1554	TINTING WHITE	374.4	748.8
1550	RED OXIDE	410.9	821.8
1501	LANDAU BLACK	421.7	843.4

5174	BISCUIT		
1559	YELLOW OXIDE	230.7	461.3
1554	TINTING WHITE	373.2	746.3
1550	RED OXIDE	417.2	834.5
1501	LANDAU BLACK	421.0	842.1

5181	DARK KHAKI		
1559	YELLOW OXIDE	239.7	479.4
1554	TINTING WHITE	364.4	728.8
1550	RED OXIDE	410.8	821.6
1501	LANDAU BLACK	420.1	840.2

MUST TOP COAT WITH 1302 LOW LUSTER CLEAR

5175	SHELL		
1554	TINTING WHITE	250.7	501.4
1559	YELLOW OXIDE	380.6	761.1
1550	RED OXIDE	426.7	853.5
1501	LANDAU BLACK	427.1	854.2

5182	COFFEE		
1559	YELLOW OXIDE	186.1	372.2
1302	LOW LUSTER CLEAR	323.4	646.8
1554	TINTING WHITE	370.8	741.6
1550	RED OXIDE	403.1	806.2
1501	LANDAU BLACK	411.5	823.1

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 122

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5183	SANDLE WOOD						
1559	YELLOW OXIDE	296.5	593.0	1559	YELLOW OXIDE	201.3	402.6
1550	RED OXIDE	353.2	706.4	1302	LOW LUSTER CLEAR	285.1	570.2
1554	TINTING WHITE	407.8	815.7	1550	RED OXIDE	339.3	678.7
1501	LANDAU BLACK	416.2	832.4	1554	TINTING WHITE	388.3	776.5
				1501	LANDAU BLACK	413.1	826.1
5184	GRAY KHAKI			5191	COCONUT		
1559	YELLOW OXIDE	223.2	446.3	1302	LOW LUSTER CLEAR	214.4	428.8
1554	TINTING WHITE	361.0	722.0	1559	YELLOW OXIDE	344.5	688.9
1550	RED OXIDE	396.6	793.3	1550	RED OXIDE	403.1	806.2
1501	LANDAU BLACK	420.4	840.8	1556	FAST GREEN	406.8	813.6
5185	COFFEE CREAM			5192	BAMB00		
1559	YELLOW OXIDE	254.3	508.6	1559	YELLOW OXIDE	196.6	393.1
1554	TINTING WHITE	376.8	753.5	1302	LOW LUSTER CLEAR	274.3	548.5
1550	RED OXIDE	409.0	818.0	1550	RED OXIDE	341.2	682.5
1501	LANDAU BLACK	419.7	839.4	1554	TINTING WHITE	392.5	785.1
				1552	FAST RED	413.4	826.9
5186	FRENCH COFFEE			5193	SANTA BROWN		
1559	YELLOW OXIDE	252.1	504.3	1559	YELLOW OXIDE	157.4	314.8
1554	TINTING WHITE	373.4	746.7	1554	TINTING WHITE	299.4	598.9
1550	RED OXIDE	405.9	811.9	1550	RED OXIDE	403.0	806.0
1501	LANDAU BLACK	419.6	839.2	1501	LANDAU BLACK	420.9	841.9
MUST TOP COAT WITH 1302 SATIN GLOSS CLEAR				MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR			
5187	DARK OATMEAL			5194	SPICE		
1559	YELLOW OXIDE	278.3	556.5	1559	YELLOW OXIDE	282.5	565.1
1554	TINTING WHITE	362.5	725.0	1550	RED OXIDE	352.1	704.1
1550	RED OXIDE	398.2	796.5	1554	TINTING WHITE	406.6	813.2
1501	LANDAU BLACK	417.5	835.1	1501	LANDAU BLACK	416.2	832.4
5188	DARK BISCUIT			5195	MED. SPICE		
1559	YELLOW OXIDE	207.0	414.0	1559	YELLOW OXIDE	166.1	332.1
1554	TINTING WHITE	340.4	680.8	1302	LOW LUSTER CLEAR	300.9	601.7
1550	RED OXIDE	403.5	806.9	1554	TINTING WHITE	354.3	708.5
1501	LANDAU BLACK	420.3	840.6	1550	RED OXIDE	406.3	812.6
				1501	LANDAU BLACK	412.2	824.4
5189	TAN			5196	COFFEE SUPREME		
1559	YELLOW OXIDE	210.0	420.1	1302	LOW LUSTER CLEAR	137.9	275.9
1554	TINTING WHITE	352.7	705.5	1559	YELLOW OXIDE	275.6	551.2
1550	RED OXIDE	407.8	815.7	1554	TINTING WHITE	360.1	720.1
1501	LANDAU BLACK	420.9	841.7	1550	RED OXIDE	399.8	799.5
				1501	LANDAU BLACK	413.5	827.1

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 123

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

5197	DOESKIN		
1554	TINTING WHITE	195.2	390.5
1559	YELLOW OXIDE	366.9	733.8
1550	RED OXIDE	399.1	798.2
1501	LANDAU BLACK	423.5	847.0

5204	DARK SPICE		
1559	YELLOW OXIDE	196.3	392.5
1302	LOW LUSTER CLEAR	332.5	665.0
1550	RED OXIDE	389.6	779.2
1501	LANDAU BLACK	408.9	817.8

MUST TOP COAT WITH 1302 SATIN GLOSS CLEAR

5198	DRIFTWOOD		
1559	YELLOW OXIDE	186.6	373.2
1554	TINTING WHITE	358.2	716.5
1550	RED OXIDE	397.7	795.3
1501	LANDAU BLACK	422.3	844.6

5205	DARK TAN		
1559	YELLOW OXIDE	185.9	371.8
1302	LOW LUSTER CLEAR	310.4	620.7
1550	RED OXIDE	392.2	784.3
1501	LANDAU BLACK	409.3	818.5

5199	MED. CASTELLA		
1554	TINTING WHITE	189.1	378.3
1559	YELLOW OXIDE	331.3	662.5
1550	RED OXIDE	394.9	789.8
1501	LANDAU BLACK	423.2	846.5

5206	DARK CHAMOIS		
1559	YELLOW OXIDE	210.2	420.5
1550	RED OXIDE	297.2	594.3
1554	TINTING WHITE	358.8	717.6
1501	LANDAU BLACK	415.6	831.3

5200	DARK CASTELLA		
1554	TINTING WHITE	147.3	294.5
1559	YELLOW OXIDE	254.8	509.6
1302	LOW LUSTER CLEAR	321.1	642.2
1550	RED OXIDE	385.5	771.0
1501	LANDAU BLACK	418.9	837.7

5207	BROWN SUGAR		
1559	YELLOW OXIDE	166.7	333.5
1550	RED OXIDE	264.3	528.6
1554	TINTING WHITE	348.3	696.5
1501	LANDAU BLACK	416.6	833.2

5201	PUMICE		
1559	YELLOW OXIDE	156.7	313.3
1554	TINTING WHITE	306.9	613.9
1550	RED OXIDE	372.7	745.4
1501	LANDAU BLACK	420.7	841.3

5208	TAUPE		
1559	YELLOW OXIDE	175.4	350.7
1554	TINTING WHITE	267.1	534.3
1501	LANDAU BLACK	347.6	695.2
1550	RED OXIDE	416.8	833.5

5202	MED. SANDSTONE		
1559	YELLOW OXIDE	177.2	354.4
1554	TINTING WHITE	345.4	690.8
1550	RED OXIDE	395.5	791.0
1501	LANDAU BLACK	422.1	844.2

5209	BROWN		
1559	YELLOW OXIDE	175.4	350.7
1550	RED OXIDE	315.7	631.4
1501	LANDAU BLACK	378.8	757.5
1554	TINTING WHITE	414.2	828.4

5203	Nature		
1302	LOW LUSTER CLEAR	137.1	274.1
1559	YELLOW OXIDE	261.5	522.9
1554	TINTING WHITE	375.8	751.6
1550	RED OXIDE	402.7	805.4
1501	LANDAU BLACK	415.2	830.5

5210	SWISS BROWN		
1559	YELLOW OXIDE	190.8	381.5
1550	RED OXIDE	322.8	645.6
1501	LANDAU BLACK	394.7	789.5
1554	TINTING WHITE	413.1	826.1

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 124

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5211	BROWNIE						
1559	YELLOW OXIDE	192.0	384.0	1559	YELLOW OXIDE	229.3	458.7
1550	RED OXIDE	322.3	644.7	1550	RED OXIDE	326.5	653.0
1501	LANDAU BLACK	394.7	789.5	1501	LANDAU BLACK	411.7	823.5
1554	TINTING WHITE	413.2	826.3				
5212	CEDAR BROWN			5219	BRANDY		
1559	YELLOW OXIDE	173.3	346.6	1559	YELLOW OXIDE	247.4	494.8
1550	RED OXIDE	314.6	629.3	1550	RED OXIDE	338.9	677.7
1501	LANDAU BLACK	378.4	756.8	1501	LANDAU BLACK	394.1	788.1
1554	TINTING WHITE	414.2	828.4	1554	TINTING WHITE	413.3	826.5
5213	REDDISH AUBURN			5220	GINGER BROWN		
1559	YELLOW OXIDE	168.8	337.6	1551	INDO YELLOW	159.5	319.0
1552	FAST RED	312.5	624.9	1550	RED OXIDE	294.9	589.8
1302	LOW LUSTER CLEAR	394.3	788.7	1302	LOW LUSTER CLEAR	376.6	753.2
1501	LANDAU BLACK	407.3	814.5	1554	TINTING WHITE	400.1	800.3
				1501	LANDAU BLACK	408.6	817.2
5214	ROSEWOOD BROW			5221	NUT BROWN		
1501	LANDAU BLACK	162.5	324.9	1302	LOW LUSTER CLEAR	133.5	267.0
1550	RED OXIDE	320.7	641.4	1551	INDO YELLOW	263.7	527.4
1554	TINTING WHITE	388.9	777.9	1550	RED OXIDE	381.4	762.9
1559	YELLOW OXIDE	414.2	828.4	1554	TINTING WHITE	401.2	802.4
				1501	LANDAU BLACK	407.6	815.1
5215	DARK CHOCOLATE			5222	HONEY BROWN		
1559	YELLOW OXIDE	163.3	326.6	1559	YELLOW OXIDE	222.4	444.8
1302	LOW LUSTER CLEAR	295.4	590.7	1550	RED OXIDE	327.8	655.7
1550	RED OXIDE	356.2	712.3	1302	LOW LUSTER CLEAR	398.1	796.3
1501	LANDAU BLACK	408.4	816.8	1501	LANDAU BLACK	411.2	822.3
5216	MED. DARK CHOCO			5223	BROWN HORSE		
1302	LOW LUSTER CLEAR	138.8	277.6	1559	YELLOW OXIDE	269.2	538.5
1559	YELLOW OXIDE	245.1	490.2	1550	RED OXIDE	399.6	799.1
1550	RED OXIDE	333.6	667.3	1501	LANDAU BLACK	413.3	826.5
1501	LANDAU BLACK	401.6	803.1				
1554	TINTING WHITE	408.3	816.6				
5217	CAMOUFLAGE			5224	PERSIMMON		
1559	YELLOW OXIDE	276.1	552.1	1550	RED OXIDE	204.8	409.6
1501	LANDAU BLACK	365.6	731.1	1559	YELLOW OXIDE	398.4	796.9
1550	RED OXIDE	399.5	799.0	1501	LANDAU BLACK	413.3	826.7
1554	TINTING WHITE	412.1	824.2				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 125

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5225	RED OAK						
1550	RED OXIDE	147.3	294.7	1551	INDO YELLOW	177.2	354.4
1302	LOW LUSTER CLEAR	283.8	567.5	1553	FAST BLUE	347.8	695.6
1559	YELLOW OXIDE	397.5	795.0	1554	TINTING WHITE	407.9	815.9
1501	LANDAU BLACK	409.3	818.5				
5226	VAQUERO						
1550	RED OXIDE	321.7	643.3	1551	INDO YELLOW	169.5	339.0
1559	YELLOW OXIDE	385.4	770.8	1554	TINTING WHITE	302.0	604.0
1501	LANDAU BLACK	407.0	814.0	1553	FAST BLUE	363.7	727.3
1554	TINTING WHITE	414.0	828.0	1501	LANDAU BLACK	414.0	828.0
5227	LIGHT VAQUERO						
1550	RED OXIDE	249.2	498.4	1556	FAST GREEN	198.7	397.5
1551	INDO YELLOW	381.9	763.8	1559	YELLOW OXIDE	358.2	716.5
1554	TINTING WHITE	400.4	800.9	1501	LANDAU BLACK	387.3	774.6
1501	LANDAU BLACK	411.6	823.3	1554	TINTING WHITE	409.4	818.7
5228	GREEN LIGHT						
1302	LOW LUSTER CLEAR	135.3	270.6	1559	YELLOW OXIDE	246.1	492.3
1556	FAST GREEN	268.0	536.0	1554	TINTING WHITE	337.9	675.8
1501	LANDAU BLACK	334.7	669.4	1553	FAST BLUE	389.6	779.2
1559	YELLOW OXIDE	386.0	772.0	1501	LANDAU BLACK	416.3	832.6
1554	TINTING WHITE	405.8	811.7				
5229	CONE GREEN						
1551	INDO YELLOW	223.0	445.9	1559	YELLOW OXIDE	250.6	501.2
1554	TINTING WHITE	312.5	624.9	1501	LANDAU BLACK	355.0	710.0
1501	LANDAU BLACK	388.5	776.9	1556	FAST GREEN	392.0	783.9
1556	FAST GREEN	411.0	821.9	1554	TINTING WHITE	411.3	822.5
5230	FOREST GREEN						
1556	FAST GREEN	152.3	304.6	1559	YELLOW OXIDE	160.5	320.9
1501	LANDAU BLACK	280.0	559.9	1553	FAST BLUE	302.2	604.4
1551	INDO YELLOW	347.1	694.3	1556	FAST GREEN	395.4	790.8
1554	TINTING WHITE	409.0	818.0	1554	TINTING WHITE	407.9	815.9
5231	BAY GREEN						
1556	FAST GREEN	198.2	396.3	1556	FAST GREEN	209.1	418.2
1551	INDO YELLOW	309.0	618.1	1501	LANDAU BLACK	313.9	627.8
1501	LANDAU BLACK	369.0	738.0	1559	YELLOW OXIDE	384.8	769.7
1554	TINTING WHITE	407.0	814.0	1554	TINTING WHITE	407.6	815.3
5232	PINE GREEN						
5233	HUNTER GREEN						
5234	GREEN LAWN						
5235	SEA GREEN						
5236	MOUNTAIN GREEN						
5237	GREEN STONE						
5238	GREEN SAGE						

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 126

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5239	EMERALD GREEN			5246	SILVER GRAY		
1556	FAST GREEN	142.8	285.6	1554	TINTING WHITE	249.5	498.9
1559	YELLOW OXIDE	254.8	509.6	1302	LOW LUSTER CLEAR	390.5	780.9
1302	LOW LUSTER CLEAR	366.8	733.6	1559	YELLOW OXIDE	406.2	812.4
1501	LANDAU BLACK	401.8	803.5	1501	LANDAU BLACK	417.8	835.6
1554	TINTING WHITE	406.1	812.3	1550	RED OXIDE	422.6	845.1
5240	SPROUT GREEN			5247	GRAY OXFORD		
1556	FAST GREEN	226.2	452.4	1554	TINTING WHITE	407.2	814.3
1302	LOW LUSTER CLEAR	292.0	584.1	1501	LANDAU BLACK	426.3	852.5
1551	INDO YELLOW	346.1	692.2	1559	YELLOW OXIDE	434.1	868.1
1501	LANDAU BLACK	378.3	756.6	1550	RED OXIDE	435.4	870.8
1554	TINTING WHITE	405.8	811.7				
5241	BRIGHT GREEN			5248	GRAY FOX		
1553	FAST BLUE	169.7	339.3	1554	TINTING WHITE	366.7	733.4
1551	INDO YELLOW	270.9	541.9	1501	LANDAU BLACK	397.9	795.7
1556	FAST GREEN	351.0	702.1	1559	YELLOW OXIDE	427.7	855.4
1554	TINTING WHITE	407.6	815.1	1550	RED OXIDE	432.9	865.8
5242	BRIAR GREEN			5249	SILVER BASE		
1302	LOW LUSTER CLEAR	152.6	305.1	1554	TINTING WHITE	195.8	391.6
1559	YELLOW OXIDE	281.8	563.5	1302	LOW LUSTER CLEAR	335.9	671.8
1553	FAST BLUE	392.4	784.9	1559	YELLOW OXIDE	376.9	753.7
1501	LANDAU BLACK	399.3	798.6	1550	RED OXIDE	407.9	815.9
1554	TINTING WHITE	405.9	811.9	1553	FAST BLUE	419.6	839.2
5243	EARTH GREEN			5250	GRAY HOUND		
1556	FAST GREEN	218.5	437.0	1554	TINTING WHITE	238.6	477.3
1501	LANDAU BLACK	326.9	653.8	1302	LOW LUSTER CLEAR	379.3	758.7
1554	TINTING WHITE	385.8	771.6	1501	LANDAU BLACK	399.0	798.0
1551	INDO YELLOW	408.7	817.4	1559	YELLOW OXIDE	418.4	836.8
				1550	RED OXIDE	421.8	843.6
5244	White Fox			5251	ASH PEARL		
1554	TINTING WHITE	304.8	609.6	1554	TINTING WHITE	360.1	720.1
1302	LOW LUSTER CLEAR	415.4	830.8	1559	YELLOW OXIDE	405.7	811.3
1501	LANDAU BLACK	420.7	841.4	1501	LANDAU BLACK	430.8	861.7
1551	INDO YELLOW	424.7	849.4	1553	FAST BLUE	432.6	865.3
1550	RED OXIDE	426.6	853.1				
5245	WHITE ROCK			5252	GRAY FERN		
1554	TINTING WHITE	271.1	542.3	1554	TINTING WHITE	243.1	486.2
1302	LOW LUSTER CLEAR	412.2	824.4	1302	LOW LUSTER CLEAR	326.9	653.8
1559	YELLOW OXIDE	417.9	835.8	1501	LANDAU BLACK	361.8	723.5
1501	LANDAU BLACK	423.3	846.6	1559	YELLOW OXIDE	393.3	786.6
1550	RED OXIDE	423.9	847.8	1550	RED OXIDE	423.5	847.0

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 127

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5253	PLATINUM GRAY			5260	GRAY MET.		
1554	TINTING WHITE	329.7	659.3	1508	SILVER	286.2	572.5
1559	YELLOW OXIDE	370.1	740.2	1501	LANDAU BLACK	378.0	756.0
1550	RED OXIDE	401.2	802.4	1552	FAST RED	404.7	809.4
1501	LANDAU BLACK	430.9	861.8	1551	INDO YELLOW	407.6	815.3
5254	SILVER FOX			5261	SILVER FOIL MET.		
1554	TINTING WHITE	310.2	620.4	1508	SILVER	260.7	521.4
1501	LANDAU BLACK	379.7	759.4	1501	LANDAU BLACK	376.8	753.5
1559	YELLOW OXIDE	416.6	833.2	1553	FAST BLUE	398.6	797.2
1550	RED OXIDE	429.0	858.0	1551	INDO YELLOW	407.3	814.5
5255	SLATE GRAY			5262	SILVER FROST		
1554	TINTING WHITE	338.2	676.4	1508	SILVER	323.3	646.6
1501	LANDAU BLACK	394.3	788.7	1554	TINTING WHITE	371.6	743.3
1559	YELLOW OXIDE	415.7	831.4	1501	LANDAU BLACK	409.5	818.9
1550	RED OXIDE	430.8	861.7	1551	INDO YELLOW	410.9	821.8
				1552	FAST RED	411.6	823.3
5256	SILVER BELL			5263	GUN POWDER MET.		
1554	TINTING WHITE	338.0	676.0	1508	SILVER	228.4	456.8
1501	LANDAU BLACK	384.5	768.9	1302	LOW LUSTER CLEAR	370.3	740.6
1559	YELLOW OXIDE	419.8	839.6	1552	FAST RED	386.7	773.3
1550	RED OXIDE	431.0	862.0	1551	INDO YELLOW	396.4	792.9
				1554	TINTING WHITE	403.0	806.0
5257	ASH GRAY			5264	DARK GRAY MET.		
1554	TINTING WHITE	291.1	582.2	1508	SILVER	261.8	523.6
1559	YELLOW OXIDE	373.3	746.5	1501	LANDAU BLACK	375.6	751.3
1501	LANDAU BLACK	416.7	833.3	1553	FAST BLUE	402.0	804.1
1550	RED OXIDE	428.5	856.9	1551	INDO YELLOW	407.2	814.3
5258	SILVER FERN			MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR			
1554	TINTING WHITE	220.1	440.2	5265	MED. GRAY		
1302	LOW LUSTER CLEAR	360.3	720.7	1554	TINTING WHITE	296.1	592.2
1551	INDO YELLOW	383.0	766.1	1501	LANDAU BLACK	374.6	749.2
1501	LANDAU BLACK	405.2	810.4	1559	YELLOW OXIDE	416.2	832.4
1550	RED OXIDE	420.3	840.6	1550	RED OXIDE	428.1	856.1
5259	GRAY MOSS			MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR			
1554	TINTING WHITE	194.1	388.2	5266	GRAY PRINT		
1559	YELLOW OXIDE	344.6	689.1	1554	TINTING WHITE	191.6	383.2
1501	LANDAU BLACK	396.6	793.3	1302	LOW LUSTER CLEAR	288.5	577.0
1550	RED OXIDE	422.8	845.7	1501	LANDAU BLACK	352.2	704.3
				1559	YELLOW OXIDE	406.8	813.6
				1550	RED OXIDE	419.7	839.4

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 128

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

5267	COOL GRAY		
1554	TINTING WHITE	226.5	453.0
1501	LANDAU BLACK	322.6	645.2
1559	YELLOW OXIDE	408.6	817.2
1550	RED OXIDE	423.8	847.6

5274	SILVERADO		
1508	SILVER	377.9	755.8
1552	FAST RED	397.1	794.2
1501	LANDAU BLACK	406.9	813.8
1551	INDO YELLOW	408.5	817.0

5268	BEN GRAY		
1554	TINTING WHITE	198.5	396.9
1501	LANDAU BLACK	275.4	550.8
1302	LOW LUSTER CLEAR	350.8	701.7
1559	YELLOW OXIDE	411.2	822.3
1550	RED OXIDE	420.5	840.9

5275	DIAMOND GRAY M		
1508	SILVER	380.4	760.8
1552	FAST RED	398.3	796.7
1551	INDO YELLOW	405.3	810.5
1501	LANDAU BLACK	408.5	817.0

MUST TOP COAT WITH 1301 SATIN GLOSS CLEAR

5269	MED. OPAL		
1302	LOW LUSTER CLEAR	178.5	357.0
1554	TINTING WHITE	255.2	510.3
1550	RED OXIDE	329.9	659.9
1559	YELLOW OXIDE	378.7	757.3
1553	FAST BLUE	411.5	823.1

5276	DARK SILVER		
1508	SILVER	220.6	441.2
1501	LANDAU BLACK	361.4	722.8
1552	FAST RED	402.0	804.1
1553	FAST BLUE	406.9	813.8

MUST TOP COAT WITH 1301 SATIN GLOSS CLEAR

5270	MED. DARK GRAY		
1554	TINTING WHITE	151.9	303.8
1300	HIGH GLOSS CLEAR	290.6	581.2
1501	LANDAU BLACK	375.3	750.5
1559	YELLOW OXIDE	400.8	801.6
1550	RED OXIDE	416.0	832.0

5277	SANDSTONE SILVE		
1508	SILVER	231.0	462.1
1501	LANDAU BLACK	375.3	750.7
1552	FAST RED	404.3	808.6
1551	INDO YELLOW	407.2	814.3

5271	GLAZE GRAY		
1554	TINTING WHITE	145.1	290.1
1300	HIGH GLOSS CLEAR	283.6	567.2
1501	LANDAU BLACK	380.6	761.1
1559	YELLOW OXIDE	400.8	801.6
1550	RED OXIDE	415.4	830.9

5278	MED SILVER STON		
1508	SILVER	224.5	449.0
1552	FAST RED	313.6	627.2
1501	LANDAU BLACK	386.0	772.0
1553	FAST BLUE	406.7	813.4

5272	DARK GRAY		
1554	TINTING WHITE	171.9	343.7
1501	LANDAU BLACK	294.6	589.2
1559	YELLOW OXIDE	380.6	761.1
1550	RED OXIDE	420.3	840.6

5279	SILVER STONE		
1508	SILVER	263.8	527.6
1552	FAST RED	336.7	673.4
1501	LANDAU BLACK	390.8	781.7
1553	FAST BLUE	407.1	814.2

5273	BRIGHT SILVER		
1508	SILVER	372.1	744.2
1501	LANDAU BLACK	405.2	810.4
1553	FAST BLUE	407.2	814.3
1551	INDO YELLOW	408.4	816.8

5280	SILVER CREEK		
1508	SILVER	221.0	441.9
1501	LANDAU BLACK	366.2	732.5
1553	FAST BLUE	393.5	787.0
1551	INDO YELLOW	406.9	813.8

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 129

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5281	SILVER CITY						
1508	SILVER	238.5	477.1	1554	TINTING WHITE	162.1	324.1
1501	LANDAU BLACK	364.9	729.8	1501	LANDAU BLACK	268.8	537.5
1552	FAST RED	404.7	809.4	1559	YELLOW OXIDE	358.1	716.1
1551	INDO YELLOW	407.2	814.3	1550	RED OXIDE	420.1	840.2
5282	SILVER BAY			5289	DARK GRAPHITE		
1508	SILVER	233.6	467.2	1302	LOW LUSTER CLEAR	135.6	271.1
1501	LANDAU BLACK	346.4	692.7	1501	LANDAU BLACK	231.6	463.2
1552	FAST RED	395.6	791.2	1554	TINTING WHITE	308.5	616.9
1551	INDO YELLOW	407.0	814.0	1559	YELLOW OXIDE	379.6	759.2
				1550	RED OXIDE	411.5	823.1
5283	SILVER QUEEN			5290	DARK BLACK GRA		
1508	SILVER	280.5	561.1	1501	LANDAU BLACK	126.4	252.7
1501	LANDAU BLACK	376.2	752.4	1559	YELLOW OXIDE	220.4	440.8
1551	INDO YELLOW	394.5	789.1	1302	LOW LUSTER CLEAR	308.6	617.1
1552	FAST RED	407.6	815.1	1554	TINTING WHITE	367.4	734.7
				1550	RED OXIDE	411.4	822.9
5284	ROCK GRAY			5291	CHEROKEE GRAY		
1554	TINTING WHITE	182.7	365.4	1501	LANDAU BLACK	140.8	281.6
1302	LOW LUSTER CLEAR	266.7	533.3	1559	YELLOW OXIDE	236.3	472.5
1559	YELLOW OXIDE	341.5	683.1	1302	LOW LUSTER CLEAR	304.5	609.0
1501	LANDAU BLACK	391.6	783.2	1554	TINTING WHITE	364.1	728.3
1550	RED OXIDE	419.8	839.6	1550	RED OXIDE	411.8	823.7
5285	MED. GRAPHITE			5292	BLACK		
1554	TINTING WHITE	134.6	269.2	1501	LANDAU BLACK	310.0	620.0
1302	LOW LUSTER CLEAR	242.9	485.8	1302	LOW LUSTER CLEAR	388.9	777.9
1501	LANDAU BLACK	311.0	622.1	1550	RED OXIDE	397.8	795.5
1559	YELLOW OXIDE	376.0	752.0	1554	TINTING WHITE	405.0	810.0
1550	RED OXIDE	416.2	832.4				
5286	CHIMNEY GRAY			5293	MED. SAGE		
1554	TINTING WHITE	182.3	364.6	1501	LANDAU BLACK	202.6	405.3
1559	YELLOW OXIDE	288.0	576.1	1559	YELLOW OXIDE	383.2	766.5
1501	LANDAU BLACK	381.1	762.3	1556	FAST GREEN	403.7	807.3
1550	RED OXIDE	421.6	843.2	1554	TINTING WHITE	409.0	818.0
5287	LUX GRAY			5294	SMOKEY MOUNTAI		
1302	LOW LUSTER CLEAR	137.8	275.7	1501	LANDAU BLACK	260.7	521.4
1554	TINTING WHITE	242.6	485.3	1554	TINTING WHITE	404.3	808.6
1559	YELLOW OXIDE	312.1	624.2	1551	INDO YELLOW	412.0	824.0
1501	LANDAU BLACK	379.1	758.1	1552	FAST RED	414.0	828.0
1550	RED OXIDE	413.5	827.1	1553	FAST BLUE	415.6	831.3

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 130

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

5295	MED. DARK CHARC		
1501	LANDAU BLACK	199.8	399.6
1554	TINTING WHITE	316.1	632.1
1559	YELLOW OXIDE	408.3	816.6
1553	FAST BLUE	415.3	830.7

5302	MED ADRIATIC ME		
1552	FAST RED	169.5	339.0
1553	FAST BLUE	329.7	659.5
1508	SILVER	369.0	738.0
1501	LANDAU BLACK	403.8	807.7

MUST TOP COAT WITH 1301 SATIN GLOSS CLEAR

5296	BROWN SPICE		
1302	LOW LUSTER CLEAR	106.8	213.6
1559	YELLOW OXIDE	210.1	420.3
1501	LANDAU BLACK	295.5	591.1
1554	TINTING WHITE	355.3	710.6
1550	RED OXIDE	411.7	823.5

5303	BLUE MOUNTAIN		
1508	SILVER	180.2	360.4
1552	FAST RED	297.6	595.3
1553	FAST BLUE	405.7	811.5

5297	BLACK COFFEE		
1501	LANDAU BLACK	243.1	486.2
1302	LOW LUSTER CLEAR	329.9	659.9
1559	YELLOW OXIDE	385.5	771.0
1550	RED OXIDE	396.0	791.9
1554	TINTING WHITE	406.4	812.8

5304	BLUE CHIP MET.		
1508	SILVER	134.6	269.2
1553	FAST BLUE	251.5	502.9
1552	FAST RED	358.2	716.3
1554	TINTING WHITE	409.0	818.0

5298	CHARCOAL BLACK		
1501	LANDAU BLACK	215.1	430.2
1302	LOW LUSTER CLEAR	304.7	609.3
1554	TINTING WHITE	352.5	704.9
1559	YELLOW OXIDE	394.3	788.5
1550	RED OXIDE	408.9	817.8

5305	NILE BLUE MET.		
1508	SILVER	159.7	319.4
1552	FAST RED	266.0	532.0
1553	FAST BLUE	343.9	687.8
1554	TINTING WHITE	410.7	821.4

MUST TOP COAT WITH 1301 SATIN GLOSS CLEAR

5299	DARK TITANIUM		
1501	LANDAU BLACK	207.3	414.6
1559	YELLOW OXIDE	329.0	658.0
1550	RED OXIDE	372.6	745.2
1554	TINTING WHITE	411.3	822.5

5306	CRYSTAL BLUE ME		
1508	SILVER	231.0	462.1
1553	FAST BLUE	356.4	712.9
1552	FAST RED	389.6	779.2
1501	LANDAU BLACK	406.2	812.4

5300	BRIGHT BLUE MET.		
1553	FAST BLUE	258.4	516.8
1508	SILVER	329.9	659.9
1556	FAST GREEN	385.6	771.2
1501	LANDAU BLACK	403.8	807.7

5307	LIGHT BLUE MET.		
1508	SILVER	311.5	623.0
1553	FAST BLUE	395.4	790.8
1552	FAST RED	405.0	810.0
1501	LANDAU BLACK	407.4	814.7

5301	BLUEBIRD MET.		
1553	FAST BLUE	216.8	433.6
1501	LANDAU BLACK	316.4	632.9
1508	SILVER	402.5	805.0
1556	FAST GREEN	404.4	808.8

5308	SABLE BLUE MET.		
1508	SILVER	222.0	444.0
1553	FAST BLUE	308.8	617.5
1501	LANDAU BLACK	368.1	736.3
1552	FAST RED	406.5	813.0

MUST TOP COAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 131

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

5309	MED CRYSTAL BLU		
1508	SILVER	235.7	471.4
1553	FAST BLUE	345.4	690.8
1552	FAST RED	388.1	776.2
1501	LANDAU BLACK	406.4	812.8

5316	DARK BLUE MET.		
1553	FAST BLUE	271.5	543.0
1501	LANDAU BLACK	337.8	675.6
1556	FAST GREEN	373.4	746.7
1508	SILVER	403.5	806.9

MUST TOP COAT WITH 1301 SATIN GLOSS CLEAR

5310	DARK TEAL		
1508	SILVER	202.9	405.8
1553	FAST BLUE	293.6	587.3
1501	LANDAU BLACK	377.1	754.1
1556	FAST GREEN	406.3	812.6

5317	DARK BLUEBIRD M		
1553	FAST BLUE	181.3	362.5
1501	LANDAU BLACK	333.0	666.0
1508	SILVER	404.6	809.2
		0.0	0.0

MUST TOP COAT WITH 1301 SATIN GLOSS CLEAR

MUST TOP WITH 1301 SATIN GLOSS CLEAR

5311	BLUE PRINT MET.		
1553	FAST BLUE	232.5	464.9
1508	SILVER	333.2	666.3
1556	FAST GREEN	376.9	753.7
1552	FAST RED	404.3	808.6

5318	DARK ADRIATIC M		
1552	FAST RED	182.6	365.2
1553	FAST BLUE	316.4	632.9
1508	SILVER	361.8	723.5
1501	LANDAU BLACK	404.0	808.1

MUST TOP COAT WITH 1301 SATIN GLOSS CLEAR

MUST TOP COAT WITH 1301 SATIN GLOSS CLEAR

5312	BLUE RIBBON		
1553	FAST BLUE	215.4	430.7
1508	SILVER	342.7	685.3
1556	FAST GREEN	389.5	779.0
1554	TINTING WHITE	399.4	798.8
1552	FAST RED	405.4	810.7

5319	THOMAS BLUE		
1501	LANDAU BLACK	144.1	288.2
1554	TINTING WHITE	272.0	544.0
1553	FAST BLUE	391.3	782.6
1550	RED OXIDE	414.3	828.6

5313	BLUE DOGWOOD M		
1553	FAST BLUE	222.2	444.4
1508	SILVER	330.0	660.1
1556	FAST GREEN	371.7	743.5
1554	TINTING WHITE	391.0	782.0
1552	FAST RED	405.7	811.5

5320	MED. LIGHT BLUE		
1554	TINTING WHITE	157.0	314.1
1553	FAST BLUE	297.4	594.9
1501	LANDAU BLACK	374.2	748.4
1550	RED OXIDE	416.7	833.3

MUST TOP COAT WITH 1301 SATIN GLOSS CLEAR

5321	BLUE MIST		
1553	FAST BLUE	156.1	312.2
1554	TINTING WHITE	248.1	496.3
1501	LANDAU BLACK	318.1	636.1
1302	LOW LUSTER CLEAR	373.3	746.5
1552	FAST RED	410.1	820.2

5315	BLUE BONNET MET		
1553	FAST BLUE	216.1	432.3
1508	SILVER	338.1	676.2
1556	FAST GREEN	390.3	780.5
1501	LANDAU BLACK	404.6	809.2

5322	ROYAL BLUE		
1553	FAST BLUE	151.3	302.7
1501	LANDAU BLACK	279.5	559.0
1554	TINTING WHITE	395.6	791.2
1559	YELLOW OXIDE	413.0	825.9

MUST TOP COAT WITH 1301 SATIN GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 132

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5323	BLUEBERRY						
1553	FAST BLUE	150.6	301.2	1551	INDO YELLOW	183.3	366.5
1554	TINTING WHITE	244.7	489.4	1554	TINTING WHITE	303.9	607.8
1501	LANDAU BLACK	320.1	640.1	1559	YELLOW OXIDE	414.5	829.0
1302	LOW LUSTER CLEAR	376.5	753.0	1556	FAST GREEN	415.6	831.3
1552	FAST RED	410.4	820.8				
5324	PEACH			5331	PERCH YELLOW		
1554	TINTING WHITE	234.8	469.7	1551	INDO YELLOW	306.9	613.7
1551	INDO YELLOW	377.0	753.9	1559	YELLOW OXIDE	362.1	724.3
1552	FAST RED	421.5	843.0	1554	TINTING WHITE	408.6	817.2
1553	FAST BLUE	421.9	843.8	1556	FAST GREEN	408.7	817.4
5325	PEACH BLOSSOM			5332	GREENWOOD		
1554	TINTING WHITE	231.4	462.8	1556	FAST GREEN	290.3	580.6
1559	YELLOW OXIDE	379.3	758.7	1554	TINTING WHITE	406.5	813.0
1552	FAST RED	424.9	849.9	1553	FAST BLUE	409.9	819.9
				1559	YELLOW OXIDE	412.9	825.7
5326	YOLK YELLOW			5333	OPAL GREEN		
1551	INDO YELLOW	298.7	597.4	1556	FAST GREEN	361.0	722.0
1554	TINTING WHITE	362.8	725.6	1554	TINTING WHITE	392.9	785.8
1559	YELLOW OXIDE	402.6	805.2	1553	FAST BLUE	403.1	806.2
1552	FAST RED	409.7	819.5	1501	LANDAU BLACK	406.3	812.6
5327	PUMPKIN YELLOW			5334	GREENSBORO		
1554	TINTING WHITE	276.5	552.9	1556	FAST GREEN	280.3	560.5
1551	INDO YELLOW	410.5	821.0	1554	TINTING WHITE	392.1	784.1
1552	FAST RED	425.1	850.3	1553	FAST BLUE	412.4	824.8
5328	SUN FLOWER YELL			5335	DARK BIMINI		
1551	INDO YELLOW	213.6	427.1	1553	FAST BLUE	183.6	367.3
1554	TINTING WHITE	314.3	628.5	1556	FAST GREEN	339.2	678.5
1559	YELLOW OXIDE	413.0	825.9	1554	TINTING WHITE	406.6	813.2
1552	FAST RED	413.7	827.5	1501	LANDAU BLACK	408.5	817.0
5329	SUN YELLOW			5336	LIGHT BIMINI		
1554	TINTING WHITE	273.4	546.8	1302	LOW LUSTER CLEAR	137.0	274.0
1551	INDO YELLOW	418.0	836.0	1556	FAST GREEN	248.4	496.9
1550	RED OXIDE	422.9	845.9	1553	FAST BLUE	358.5	717.1
1556	FAST GREEN	425.0	850.1	1554	TINTING WHITE	406.3	812.6

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 133

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5337	AQUANAUT						
1554	TINTING WHITE	211.4	422.8	1551	INDO YELLOW	239.7	479.4
1556	FAST GREEN	344.9	689.7	1556	FAST GREEN	311.5	623.0
1553	FAST BLUE	409.8	819.7	1554	TINTING WHITE	364.8	729.6
1559	YELLOW OXIDE	420.1	840.2	1553	FAST BLUE	407.9	815.9
5338	AQUARIUM			5345	LIGHT MOSS GREE		
1554	TINTING WHITE	246.3	492.7	1551	INDO YELLOW	165.5	331.0
1556	FAST GREEN	367.7	735.5	1554	TINTING WHITE	300.9	601.7
1553	FAST BLUE	420.6	841.1	1556	FAST GREEN	407.1	814.2
1551	INDO YELLOW	422.7	845.3	1501	LANDAU BLACK	414.4	828.8
5339	LIGHT GREEN			5346	OCEAN GREEN		
1554	TINTING WHITE	410.3	820.6	1559	YELLOW OXIDE	175.8	351.5
1556	FAST GREEN	428.7	857.5	1556	FAST GREEN	328.8	657.6
1551	INDO YELLOW	434.1	868.1	1554	TINTING WHITE	403.3	806.6
1501	LANDAU BLACK	435.3	870.6	1501	LANDAU BLACK	413.6	827.3
5340	REGAL BLUE			5347	ORANGEBURG		
1554	TINTING WHITE	365.7	731.3	1551	INDO YELLOW	313.5	627.0
1553	FAST BLUE	414.0	828.0	1554	TINTING WHITE	360.5	721.1
1556	FAST GREEN	429.1	858.2	1552	FAST RED	407.6	815.1
1501	LANDAU BLACK	431.7	863.4				
5341	MED. BLUE MIST			5348	ORANGE BLOSSOM		
1554	TINTING WHITE	336.3	672.6	1551	INDO YELLOW	246.9	493.8
1553	FAST BLUE	416.2	832.4	1552	FAST RED	351.4	702.8
1550	RED OXIDE	428.2	856.3	1554	TINTING WHITE	408.4	816.8
1559	YELLOW OXIDE	429.6	859.2				
5342	MED. EMERALD GR			5349	BRIGHT ORANGE		
1556	FAST GREEN	282.7	565.4	1552	FAST RED	193.1	386.3
1551	INDO YELLOW	361.0	722.0	1551	INDO YELLOW	340.3	680.6
1554	TINTING WHITE	407.6	815.1	1554	TINTING WHITE	409.3	818.5
5343	LIGHT EMERALD			5350	BLUE BEARD MET.		
1556	FAST GREEN	276.9	553.9	1553	FAST BLUE	138.2	276.5
1551	INDO YELLOW	345.8	691.6	1508	SILVER	270.0	540.0
1554	TINTING WHITE	408.9	817.8	1552	FAST RED	388.9	777.9
				1557	MAGENTA	405.0	810.0

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 134

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5351	BLUE JAY MET.						
1557	MAGENTA	150.7	301.3	1551	INDO YELLOW	155.2	310.5
1508	SILVER	297.6	595.3	1508	SILVER	278.9	557.8
1553	FAST BLUE	405.3	810.5	1552	FAST RED	400.1	800.3
				1501	LANDAU BLACK	405.5	810.9
5352	TRUE BLUE			5359	WINTER GREEN		
1302	LOW LUSTER CLEAR	198.9	397.9	1559	YELLOW OXIDE	177.3	354.5
1553	FAST BLUE	364.7	729.4	1556	FAST GREEN	313.7	627.4
1554	TINTING WHITE	397.9	795.7	1554	TINTING WHITE	367.7	735.3
1501	LANDAU BLACK	401.9	803.7	1501	LANDAU BLACK	412.2	824.4
1552	FAST RED	404.5	809.0				
5353	DARK TRUE BLUE			5360	TONNEAU GREEN		
1302	LOW LUSTER CLEAR	147.9	295.8	1551	INDO YELLOW	136.7	273.4
1553	FAST BLUE	265.1	530.3	1554	TINTING WHITE	250.6	501.2
1552	FAST RED	357.6	715.2	1302	LOW LUSTER CLEAR	338.2	676.4
1554	TINTING WHITE	406.2	812.4	1501	LANDAU BLACK	381.3	762.7
				1552	FAST RED	412.2	824.4
5354	MED. TRUE BLUE			5361	GREEN PASTURE		
1553	FAST BLUE	338.6	677.2	1559	YELLOW OXIDE	289.4	578.7
1554	TINTING WHITE	393.2	786.4	1554	TINTING WHITE	397.7	795.3
1556	FAST GREEN	402.9	805.8	1556	FAST GREEN	408.4	816.8
1559	YELLOW OXIDE	407.0	814.0	1501	LANDAU BLACK	418.8	837.5
5355	DARK RUBY			5362	MEADOW GREEN		
1552	FAST RED	383.4	766.8	1551	INDO YELLOW	185.3	370.7
1501	LANDAU BLACK	391.6	783.2	1554	TINTING WHITE	354.5	709.1
1554	TINTING WHITE	398.1	796.1	1501	LANDAU BLACK	408.5	817.0
1553	FAST BLUE	404.5	809.0	1556	FAST GREEN	417.0	833.9
5356	LIGHT TRUE BLUE			5363	LIGHT AQUA		
1552	FAST RED	130.5	261.1	1554	TINTING WHITE	350.8	701.7
1553	FAST BLUE	241.5	483.0	1553	FAST BLUE	387.5	775.0
1302	LOW LUSTER CLEAR	349.8	699.6	1556	FAST GREEN	411.3	822.5
1554	TINTING WHITE	407.2	814.3	1559	YELLOW OXIDE	431.1	862.2
5357	VERY DARK BLUE			5364	Light Parchment		
1501	LANDAU BLACK	272.6	545.1	1554	TINTING WHITE	291.8	583.6
1554	TINTING WHITE	415.7	831.4	1302	LOW LUSTER CLEAR	405.1	810.2
		0.0	0.0	1559	YELLOW OXIDE	430.7	861.3
				1501	LANDAU BLACK	436.6	873.1

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 135

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5365	MED. DK PARCHME	Ford Motor		5372	MED. PORTLAND	Ford Motor	
							UGC
1559	YELLOW OXIDE	144.7	289.4	1554	TINTING WHITE	151.1	302.3
1302	LOW LUSTER CLEAR	241.1	482.2	1501	LANDAU BLACK	287.1	574.2
1501	LANDAU BLACK	302.9	605.7	1302	LOW LUSTER CLEAR	363.5	726.9
1550	RED OXIDE	359.8	719.5	1551	INDO YELLOW	403.8	807.5
1554	TINTING WHITE	412.2	824.4	1550	RED OXIDE	415.6	831.3
5366	DK. TAUPE	Chrysler Motors		5373	LT CACTUS	Ford Motor	
			L8				UFA
1559	YELLOW OXIDE	124.4	248.7	1554	TINTING WHITE	151.3	302.7
1302	LOW LUSTER CLEAR	233.1	466.3	1559	YELLOW OXIDE	259.0	517.9
1501	LANDAU BLACK	312.4	624.7	1302	LOW LUSTER CLEAR	344.4	688.8
1554	TINTING WHITE	367.7	735.3	1501	LANDAU BLACK	412.0	824.0
1550	RED OXIDE	411.4	822.9	1556	FAST GREEN	417.5	835.1
5367	LT.CAMEL	Chrysler Motors		5374	SCHOOL BUS GRAY		
			K4				
1554	TINTING WHITE	223.4	446.9	1554	TINTING WHITE	230.7	461.3
1559	YELLOW OXIDE	328.1	656.3	1501	LANDAU BLACK	346.8	693.7
1302	LOW LUSTER CLEAR	398.0	795.9	1559	YELLOW OXIDE	416.9	833.7
1550	RED OXIDE	413.5	827.1	1550	RED OXIDE	423.6	847.2
1501	LANDAU BLACK	423.3	846.6				
5368	TUXEDO BLUE	General Motors		5375	DP ROYAL BLUE	Chrysler Motors	
			WA400G				BP
1501	LANDAU BLACK	208.3	416.7	1501	LANDAU BLACK	185.9	371.8
1554	TINTING WHITE	285.8	571.5	1553	FAST BLUE	316.5	633.1
1302	LOW LUSTER CLEAR	354.8	709.7	1302	LOW LUSTER CLEAR	372.5	745.0
1553	FAST BLUE	384.6	769.1	1550	RED OXIDE	389.0	778.1
1559	YELLOW OXIDE	410.5	821.0	1554	TINTING WHITE	405.2	810.4
5369	MED DARK SABLE	General Motors		5376	NAVY BLUE	Chrysler Motors	
			64				QL
1559	YELLOW OXIDE	150.6	301.2	1501	LANDAU BLACK	150.5	301.0
1501	LANDAU BLACK	231.2	462.5	1553	FAST BLUE	277.2	554.4
1302	LOW LUSTER CLEAR	300.5	601.0	1302	LOW LUSTER CLEAR	369.6	739.3
1550	RED OXIDE	359.7	719.3	1554	TINTING WHITE	402.1	804.3
1554	TINTING WHITE	412.6	825.2	1551	INDO YELLOW	405.8	811.7
5370	MD MOSS	General Motors		5377	CREAM	Chrysler Motors	
			43				T1
1559	YELLOW OXIDE	204.3	408.7	1554	TINTING WHITE	275.6	551.2
1554	TINTING WHITE	290.6	581.2	1302	LOW LUSTER CLEAR	354.8	709.7
1501	LANDAU BLACK	354.3	708.5	1559	YELLOW OXIDE	415.6	831.3
1302	LOW LUSTER CLEAR	407.9	815.9	1550	RED OXIDE	421.6	843.2
1550	RED OXIDE	415.1	830.1	1501	LANDAU BLACK	426.1	852.2
5371	LT MINK	Ford Motor		5378	MD SLATE	Chrysler Motors	
			BHA				XDH
1554	TINTING WHITE	164.7	329.5	1501	LANDAU BLACK	143.3	286.5
1559	YELLOW OXIDE	273.5	547.0	1554	TINTING WHITE	241.8	483.6
1302	LOW LUSTER CLEAR	353.5	707.0	1559	YELLOW OXIDE	323.1	646.2
1501	LANDAU BLACK	388.1	776.2	1302	LOW LUSTER CLEAR	401.3	802.6
1550	RED OXIDE	419.4	838.9	1550	RED OXIDE	413.4	826.9

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 136

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5379	DK SLATE GRAY	Chrysler Motors	DV	5386	BLACK	Chrysler Motors	AC20157
1501	LANDAU BLACK	218.0	436.1	1501	LANDAU BLACK	243.9	487.7
1559	YELLOW OXIDE	300.4	600.8	1302	LOW LUSTER CLEAR	365.8	731.5
1302	LOW LUSTER CLEAR	359.7	719.3	1551	INDO YELLOW	380.0	760.0
1554	TINTING WHITE	386.3	772.5	1554	TINTING WHITE	392.6	785.3
1550	RED OXIDE	408.6	817.2	1552	FAST RED	404.8	809.6
5380	VY LT OAK	General Motors	640H	5387	EBONY BLACK	Honda	A,D,J,Y,Z
1554	TINTING WHITE	182.8	365.6	1501	LANDAU BLACK	260.6	521.2
1559	YELLOW OXIDE	319.9	639.7	1302	LOW LUSTER CLEAR	362.0	723.9
1302	LOW LUSTER CLEAR	398.6	797.2	1554	TINTING WHITE	384.6	769.1
1552	FAST RED	412.2	824.4	1553	FAST BLUE	395.6	791.2
1501	LANDAU BLACK	420.4	840.8	1551	INDO YELLOW	405.7	811.5
5381	MD OAK	General Motors	641H	5388	DK LAPIS	Honda	C
1559	YELLOW OXIDE	182.8	365.6	1501	LANDAU BLACK	234.3	468.5
1554	TINTING WHITE	281.5	563.0	1302	LOW LUSTER CLEAR	320.0	639.9
1302	LOW LUSTER CLEAR	372.9	745.8	1554	TINTING WHITE	382.8	765.5
1552	FAST RED	401.0	802.0	1553	FAST BLUE	402.4	804.8
1501	LANDAU BLACK	414.9	829.7	1551	INDO YELLOW	408.7	817.4
5382	VY DK PEWTER	General Motors	WA642H	5389	LAPIS	Honda	C
1559	YELLOW OXIDE	130.4	260.9	1554	TINTING WHITE	155.4	310.8
1501	LANDAU BLACK	242.5	485.1	1501	LANDAU BLACK	296.1	592.2
1302	LOW LUSTER CLEAR	324.0	648.1	1302	LOW LUSTER CLEAR	373.3	746.5
1554	TINTING WHITE	369.6	739.3	1559	YELLOW OXIDE	400.0	800.1
1552	FAST RED	410.1	820.2	1550	RED OXIDE	416.7	833.3
5383	BROWN	Toyota		5390	DK IVORY	Honda	F/Q
1559	YELLOW OXIDE	139.5	278.9	1559	YELLOW OXIDE	142.7	285.4
1554	TINTING WHITE	251.8	503.5	1302	LOW LUSTER CLEAR	242.6	485.3
1302	LOW LUSTER CLEAR	337.8	675.6	1554	TINTING WHITE	306.0	612.0
1501	LANDAU BLACK	384.3	768.6	1501	LANDAU BLACK	362.5	725.0
1550	RED OXIDE	415.9	831.8	1550	RED OXIDE	412.8	825.6
5384	LT GRAY	Chrysler Motors	AC20650	5391	IVORY	Honda	F/G
1554	TINTING WHITE	186.9	373.7	1554	TINTING WHITE	145.7	291.5
1302	LOW LUSTER CLEAR	270.8	541.5	1559	YELLOW OXIDE	269.8	539.6
1501	LANDAU BLACK	337.8	675.6	1302	LOW LUSTER CLEAR	365.3	730.6
1559	YELLOW OXIDE	408.3	816.6	1550	RED OXIDE	395.8	791.5
1550	RED OXIDE	419.7	839.4	1501	LANDAU BLACK	418.0	836.0
5385	BEIGE	Chrysler Motors	AC20656	5392	PARCHMENT	Honda	F/T
1554	TINTING WHITE	170.1	340.3	1559	YELLOW OXIDE	163.2	326.4
1559	YELLOW OXIDE	289.6	579.1	1302	LOW LUSTER CLEAR	252.2	504.5
1302	LOW LUSTER CLEAR	372.0	744.0	1554	TINTING WHITE	310.7	621.3
1550	RED OXIDE	399.4	798.8	1501	LANDAU BLACK	367.0	734.0
1501	LANDAU BLACK	419.8	839.6	1550	RED OXIDE	412.7	825.4

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 137

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
5393	TAUPE	Honda		P	5400	DK GRAY	Honda	K/X/Y
1559	YELLOW OXIDE	135.9	271.7		1501	LANDAU BLACK	182.1	364.2
1302	LOW LUSTER CLEAR	238.1	476.1		1302	LOW LUSTER CLEAR	278.7	557.5
1554	TINTING WHITE	308.8	617.5		1559	YELLOW OXIDE	353.2	706.4
1501	LANDAU BLACK	365.8	731.5		1554	TINTING WHITE	395.2	790.4
1550	RED OXIDE	413.1	826.1		1550	RED OXIDE	409.0	818.0
5394	CAMEL	Honda		Y	5402	NEUTRAL	General Motors	521/WA325CU
1559	YELLOW OXIDE	186.5	373.0		1554	TINTING WHITE	145.9	291.8
1554	TINTING WHITE	300.8	601.5		1559	YELLOW OXIDE	281.4	562.8
1302	LOW LUSTER CLEAR	383.6	767.2		1302	LOW LUSTER CLEAR	350.8	701.7
1550	RED OXIDE	410.4	820.8		1550	RED OXIDE	388.4	776.7
1501	LANDAU BLACK	417.1	834.1		1501	LANDAU BLACK	418.6	837.1
5395	BEIGE	Honda		181	5403	NEUTRAL SHALE	General Motors	601/WA172D
1559	YELLOW OXIDE	147.6	295.3		1554	TINTING WHITE	288.9	577.8
1302	LOW LUSTER CLEAR	226.4	452.8		1501	LANDAU BLACK	310.3	620.5
1550	RED OXIDE	291.3	582.5		1550	RED OXIDE	328.3	656.6
1554	TINTING WHITE	355.8	711.6		1559	YELLOW OXIDE	428.8	857.7
1501	LANDAU BLACK	413.4	826.9					
5396	GRAY	Honda		A	5404	DK GOLD	General Motors	UCV 2-1332
1554	TINTING WHITE	146.1	292.2		1559	YELLOW OXIDE	237.4	474.8
1501	LANDAU BLACK	239.3	478.6		1550	RED OXIDE	281.8	563.5
1302	LOW LUSTER CLEAR	318.0	635.9		1554	TINTING WHITE	333.1	666.1
1559	YELLOW OXIDE	392.0	783.9		1501	LANDAU BLACK	345.1	690.3
1550	RED OXIDE	417.1	834.3		1302	LOW LUSTER CLEAR	413.9	827.8
5397	DK QUARTZ	Honda		B-Y	5405	DK MAROON	General Motors	UCV 2-1335
1501	LANDAU BLACK	132.1	264.3		1552	FAST RED	286.0	572.1
1302	LOW LUSTER CLEAR	222.3	444.6		1302	LOW LUSTER CLEAR	393.0	786.0
1554	TINTING WHITE	297.4	594.9		1553	FAST BLUE	400.5	801.0
1559	YELLOW OXIDE	363.6	727.1		1554	TINTING WHITE	403.5	806.9
1550	RED OXIDE	412.2	824.4					
5398	QUARTZ	Honda		B	5406	BLUE	Toyota	807/B
1554	TINTING WHITE	153.3	306.7		1553	FAST BLUE	163.8	327.6
1559	YELLOW OXIDE	238.9	477.9		1501	LANDAU BLACK	298.8	597.6
1302	LOW LUSTER CLEAR	318.8	637.6		1302	LOW LUSTER CLEAR	356.3	712.5
1501	LANDAU BLACK	379.5	759.1		1551	INDO YELLOW	382.1	764.2
1550	RED OXIDE	418.2	836.4		1554	TINTING WHITE	405.1	810.2
5399	LT GRAY	Honda		F	5407	NEUTRAL	General Motors	521/WA323C
1501	LANDAU BLACK	112.4	224.8		1559	YELLOW OXIDE	140.4	280.8
1554	TINTING WHITE	214.1	428.3		1501	LANDAU BLACK	251.3	502.6
1302	LOW LUSTER CLEAR	310.5	620.9		1554	TINTING WHITE	328.8	657.6
1559	YELLOW OXIDE	397.1	794.2		1552	FAST RED	375.6	751.3
1550	RED OXIDE	413.8	827.6		1302	LOW LUSTER CLEAR	413.1	826.1

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 138

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

5408	DK BROWN	Mitsubishi	C46
1559	YELLOW OXIDE	189.5	379.1
1554	TINTING WHITE	294.8	589.6
1501	LANDAU BLACK	378.2	756.4
1550	RED OXIDE	417.3	834.7

5415	PINK	Mitsubishi	P89
1554	TINTING WHITE	329.3	658.5
1559	YELLOW OXIDE	384.3	768.6
1557	MAGENTA	408.6	817.2
1501	LANDAU BLACK	430.4	860.7

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

5409	WHITE	Mitsubishi	WO9
1554	TINTING WHITE	420.7	841.3
1559	YELLOW OXIDE	433.1	866.2
1501	LANDAU BLACK	435.8	871.5
1553	FAST BLUE	436.4	872.9

5416	LT GREEN	Mitsubishi	G 73
1554	TINTING WHITE	287.1	574.2
1501	LANDAU BLACK	317.4	634.8
1559	YELLOW OXIDE	390.5	781.1
1553	FAST BLUE	427.5	855.0

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

5410	CHARCOAL	General Motors	UCV 1370
1501	LANDAU BLACK	297.9	595.8
1559	YELLOW OXIDE	346.2	692.4
1554	TINTING WHITE	373.4	746.7
1553	FAST BLUE	377.5	755.1
1302	LOW LUSTER CLEAR	407.7	815.5

5417	NATURAL BEIGE	General Motors	UCV2-1369
1554	TINTING WHITE	222.6	445.2
1501	LANDAU BLACK	237.1	474.2
1550	RED OXIDE	254.3	508.6
1559	YELLOW OXIDE	351.2	702.4
1302	LOW LUSTER CLEAR	423.0	846.1

5411	SHADOW BLUE	General Motors	821/WA173D
1554	TINTING WHITE	223.1	446.1
1559	YELLOW OXIDE	306.1	612.2
1501	LANDAU BLACK	348.2	696.4
1550	RED OXIDE	368.3	736.6
1302	LOW LUSTER CLEAR	423.1	846.3

5418	EBONY BLACK	General Motors	801/WA174D
1501	LANDAU BLACK	276.5	553.1
1302	LOW LUSTER CLEAR	331.8	663.7
1553	FAST BLUE	373.5	747.1
1551	INDO YELLOW	401.2	802.4
1554	TINTING WHITE	404.4	808.8

5412	DK GRAY	Mitsubishi	H52
1501	LANDAU BLACK	192.9	385.7
1559	YELLOW OXIDE	356.1	712.1
1554	TINTING WHITE	383.0	766.1
1550	RED OXIDE	410.8	821.6

5419	TAN	Toyota	
1554	TINTING WHITE	33.4	66.9
1501	LANDAU BLACK	76.2	152.4
1550	RED OXIDE	139.4	278.7
1559	YELLOW OXIDE	356.8	713.6
1302	LOW LUSTER CLEAR	412.6	825.2

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

5413	YELLOW	Mitsubishi	YB7
1554	TINTING WHITE	230.9	461.9
1551	INDO YELLOW	419.9	839.8
1553	FAST BLUE	420.8	841.5
1550	RED OXIDE	421.6	843.2

5420	BURGUNDY	Toyota	
1554	TINTING WHITE	16.2	32.3
1501	LANDAU BLACK	136.6	273.2
1550	RED OXIDE	278.7	557.5
1552	FAST RED	409.1	818.1

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

5414	DK BROWN	Mitsubishi	C 46
1554	TINTING WHITE	104.5	209.0
1501	LANDAU BLACK	191.0	382.1
1550	RED OXIDE	232.3	464.6
1559	YELLOW OXIDE	417.2	834.5

5421	SMOKE	Toyota	
1302	LOW LUSTER CLEAR	153.9	307.8
1501	LANDAU BLACK	269.3	538.7
1559	YELLOW OXIDE	338.6	677.2
1552	FAST RED	382.6	765.1
1554	TINTING WHITE	406.8	813.6

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

MUST TOP COAT WITH 1302 LOW LUSTER CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 139

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

5422	DK BLUE	Toyota	
1501	LANDAU BLACK	113.6	227.2
1553	FAST BLUE	177.7	355.3
1554	TINTING WHITE	227.4	454.9
1550	RED OXIDE	240.4	480.7
1302	LOW LUSTER CLEAR	407.1	814.2

5429	MD MAROON	General Motors UVC2-1333	
1552	FAST RED	211.4	422.8
1550	RED OXIDE	288.2	576.5
1501	LANDAU BLACK	300.1	600.2
1554	TINTING WHITE	310.0	620.0
1302	LOW LUSTER CLEAR	406.0	812.1

5423	NAVY BLUE	Toyota	
1553	FAST BLUE	181.6	363.3
1501	LANDAU BLACK	256.3	512.6
1302	LOW LUSTER CLEAR	329.6	659.1
1556	FAST GREEN	388.2	776.3
1554	TINTING WHITE	404.3	808.6

5430	DK NATURAL BEIG	General Motors UCV2-1422	
1559	YELLOW OXIDE	135.5	270.9
1554	TINTING WHITE	230.6	461.1
1302	LOW LUSTER CLEAR	311.2	622.4
1501	LANDAU BLACK	381.2	762.5
1550	RED OXIDE	414.8	829.5

5424	GRAY	General Motors CV2-1623 NEW	
1554	TINTING WHITE	50.3	100.5
1501	LANDAU BLACK	226.0	452.0
1550	RED OXIDE	235.5	471.0
1551	INDO YELLOW	256.9	513.8
1302	LOW LUSTER CLEAR	407.6	815.1

5431	LT TAN	Subaru	
1559	YELLOW OXIDE	204.9	409.8
1554	TINTING WHITE	266.4	532.8
1550	RED OXIDE	304.3	608.6
1302	LOW LUSTER CLEAR	397.5	795.0
1501	LANDAU BLACK	413.6	827.3

5425	BEIGE	Mitsubishi S 55	
1554	TINTING WHITE	342.0	684.0
1501	LANDAU BLACK	358.2	716.5
1550	RED OXIDE	370.0	740.1
1559	YELLOW OXIDE	431.8	863.6

5432	LT GRAY	General Motors RPO 181	
1554	TINTING WHITE	199.6	399.2
1302	LOW LUSTER CLEAR	282.5	565.1
1559	YELLOW OXIDE	348.8	697.7
1501	LANDAU BLACK	400.5	801.0
1550	RED OXIDE	420.8	841.5

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

5426	BLUE	Mitsubishi T 85	
1554	TINTING WHITE	317.4	634.8
1501	LANDAU BLACK	402.6	805.2
1559	YELLOW OXIDE	406.8	813.6
1553	FAST BLUE	428.5	857.1

5433	MD NEUTRAL	General Motors CV2 1620 NEW	
1302	LOW LUSTER CLEAR	166.6	333.3
1559	YELLOW OXIDE	278.5	557.1
1554	TINTING WHITE	339.2	678.5
1501	LANDAU BLACK	379.0	757.9
1550	RED OXIDE	410.9	821.8

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

5427	BLACK	Mitsubishi XA4	
1501	LANDAU BLACK	376.7	753.4
1553	FAST BLUE	404.9	809.8

5434	BLACK	General Motors 181	
1501	LANDAU BLACK	225.3	450.7
1554	TINTING WHITE	286.5	573.0
1302	LOW LUSTER CLEAR	342.2	684.4
1551	INDO YELLOW	384.8	769.5
1550	RED OXIDE	409.5	819.1

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

5428	RED	Mitsubishi R 52	
1550	RED OXIDE	252.4	504.8
1552	FAST RED	371.6	743.3
1551	INDO YELLOW	395.4	790.8
1554	TINTING WHITE	411.4	822.7

5435	BEIGE	Mitsubishi S55	
1554	TINTING WHITE	341.4	682.9
1559	YELLOW OXIDE	402.8	805.6
1501	LANDAU BLACK	420.6	841.1
1550	RED OXIDE	431.8	863.6

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 140

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5436	SMOKE	Toyota	A.B	5443	WHITE SATIN	Chrysler Motors	AB61-EW1
1501	LANDAU BLACK	194.1	388.2	1554	TINTING WHITE	295.5	591.1
1302	LOW LUSTER CLEAR	267.1	534.3	1302	LOW LUSTER CLEAR	404.4	808.8
1559	YELLOW OXIDE	361.2	722.4	1559	YELLOW OXIDE	424.7	849.3
1550	RED OXIDE	390.9	781.9	1501	LANDAU BLACK	426.2	852.3
1554	TINTING WHITE	408.1	816.2	1550	RED OXIDE	426.3	852.5
5437	LT GRAY	Toyota	A 195	5444	DK MAIZE	General Motors	4-0451-6
1554	TINTING WHITE	383.6	767.2	1559	YELLOW OXIDE	336.2	672.4
1559	YELLOW OXIDE	410.3	820.6	1554	TINTING WHITE	366.6	733.2
1501	LANDAU BLACK	427.5	855.0	1501	LANDAU BLACK	395.5	791.0
1550	RED OXIDE	434.0	867.9	1550	RED OXIDE	414.3	828.6
5438	BLACK	General Motors	191/WA322C	5445	GREEN INT	American Moto	75R3
1501	LANDAU BLACK	237.8	475.6	1556	FAST GREEN	126.6	253.3
1302	LOW LUSTER CLEAR	290.3	580.6	1554	TINTING WHITE	238.9	477.9
1551	INDO YELLOW	337.5	675.1	1302	LOW LUSTER CLEAR	320.1	640.1
1554	TINTING WHITE	384.3	768.6	1550	RED OXIDE	394.7	789.5
1550	RED OXIDE	408.4	816.8	1551	INDO YELLOW	413.9	827.8
5439	IVORY	Toyota	A 025	5446	BLUE	General Motors	UCV-2144
1554	TINTING WHITE	273.9	547.8	1554	TINTING WHITE	159.6	319.2
1559	YELLOW OXIDE	332.7	665.4	1553	FAST BLUE	269.7	539.4
1300	HIGH GLOSS CLEAR	396.4	792.9	1302	LOW LUSTER CLEAR	352.6	705.3
1550	RED OXIDE	415.7	831.4	1501	LANDAU BLACK	404.4	808.8
1501	LANDAU BLACK	426.4	852.7	1551	INDO YELLOW	415.3	830.7
5440	GRAY	Mitsubishi	H84	5447	MD TAUPE	General Motors	BN 69
1554	TINTING WHITE	363.8	727.5	1559	YELLOW OXIDE	216.9	433.8
1501	LANDAU BLACK	403.1	806.2	1554	TINTING WHITE	349.5	699.0
1559	YELLOW OXIDE	427.0	854.1	1501	LANDAU BLACK	386.7	773.5
1550	RED OXIDE	432.5	865.1	1550	RED OXIDE	419.9	839.8
MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR							
5441	LT GRAY	General Motors	UCV2-1622 NEW	5448	GREEN INT	American Moto	73R2
1554	TINTING WHITE	195.3	390.6	1559	YELLOW OXIDE	149.7	299.4
1559	YELLOW OXIDE	261.0	521.9	1302	LOW LUSTER CLEAR	253.7	507.3
1501	LANDAU BLACK	317.8	635.6	1554	TINTING WHITE	326.1	652.3
1550	RED OXIDE	338.5	677.0	1556	FAST GREEN	375.7	751.5
1302	LOW LUSTER CLEAR	420.6	841.1	1501	LANDAU BLACK	412.3	824.6
5442	DK SADDLE	General Motors	CN 65	5449	MD MAIZE	General Motors	UCV2-163
1559	YELLOW OXIDE	217.6	435.1	1559	YELLOW OXIDE	280.7	561.5
1302	LOW LUSTER CLEAR	335.0	669.9	1554	TINTING WHITE	402.3	804.7
1550	RED OXIDE	388.4	776.7	1501	LANDAU BLACK	415.9	831.8
1501	LANDAU BLACK	404.2	808.5	1550	RED OXIDE	419.6	839.2
1554	TINTING WHITE	409.8	819.7				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 141

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5450	MIDNIGHT BLUE	General Motors	DN 29	5457	DK CHAMOIS	General Motors	WOA/4297
1553	FAST BLUE	152.1	304.2	1559	YELLOW OXIDE	254.7	509.4
1501	LANDAU BLACK	268.5	536.9	1302	LOW LUSTER CLEAR	371.8	743.7
1302	LOW LUSTER CLEAR	349.7	699.4	1550	RED OXIDE	390.5	781.1
1554	TINTING WHITE	383.5	767.0	1501	LANDAU BLACK	401.9	803.9
1559	YELLOW OXIDE	406.2	812.4	1551	INDO YELLOW	409.3	818.5
5451	WHITE	General Motors	N 10	5458	MIDNIGHT NEUTR	General Motors	DN/60
1554	TINTING WHITE	323.0	646.0	1559	YELLOW OXIDE	188.8	377.5
1302	LOW LUSTER CLEAR	408.6	817.2	1501	LANDAU BLACK	313.4	626.8
1559	YELLOW OXIDE	425.7	851.4	1550	RED OXIDE	369.6	739.3
1501	LANDAU BLACK	427.8	855.6	1551	INDO YELLOW	409.9	819.9
1550	RED OXIDE	428.5	856.9				
5452	MD BLUE	General Motors	BN 21	5459	DK SADDLE	General Motors	CN/63
1554	TINTING WHITE	226.3	452.6	1559	YELLOW OXIDE	276.2	552.3
1553	FAST BLUE	310.1	620.2	1550	RED OXIDE	376.1	752.2
1550	RED OXIDE	370.1	740.2	1554	TINTING WHITE	395.1	790.2
1501	LANDAU BLACK	422.7	845.3	1501	LANDAU BLACK	414.1	828.2
5453	DK BLUE	General Motors	CN 21	5460	OXBLOOD	General Motors	CN 73
1554	TINTING WHITE	181.5	362.9	1552	FAST RED	329.7	659.5
1553	FAST BLUE	289.8	579.7	1551	INDO YELLOW	371.9	743.9
1550	RED OXIDE	363.8	727.5	1554	TINTING WHITE	398.7	797.4
1501	LANDAU BLACK	419.3	838.7	1553	FAST BLUE	406.0	812.1
5454	MIDNIGHT BLUE	General Motors	DN 29	5461	MD GRAY	General Motors	BN 11
1553	FAST BLUE	236.5	472.9	1554	TINTING WHITE	270.1	540.2
1550	RED OXIDE	340.8	681.5	1559	YELLOW OXIDE	350.1	700.2
1554	TINTING WHITE	376.6	753.2	1501	LANDAU BLACK	420.6	841.1
1551	INDO YELLOW	408.4	816.8	1550	RED OXIDE	426.7	853.5
5455	DK GREEN	General Motors	CN 44	5462	DK TEAL	General Motors	CN 32
1559	YELLOW OXIDE	193.8	387.6	1556	FAST GREEN	141.9	283.9
1556	FAST GREEN	305.8	611.6	1550	RED OXIDE	274.6	549.1
1501	LANDAU BLACK	375.7	751.5	1553	FAST BLUE	346.1	692.2
1554	TINTING WHITE	411.3	822.5	1554	TINTING WHITE	412.0	824.0
5456	MD CHAMOIS	General Motors	BN/54	5463	MD MAIZE	General Motors	BN 51
1559	YELLOW OXIDE	269.8	539.6	1559	YELLOW OXIDE	275.8	551.6
1554	TINTING WHITE	372.4	744.8	1554	TINTING WHITE	394.6	789.3
1302	LOW LUSTER CLEAR	410.4	820.8	1501	LANDAU BLACK	412.6	825.2
1550	RED OXIDE	414.2	828.4	1551	INDO YELLOW	419.3	838.7
1501	LANDAU BLACK	417.6	835.2				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 142

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5464	DK MAIZE	General Motors	CM/51	5471	DK SADDLE	General Motors	CN 63
1559	YELLOW OXIDE	308.6	617.1	1559	YELLOW OXIDE	205.2	410.4
1554	TINTING WHITE	386.1	772.2	1302	LOW LUSTER CLEAR	323.1	646.2
1501	LANDAU BLACK	409.5	818.9	1550	RED OXIDE	393.9	787.7
1550	RED OXIDE	417.0	833.9	1551	INDO YELLOW	402.4	804.8
				1553	FAST BLUE	409.5	818.9
5465	MD BEIGE	General Motors	BN/61	5472	DK TAUPE	General Motors	CN/68
1559	YELLOW OXIDE	213.4	426.7	1559	YELLOW OXIDE	194.3	388.6
1554	TINTING WHITE	353.6	707.2	1302	LOW LUSTER CLEAR	311.1	622.3
1550	RED OXIDE	398.0	795.9	1501	LANDAU BLACK	353.5	707.0
1501	LANDAU BLACK	420.6	841.1	1550	RED OXIDE	387.7	775.4
				1554	TINTING WHITE	410.2	820.4
5466	DK BEIGE	General Motors	CN/61	5473	BERRY INT	American Moto	75R45
1559	YELLOW OXIDE	245.9	491.7	1550	RED OXIDE	259.3	518.5
1550	RED OXIDE	324.4	648.9	1302	LOW LUSTER CLEAR	334.9	669.8
1554	TINTING WHITE	372.8	745.6	1552	FAST RED	388.2	776.3
1501	LANDAU BLACK	415.2	830.5	1554	TINTING WHITE	401.5	802.9
				1553	FAST BLUE	410.9	821.8
5467	DK TAUPE	General Motors	CN/69	5474	MD AMBER	General Motors	BN/59
1559	YELLOW OXIDE	250.1	500.3	1559	YELLOW OXIDE	357.1	714.2
1554	TINTING WHITE	313.7	627.4	1550	RED OXIDE	398.6	797.2
1501	LANDAU BLACK	370.0	740.1	1554	TINTING WHITE	409.5	818.9
1550	RED OXIDE	415.7	831.4	1501	LANDAU BLACK	413.8	827.6
5468	DK RED	General Motors	WOA/4462	5475	TAN INT	American Moto	75R8
1552	FAST RED	171.6	343.1	1559	YELLOW OXIDE	275.3	550.6
1302	LOW LUSTER CLEAR	287.9	575.9	1550	RED OXIDE	347.7	695.4
1550	RED OXIDE	389.8	779.6	1554	TINTING WHITE	401.9	803.7
1554	TINTING WHITE	404.9	809.8	1501	LANDAU BLACK	416.1	832.2
1501	LANDAU BLACK	406.9	813.8				
5469	DK TEAL	General Motors	WOA-4292	5476	DK LIME	General Motors	CN47
1556	FAST GREEN	107.4	214.9	1559	YELLOW OXIDE	331.6	663.3
1550	RED OXIDE	211.7	423.3	1556	FAST GREEN	379.0	757.9
1302	LOW LUSTER CLEAR	293.6	587.1	1554	TINTING WHITE	408.3	816.6
1553	FAST BLUE	356.4	712.9	1501	LANDAU BLACK	413.6	827.3
1554	TINTING WHITE	409.8	819.7				
5470	DK MAIZE	General Motors	CN/51	5477	MD GREEN	General Motors	BN44
1559	YELLOW OXIDE	240.4	480.9	1559	YELLOW OXIDE	230.6	461.1
1302	LOW LUSTER CLEAR	360.6	721.2	1302	LOW LUSTER CLEAR	311.8	623.6
1554	TINTING WHITE	392.7	785.5	1554	TINTING WHITE	384.2	768.4
1501	LANDAU BLACK	407.7	815.5	1553	FAST BLUE	401.4	802.8
1550	RED OXIDE	411.1	822.1	1501	LANDAU BLACK	414.0	828.0

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 143

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5478	DK SADDLE	General Motors	CN/59	5485	DK BEIGE	Ford Motor	M/4071J
1559	YELLOW OXIDE	338.6	677.2	1559	YELLOW OXIDE	259.7	519.5
1550	RED OXIDE	394.7	789.5	1302	LOW LUSTER CLEAR	329.8	659.7
1501	LANDAU BLACK	405.1	810.2	1554	TINTING WHITE	385.9	771.8
1551	INDO YELLOW	413.0	825.9	1550	RED OXIDE	402.7	805.4
				1501	LANDAU BLACK	413.9	827.8
5479	DK GREEN	General Motors	CN44	5486	DK JADE POLY	Ford Motor	M-4074-J
1559	YELLOW OXIDE	306.7	613.3	1556	FAST GREEN	282.7	565.4
1554	TINTING WHITE	371.1	742.1	1302	LOW LUSTER CLEAR	345.8	691.6
1501	LANDAU BLACK	394.2	788.3	1501	LANDAU BLACK	368.0	736.1
1553	FAST BLUE	415.6	831.3	1508	SILVER	388.5	776.9
				1551	INDO YELLOW	403.8	807.7
5480	LT AQUA POLY	Ford Motor	M-4068-G	5487	MD AVOCADÉ	Ford Motor	M-4034-J
1554	TINTING WHITE	184.2	368.4	1551	INDO YELLOW	177.4	354.7
1508	SILVER	280.9	561.8	1554	TINTING WHITE	285.8	571.5
1556	FAST GREEN	350.0	700.0	1302	LOW LUSTER CLEAR	367.9	735.9
1553	FAST BLUE	391.4	782.8	1501	LANDAU BLACK	406.0	812.1
1552	FAST RED	419.0	838.1	1550	RED OXIDE	411.9	823.8
5481	MD AQUA POLY	Ford Motor	M-4069-J	5488	MD GOLD	Ford Motor	M-4027-J
1553	FAST BLUE	205.4	410.8	1559	YELLOW OXIDE	252.5	505.0
1559	YELLOW OXIDE	335.1	670.1	1302	LOW LUSTER CLEAR	336.7	673.4
1508	SILVER	395.7	791.4	1554	TINTING WHITE	381.4	762.9
1552	FAST RED	406.8	813.6	1501	LANDAU BLACK	399.6	799.1
				1550	RED OXIDE	412.7	825.4
5482	MD GREEN	Ford Motor	M-4065-J	5489	DK BLUE POLY	Ford Motor	M-1847-J
1551	INDO YELLOW	208.1	416.3	1553	FAST BLUE	254.0	508.1
1302	LOW LUSTER CLEAR	282.5	565.1	1501	LANDAU BLACK	313.3	626.6
1501	LANDAU BLACK	339.1	678.1	1302	LOW LUSTER CLEAR	360.3	720.7
1554	TINTING WHITE	375.3	750.7	1508	SILVER	382.4	764.8
1556	FAST GREEN	393.2	786.4	1551	INDO YELLOW	403.1	806.2
5483	MD GREEN POLY	Ford Motor	M-4061-J	5490	MD TAN	Chrysler Motors	AB61/HT7
1551	INDO YELLOW	179.5	358.9	1559	YELLOW OXIDE	233.1	466.3
1501	LANDAU BLACK	255.2	510.3	1302	LOW LUSTER CLEAR	350.3	700.5
1508	SILVER	324.9	649.8	1550	RED OXIDE	388.9	777.9
1302	LOW LUSTER CLEAR	374.8	749.6	1554	TINTING WHITE	400.6	801.2
1556	FAST GREEN	404.7	809.4	1501	LANDAU BLACK	410.3	820.6
5484	LT GOLD	General Motors		5491	DK GREEN	Chrysler Motors	AB5-HF6
1559	YELLOW OXIDE	289.2	578.4	1559	YELLOW OXIDE	297.3	594.5
1554	TINTING WHITE	409.6	819.3	1501	LANDAU BLACK	355.9	711.7
1501	LANDAU BLACK	415.2	830.5	1556	FAST GREEN	410.8	821.6
1550	RED OXIDE	419.7	839.4				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 144

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5492	DK GOLD	Chrysler Motors	AB3/JY7	5499	GREEN INT	American Moto	73R25
1559	YELLOW OXIDE	308.5	616.9	1554	TINTING WHITE	191.3	382.7
1554	TINTING WHITE	360.1	720.3	1551	INDO YELLOW	272.5	544.9
1550	RED OXIDE	399.3	798.6	1501	LANDAU BLACK	348.2	696.4
1501	LANDAU BLACK	415.8	831.6	1556	FAST GREEN	418.9	837.7
5493	DK BLUE	Chrysler Motors	AB5-HB8	5500	MD TAUPE POLY	Ford Motor	M4062-J
1553	FAST BLUE	209.9	419.7	1552	FAST RED	179.7	359.5
1554	TINTING WHITE	304.6	609.1	1508	SILVER	256.8	513.6
1550	RED OXIDE	364.4	728.8	1551	INDO YELLOW	324.1	648.3
1501	LANDAU BLACK	412.0	824.0	1302	LOW LUSTER CLEAR	388.4	776.7
				1553	FAST BLUE	404.4	808.8
5494	BRITE BLUE POLY	Chrysler Motors	AB62-GB5	5501	LT SMOKE GRAY	General Motors	BN/75
1553	FAST BLUE	255.6	511.1	1554	TINTING WHITE	372.4	744.8
1508	SILVER	358.4	716.9	1559	YELLOW OXIDE	408.3	816.6
1552	FAST RED	370.0	740.1	1501	LANDAU BLACK	430.4	860.9
1302	LOW LUSTER CLEAR	403.8	807.7	1550	RED OXIDE	433.3	866.6
5495	DK BLUE	Chrysler Motors	AB3-KB7	5502	DK. BLUE GREEN	Chrysler Motors	CN32
1553	FAST BLUE	171.6	343.1	1556	FAST GREEN	327.3	654.6
1554	TINTING WHITE	279.4	558.8	1501	LANDAU BLACK	371.7	743.5
1559	YELLOW OXIDE	352.9	705.9	1554	TINTING WHITE	393.8	787.6
1501	LANDAU BLACK	413.3	826.7	1550	RED OXIDE	406.1	812.3
MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR							
5496	LT PARCHMENT	Chrysler Motors	AB3-KL2	5503	MD SILVER BLUE	Ford Motor	M-4054-J
1554	TINTING WHITE	311.3	622.6	1554	TINTING WHITE	133.8	267.5
1559	YELLOW OXIDE	412.4	824.8	1559	YELLOW OXIDE	224.1	448.2
1501	LANDAU BLACK	422.7	845.3	1302	LOW LUSTER CLEAR	307.7	615.4
1550	RED OXIDE	430.2	860.3	1501	LANDAU BLACK	384.7	769.3
				1553	FAST BLUE	415.7	831.4
MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR							
5497	LT PARCHMENT SA	Chrysler Motors	AB61/HL2	5504	SILVER POLYLT G	Ford Motor	M-4039-J
1554	TINTING WHITE	212.5	425.0	1508	SILVER	308.2	616.4
1302	LOW LUSTER CLEAR	345.3	690.7	1501	LANDAU BLACK	354.4	708.9
1559	YELLOW OXIDE	413.3	826.5	1553	FAST BLUE	396.1	792.1
1501	LANDAU BLACK	417.7	835.4	1551	INDO YELLOW	407.6	815.3
1550	RED OXIDE	430.2	860.3				
5498	GREEN INT	American Moto	75R7	5505	SILVER POLY MD.G	Ford Motor	M-4051-J
1559	YELLOW OXIDE	246.0	491.9	1501	LANDAU BLACK	167.8	335.5
1554	TINTING WHITE	351.3	702.6	1508	SILVER	306.2	612.4
1553	FAST BLUE	405.6	811.1	1302	LOW LUSTER CLEAR	367.8	735.7
1501	LANDAU BLACK	417.2	834.5	1553	FAST BLUE	386.1	772.2
				1559	INDO YELLOW	396.7	793.4

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 145

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5506	LT BEIGE	Ford Motor	M4028-G	5513	DK RED	Ford Motor	M/4056J
1554	TINTING WHITE	259.4	518.9	1552	FAST RED	315.5	631.0
1559	YELLOW OXIDE	390.4	780.7	1302	LOW LUSTER CLEAR	355.6	711.2
1550	RED OXIDE	416.1	832.2	1559	YELLOW OXIDE	387.7	775.4
1501	LANDAU BLACK	427.3	854.6	1554	TINTING WHITE	397.6	795.2
				1501	LANDAU BLACK	404.8	809.6
5507	MD ORANGE POLY	Ford Motor	M4041-J	5514	MD GINGER	Ford Motor	M3605-G
1551	INDO YELLOW	170.5	341.1	1559	YELLOW OXIDE	312.6	625.3
1552	FAST RED	296.4	592.8	1550	RED OXIDE	395.0	790.0
1554	TINTING WHITE	389.8	779.6	1501	LANDAU BLACK	411.3	822.5
1508	SILVER	410.1	820.2	1554	TINTING WHITE	413.2	826.3
1501	LANDAU BLACK	411.4	822.7				
5508	LT GOLD	Ford Motor	M-4026-G	5515	DK GINGER	Ford Motor	M3606-J
1559	YELLOW OXIDE	292.2	584.4	1559	YELLOW OXIDE	231.9	463.8
1554	TINTING WHITE	394.4	788.9	1550	RED OXIDE	311.6	623.2
1501	LANDAU BLACK	410.4	820.8	1302	LOW LUSTER CLEAR	376.7	753.4
1550	RED OXIDE	418.6	837.1	1501	LANDAU BLACK	407.3	814.5
				1554	TINTING WHITE	411.2	822.3
5509	TOBACCO POLY	Ford Motor	M-4018-J	5516	WHITE	Ford Motor	M3209-G
1552	FAST RED	183.4	366.7	1554	TINTING WHITE	400.9	801.8
1551	INDO YELLOW	283.5	567.0	1559	YELLOW OXIDE	430.6	861.3
1302	LOW LUSTER CLEAR	348.5	696.9	1550	RED OXIDE	434.4	868.9
1501	LANDAU BLACK	384.8	769.7	1553	FAST BLUE	435.3	870.6
1508	SILVER	403.8	807.7				
5510	LT TAN	Ford Motor	M4042-G	5517	MD SADDLE POLY	Ford Motor	M-4050-J
1559	YELLOW OXIDE	218.2	436.4	1552	FAST RED	161.3	322.6
1554	TINTING WHITE	392.0	783.9	1551	INDO YELLOW	287.9	575.7
1550	RED OXIDE	418.7	837.3	1302	LOW LUSTER CLEAR	351.1	702.2
1501	LANDAU BLACK	422.8	845.5	1508	SILVER	380.9	761.7
				1501	LANDAU BLACK	403.9	807.9
5511	DK CRANBERRY	Ford Motor	M-4022-J	5519	DK TERRA RED	General Motors	CN 71
1552	FAST RED	227.1	454.1	1550	RED OXIDE	398.2	796.5
1557	MAGENTA	335.8	671.7	1553	FAST BLUE	406.8	813.6
1302	LOW LUSTER CLEAR	388.6	777.3	1554	TINTING WHITE	414.4	828.8
1554	TINTING WHITE	401.7	803.3				
1553	FAST BLUE	404.6	809.2				
5512	MD BLUE	Ford Motor	M-4036-J	5520	DK SADDLE	General Motors	CN/65
1553	FAST BLUE	119.7	239.4	1559	YELLOW OXIDE	289.7	579.3
1559	YELLOW OXIDE	218.3	436.6	1550	RED OXIDE	366.2	732.5
1552	FAST RED	305.0	609.9	1554	TINTING WHITE	390.6	781.3
1302	LOW LUSTER CLEAR	383.7	767.4	1501	LANDAU BLACK	414.2	828.4
1554	TINTING WHITE	407.0	814.0				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 146

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5521	RUSSET	General Motors	WOA-4543	5528	DK RED	Chrysler Motors	AB5-LE8
1550	RED OXIDE	190.2	380.4	1552	FAST RED	350.0	700.0
1559	YELLOW OXIDE	280.7	561.5	1559	YELLOW OXIDE	386.9	773.9
1302	LOW LUSTER CLEAR	371.3	742.5	1553	FAST BLUE	400.2	800.5
1551	INDO YELLOW	395.3	790.6	1554	TINTING WHITE	405.1	810.2
1501	LANDAU BLACK	410.0	820.0				
5522	MD SADDLE	General Motors	W25A/4432	5529	MD SANDSTONE	General Motors	BN/55
1559	YELLOW OXIDE	255.6	511.3	1559	YELLOW OXIDE	194.1	388.2
1554	TINTING WHITE	364.0	728.1	1554	TINTING WHITE	355.5	711.0
1550	RED OXIDE	407.8	815.7	1302	LOW LUSTER CLEAR	394.8	789.6
1501	LANDAU BLACK	419.0	838.1	1550	RED OXIDE	410.2	820.4
				1501	LANDAU BLACK	420.9	841.7
5523	TAN	General Motors	M4043-J	5530	MANDARIN ORANG	General Motors	BN/66
1559	YELLOW OXIDE	244.3	488.7	1559	YELLOW OXIDE	352.5	704.9
1302	LOW LUSTER CLEAR	309.5	619.0	1557	MAGENTA	380.2	760.4
1554	TINTING WHITE	362.3	724.7	1550	RED OXIDE	406.3	812.6
1550	RED OXIDE	404.7	809.4	1554	TINTING WHITE	413.0	825.9
1501	LANDAU BLACK	414.1	828.2				
5524	MD RED	General Motors	BN/75	5531	LT BLUE	General Motors	4675
1552	FAST RED	246.2	492.5	1554	TINTING WHITE	201.7	403.4
1551	INDO YELLOW	364.8	729.6	1302	LOW LUSTER CLEAR	285.7	571.3
1554	TINTING WHITE	393.2	786.4	1550	RED OXIDE	358.9	717.8
1559	YELLOW OXIDE	406.4	812.8	1553	FAST BLUE	407.3	814.5
				1551	INDO YELLOW	420.4	840.8
5525	OLIVE MET	Toyota	T654	5532	BLUE INT	American Moto	75R6
1501	LANDAU BLACK	153.3	306.7	1554	TINTING WHITE	141.1	282.2
1551	INDO YELLOW	287.6	575.1	1553	FAST BLUE	279.7	559.4
1552	FAST RED	357.0	714.0	1550	RED OXIDE	360.1	720.3
1508	SILVER	404.9	809.8	1559	YELLOW OXIDE	417.4	834.9
MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR							
5526	DK CRANBERRY	General Motors	WOA-4514	5533	SILVER MET	General Motors	AM/15
1552	FAST RED	314.2	628.3	1508	SILVER	403.9	807.9
1302	LOW LUSTER CLEAR	383.4	766.8	1559	YELLOW OXIDE	408.4	816.8
1554	TINTING WHITE	399.1	798.2	1552	FAST RED	408.8	817.6
1553	FAST BLUE	404.6	809.2				
5527	MD RED	General Motors	M-4072-J	5534	DK GRAYSTONE	General Motors	CN/16
1552	FAST RED	280.9	561.8	1559	YELLOW OXIDE	184.7	369.4
1302	LOW LUSTER CLEAR	345.3	690.7	1554	TINTING WHITE	324.5	649.0
1551	INDO YELLOW	387.6	775.2	1501	LANDAU BLACK	400.6	801.2
1554	TINTING WHITE	402.3	804.7	1550	RED OXIDE	419.4	838.9
1501	LANDAU BLACK	404.6	809.2				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 147

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5535	DK ROSEWOOD	General Motors	CN/79	5542	GRAY	Honda	180
1559	YELLOW OXIDE	211.5	422.9	1501	LANDAU BLACK	108.9	217.7
1550	RED OXIDE	332.5	665.0	1302	LOW LUSTER CLEAR	213.3	426.6
1554	TINTING WHITE	385.1	770.3	1559	YELLOW OXIDE	307.2	614.5
1501	LANDAU BLACK	415.7	831.4	1554	TINTING WHITE	386.3	772.5
				1550	RED OXIDE	412.2	824.4
5536	DK SANDSTONE	General Motors	CN/55	5543	DK FERN	Honda	G
1559	YELLOW OXIDE	288.0	576.1	1501	LANDAU BLACK	135.2	270.4
1554	TINTING WHITE	360.9	721.8	1559	YELLOW OXIDE	266.3	532.6
1550	RED OXIDE	396.5	793.1	1302	LOW LUSTER CLEAR	360.9	721.8
1501	LANDAU BLACK	416.9	833.7	1554	TINTING WHITE	406.6	813.2
				1550	RED OXIDE	410.1	820.2
5537	DK BROWN	General Motors	WOA-4646	5544	FERN	Honda	G
1559	YELLOW OXIDE	175.9	351.9	1554	TINTING WHITE	147.2	294.3
1302	LOW LUSTER CLEAR	265.9	531.8	1302	LOW LUSTER CLEAR	254.4	508.8
1550	RED OXIDE	334.9	669.8	1501	LANDAU BLACK	358.6	717.3
1501	LANDAU BLACK	392.7	785.5	1551	INDO YELLOW	403.1	806.2
1551	INDO YELLOW	409.3	818.5	1553	FAST BLUE	414.8	829.5
5538	DK MANDARIN	General Motors	CN/67	5545	KHAKI	Chrysler Motors	ZJ3
1559	YELLOW OXIDE	221.6	443.3	1559	YELLOW OXIDE	127.5	255.0
1550	RED OXIDE	334.8	669.6	1302	LOW LUSTER CLEAR	239.4	478.8
1551	INDO YELLOW	411.7	823.5	1554	TINTING WHITE	338.9	677.7
				1501	LANDAU BLACK	385.5	771.0
				1550	RED OXIDE	414.4	828.8
5539	LT BUCKSKIN	General Motors	AN/64	5546	DK KHAKI	Chrysler Motors	ZJ8
1559	YELLOW OXIDE	231.3	462.7	1559	YELLOW OXIDE	164.8	329.7
1554	TINTING WHITE	379.5	759.1	1501	LANDAU BLACK	247.1	494.2
1550	RED OXIDE	416.6	833.2	1302	LOW LUSTER CLEAR	328.7	657.4
1553	FAST BLUE	421.3	842.7	1554	TINTING WHITE	377.3	754.7
				1550	RED OXIDE	411.9	823.8
5540	DK FIRETHORN	Chrysler Motors	CN/71	5547	MIDNIGHT CREEK	Nissan	PK55
1552	FAST RED	267.2	534.5	1501	LANDAU BLACK	140.1	280.3
1559	YELLOW OXIDE	404.3	808.6	1302	LOW LUSTER CLEAR	280.3	560.5
1553	FAST BLUE	405.8	811.7	1552	FAST RED	344.8	689.5
1554	TINTING WHITE	407.2	814.3	1554	TINTING WHITE	375.6	751.3
				1559	YELLOW OXIDE	406.5	813.0
5541	DK BEIGE	Ford Motor		5548	DK PORTLAND	Ford Motor	UGE
1559	YELLOW OXIDE	225.9	451.8	1501	LANDAU BLACK	117.0	234.1
1554	TINTING WHITE	289.2	578.4	1302	LOW LUSTER CLEAR	233.3	466.6
1550	RED OXIDE	341.5	683.1	1559	YELLOW OXIDE	343.1	686.3
1302	LOW LUSTER CLEAR	379.1	758.3	1554	TINTING WHITE	388.4	776.7
1501	LANDAU BLACK	415.0	829.9	1552	FAST RED	409.3	818.5

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 148

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5549	DK MINK	Ford Motor	BHE	5556	LIGHT CAMEL	Chrysler Motors	K4/RK4
1554	TINTING WHITE	109.1	218.1	1554	TINTING WHITE	268.8	537.5
1559	YELLOW OXIDE	218.1	436.2	1302	LOW LUSTER CLEAR	353.3	706.6
1302	LOW LUSTER CLEAR	300.7	601.4	1551	INDO YELLOW	388.2	776.3
1501	LANDAU BLACK	364.4	728.8	1550	RED OXIDE	413.5	827.1
1550	RED OXIDE	415.6	831.3	1501	LANDAU BLACK	424.7	849.3
5550	DK SABLE	General Motors	4056	5557	NATURAL BEIGE	Chrysler Motors	L2/TL2
1302	LOW LUSTER CLEAR	108.8	217.6	1554	TINTING WHITE	245.7	491.3
1551	INDO YELLOW	197.0	394.1	1302	LOW LUSTER CLEAR	328.7	657.4
1501	LANDAU BLACK	280.9	561.8	1559	YELLOW OXIDE	386.8	773.7
1550	RED OXIDE	347.7	695.4	1501	LANDAU BLACK	406.1	812.3
1554	TINTING WHITE	409.8	819.7	1550	RED OXIDE	424.1	848.2
5551	MD DK OAK II	General Motors	112E	5558	LIGHT SANDSTONE	Chrysler Motors	TA/XTA
1559	YELLOW OXIDE	255.8	511.7	1554	TINTING WHITE	187.2	374.3
1302	LOW LUSTER CLEAR	305.2	610.5	1559	YELLOW OXIDE	284.7	569.4
1554	TINTING WHITE	354.6	709.3	1302	LOW LUSTER CLEAR	375.1	750.1
1550	RED OXIDE	396.2	792.5	1550	RED OXIDE	400.7	801.4
1501	LANDAU BLACK	414.2	828.4	1501	LANDAU BLACK	420.6	841.1
5552	GRAPHITE	General Motors	142E	5559	DARK SANDSTONE	Chrysler Motors	TM/XTM
1501	LANDAU BLACK	278.8	557.7	1554	TINTING WHITE	112.9	225.7
1302	LOW LUSTER CLEAR	360.1	720.3	1550	RED OXIDE	199.6	399.2
1554	TINTING WHITE	406.6	813.2	1551	INDO YELLOW	281.8	563.5
1553	FAST BLUE	407.7	815.5	1302	LOW LUSTER CLEAR	359.3	718.6
				1501	LANDAU BLACK	414.5	829.0
5553	LT TAUPE	Chrysler Motors	L2	5560	DARK CIRRUS GRA	Chrysler Motors	C8/RC8
1554	TINTING WHITE	229.5	459.0	1501	LANDAU BLACK	148.4	296.8
1302	LOW LUSTER CLEAR	314.5	629.1	1554	TINTING WHITE	256.0	512.1
1559	YELLOW OXIDE	381.2	762.5	1302	LOW LUSTER CLEAR	357.9	715.7
1501	LANDAU BLACK	402.6	805.2	1550	RED OXIDE	401.6	803.1
1550	RED OXIDE	423.0	846.1	1559	YELLOW OXIDE	413.3	826.5
5554	NEW ECRU	Toyota	008B	5561	LIGHT CIRRUS GRA	Chrysler Motors	C1/RC1
1554	TINTING WHITE	284.7	569.4	1554	TINTING WHITE	241.6	483.2
1302	LOW LUSTER CLEAR	384.0	768.0	1302	LOW LUSTER CLEAR	334.8	669.6
1559	YELLOW OXIDE	419.7	839.4	1501	LANDAU BLACK	368.6	737.2
1501	LANDAU BLACK	423.7	847.4	1559	YELLOW OXIDE	398.6	797.2
1550	RED OXIDE	425.9	851.8	1550	RED OXIDE	423.1	846.3
5555	BLACK	Toyota	136B	5562	LIGHT SILVER FER	Chrysler Motors	JJ/RJJ
1501	LANDAU BLACK	284.2	568.5	1508	SILVER	189.3	378.7
1302	LOW LUSTER CLEAR	361.8	723.5	1302	LOW LUSTER CLEAR	292.6	585.2
1551	INDO YELLOW	390.5	781.1	1554	TINTING WHITE	344.3	688.6
1554	TINTING WHITE	403.1	806.2	1551	INDO YELLOW	378.7	757.3
1553	FAST BLUE	405.2	810.4	1501	LANDAU BLACK	402.8	805.6
				1550	RED OXIDE	409.6	819.3

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 149

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5563	DARK SILVERFERN	Chrysler Motors	JL/RJL	5570	MIDNIGHT DENIM	Ford Motor	KY6A
1508	SILVER	130.8	261.6	1501	LANDAU BLACK	214.2	428.5
1501	LANDAU BLACK	261.3	522.7	1302	LOW LUSTER CLEAR	297.9	595.8
1302	LOW LUSTER CLEAR	359.3	718.6	1553	FAST BLUE	336.4	672.8
1551	INDO YELLOW	389.6	779.2	1554	TINTING WHITE	373.3	746.5
1554	TINTING WHITE	399.4	798.8	1552	FAST RED	406.7	813.4
1553	FAST BLUE	405.9	811.9				
5564	DARK CRIMSON RE	Chrysler Motors	M8/LM8	5571	NEUTRAL	General Motors	521/WA178E
1552	FAST RED	176.4	352.8	1559	YELLOW OXIDE	154.4	308.8
1302	LOW LUSTER CLEAR	255.6	511.1	1302	LOW LUSTER CLEAR	251.8	503.7
1501	LANDAU BLACK	327.9	655.9	1554	TINTING WHITE	318.2	636.3
1550	RED OXIDE	394.6	789.3	1501	LANDAU BLACK	370.1	740.2
1554	TINTING WHITE	406.1	812.3	1550	RED OXIDE	413.1	826.1
5565	DARK CLARET ME	Chrysler Motors	GM4	5572	NEUTRAL	General Motors	601/WA640F
1552	FAST RED	319.7	639.4	1559	YELLOW OXIDE	146.4	292.8
1300	HIGH GLOSS CLEAR	381.4	762.9	1302	LOW LUSTER CLEAR	230.0	460.0
1551	INDO YELLOW	392.3	784.5	1552	FAST RED	296.9	593.8
1508	SILVER	399.7	799.3	1501	LANDAU BLACK	362.0	724.1
1553	FAST BLUE	403.7	807.3	1554	TINTING WHITE	410.5	821.0
5566	PLATINUM SILVER	Chrysler Motors	HD1	5573	CHARCOAL	General Motors	801/WA637F
1508	SILVER	246.0	491.9	1501	LANDAU BLACK	196.0	392.0
3520	PLATINUM PEARL	332.0	664.1	1559	YELLOW OXIDE	282.4	564.9
1300	HIGH GLOSS CLEAR	405.8	811.7	1302	LOW LUSTER CLEAR	357.6	715.2
1552	FAST RED	424.3	848.5	1554	TINTING WHITE	387.1	774.3
1551	INDO YELLOW	429.7	859.4	1550	RED OXIDE	408.7	817.4
MUST BE TOP COATED WITH 1300							
5567	DARK SILVER MET	Chrysler Motors	KS7	5574	MEDIUM OAK	Toyota	435B
1501	LANDAU BLACK	199.0	398.1	1559	YELLOW OXIDE	132.0	263.9
1508	SILVER	361.6	723.1	1554	TINTING WHITE	263.2	526.5
1553	FAST BLUE	406.2	812.4	1302	LOW LUSTER CLEAR	352.5	704.9
				1550	RED OXIDE	390.6	781.3
				1501	LANDAU BLACK	417.4	834.9
5568	MED DARK PUMICE	Ford Motor	DC4A	5578	Bahama Beige		SUC
1559	YELLOW OXIDE	132.1	264.3	1559	YELLOW OXIDE	259.9	519.9
1302	LOW LUSTER CLEAR	227.6	455.2	1554	TINTING WHITE	345.0	690.0
1554	TINTING WHITE	307.5	615.0	1550	RED OXIDE	394.6	789.2
1550	RED OXIDE	361.0	722.0	1501	LANDAU BLACK	427.7	855.4
1501	LANDAU BLACK	413.8	827.6				
5569	DARK PARCHMENT	Ford Motor	BJ/5A	5585	Med. Dk. Pewter II	General Motors	WA184D
1559	YELLOW OXIDE	143.7	287.5	1559	YELLOW OXIDE	127.8	255.7
1302	LOW LUSTER CLEAR	229.3	458.7	1554	TINTING WHITE	228.1	456.3
1501	LANDAU BLACK	301.5	603.1	1501	LANDAU BLACK	308.4	616.8
1554	TINTING WHITE	363.1	726.2	1302	LOW LUSTER CLEAR	393.4	786.8
1550	RED OXIDE	412.7	825.4	1550	RED OXIDE	425.0	850.0

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 150

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5597	Grayish Blue	Toyota	814B	5606	SAGE	Toyota	611B
1553	FAST BLUE	244.9	489.8	1554	TINTING WHITE	191.1	382.3
1302	LOW LUSTER CLEAR	343.1	686.2	1559	YELLOW OXIDE	283.4	566.8
1501	LANDAU BLACK	382.9	765.9	1302	LOW LUSTER CLEAR	365.8	731.5
1551	INDO YELLOW	408.6	817.1	1501	LANDAU BLACK	407.0	814.0
1554	TINTING WHITE	412.6	825.3	1550	RED OXIDE	420.5	840.9
5600	KHAKI	Toyota	601B	5607	SLATE GREEN	Toyota	612B
1559	YELLOW OXIDE	158.4	316.7	1559	YELLOW OXIDE	117.5	235.0
1501	LANDAU BLACK	279.5	559.0	1501	LANDAU BLACK	218.7	437.4
1302	LOW LUSTER CLEAR	372.7	745.4	1554	TINTING WHITE	312.6	625.1
1554	TINTING WHITE	391.6	783.2	1302	LOW LUSTER CLEAR	384.8	769.5
1550	RED OXIDE	409.0	818.0	1553	FAST BLUE	413.4	826.9
5601	LT KHAKI	Toyota	602B	5608	LT GREEN	Toyota	613B
1559	YELLOW OXIDE	136.7	273.4	1554	TINTING WHITE	233.2	466.5
1554	TINTING WHITE	254.5	509.0	1302	LOW LUSTER CLEAR	314.2	628.3
1302	LOW LUSTER CLEAR	348.7	697.5	1559	YELLOW OXIDE	375.7	751.5
1501	LANDAU BLACK	394.9	789.8	1501	LANDAU BLACK	421.0	842.1
1550	RED OXIDE	416.0	832.0	1556	FAST GREEN	422.7	845.3
5602	DARK SPRUCE	Toyota	603B	5609	MIST GREEN	Toyota	615B
1501	LANDAU BLACK	160.5	320.9	1554	TINTING WHITE	185.9	371.8
1554	TINTING WHITE	254.8	509.6	1559	YELLOW OXIDE	279.9	559.7
1302	LOW LUSTER CLEAR	337.5	675.1	1302	LOW LUSTER CLEAR	363.8	727.5
1551	INDO YELLOW	393.8	787.6	1501	LANDAU BLACK	414.4	828.8
1553	FAST BLUE	411.0	821.9	1553	FAST BLUE	419.8	839.6
5603	SPRUCE	Toyota	604B	5610	DARK AGATE	Toyota	607B
1554	TINTING WHITE	210.4	420.9	1501	LANDAU BLACK	159.8	319.6
1302	LOW LUSTER CLEAR	301.3	602.7	1559	YELLOW OXIDE	273.5	547.0
1559	YELLOW OXIDE	362.6	725.2	1302	LOW LUSTER CLEAR	365.7	731.3
1501	LANDAU BLACK	415.9	831.8	1554	TINTING WHITE	404.0	808.1
1553	FAST BLUE	420.9	841.7	1553	FAST BLUE	409.3	818.5
5604	JADE	Toyota	606B	5611	AGATE	Toyota	608B
1501	LANDAU BLACK	156.8	313.7	1559	YELLOW OXIDE	131.1	262.2
1559	YELLOW OXIDE	287.0	574.0	1302	LOW LUSTER CLEAR	229.4	458.9
1302	LOW LUSTER CLEAR	370.4	740.8	1550	RED OXIDE	303.1	606.3
1553	FAST BLUE	400.8	801.6	1554	TINTING WHITE	368.7	737.4
1554	TINTING WHITE	407.2	814.3	1553	FAST BLUE	413.0	825.9
5605	DARK SAGE	Toyota	610B	5612	TAN	Toyota	424B
1559	YELLOW OXIDE	131.3	262.6	1559	YELLOW OXIDE	211.9	423.7
1501	LANDAU BLACK	239.8	479.6	1302	LOW LUSTER CLEAR	314.6	629.3
1554	TINTING WHITE	313.1	626.2	1554	TINTING WHITE	379.7	759.4
1302	LOW LUSTER CLEAR	384.5	768.9	1550	RED OXIDE	408.5	817.0
1550	RED OXIDE	413.0	825.9	1501	LANDAU BLACK	413.6	827.3

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 151

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
5613	LIGHT GREIGE	Toyota		425B	5621	MED DARK NEUTR	Toyota	439B
1554	TINTING WHITE	169.6	339.2		1559	YELLOW OXIDE	148.9	297.7
1559	YELLOW OXIDE	288.5	577.0		1554	TINTING WHITE	243.4	486.8
1302	LOW LUSTER CLEAR	375.9	751.8		1302	LOW LUSTER CLEAR	329.9	659.9
1550	RED OXIDE	401.1	802.2		1501	LANDAU BLACK	375.0	749.9
1501	LANDAU BLACK	419.6	839.2		1550	RED OXIDE	415.2	830.3
5614	JADE	Toyota		606B	5622	MED NEUTRAL	Toyota	440B
1554	TINTING WHITE	180.7	361.4		1554	TINTING WHITE	141.6	283.1
1559	YELLOW OXIDE	321.3	642.6		1559	YELLOW OXIDE	263.8	527.6
1302	LOW LUSTER CLEAR	405.0	810.0		1302	LOW LUSTER CLEAR	351.2	702.4
1550	RED OXIDE	418.7	837.3		1550	RED OXIDE	387.9	775.8
1501	LANDAU BLACK	420.7	841.3		1501	LANDAU BLACK	417.9	835.8
5615	CHOCOLATE BRO	Toyota		429B	5623	ORCHID BROWN	Toyota	441B
1551	INDO YELLOW	112.5	225.0		1501	LANDAU BLACK	120.1	240.2
1302	LOW LUSTER CLEAR	211.8	423.5		1559	YELLOW OXIDE	230.2	460.4
1501	LANDAU BLACK	304.4	608.8		1302	LOW LUSTER CLEAR	313.6	627.2
1550	RED OXIDE	390.5	780.9		1550	RED OXIDE	363.0	726.0
1554	TINTING WHITE	407.0	814.0		1554	TINTING WHITE	411.1	822.1
5616	ANTELOPE	Toyota		432B	5624	SANDLEWOOD	Toyota	446B
1559	YELLOW OXIDE	125.0	250.0		1559	YELLOW OXIDE	143.4	286.7
1501	LANDAU BLACK	243.8	487.5		1302	LOW LUSTER CLEAR	230.8	461.5
1302	LOW LUSTER CLEAR	322.0	643.9		1554	TINTING WHITE	307.7	615.4
1550	RED OXIDE	372.6	745.2		1501	LANDAU BLACK	361.2	722.4
1554	TINTING WHITE	410.7	821.4		1552	FAST RED	412.6	825.2
5617	LIGHT ANTELOPE	Toyota		433B	5625	FAWN	Toyota	447B
1554	TINTING WHITE	178.0	356.1		1554	TINTING WHITE	163.2	326.4
1302	LOW LUSTER CLEAR	276.1	552.1		1559	YELLOW OXIDE	273.8	547.6
1559	YELLOW OXIDE	351.2	702.4		1302	LOW LUSTER CLEAR	361.6	723.1
1501	LANDAU BLACK	386.8	773.7		1501	LANDAU BLACK	390.7	781.5
1550	RED OXIDE	419.5	839.0		1552	FAST RED	418.5	837.0
5618	OAK	Toyota		434B	5626	DARK GREIGE	Toyota	422B
1559	YELLOW OXIDE	155.2	310.5		1501	LANDAU BLACK	141.6	283.3
1302	LOW LUSTER CLEAR	240.5	481.1		1302	LOW LUSTER CLEAR	231.1	462.3
1501	LANDAU BLACK	298.5	597.0		1554	TINTING WHITE	296.8	593.6
1550	RED OXIDE	356.4	712.9		1551	INDO YELLOW	359.4	718.8
1554	TINTING WHITE	412.7	825.4		1550	RED OXIDE	410.1	820.2
5620	LIGHT OAK	Toyota		436B	5627	QUARTZ	Toyota	431B
1554	TINTING WHITE	200.9	401.9		1554	TINTING WHITE	178.0	356.1
1559	YELLOW OXIDE	292.9	585.8		1302	LOW LUSTER CLEAR	262.8	525.5
1302	LOW LUSTER CLEAR	378.0	756.0		1559	YELLOW OXIDE	337.3	674.7
1550	RED OXIDE	405.6	811.1		1550	RED OXIDE	381.4	762.9
1501	LANDAU BLACK	421.5	843.0		1501	LANDAU BLACK	419.7	839.4

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 152

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5628	ORCHID	Toyota	442B	5635	IVORY	Toyota	007B
1554	TINTING WHITE	139.5	278.9	1554	TINTING WHITE	204.9	409.8
1559	YELLOW OXIDE	230.9	461.9	1559	YELLOW OXIDE	306.0	612.0
1302	LOW LUSTER CLEAR	316.0	631.9	1302	LOW LUSTER CLEAR	391.4	782.8
1501	LANDAU BLACK	372.8	745.6	1550	RED OXIDE	407.8	815.7
1550	RED OXIDE	417.3	834.7	1501	LANDAU BLACK	421.8	843.6
5629	DARK ROSE	Toyota	417B	5636	SABLE	Toyota	407B
1501	LANDAU BLACK	135.9	271.9	1559	YELLOW OXIDE	134.6	269.2
1559	YELLOW OXIDE	241.0	482.0	1501	LANDAU BLACK	236.9	473.9
1302	LOW LUSTER CLEAR	323.1	646.2	1302	LOW LUSTER CLEAR	316.8	633.7
1550	RED OXIDE	405.2	810.4	1550	RED OXIDE	392.0	783.9
1554	TINTING WHITE	408.5	817.0	1554		409.8	819.7
5630	ROSE	Toyota	418B	5637	LIGHT SABLE	Toyota	408B
1559	YELLOW OXIDE	134.0	267.9	1559	YELLOW OXIDE	153.5	307.0
1550	RED OXIDE	224.4	448.8	1302	LOW LUSTER CLEAR	238.8	477.7
1302	LOW LUSTER CLEAR	308.1	616.2	1554	TINTING WHITE	308.8	617.5
1501	LANDAU BLACK	366.7	733.4	1550	RED OXIDE	370.1	740.2
1554	TINTING WHITE	412.2	824.4	1501	LANDAU BLACK	413.8	827.6
5631	LIGHT ROSE	Toyota	427B	5638	BROWN	Toyota	411B
1554	TINTING WHITE	155.2	310.5	1559	YELLOW OXIDE	207.8	415.5
1559	YELLOW OXIDE	251.4	502.7	1302	LOW LUSTER CLEAR	291.6	583.1
1302	LOW LUSTER CLEAR	337.3	674.5	1550	RED OXIDE	362.0	723.9
1550	RED OXIDE	386.0	772.0	1501	LANDAU BLACK	396.8	793.6
1501	LANDAU BLACK	418.6	837.1	1551	INDO YELLOW	409.9	819.9
5632	IVORY	Toyota	002B	5639	LIGHT BROWN	Toyota	412B
1554	TINTING WHITE	198.3	396.5	1559	YELLOW OXIDE	222.0	444.0
1559	YELLOW OXIDE	312.1	624.2	1302	LOW LUSTER CLEAR	308.8	617.5
1302	LOW LUSTER CLEAR	397.6	795.2	1554	TINTING WHITE	357.3	714.6
1550	RED OXIDE	414.7	829.4	1550	RED OXIDE	402.4	804.8
1501	LANDAU BLACK	421.5	843.0	1501	LANDAU BLACK	413.2	826.3
5633	IVORY	Toyota	003B	5640	MED GREIGE	Toyota	416B
1554	TINTING WHITE	191.5	383.0	1559	YELLOW OXIDE	170.3	340.7
1559	YELLOW OXIDE	298.3	596.6	1302	LOW LUSTER CLEAR	257.2	514.3
1302	LOW LUSTER CLEAR	383.0	766.1	1501	LANDAU BLACK	312.3	624.5
1550	RED OXIDE	404.7	809.4	1550	RED OXIDE	362.3	724.7
1501	LANDAU BLACK	420.9	841.9	1554	TINTING WHITE	412.4	824.8
5634	IVORY	Toyota	006B	5641	DK NEUTRAL BONE	Toyota	445B
1554	TINTING WHITE	257.4	514.7	1559	YELLOW OXIDE	161.5	323.0
1302	LOW LUSTER CLEAR	341.0	681.9	1302	LOW LUSTER CLEAR	247.4	494.8
1559	YELLOW OXIDE	404.4	808.8	1554	TINTING WHITE	313.7	627.4
1550	RED OXIDE	416.5	833.0	1501	LANDAU BLACK	368.7	737.4
1501	LANDAU BLACK	424.8	849.7	1550	RED OXIDE	413.3	826.7

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 153

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5642	MED NEUTRAL BO	Toyota	443B	5649	BLACK	Toyota	201B
1554	TINTING WHITE	173.9	347.9	1552	FAST RED	121.0	242.1
1559	YELLOW OXIDE	284.6	569.2	1556	FAST GREEN	234.7	469.5
1302	LOW LUSTER CLEAR	371.1	742.1	1302	LOW LUSTER CLEAR	326.4	652.8
1550	RED OXIDE	397.4	794.8	1501	LANDAU BLACK	403.5	806.9
1501	LANDAU BLACK	419.9	839.8				
5643	GRAY	Toyota	103B	5650	SHADOW BLUE	Toyota	101B
1501	LANDAU BLACK	131.9	263.7	1501	LANDAU BLACK	246.3	492.7
1554	TINTING WHITE	219.0	438.0	1559	YELLOW OXIDE	329.1	658.2
1559	YELLOW OXIDE	303.5	607.1	1554	TINTING WHITE	392.5	785.1
1302	LOW LUSTER CLEAR	383.3	766.7	1550	RED OXIDE	411.8	823.7
1550	RED OXIDE	413.0	825.9				
5644	DK STONE	Toyota	133B	5651	LIGHT GRAY	Toyota	102B
1501	LANDAU BLACK	116.2	232.4	1554	TINTING WHITE	203.0	406.0
1554	TINTING WHITE	209.6	419.1	1302	LOW LUSTER CLEAR	286.2	572.5
1559	YELLOW OXIDE	296.5	593.0	1559	YELLOW OXIDE	352.8	705.7
1302	LOW LUSTER CLEAR	377.0	753.9	1501	LANDAU BLACK	399.5	799.0
1550	RED OXIDE	413.6	827.3	1550	RED OXIDE	421.1	842.3
5645	STONE	Toyota	134B	5652	SLATE GRAY	Toyota	104B
1554	TINTING WHITE	172.4	344.9	1554	TINTING WHITE	147.7	295.5
1302	LOW LUSTER CLEAR	256.9	513.8	1501	LANDAU BLACK	233.5	467.0
1559	YELLOW OXIDE	333.0	666.0	1302	LOW LUSTER CLEAR	312.9	625.9
1501	LANDAU BLACK	391.1	782.2	1559	YELLOW OXIDE	386.0	772.0
1550	RED OXIDE	419.1	838.3	1550	RED OXIDE	417.4	834.9
5646	NEW MAROON	Toyota	304B	5653	LIGHT GRAY	Toyota	105B
1552	FAST RED	238.0	476.0	1554	TINTING WHITE	260.9	521.7
1550	RED OXIDE	329.9	659.9	1302	LOW LUSTER CLEAR	344.5	688.9
1501	LANDAU BLACK	398.7	797.4	1559	YELLOW OXIDE	393.6	787.2
1554	TINTING WHITE	407.1	814.2	1501	LANDAU BLACK	415.6	831.3
				1550	RED OXIDE	424.7	849.3
5647	MAUVE	Toyota	306B	5654	BLuish GRAY	Toyota	109B
1552	FAST RED	199.1	398.2	1501	LANDAU BLACK	146.7	293.4
1302	LOW LUSTER CLEAR	300.7	601.4	1554	TINTING WHITE	252.1	504.3
1501	LANDAU BLACK	365.7	731.3	1302	LOW LUSTER CLEAR	328.5	657.0
1550	RED OXIDE	400.2	800.5	1559	YELLOW OXIDE	392.7	785.5
1554	TINTING WHITE	404.7	809.4	1550	RED OXIDE	413.8	827.6
5648	RED	Toyota	303B	5655	LIGHT GRAY	Toyota	110B
1552	FAST RED	272.4	544.7	1554	TINTING WHITE	233.0	466.1
1302	LOW LUSTER CLEAR	359.7	719.3	1302	LOW LUSTER CLEAR	316.9	633.8
1551	INDO YELLOW	387.2	774.4	1559	YELLOW OXIDE	370.6	741.2
1554	TINTING WHITE	398.7	797.4	1501	LANDAU BLACK	407.5	814.9
1501	LANDAU BLACK	404.3	808.6	1550	RED OXIDE	422.8	845.7

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 154

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
5656	BLUE GRAY	Toyota		111B	5663	MED MOONMIST	Toyota	126B
1554	TINTING WHITE	132.0	263.9		1554	TINTING WHITE	135.6	271.1
1501	LANDAU BLACK	263.9	527.8		1501	LANDAU BLACK	258.8	517.6
1302	LOW LUSTER CLEAR	345.3	690.7		1302	LOW LUSTER CLEAR	346.8	693.5
1559	YELLOW OXIDE	415.3	830.7		1550	RED OXIDE	403.1	806.2
					1553	FAST BLUE	415.4	830.9
5657	DARK BLUE GRAY	Toyota		112B	5664	MOONMIST	Toyota	128B
1501	LANDAU BLACK	215.1	430.2		1554	TINTING WHITE	271.9	543.8
1302	LOW LUSTER CLEAR	297.8	595.7		1302	LOW LUSTER CLEAR	354.7	709.5
1554	TINTING WHITE	351.4	702.8		1501	LANDAU BLACK	410.1	820.2
1559	YELLOW OXIDE	404.3	808.6		1550	RED OXIDE	424.4	848.7
1553	FAST BLUE	409.3	818.5		1553	FAST BLUE	424.7	849.3
5658	MEDIUM GRAY	Toyota		113B	5665	MED CHARCOAL	Toyota	128B
1554	TINTING WHITE	155.0	310.1		1554	TINTING WHITE	197.5	395.0
1501	LANDAU BLACK	245.5	491.0		1302	LOW LUSTER CLEAR	281.8	563.5
1302	LOW LUSTER CLEAR	326.2	652.5		1559	YELLOW OXIDE	355.9	711.7
1559	YELLOW OXIDE	394.1	788.1		1501	LANDAU BLACK	392.3	784.5
1550	RED OXIDE	417.6	835.2		1550	RED OXIDE	420.9	841.9
5659	LIGHT BLUISH GRA	Toyota		119B	5666	LIGHT GRAY	Toyota	130B
1554	TINTING WHITE	303.2	606.5		1554	TINTING WHITE	290.0	580.1
1501	LANDAU BLACK	376.0	752.0		1302	LOW LUSTER CLEAR	375.2	750.3
1559	YELLOW OXIDE	402.3	804.7		1501	LANDAU BLACK	404.8	809.6
1550	RED OXIDE	428.6	857.3		1559	YELLOW OXIDE	418.4	836.8
					1550	RED OXIDE	426.2	852.3
5660	DARK BLUE GRAY	Toyota		120B	5667	AMETHYST	Toyota	
1501	LANDAU BLACK	227.2	454.5		1554	TINTING WHITE	107.4	214.7
1302	LOW LUSTER CLEAR	324.6	649.2		1501	LANDAU BLACK	212.5	425.0
1554	TINTING WHITE	377.2	754.5		1302	LOW LUSTER CLEAR	290.3	580.6
1559	YELLOW OXIDE	398.1	796.1		1559	YELLOW OXIDE	355.7	711.4
1550	RED OXIDE	408.8	817.6		1550	RED OXIDE	414.8	829.5
5661	BLUE GRAY	Toyota		121B	5668	LIGHT AMETHYST	Toyota	132B
1554	TINTING WHITE	154.3	308.6		1554	TINTING WHITE	203.4	406.8
1501	LANDAU BLACK	253.9	507.9		1302	LOW LUSTER CLEAR	285.4	570.8
1302	LOW LUSTER CLEAR	334.3	668.6		1559	YELLOW OXIDE	344.5	688.9
1559	YELLOW OXIDE	392.4	784.9		1501	LANDAU BLACK	386.2	772.4
1550	RED OXIDE	417.5	835.1		1550	RED OXIDE	421.3	842.7
5662	DARK CHARCOAL	Toyota		124B	5669	SADDLE GRAY	Toyota	135B
1554	TINTING WHITE	133.3	266.6		1501	LANDAU BLACK	163.5	327.0
1501	LANDAU BLACK	242.2	484.3		1559	YELLOW OXIDE	254.0	508.1
1302	LOW LUSTER CLEAR	321.5	643.0		1302	LOW LUSTER CLEAR	341.6	683.2
1550	RED OXIDE	373.8	747.7		1554	TINTING WHITE	376.7	753.4
1551	INDO YELLOW	415.1	830.1		1550	RED OXIDE	409.4	818.7

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 155

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5670	MED RED	Ford Motor	WA4899/2-520	5677	LT SATIN SILVER M	Ford Motor	2PBE
1552	FAST RED	269.9	539.8	1554	TINTING WHITE	199.6	399.2
1551	INDO YELLOW	370.7	741.4	1508	SILVER	328.8	657.6
1554	TINTING WHITE	388.2	776.3	1559	YELLOW OXIDE	351.1	702.2
1302	LOW LUSTER CLEAR	403.0	806.0	1501	LANDAU BLACK	362.0	723.9
1550	RED OXIDE	405.2	810.4	1550	RED OXIDE	367.1	734.2
5671	MED BERYL MET.	Ford Motor	MKCC/2-251	5678	MD SATIN NICKEL	Ford Motor	2P3C
1556	FAST GREEN	147.8	295.6	1508	SILVER	279.4	558.8
1553	FAST BLUE	293.4	586.7	1300	HIGH GLOSS CLEAR	359.7	719.3
1508	SILVER	357.7	715.4	1552	FAST RED	379.0	757.9
1501	LANDAU BLACK	404.3	808.6	1551	INDO YELLOW	397.3	794.6
				1501	LANDAU BLACK	406.9	813.8
5672	MED BERYL MET.	Ford Motor	MKMC/2-685	5679	LT SATIN SILVER M	Ford Motor	2PBC
1508	SILVER	201.6	403.2	1554	TINTING WHITE	183.3	366.5
1553	FAST BLUE	359.0	718.0	1508	SILVER	362.9	725.8
1551	INDO YELLOW	405.7	811.5	1559	YELLOW OXIDE	395.2	790.4
				1501	LANDAU BLACK	412.5	825.0
				1550	RED OXIDE	421.1	842.3
5673	INSPIRATION YELL	Ford Motor	1FDA	5680	COLORADO RED	Ford Motor	NDDA
1554	TINTING WHITE	286.4	572.9	1552	FAST RED	216.0	432.1
1302	LOW LUSTER CLEAR	368.7	737.4	1551	INDO YELLOW	340.2	680.4
1551	INDO YELLOW	424.7	849.3	1302	LOW LUSTER CLEAR	376.2	752.4
1556	FAST GREEN	425.3	850.6	1554	TINTING WHITE	403.2	806.4
				1550	RED OXIDE	405.8	811.7
5674	DK MIDNIGHT BLK	Ford Motor	ZU8C	5681	SEAMIST GREEN	Chrysler Motors	ZP7
1501	LANDAU BLACK	225.9	451.8	1302	LOW LUSTER CLEAR	108.8	217.6
1300	HIGH GLOSS CLEAR	306.6	613.1	1551	INDO YELLOW	205.7	411.4
1552	FAST RED	354.6	709.3	1501	LANDAU BLACK	301.8	603.6
1508	SILVER	394.3	788.7	1553	FAST BLUE	383.5	767.0
1551	INDO YELLOW	404.7	809.4	1554	TINTING WHITE	404.7	809.4
5675	T-BIRD BLUE	Ford Motor	KSEA	5681	Seamist Green	Chrysler Motors	ZP7
1554	TINTING WHITE	243.9	487.7	1553	FAST BLUE	156.8	313.7
1302	LOW LUSTER CLEAR	322.5	645.1	1302	LOW LUSTER CLEAR	275.1	550.2
1559	YELLOW OXIDE	376.7	753.4	1551	INDO YELLOW	343.8	687.6
1553	FAST BLUE	406.2	812.4	1501	LANDAU BLACK	400.9	801.7
1556	FAST GREEN	423.2	846.5	1554	TINTING WHITE	413.6	827.2
5676	CHARCOAL GRAY	Ford Motor	ZJDC	5682	DK GRAY	Toyota	137B
1508	SILVER	262.3	524.6	1501	LANDAU BLACK	129.4	258.8
1300	HIGH GLOSS CLEAR	331.4	662.7	1559	YELLOW OXIDE	224.2	448.4
1501	LANDAU BLACK	384.8	769.7	1554	TINTING WHITE	305.9	611.8
1552	FAST RED	395.9	791.7	1302	LOW LUSTER CLEAR	387.6	775.2
1551	INDO YELLOW	406.9	813.8	1550	RED OXIDE	412.8	825.6

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 156

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
5683	LT WARM GREY	General Motors		11	5690	BLACK INK	Ford Motor	2B5A
1559	YELLOW OXIDE	146.4	292.8		1501	LANDAU BLACK	197.3	394.6
1302	LOW LUSTER CLEAR	227.9	455.8		1553	FAST BLUE	270.1	540.2
1554	TINTING WHITE	299.6	599.3		1552	FAST RED	335.6	671.3
1501	LANDAU BLACK	360.2	720.5		1302	LOW LUSTER CLEAR	398.5	797.1
1552	FAST RED	412.4	824.8		1554	TINTING WHITE	404.2	808.5
5684	THOMAS GREY				5691	LOW GLOSS BLAC	Chrysler Motors	X4
1554	TINTING WHITE	234.7	469.3		1501	LANDAU BLACK	248.3	496.7
1501	LANDAU BLACK	329.7	659.3		1302	LOW LUSTER CLEAR	403.6	807.1
1559	YELLOW OXIDE	417.4	834.9					
1550	RED OXIDE	424.2	848.4					
MUST BE TOP COATED WITH 1300								
5685	THOMAS GREEN				5692	DK GRAY	General Motors	176E
1501	LANDAU BLACK	166.3	332.7		1554	TINTING WHITE	109.2	218.3
1551	INDO YELLOW	279.0	558.0		1559	YELLOW OXIDE	204.5	409.1
1554	TINTING WHITE	368.2	736.4		1501	LANDAU BLACK	293.2	586.3
1553	FAST BLUE	411.1	822.1		1302	LOW LUSTER CLEAR	373.4	746.9
					1550	RED OXIDE	415.2	830.3
MUST BE TOP COATED WITH 1300								
5686	BLUE BIRD GREEN				5693	MED GRAY	General Motors	604F
1551	INDO YELLOW	172.8	345.6		1559	YELLOW OXIDE	106.8	213.6
1553	FAST BLUE	272.5	544.9		1554	TINTING WHITE	212.2	424.5
1554	TINTING WHITE	351.0	702.1		1501	LANDAU BLACK	310.3	620.5
1501	LANDAU BLACK	409.6	819.3		1302	LOW LUSTER CLEAR	391.4	782.8
					1550	RED OXIDE	414.8	829.5
MUST BE TOP COATED WITH 1300								
5687	BLUE BIRD BROWN				5694	MED FLINT	Ford Motor	2NCA
1559	YELLOW OXIDE	189.3	378.7		1554	TINTING WHITE	158.3	316.5
1300	HIGH GLOSS CLEAR	269.8	539.6		1559	YELLOW OXIDE	248.0	495.9
1550	RED OXIDE	340.0	680.0		1302	LOW LUSTER CLEAR	329.2	658.4
1501	LANDAU BLACK	379.6	759.2		1501	LANDAU BLACK	398.7	797.4
1554	TINTING WHITE	412.1	824.2		1550	RED OXIDE	418.2	836.4
5688	SILVER MET	Chrysler Motors		BA2	5695	DK FLINT	Ford Motor	2N5A
1508	SILVER	405.7	811.3		1559	YELLOW OXIDE	126.0	251.9
1554	TINTING WHITE	407.7	815.5		1501	LANDAU BLACK	251.2	502.4
1551	INDO YELLOW	409.0	818.0		1302	LOW LUSTER CLEAR	333.4	666.7
					1554	TINTING WHITE	379.9	759.8
					1550	RED OXIDE	410.9	821.8
5689	BLACK	Ford Motor		JA6A	5696	MED TITANIUM ME	Ford Motor	M6432G
1501	LANDAU BLACK	213.3	426.6		1508	SILVER	225.5	451.1
1302	LOW LUSTER CLEAR	299.1	598.1		1501	LANDAU BLACK	341.4	682.9
1551	INDO YELLOW	348.6	697.1		1552	FAST RED	383.0	766.1
1554	TINTING WHITE	393.5	787.0		1551	INDO YELLOW	407.0	814.0
1550	RED OXIDE	407.7	815.5					

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 157

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5697	MED DARK MAPLE	General Motors	77CN	5709	SALSA RED	General Motors	WA723H
1552	FAST RED	183.7	367.5	1552	FAST RED	184.5	369.0
1559	YELLOW OXIDE	363.5	726.9	1551	INDO YELLOW	289.3	578.6
1554	TINTING WHITE	398.6	797.2	1302	LOW LUSTER CLEAR	368.6	737.2
1553	FAST BLUE	404.4	808.8	1554	TINTING WHITE	401.0	802.0
1501	LANDAU BLACK	410.6	821.2	1550	RED OXIDE	406.0	812.1
5698	LIGHT KHAKI	Chrysler Motors	JK1	5710	RIDGE CHARCOAL	General Motors	634H
1554	TINTING WHITE	162.6	325.3	1559	YELLOW OXIDE	154.4	308.8
1302	LOW LUSTER CLEAR	269.0	538.1	1501	LANDAU BLACK	269.9	539.8
1559	YELLOW OXIDE	374.2	748.4	1302	LOW LUSTER CLEAR	339.8	679.6
1501	LANDAU BLACK	400.3	800.7	1554	TINTING WHITE	379.2	758.5
1550	RED OXIDE	418.6	837.1	1550	RED OXIDE	411.2	822.3
5699	VERY DK KHAKI	Chrysler Motors	ZJV	5711	RIDGE CHARCOAL	General Motors	635H
1559	YELLOW OXIDE	136.7	273.4	1551	INDO YELLOW	122.2	244.3
1501	LANDAU BLACK	258.0	516.0	1501	LANDAU BLACK	208.5	417.1
1302	LOW LUSTER CLEAR	349.0	698.1	1302	LOW LUSTER CLEAR	284.3	568.7
1554	TINTING WHITE	385.4	770.8	1554	TINTING WHITE	347.4	694.8
1550	RED OXIDE	410.1	820.2	1550	RED OXIDE	410.1	820.2
5705	NATURAL TAN	Chrysler Motors	BU4	5712	HANGLIDE RED	General Motors	141 WCK
1559	YELLOW OXIDE	180.5	361.0	1552	FAST RED	233.1	466.3
1550	RED OXIDE	300.6	601.2	1551	INDO YELLOW	356.2	712.3
1302	LOW LUSTER CLEAR	392.8	785.7	1302	LOW LUSTER CLEAR	403.3	806.6
1501	LANDAU BLACK	406.0	812.1	1501	LANDAU BLACK	403.7	807.3
1554	TINTING WHITE	410.7	821.4				
5706	LIGHT SILVERFER	Chrysler Motors	RJJ	5713	TWILIGHT BLUE		UCV2-1277
1554	TINTING WHITE	217.1	434.2	1501	LANDAU BLACK	164.8	329.7
1559	YELLOW OXIDE	309.7	619.4	1554	TINTING WHITE	303.2	606.5
1302	LOW LUSTER CLEAR	390.1	780.1	1559	YELLOW OXIDE	377.2	754.5
1501	LANDAU BLACK	415.8	831.6	1553	FAST BLUE	416.5	833.0
1550	RED OXIDE	422.3	844.6				
5707	DK SILVERFERN	Chrysler Motors	JL/RJL	5714	MINERAL GRAY	Ford Motor	ZSTAFUG
1559	YELLOW OXIDE	142.4	284.8	1501	LANDAU BLACK	101.6	203.1
1554	TINTING WHITE	233.1	466.3	1554	TINTING WHITE	194.2	388.4
1501	LANDAU BLACK	322.5	645.1	1302	LOW LUSTER CLEAR	273.2	546.4
1302	LOW LUSTER CLEAR	405.4	810.7	1551	INDO YELLOW	350.7	701.5
1550	RED OXIDE	414.0	828.0	1552	FAST RED	410.8	821.6
5708	CEDAR GREEN	General Motors	WA722H	5715	ASH 2	Ford Motor	3NCA
1559	YELLOW OXIDE	219.1	438.1	1554	TINTING WHITE	219.1	438.1
1302	LOW LUSTER CLEAR	299.5	599.1	1559	YELLOW OXIDE	302.5	605.0
1552	FAST RED	356.2	712.3	1302	LOW LUSTER CLEAR	384.3	768.6
1553	FAST BLUE	395.4	790.8	1501	LANDAU BLACK	419.6	839.2
1554	TINTING WHITE	409.3	818.5	1550	RED OXIDE	422.3	844.6

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 158

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5716	ASH 6	Ford Motor	3N5A	5722	Dk Stone	Ford Motor	1T5A
1559	YELLOW OXIDE	127.2	254.4	1559	YELLOW OXIDE	142.6	285.1
1554	TINTING WHITE	222.9	445.7	1302	LOW LUSTER CLEAR	246.8	493.5
1302	LOW LUSTER CLEAR	314.0	628.0	1501	LANDAU BLACK	329.3	658.7
1501	LANDAU BLACK	395.7	791.4	1554	TINTING WHITE	385.0	770.1
1550	RED OXIDE	414.2	828.4	1550	RED OXIDE	421.8	843.7
5717	ESPRESSO	Ford Motor	2T5A	5723	ADOBE RED	Chrysler Motors	AEJ
1552	FAST RED	100.0	200.1	1550	RED OXIDE	260.2	520.4
1302	LOW LUSTER CLEAR	216.3	432.6	1302	LOW LUSTER CLEAR	342.3	684.6
1501	LANDAU BLACK	307.0	614.1	1553	FAST BLUE	375.1	750.1
1551	INDO YELLOW	373.4	746.7	1552	FAST RED	400.3	800.7
1554	TINTING WHITE	405.9	811.9	1554	TINTING WHITE	410.5	821.0
5718	PEBBLE	Ford Motor	3TCA	5724	NEW SLATE	Chrysler Motors	BD5
1559	YELLOW OXIDE	147.2	294.3	1554	TINTING WHITE	125.2	250.4
1554	TINTING WHITE	283.9	567.7	1559	YELLOW OXIDE	225.2	450.5
1302	LOW LUSTER CLEAR	365.6	731.1	1302	LOW LUSTER CLEAR	308.0	616.0
1550	RED OXIDE	392.7	785.5	1501	LANDAU BLACK	398.1	796.1
1501	LANDAU BLACK	417.9	835.8	1550	RED OXIDE	415.9	831.8
5719	LIGHT FLINT	Ford Motor	2NBA	5725	LT GREYSTONE	Chrysler Motors	BD1
1554	TINTING WHITE	259.3	518.5	1554	TINTING WHITE	215.4	430.7
1302	LOW LUSTER CLEAR	340.8	681.5	1302	LOW LUSTER CLEAR	330.2	660.4
1559	YELLOW OXIDE	389.3	778.6	1559	YELLOW OXIDE	389.4	778.8
1501	LANDAU BLACK	416.0	832.0	1501	LANDAU BLACK	409.8	819.7
1550	RED OXIDE	424.5	848.9	1550	RED OXIDE	421.3	842.7
5720	MED DARK FLINT	Ford Motor	2N4A	5728	ANTHRACITE	Ford Motor	ZKEA
1559	YELLOW OXIDE	111.1	222.1	1501	LANDAU BLACK	257.8	515.7
1501	LANDAU BLACK	218.7	437.4	1559	YELLOW OXIDE	354.3	708.5
1554	TINTING WHITE	312.9	625.9	1554	TINTING WHITE	386.7	773.5
1302	LOW LUSTER CLEAR	390.7	781.5	1550	RED OXIDE	409.9	819.9
1550	RED OXIDE	414.1	828.2				
5721	MED LT STONE	Ford Motor	1T3A	5729	WARM STEEL MET	Ford Motor	3Q4C
1554	TINTING WHITE	199.8	399.5	1508	SILVER	191.0	381.9
1559	YELLOW OXIDE	289.9	579.9	1501	LANDAU BLACK	316.7	633.5
1302	LOW LUSTER CLEAR	374.2	748.4	1559	YELLOW OXIDE	398.3	796.7
1501	LANDAU BLACK	398.9	797.7	1550	RED OXIDE	408.7	817.4
1550	RED OXIDE	421.3	842.6				
5722	DARK STONE	Ford Motor	1T5A	5730	MED GRAY MET	Ford Motor	ZRDC
1559	YELLOW OXIDE	149.1	298.1	1508	SILVER	229.6	459.2
1501	LANDAU BLACK	231.3	462.7	1501	LANDAU BLACK	375.4	750.9
1302	LOW LUSTER CLEAR	309.8	619.6	1559	YELLOW OXIDE	397.3	794.6
1554	TINTING WHITE	371.0	742.0	1550	RED OXIDE	407.8	815.7
1550	RED OXIDE	412.7	825.4				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 159

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

5731	SATIN CREAM	Ford Motor	3LCC
1508	SILVER	357.7	715.4
1551	INDO YELLOW	385.8	771.6
1552	FAST RED	408.2	816.4

5738	MED STONE	Ford Motor	1TCA
1554	TINTING WHITE	207.7	415.3
1559	YELLOW OXIDE	341.7	683.4
1501	LANDAU BLACK	386.4	772.7
1550	RED OXIDE	423.8	847.6

MUST BE TOPCOATED WITH 1300 HIGH GLOSS CLEAR

5732	SATIN ALUMINUM	Ford Motor	UA2C
1508	SILVER	405.2	810.4
1559	YELLOW OXIDE	408.0	816.1
1552	FAST RED	408.9	817.8

5739	KING RANCH TAN	Ford Motor	1U5A
1559	YELLOW OXIDE	179.3	358.5
1550	RED OXIDE	283.5	567.0
1302	LOW LUSTER CLEAR	364.4	728.8
1501	LANDAU BLACK	406.5	813.0
1554	TINTING WHITE	409.7	819.5
1551	INDO YELLOW	410.4	820.8

5733	DARK GREY MET	Ford Motor	YJEC
1501	LANDAU BLACK	180.3	360.6
1559	YELLOW OXIDE	275.4	550.8
1302	LOW LUSTER CLEAR	353.7	707.4
1550	RED OXIDE	382.0	764.0
1508	SILVER	407.0	814.0

5740	PEBBLE 5	Ford Motor	3T5A
1559	YELLOW OXIDE	189.6	379.2
1302	LOW LUSTER CLEAR	266.1	532.2
1554	TINTING WHITE	327.3	654.6
1501	LANDAU BLACK	374.7	749.4
1550	RED OXIDE	413.5	827.1

5734	DARK GRAY MET	Ford Motor	3MEC
1501	LANDAU BLACK	181.5	362.9
1508	SILVER	280.7	561.5
1302	LOW LUSTER CLEAR	342.8	685.5
1559	YELLOW OXIDE	380.0	760.0
1550	RED OXIDE	406.7	813.4

5741	PEBBLE 4	Ford Motor	3T4A
1559	YELLOW OXIDE	170.5	341.1
1554	TINTING WHITE	259.0	517.9
1302	LOW LUSTER CLEAR	337.9	675.8
1501	LANDAU BLACK	377.1	754.1
1550	RED OXIDE	415.0	829.9

5735	DARK TITANIUM M	Ford Motor	8P6C
1501	LANDAU BLACK	151.0	301.9
1508	SILVER	234.7	469.3
1302	LOW LUSTER CLEAR	309.7	619.4
1559	YELLOW OXIDE	370.0	740.1
1550	RED OXIDE	407.3	814.5

5742	DARK PARCHMENT	Ford Motor	BJ5A
1559	YELLOW OXIDE	160.1	320.2
1302	LOW LUSTER CLEAR	237.2	474.4
1501	LANDAU BLACK	310.3	620.5
1554	TINTING WHITE	366.4	732.8
1550	RED OXIDE	412.7	825.4

5736	RED	Ford Motor	EBDA
1552	FAST RED	231.9	463.8
1551	INDO YELLOW	359.9	719.7
1554	TINTING WHITE	406.3	812.6
1550	RED OXIDE	407.6	815.1

5743	SADDLE 6	Ford Motor	3U6A
1559	YELLOW OXIDE	169.8	339.5
1550	RED OXIDE	311.3	622.6
1302	LOW LUSTER CLEAR	387.1	774.3
1554	TINTING WHITE	403.2	806.4
1556	FAST GREEN	412.0	824.0

MUST BE TOPCOATED WITH 1300 HIGH GLOSS CLEAR

5737	MED SILVER MET	Ford Motor	EBDA
1508	SILVER	406.4	812.8
1559	YELLOW OXIDE	407.3	814.5
1552	FAST RED	408.1	816.2
1551	INDO YELLOW	409.0	818.0

5744	SLATE MET	General Motors	WA759J
1501	LANDAU BLACK	187.2	374.3
1508	SILVER	279.7	559.4
1559	YELLOW OXIDE	368.8	737.6
1550	RED OXIDE	408.5	817.0

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 160

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5745	MED MOCHA	Ford Motor	M6643C	5752	PEBBLE 1	Ford Motor	3T3A
1559	YELLOW OXIDE	177.8	355.7	1554	TINTING WHITE	194.6	389.1
1550	RED OXIDE	277.6	555.2	1559	YELLOW OXIDE	303.6	607.2
1554	TINTING WHITE	362.3	724.7	1302	LOW LUSTER CLEAR	385.8	771.6
1501	LANDAU BLACK	417.1	834.1	1550	RED OXIDE	405.6	811.1
				1501	LANDAU BLACK	421.3	842.7
MUST BE TOPCOATED WITH 1300 HIGH GLOSS CLEAR							
5746	DARK BLUE MET	General Motors		5753	MED LT FLINT	Ford Motor	2N3A
1553	FAST BLUE	219.9	439.9	1554	TINTING WHITE	202.9	405.8
1302	LOW LUSTER CLEAR	324.0	647.9	1302	LOW LUSTER CLEAR	285.2	570.4
1559	YELLOW OXIDE	383.4	766.8	1559	YELLOW OXIDE	358.2	716.5
1508	SILVER	400.0	800.1	1501	LANDAU BLACK	405.9	811.9
1501	LANDAU BLACK	403.9	807.9	1550	RED OXIDE	421.0	842.1
5747	DARK GRAYSTONE	Chrysler Motors	TW	5754	MEDIUM KHAKI	Chrysler Motors	ZJ3
1559	YELLOW OXIDE	120.6	241.1	1559	YELLOW OXIDE	140.9	281.8
1501	LANDAU BLACK	235.7	471.4	1554	TINTING WHITE	243.2	486.4
1302	LOW LUSTER CLEAR	326.2	652.5	1302	LOW LUSTER CLEAR	333.7	667.5
1550	RED OXIDE	386.3	772.5	1501	LANDAU BLACK	385.0	770.1
1554	TINTING WHITE	409.5	819.1	1550	RED OXIDE	415.2	830.5
5748	MED DK CASHMER	General Motors	WA832K	5755	MEDIUM TAUPE	Chrysler Motors	WL5
1559	YELLOW OXIDE	156.8	313.5	1554	TINTING WHITE	120.5	240.9
1302	LOW LUSTER CLEAR	248.4	496.9	1559	YELLOW OXIDE	236.3	472.5
1554	TINTING WHITE	329.7	659.5	1302	LOW LUSTER CLEAR	328.9	657.8
1550	RED OXIDE	378.3	756.6	1501	LANDAU BLACK	377.1	754.1
1501	LANDAU BLACK	414.4	828.8	1550	RED OXIDE	416.3	832.6
5749	MED CASHMERE	General Motors	WA831K	5756	DEEP SEAMIST GR	Chrysler Motors	ZP7
1559	YELLOW OXIDE	151.8	303.6	1501	LANDAU BLACK	175.6	351.1
1554	TINTING WHITE	261.2	522.3	1556	FAST GREEN	276.0	552.0
1302	LOW LUSTER CLEAR	354.1	708.1	1302	LOW LUSTER CLEAR	357.0	714.0
1550	RED OXIDE	391.9	783.8	1551	INDO YELLOW	386.8	773.7
1501	LANDAU BLACK	416.0	832.0	1554	TINTING WHITE	405.3	810.5
5750	LIGHT CASHMERE	General Motors	WA830K	5757	NAVY BLUE	Chrysler Motors	YQL
1554	TINTING WHITE	179.4	358.7	1553	FAST BLUE	125.6	251.2
1559	YELLOW OXIDE	298.5	597.0	1302	LOW LUSTER CLEAR	220.1	440.2
1302	LOW LUSTER CLEAR	386.1	772.2	1556	FAST GREEN	305.1	610.3
1550	RED OXIDE	407.8	815.7	1501	LANDAU BLACK	390.2	780.3
1501	LANDAU BLACK	420.5	840.9	1554	TINTING WHITE	404.0	808.1
5751	YELLOW			5758	DEEP SEAMIST	Chrysler Motors	ZP7
1551	INDO YELLOW	309.7	619.4	1556	FAST GREEN	177.1	354.2
1554	TINTING WHITE	411.4	822.9	1501	LANDAU BLACK	268.9	537.9
1553	FAST BLUE	411.7	823.5	1302	LOW LUSTER CLEAR	355.1	710.2
				1550	RED OXIDE	394.0	787.9
				1554	TINTING WHITE	405.5	810.9

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 161

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5759	LIGHT STEEL GRE	General Motors	WA922L	5769	SAND BEIGE	Kia	78
1554	TINTING WHITE	248.1	496.3	1554	TINTING WHITE	170.1	340.1
1302	LOW LUSTER CLEAR	330.9	661.8	1559	YELLOW OXIDE	305.4	610.9
1501	LANDAU BLACK	380.9	761.7	1302	LOW LUSTER CLEAR	385.6	771.2
1559	YELLOW OXIDE	417.0	833.9	1550	RED OXIDE	407.1	814.2
1550	RED OXIDE	423.6	847.2	1501	LANDAU BLACK	419.9	839.8
5760	DOVE GREY	Ford Motor	4N1A	5771	GRAY	Kia	96
1554	TINTING WHITE	272.5	544.9	1501	LANDAU BLACK	113.7	227.4
1302	LOW LUSTER CLEAR	356.7	713.5	1559	YELLOW OXIDE	221.5	443.1
1559	YELLOW OXIDE	388.7	777.5	1302	LOW LUSTER CLEAR	309.4	618.8
1501	LANDAU BLACK	418.1	836.2	1554	TINTING WHITE	384.4	768.7
1550	RED OXIDE	425.2	850.4	1550	RED OXIDE	412.5	825.0
5761	SHALE	Ford Motor	4N5A	5775	OAK BEIGE	Kia	BT
1554	TINTING WHITE	130.5	261.1	1559	YELLOW OXIDE	160.8	321.7
1501	LANDAU BLACK	240.6	481.3	1554	TINTING WHITE	261.0	521.9
1302	LOW LUSTER CLEAR	319.3	638.6	1300	HIGH GLOSS CLEAR	341.7	683.4
1559	YELLOW OXIDE	392.3	784.5	1550	RED OXIDE	378.9	757.7
1550	RED OXIDE	415.8	831.6	1501	LANDAU BLACK	415.7	831.4
5762	ASH 3	Ford Motor	3N3A	5781	SLATE GRAY	Kia	GJ
1554	TINTING WHITE	186.6	373.2	1501	LANDAU BLACK	261.1	522.1
1302	LOW LUSTER CLEAR	294.5	589.0	1302	LOW LUSTER CLEAR	328.9	657.8
1559	YELLOW OXIDE	374.4	748.8	1554	TINTING WHITE	370.4	740.8
1501	LANDAU BLACK	415.7	831.4	1553	FAST BLUE	392.9	785.8
1550	RED OXIDE	419.4	838.9	1550	RED OXIDE	407.6	815.1
5763	LIGHT OAK	Ford Motor	4U1A	5786	BEIGE	Kia	75
1554	TINTING WHITE	183.0	365.9	1554	TINTING WHITE	180.1	360.2
1559	YELLOW OXIDE	296.9	593.8	1559	YELLOW OXIDE	301.9	603.8
1302	LOW LUSTER CLEAR	394.5	789.1	1302	LOW LUSTER CLEAR	383.8	767.6
1550	RED OXIDE	413.1	826.1	1550	RED OXIDE	402.8	805.6
1501	LANDAU BLACK	420.2	840.4	1501	LANDAU BLACK	420.5	840.9
5764	LIGHT GRAY	Kia	05	5791	MEDIUM SLATE	Chrysler Motors	D5
1554	TINTING WHITE	237.6	475.2	1554	TINTING WHITE	134.2	268.5
1302	LOW LUSTER CLEAR	333.2	666.3	1559	YELLOW OXIDE	227.6	455.2
1559	YELLOW OXIDE	385.0	770.1	1501	LANDAU BLACK	316.1	632.1
1501	LANDAU BLACK	409.6	819.3	1302	LOW LUSTER CLEAR	399.2	798.4
1550	RED OXIDE	423.0	846.1	1550	RED OXIDE	416.5	833.0
5766	DARK GRAY	Kia	08	5792	CHARCOAL	Ford Motor	3PDA
1501	LANDAU BLACK	148.6	297.2	1501	LANDAU BLACK	168.4	336.9
1552	FAST RED	268.4	536.8	1559	YELLOW OXIDE	288.5	577.0
1302	LOW LUSTER CLEAR	352.3	704.5	1554	TINTING WHITE	391.5	783.0
1554	TINTING WHITE	382.0	764.0	1550	RED OXIDE	415.5	831.1
1553	FAST BLUE	405.9	811.9				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 162

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5793	PASTEL PEBBLE BE	Chrysler Motors	KA	5799	TARRAGON	Ford Motor	4MBC
1554	TINTING WHITE	181.6	363.3	1508	SILVER	271.9	543.8
1559	YELLOW OXIDE	296.5	593.0	1300	HIGH GLOSS CLEAR	383.9	767.8
1302	LOW LUSTER CLEAR	381.0	761.9	1551	INDO YELLOW	406.6	813.2
1550	RED OXIDE	402.2	804.5				
1501	LANDAU BLACK	420.5	840.9				
5793	PASTEL PEBBLE BE	Chrysler Motors	DK4	5800	MEDIUM STEEL GR	General Motors	923L
1554	TINTING WHITE	181.6	363.3	1554	TINTING WHITE	183.0	365.9
1559	YELLOW OXIDE	296.5	593.0	1501	LANDAU BLACK	276.3	552.5
1302	LOW LUSTER CLEAR	381.0	761.9	1302	LOW LUSTER CLEAR	367.7	735.5
1550	RED OXIDE	402.2	804.5	1559	YELLOW OXIDE	417.7	835.4
1501	LANDAU BLACK	420.5	840.9	1553	FAST BLUE	418.7	837.3
5794	PEARL	Chrysler Motors	DWI	5801	DARK STEEL GRAY	General Motors	924L
1554	TINTING WHITE	317.4	634.8	1501	LANDAU BLACK	142.5	285.0
1302	LOW LUSTER CLEAR	401.9	803.7	1554	TINTING WHITE	256.5	513.0
1559	YELLOW OXIDE	421.4	842.8	1302	LOW LUSTER CLEAR	349.4	698.8
1501	LANDAU BLACK	426.5	852.9	1559	YELLOW OXIDE	413.8	827.6
1550	RED OXIDE	428.2	856.3				
5795	BRONZE MET	Ford Motor	4TCCXXH	5802	VERY DARK STEEL	General Motors	925L
1300	HIGH GLOSS CLEAR	119.1	238.3	1501	LANDAU BLACK	184.2	368.4
1508	SILVER	235.7	471.4	1302	LOW LUSTER CLEAR	271.8	543.6
1559	YELLOW OXIDE	333.6	667.3	1554	TINTING WHITE	344.2	688.4
1501	LANDAU BLACK	377.9	755.8	1559	YELLOW OXIDE	407.3	814.5
1552	FAST RED	407.1	814.2	1553	FAST BLUE	410.8	821.6
5796	MEDIUM LIGHT AL	Ford Motor	4M3CXXH	5803	DARK GRAY	Kia	B1
1508	SILVER	185.0	369.9	1554	TINTING WHITE	144.4	288.8
1300	HIGH GLOSS CLEAR	290.4	580.8	1302	LOW LUSTER CLEAR	226.5	453.0
1559	YELLOW OXIDE	361.2	722.4	1501	LANDAU BLACK	307.5	615.0
1501	LANDAU BLACK	407.3	814.5	1559	YELLOW OXIDE	373.8	747.7
				1550	RED OXIDE	417.1	834.3
5797	PEBBLE 3.5	Ford Motor	3TDA	5804	SAND BEIGE	Kia	B3
1559	YELLOW OXIDE	168.6	337.3	1554	TINTING WHITE	155.8	311.6
1554	TINTING WHITE	272.8	545.7	1559	YELLOW OXIDE	298.0	596.0
1302	LOW LUSTER CLEAR	357.2	714.4	1302	LOW LUSTER CLEAR	378.9	757.7
1501	LANDAU BLACK	387.6	775.2	1550	RED OXIDE	407.3	814.5
1550	RED OXIDE	415.9	831.8	1501	LANDAU BLACK	419.2	838.5
5798	SATIN STEEL	Ford Motor	5Q4C	5805	BEIGE	Kia	A4
1508	SILVER	185.3	370.5	1559	YELLOW OXIDE	177.7	355.5
1300	HIGH GLOSS CLEAR	309.7	619.4	1554	TINTING WHITE	271.5	543.0
1501	LANDAU BLACK	381.9	763.8	1302	LOW LUSTER CLEAR	352.4	704.7
1559	YELLOW OXIDE	405.4	810.7	1501	LANDAU BLACK	385.0	770.1
1552	FAST RED	406.2	812.4	1550	RED OXIDE	415.4	830.9

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 163

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5806	DARK GRAY	Kia		A7	5814	LIGHT GRAY	BOSE
1501	LANDAU BLACK	174.4	348.8		1554	TINTING WHITE	335.1 670.1
1554	TINTING WHITE	302.1	604.2		1559	YELLOW OXIDE	393.8 787.6
1302	LOW LUSTER CLEAR	378.1	756.2		1501	LANDAU BLACK	426.5 852.9
1551	INDO YELLOW	402.4	804.8		1550	RED OXIDE	431.0 862.0
1550	RED OXIDE	414.0	828.0				
5807	BEIGE	Kia		C2	5815	BLACK	BOSE
1554	TINTING WHITE	99.8	199.7		1501	LANDAU BLACK	202.8 405.7
1551	INDO YELLOW	196.7	393.5		1559	YELLOW OXIDE	317.7 635.4
1302	LOW LUSTER CLEAR	284.9	569.8		1554	TINTING WHITE	399.3 798.6
1501	LANDAU BLACK	349.8	699.6		1550	RED OXIDE	413.6 827.3
1550	RED OXIDE	412.7	825.4				
5809	GRAY	Kia		C3	5816	DARK GRAY	BOSE
1554	TINTING WHITE	123.7	247.4		1501	LANDAU BLACK	154.9 309.9
1501	LANDAU BLACK	228.3	456.6		1559	YELLOW OXIDE	276.7 553.5
1559	YELLOW OXIDE	307.5	615.0		1302	LOW LUSTER CLEAR	339.8 679.6
1302	LOW LUSTER CLEAR	386.7	773.5		1554	TINTING WHITE	397.6 795.2
1550	RED OXIDE	415.6	831.3		1550	RED OXIDE	411.4 822.9
5810	CASHMERE	Toyota		009B	5817	GRANITE	Ford Motor 4N7A
1554	TINTING WHITE	194.4	388.7		1501	LANDAU BLACK	139.9 279.9
1302	LOW LUSTER CLEAR	312.2	624.3		1559	YELLOW OXIDE	257.1 514.1
1559	YELLOW OXIDE	402.6	805.2		1302	LOW LUSTER CLEAR	339.3 678.7
1550	RED OXIDE	412.6	825.2		1554	TINTING WHITE	396.2 792.5
1501	LANDAU BLACK	420.3	840.6		1550	RED OXIDE	411.1 822.1
5811	ASH	Toyota		140B	5818	LT. CHARCOAL	General Motors WA500F
1554	TINTING WHITE	204.3	408.7		1559	YELLOW OXIDE	138.5 277.0
1302	LOW LUSTER CLEAR	322.8	645.6		1501	LANDAU BLACK	269.3 538.7
1559	YELLOW OXIDE	367.3	734.5		1554	TINTING WHITE	386.3 772.5
1501	LANDAU BLACK	403.4	806.7		1550	RED OXIDE	417.1 834.1
1550	RED OXIDE	420.3	840.6				
5812	VERY DARK CASH	General Motors		WA935L	5819	DK GREY MET.	General Motors WA5LI-643H
1559	YELLOW OXIDE	176.5	353.0		1501	LANDAU BLACK	178.8 357.6
1302	LOW LUSTER CLEAR	255.3	510.5		1508	SILVER	261.4 522.9
1501	LANDAU BLACK	317.7	635.4		1302	LOW LUSTER CLEAR	328.5 657.0
1550	RED OXIDE	371.3	742.5		1552	FAST RED	370.7 741.4
1554	TINTING WHITE	411.9	823.8		1551	INDO YELLOW	405.1 810.2
5813	BLACK VINYL	BOSE			5820	GREY METALLIC	General Motors WZ15MP-945
1501	LANDAU BLACK	214.9	429.8		1501	LANDAU BLACK	164.4 328.9
1554	TINTING WHITE	322.1	644.3		1508	SILVER	288.5 577.0
1551	INDO YELLOW	393.8	787.6		1302	LOW LUSTER CLEAR	369.9 739.9
1550	RED OXIDE	413.3	826.5		1551	INDO YELLOW	392.1 784.1
					1552	FAST RED	405.5 810.9

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 164

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5821	COBALT RED	General Motors	WA217M	5829	MED STEEL BLUE	Ford Motor	5D6
1552	FAST RED	246.7	493.4	1501	LANDAU BLACK	142.4	284.8
1302	LOW LUSTER CLEAR	337.8	675.6	1554	TINTING WHITE	267.0	533.9
1551	INDO YELLOW	397.5	795.0	1302	LOW LUSTER CLEAR	369.1	738.2
1554	TINTING WHITE	403.4	806.7	1553	FAST BLUE	403.6	807.1
1501	LANDAU BLACK	403.8	807.7	1559	YELLOW OXIDE	413.3	826.5
5823	LT PEBBLE BEIGE	Chrysler Motors		5830	MED DOVE GRAY	Ford Motor	4N3
1559	YELLOW OXIDE	132.9	265.8	1554	TINTING WHITE	201.3	402.6
1302	LOW LUSTER CLEAR	254.9	509.8	1302	LOW LUSTER CLEAR	284.1	568.1
1554	TINTING WHITE	359.8	719.5	1559	YELLOW OXIDE	353.6	707.2
1550	RED OXIDE	387.8	775.6	1501	LANDAU BLACK	409.5	819.1
1501	LANDAU BLACK	415.0	829.9	1550	RED OXIDE	420.8	841.5
5824	DK PEBBLE BEIGE	Chrysler Motors	K7	5831	CHARCOAL BLACK	Ford Motor	5B8A
1559	YELLOW OXIDE	151.1	302.1	1501	LANDAU BLACK	184.6	369.2
1302	LOW LUSTER CLEAR	292.7	585.4	1302	LOW LUSTER CLEAR	286.6	573.2
1501	LANDAU BLACK	337.8	675.6	1559	YELLOW OXIDE	356.6	713.3
1554	TINTING WHITE	375.6	751.3	1554	TINTING WHITE	383.1	766.3
1550	RED OXIDE	410.3	820.6	1550	RED OXIDE	407.9	815.9
5825	MED CHARCOAL	Chrysler Motors	BDL	5832	CAMEL	Ford Motor	4T1A
1554	TINTING WHITE	155.5	311.0	1554	TINTING WHITE	187.2	374.5
1501	LANDAU BLACK	289.9	579.9	1559	YELLOW OXIDE	297.4	594.9
1559	YELLOW OXIDE	388.4	776.7	1302	LOW LUSTER CLEAR	393.3	786.6
1550	RED OXIDE	419.1	838.3	1550	RED OXIDE	409.0	818.0
				1501	LANDAU BLACK	420.5	840.9
5826	MERLOT	Ford Motor	3KW	5833	LIGHT OAK	Ford Motor	4U1
1552	FAST RED	289.8	579.7	1559	YELLOW OXIDE	173.7	347.3
1302	LOW LUSTER CLEAR	360.0	719.9	1554	TINTING WHITE	309.9	619.8
1551	INDO YELLOW	385.2	770.5	1302	LOW LUSTER CLEAR	389.8	779.6
1553	FAST BLUE	395.8	791.5	1550	RED OXIDE	410.6	821.2
1554	TINTING WHITE	404.2	808.5	1501	LANDAU BLACK	418.3	836.6
5827	VICTORY RED	General Motors	WA341M	5834	MOROCCO	General Motors	WA260M
1552	FAST RED	184.9	369.7	1559	YELLOW OXIDE	200.8	401.7
1302	LOW LUSTER CLEAR	303.7	607.4	1550	RED OXIDE	313.3	626.6
1551	INDO YELLOW	382.9	765.9	1302	LOW LUSTER CLEAR	391.2	782.4
1554	TINTING WHITE	398.8	797.6	1501	LANDAU BLACK	405.9	811.9
1550	RED OXIDE	404.6	809.2	1554	TINTING WHITE	411.2	822.3
5828	RALLY CHARCOAL	General Motors	WA9606	5835	COOL VANILLA	Chrysler Motors	BWN
1559	YELLOW OXIDE	139.3	278.5	1554	TINTING WHITE	412.2	824.4
1501	LANDAU BLACK	268.2	536.4	1559	YELLOW OXIDE	433.9	867.7
1554	TINTING WHITE	333.0	666.0	1501	LANDAU BLACK	436.0	871.9
1550	RED OXIDE	378.9	757.7				
1302	LOW LUSTER CLEAR	413.3	826.7				

MUST BE TOP COATED WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 165

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5836	LIGHT SHALE	Chrysler Motors	ES3	5840	CEDAR RED	Chrysler Motors	RK
1554	TINTING WHITE	266.5	533.0	1550	RED OXIDE	219.2	438.3
1302	LOW LUSTER CLEAR	351.3	702.6	1559	YELLOW OXIDE	311.3	622.6
1559	YELLOW OXIDE	397.9	795.7	1302	LOW LUSTER CLEAR	393.6	787.2
1501	LANDAU BLACK	416.9	833.7	1554	TINTING WHITE	412.3	824.6
1550	RED OXIDE	425.0	850.1				
5837	PASTEL SLATE GR	Chrysler Motors	DA	5841	CASHMERE	Ford Motor	5VOA
1554	TINTING WHITE	266.5	533.0	1554	TINTING WHITE	322.7	645.4
1302	LOW LUSTER CLEAR	351.3	702.6	1302	LOW LUSTER CLEAR	405.9	811.9
1559	YELLOW OXIDE	397.9	795.7	1559	YELLOW OXIDE	423.9	847.8
1501	LANDAU BLACK	416.9	833.7	1501	LANDAU BLACK	426.9	853.9
1550	RED OXIDE	425.0	850.1	1550	RED OXIDE	428.6	857.3
5838	MED PEBBLE BEIG	Chrysler Motors	DK5	5842	SATIN BLACK	Ford Motor	YYWA
1554	TINTING WHITE	255.8	511.7	1501	LANDAU BLACK	269.1	538.3
1302	LOW LUSTER CLEAR	348.3	696.5	1302	LOW LUSTER CLEAR	378.3	756.6
1559	YELLOW OXIDE	388.6	777.3	1556	FAST GREEN	394.3	788.7
1501	LANDAU BLACK	415.4	830.9	1554	TINTING WHITE	401.1	802.2
1550	RED OXIDE	424.1	848.2	1551	INDO YELLOW	404.5	809.0
5839	LIGHT PEARL	Chrysler Motors	W1	5843	DARK SMOKE GRE	General Motors	WA501F
1554	TINTING WHITE	297.4	594.9	1300	HIGH GLOSS CLEAR	152.7	305.3
1302	LOW LUSTER CLEAR	403.7	807.3	1501	LANDAU BLACK	285.0	570.0
1559	YELLOW OXIDE	420.7	841.3	1559	YELLOW OXIDE	362.3	724.7
1501	LANDAU BLACK	425.2	850.4	1550	RED OXIDE	386.9	773.9
1550	RED OXIDE	426.5	852.9	1554	TINTING WHITE	407.3	814.5
5840	PEARL	Chrysler Motors	DW1	5844	GRAPHITE	Toyota	138B
1554	TINTING WHITE	297.4	594.9	1554	TINTING WHITE	171.6	343.1
1302	LOW LUSTER CLEAR	403.7	807.3	1302	LOW LUSTER CLEAR	260.3	520.6
1559	YELLOW OXIDE	420.7	841.3	1501	LANDAU BLACK	333.4	666.7
1501	LANDAU BLACK	425.2	850.4	1559	YELLOW OXIDE	400.0	799.9
1550	RED OXIDE	426.5	852.9	1550	RED OXIDE	418.6	837.1
5841	CRIMSON RED	Ford Motor	5R7A	5845	BLACK	General Motors	WA658E
1552	FAST RED	232.6	465.1	1501	LANDAU BLACK	375.7	751.5
1302	LOW LUSTER CLEAR	331.5	662.9	1559	YELLOW OXIDE	400.8	801.6
1551	INDO YELLOW	383.4	766.8	1550	RED OXIDE	403.3	806.6
1554	TINTING WHITE	404.0	808.1	1554	TINTING WHITE	405.7	811.5
1501	LANDAU BLACK	404.9	809.8				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 166

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5847	GRAYSTONE	Ford Motor	6T7A	5854	LIGHT TITANIUM	General Motors	WA311N/D862
1559	YELLOW OXIDE	124.8	249.7	1554	TINTING WHITE	249.4	498.8
1501	LANDAU BLACK	233.7	467.4	1302	LOW LUSTER CLEAR	328.1	656.3
1302	LOW LUSTER CLEAR	307.5	615.0	1559	YELLOW OXIDE	383.2	766.5
1554	TINTING WHITE	369.5	738.9	1501	LANDAU BLACK	411.0	821.9
1550	RED OXIDE	412.3	824.6	1550	RED OXIDE	424.2	848.4
5848	SAND	Ford Motor	6X0A	5855	MED. TITANIUM	General Motors	WA312N
1554	TINTING WHITE	289.2	578.4	1554	TINTING WHITE	169.3	338.6
1302	LOW LUSTER CLEAR	368.6	737.2	1559	YELLOW OXIDE	264.1	528.2
1559	YELLOW OXIDE	416.3	832.6	1302	LOW LUSTER CLEAR	343.0	686.1
1550	RED OXIDE	421.7	843.4	1501	LANDAU BLACK	396.7	793.4
1501	LANDAU BLACK	426.8	853.7	1550	RED OXIDE	419.1	838.3
5849	LIGHT CAMEL	Ford Motor	4T0A	5856	DARK TITANIUM	General Motors	WA313N
1554	TINTING WHITE	248.6	497.2	1554	TINTING WHITE	116.9	233.9
1302	LOW LUSTER CLEAR	329.7	659.5	1559	YELLOW OXIDE	225.3	450.7
1559	YELLOW OXIDE	407.3	814.5	1302	LOW LUSTER CLEAR	307.5	615.0
1552	FAST RED	416.0	832.0	1501	LANDAU BLACK	389.0	778.1
1501	LANDAU BLACK	424.1	848.2	1550	RED OXIDE	415.6	831.3
5850	MED. CAMEL	Ford Motor	4T3A	5857	TAN	Acura	
1559	YELLOW OXIDE	152.4	304.8	1554	TINTING WHITE	178.3	356.6
1554	TINTING WHITE	284.3	568.7	1559	YELLOW OXIDE	313.3	626.6
1302	LOW LUSTER CLEAR	365.4	730.7	1302	LOW LUSTER CLEAR	399.9	799.7
1550	RED OXIDE	393.6	787.2	1550	RED OXIDE	413.1	826.1
1501	LANDAU BLACK	417.6	835.2	1501	LANDAU BLACK	420.4	840.8
5851	LIGHT STONE	Ford Motor	1TBA	5858	CREAMY IVORY	Acura	
1554	TINTING WHITE	244.1	488.1	1554	TINTING WHITE	188.2	376.4
1302	LOW LUSTER CLEAR	325.4	650.8	1559	YELLOW OXIDE	314.8	629.7
1559	YELLOW OXIDE	393.7	787.4	1302	LOW LUSTER CLEAR	400.4	800.9
1501	LANDAU BLACK	409.9	819.9	1550	RED OXIDE	414.1	828.2
1550	RED OXIDE	423.9	847.8	1501	LANDAU BLACK	420.9	841.9
5852	LIGHT GRAY	Ford Motor		5859	CHARCOAL	Acura	
1501	LANDAU BLACK	122.3	244.5	1554	TINTING WHITE	112.6	225.2
1508	SILVER	242.1	484.1	1559	YELLOW OXIDE	218.4	436.8
1552	FAST RED	309.8	619.6	1501	LANDAU BLACK	315.6	631.2
1302	LOW LUSTER CLEAR	361.9	723.7	1302	LOW LUSTER CLEAR	395.8	791.5
1553	FAST BLUE	398.3	796.7	1550	RED OXIDE	415.1	830.1
1551	INDO YELLOW	405.3	810.5				
5853	DK. GRAY	Ford Motor		5860	MED. NEUTRAL	BMW	
1501	LANDAU BLACK	224.9	449.7	1559	YELLOW OXIDE	143.0	286.0
1559	YELLOW OXIDE	310.6	621.1	1554	TINTING WHITE	256.6	513.2
1302	LOW LUSTER CLEAR	350.7	701.5	1302	LOW LUSTER CLEAR	338.2	676.4
1554	TINTING WHITE	382.6	765.1	1550	RED OXIDE	382.9	765.9
1550	RED OXIDE	409.4	818.7	1501	LANDAU BLACK	416.6	833.2

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 167

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5861	Silver Gray	BMW		5868	CARAVAN GRAY G	Chrysler Motors	
1554	TINTING WHITE	230.5	461.1	1559	YELLOW OXIDE	153.6	307.2
1302	LOW LUSTER CLEAR	357.1	714.1	1501	LANDAU BLACK	289.5	578.9
1559	YELLOW OXIDE	396.3	792.7	1302	LOW LUSTER CLEAR	363.5	726.9
1550	RED OXIDE	418.6	837.3	1554	TINTING WHITE	405.2	810.4
1553	FAST BLUE	432.4	864.8	1553	FAST BLUE	410.5	821.0
5862	CLASSY GRAY	Honda		5869	EXPLORER DARK G	Ford Motor	
1501	LANDAU BLACK	190.4	380.8	1501	LANDAU BLACK	153.6	307.2
1559	YELLOW OXIDE	290.8	581.6	1559	YELLOW OXIDE	275.4	550.8
1302	LOW LUSTER CLEAR	369.2	738.3	1302	LOW LUSTER CLEAR	345.9	691.8
1554	TINTING WHITE	405.3	810.5	1554	TINTING WHITE	383.7	767.4
1550	RED OXIDE	409.1	818.1	1550	RED OXIDE	410.2	820.4
5863	MILD BEIGE	Honda		5870	SPORT TRAC GRAY	Ford Motor	
1554	TINTING WHITE	142.3	284.6	1554	TINTING WHITE	151.6	303.2
1559	YELLOW OXIDE	272.8	545.7	1501	LANDAU BLACK	247.7	495.3
1302	LOW LUSTER CLEAR	356.5	713.1	1302	LOW LUSTER CLEAR	323.2	646.4
1550	RED OXIDE	393.4	786.8	1551	INDO YELLOW	373.4	746.7
1501	LANDAU BLACK	418.2	836.4	1550	RED OXIDE	416.6	833.2
5864	OAK	Toyota		5871	CHEROKEE DRIFT	Chrysler Motors	
1554	TINTING WHITE	139.4	278.7	1559	YELLOW OXIDE	114.8	229.5
1559	YELLOW OXIDE	264.0	528.0	1554	TINTING WHITE	217.3	434.5
1302	LOW LUSTER CLEAR	343.9	687.8	1501	LANDAU BLACK	303.3	606.7
1550	RED OXIDE	388.6	777.3	1302	LOW LUSTER CLEAR	383.9	767.8
1501	LANDAU BLACK	418.1	836.2	1550	RED OXIDE	414.9	829.7
5865	IVORY	Toyota		5872	CHEROKEE GRAY	Chrysler Motors	
1554	TINTING WHITE	185.7	371.5	1501	LANDAU BLACK	217.6	435.1
1559	YELLOW OXIDE	299.5	599.1	1302	LOW LUSTER CLEAR	280.3	560.5
1302	LOW LUSTER CLEAR	383.2	766.5	1559	YELLOW OXIDE	327.7	655.3
1550	RED OXIDE	402.6	805.2	1554	TINTING WHITE	369.0	738.0
1501	LANDAU BLACK	420.7	841.3	1550	RED OXIDE	409.4	818.7
5866	BLUE GRAY	Toyota		5873	CHEROKEE BLACK	Chrysler Motors	
1554	TINTING WHITE	156.3	312.6	1501	LANDAU BLACK	227.2	454.5
1501	LANDAU BLACK	242.7	485.5	1559	YELLOW OXIDE	305.8	611.6
1302	LOW LUSTER CLEAR	325.9	651.7	1302	LOW LUSTER CLEAR	367.0	734.0
1559	YELLOW OXIDE	394.1	788.1	1554	TINTING WHITE	401.5	802.9
1550	RED OXIDE	417.7	835.4	1550	RED OXIDE	408.6	817.2
5867	CARAVAN GRAY	Chrysler Motors		5874	FRONTIER GRAY	Nissan	
1501	LANDAU BLACK	141.3	282.5	1501	LANDAU BLACK	139.3	278.5
1559	YELLOW OXIDE	222.6	445.2	1559	YELLOW OXIDE	267.3	534.7
1302	LOW LUSTER CLEAR	296.5	593.0	1302	LOW LUSTER CLEAR	343.0	686.1
1554	TINTING WHITE	369.8	739.7	1554	TINTING WHITE	394.8	789.6
1550	RED OXIDE	412.4	824.8	1550	RED OXIDE	411.2	822.3

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 168

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

5875	PREVIA GRAY	Toyota	
1501	LANDAU BLACK	146.9	293.7
1559	YELLOW OXIDE	237.4	474.8
1554	TINTING WHITE	322.7	645.4
1302	LOW LUSTER CLEAR	399.7	799.3
1550	RED OXIDE	412.6	825.2

5882	MOSS	Ford Motor	6H5A
1559	YELLOW OXIDE	153.0	306.1
1554	TINTING WHITE	241.4	482.8
1302	LOW LUSTER CLEAR	323.2	646.4
1501	LANDAU BLACK	385.3	770.6
1550	RED OXIDE	414.4	828.8

5876	BLACK	Chrysler Motors	JX8
1501	LANDAU BLACK	247.1	494.2
1302	LOW LUSTER CLEAR	337.0	673.9
1551	INDO YELLOW	375.0	749.9
1553	FAST BLUE	392.9	785.8
1554	TINTING WHITE	404.9	809.8

5883	MED. DK. STONE	Ford Motor	1T4A
1559	YELLOW OXIDE	136.8	273.6
1554	TINTING WHITE	242.5	485.1
1302	LOW LUSTER CLEAR	322.6	645.2
1501	LANDAU BLACK	378.4	756.8
1550	RED OXIDE	415.5	831.1

5877	GRENADE GREEN	General Motors	WA-209
1559	YELLOW OXIDE	222.9	445.7
1501	LANDAU BLACK	303.9	607.8
1556	FAST GREEN	371.2	742.3
1508	SILVER	409.5	819.1

5884	GHIN RIME	Ford Motor	3P2C
1508	SILVER	254.6	509.2
1302	LOW LUSTER CLEAR	337.8	675.6
1559	YELLOW OXIDE	379.4	758.9
1501	LANDAU BLACK	396.1	792.1
1550	RED OXIDE	407.7	815.5

MUST BE TOP COATED WITH 1300 HIGH GLOSS CLEAR

5878	DK. GRAY MET.	General Motors	WA610F
1501	LANDAU BLACK	242.9	485.8
1508	SILVER	352.1	704.1
1550	RED OXIDE	379.3	758.7
1551	INDO YELLOW	406.6	813.2

5885	MED. LT. ALLOY	Ford Motor	4M3C
1508	SILVER	276.5	552.9
1559	YELLOW OXIDE	344.0	688.0
1501	LANDAU BLACK	396.6	793.3
1550	RED OXIDE	409.3	818.5

5879	SATIN NICKEL MET	General Motors	WA733J
1508	SILVER	381.0	761.9
1551	INDO YELLOW	395.4	790.8
1552	FAST RED	406.4	812.8
1501	LANDAU BLACK	408.5	817.0

5886	STAINLESS SILVER	Ford Motor	CDK
1508	SILVER	355.5	711.0
1559	YELLOW OXIDE	389.8	779.6
1501	LANDAU BLACK	406.9	813.8
1550	RED OXIDE	409.1	818.1

MUST BE TOP COATED WITH 1301 SATIN GLOSS CLEAR

5880	MED. BISCUIT	C9646GJ	
1554	TINTING WHITE	168.2	336.5
1559	YELLOW OXIDE	290.5	581.0
1302	LOW LUSTER CLEAR	373.8	747.7
1550	RED OXIDE	402.1	804.3
1501	LANDAU BLACK	419.8	839.6

5887	PEBBLE BEIGE	Chrysler Motors	DKC
1554	TINTING WHITE	162.3	324.5
1559	YELLOW OXIDE	274.4	548.7
1302	LOW LUSTER CLEAR	376.3	752.6
1550	RED OXIDE	398.0	795.9
1501	LANDAU BLACK	418.9	837.7

5881	YELLOW	YS223J	
1554	TINTING WHITE	197.5	395.0
1559	YELLOW OXIDE	317.6	635.2
1302	LOW LUSTER CLEAR	396.0	791.9
1550	RED OXIDE	416.7	833.3
1501	LANDAU BLACK	421.7	843.4

5888	VERY LT. CASHME	General Motors	WA314N
1554	TINTING WHITE	264.5	529.0
1302	LOW LUSTER CLEAR	347.5	695.0
1559	YELLOW OXIDE	413.9	827.8
1550	RED OXIDE	420.9	841.7
1501	LANDAU BLACK	425.1	850.3

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 169

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

5889	BRICK	General Motors	WA422P
1550	RED OXIDE	174.5	349.0
1559	YELLOW OXIDE	311.3	622.6
1302	LOW LUSTER CLEAR	390.5	780.9
1501	LANDAU BLACK	404.7	809.4
1554	TINTING WHITE	411.4	822.7

5896	DARK BROWN		
1501	LANDAU BLACK	132.8	265.6
1554	TINTING WHITE	262.4	524.8
1559	YELLOW OXIDE	387.6	775.2
1550	RED OXIDE	417.7	835.4

5890	COCOA	General Motors	WA413P
1501	LANDAU BLACK	135.0	270.0
1559	YELLOW OXIDE	244.9	489.8
1302	LOW LUSTER CLEAR	326.4	652.8
1550	RED OXIDE	389.7	779.4
1554	TINTING WHITE	409.3	818.5

5897	DK. ARGENT MET	General Motors	WA6246
1501	LANDAU BLACK	250.8	501.6
1508	SILVER	378.3	756.6
1552	FAST RED	394.5	789.1
1551	INDO YELLOW	406.1	812.3

MUST BE TOP COATED WITH 1300 HIGH GLOSS CLEAR

5891	BEIGE		
1554	TINTING WHITE	165.4	330.8
1559	YELLOW OXIDE	276.5	553.1
1302	LOW LUSTER CLEAR	362.8	725.6
1501	LANDAU BLACK	398.3	796.7
1550	RED OXIDE	419.0	838.1

5898	DK. GRAY MET.	General Motors	W30A-8489
1508	SILVER	239.8	479.6
1501	LANDAU BLACK	377.0	753.9
1552	FAST RED	393.3	786.6
1551	INDO YELLOW	407.2	814.3

MUST BE TOP COATED WITH 1300 HIGH GLOSS CLEAR

5892	LT. GRAY		
1554	TINTING WHITE	257.2	514.3
1302	LOW LUSTER CLEAR	340.7	681.3
1501	LANDAU BLACK	396.2	792.3
1551	INDO YELLOW	414.2	828.4
1550	RED OXIDE	423.5	847.0

5899	NOVA SILVER	General Motors	WA324N
1508	SILVER	343.0	686.1
1552	FAST RED	384.6	769.1
1556	FAST GREEN	396.5	793.1
1551	INDO YELLOW	408.1	816.2

MUST BE TOP COATED WITH 1300 HIGH GLOSS CLEAR

5893	DARK BEIGE		
1554	TINTING WHITE	181.1	362.1
1559	YELLOW OXIDE	319.3	638.6
1501	LANDAU BLACK	383.2	766.5
1550	RED OXIDE	422.0	844.0

5900	TITANIUM	General Motors	W5A912K
1508	SILVER	255.3	510.5
1501	LANDAU BLACK	368.0	736.1
1551	INDO YELLOW	387.7	775.4
1552	FAST RED	407.4	814.7

MUST BE TOP COATED WITH 1300 HIGH GLOSS CLEAR

5894	BROWN		
1554	TINTING WHITE	163.5	327.0
1559	YELLOW OXIDE	276.8	553.7
1501	LANDAU BLACK	367.5	734.9
1550	RED OXIDE	420.5	840.9

5901	VY. DK. SILVER GR	General Motors	WA-739J
1501	LANDAU BLACK	211.6	423.1
1508	SILVER	399.9	799.7
1551	INDO YELLOW	404.5	809.0
1552	FAST RED	406.8	813.6

MUST BE TOP COATED WITH 1300 HIGH GLOSS CLEAR

5895	MEDIUM BROWN		
1559	YELLOW OXIDE	128.6	257.3
1554	TINTING WHITE	236.9	473.9
1501	LANDAU BLACK	315.8	631.6
1302	LOW LUSTER CLEAR	383.5	767.0
1550	RED OXIDE	415.6	831.3

5902	DK. SATIN NICKEL	General Motor	WA20WR-731J
1508	SILVER	257.4	514.7
1501	LANDAU BLACK	359.0	718.0
1552	FAST RED	384.8	769.5
1551	INDO YELLOW	407.3	814.5

MUST BE TOP COATED WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 170

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

5903	MED. DK. GRAY	General Motors	WA8247
1554	TINTING WHITE	172.0	343.9
1501	LANDAU BLACK	272.1	544.2
1302	LOW LUSTER CLEAR	354.4	708.9
1559	YELLOW OXIDE	412.8	825.6
1553	FAST BLUE	418.0	836.0

5910	BROWN	KW 900	
1554	TINTING WHITE	166.3	332.7
1501	LANDAU BLACK	252.7	505.4
1302	LOW LUSTER CLEAR	332.0	664.1
1551	INDO YELLOW	374.9	749.7
1552	FAST RED	416.5	833.0

5904	PIANO BLACK	General Motors	WA424P
1501	LANDAU BLACK	237.6	475.2
1553	FAST BLUE	403.9	807.9

5911	DK. BROWN	KW 900	
1501	LANDAU BLACK	116.4	232.8
1302	LOW LUSTER CLEAR	193.3	386.7
1554	TINTING WHITE	267.8	535.6
1552	FAST RED	341.1	682.1
1551	INDO YELLOW	409.4	818.7

MUST BE TOP COATED WITH 1300 HIGH GLOSS CLEAR

5905	Gray		
1554	TINTING WHITE	282.2	564.3
1302	LOW LUSTER CLEAR	353.0	706.0
1501	LANDAU BLACK	398.8	797.7
1551	INDO YELLOW	418.4	836.9
1557	MAGENTA	425.2	850.3

5912	ARGENTANIUM	General Motors	WA226M
1508	SILVER	255.0	510.0
1300	HIGH GLOSS CLEAR	332.7	665.4
1501	LANDAU BLACK	376.2	752.4
1552	FAST RED	392.4	784.7
1551	INDO YELLOW	406.7	813.4

5906	Gray		
1554	TINTING WHITE	268.7	537.5
1302	LOW LUSTER CLEAR	353.5	707.1
1501	LANDAU BLACK	394.7	789.5
1551	INDO YELLOW	413.3	826.6
1557	MAGENTA	424.0	848.0

5913	MED. SILVER MET.	General Motors	WA25LA-744J
1508	SILVER	235.3	470.6
1300	HIGH GLOSS CLEAR	344.8	689.5
1501	LANDAU BLACK	385.8	771.6
1552	FAST RED	398.3	796.7
1551	INDO YELLOW	406.3	812.6

5907	Taupe		
1554	TINTING WHITE	238.8	477.6
1302	LOW LUSTER CLEAR	321.4	642.7
1501	LANDAU BLACK	380.6	761.1
1551	INDO YELLOW	401.5	802.9
1552	FAST RED	421.8	843.6

5914	SILVER MET.	General Motors	WA5WR-2779
1508	SILVER	403.1	806.2
1552	FAST RED	406.3	812.6
1551	INDO YELLOW	408.7	817.4

5908	Taupe	Pete379	
1554	TINTING WHITE	222.3	444.7
1501	LANDAU BLACK	293.5	587.1
1302	LOW LUSTER CLEAR	363.6	727.3
1551	INDO YELLOW	394.3	788.7
1557	MAGENTA	420.6	841.3

5915	DARK FOUNDRY	Ford Motor	7NEC
1501	LANDAU BLACK	199.9	399.8
1508	SILVER	369.3	738.5
1552	FAST RED	388.6	777.1
1551	INDO YELLOW	406.5	813.0

5909	DK. TAUPE	PETE379	
1554	TINTING WHITE	222.6	445.2
1302	LOW LUSTER CLEAR	304.6	609.1
1501	LANDAU BLACK	376.0	752.0
1551	INDO YELLOW	401.6	803.1
1552	FAST RED	420.6	841.1

5916	MANDARIN BLACK	Ford Motor	6AEAWWA
1501	LANDAU BLACK	230.9	461.7
1553	FAST BLUE	403.9	807.9

MUST BE TOP COATED WITH 1300 HIGH GLOSS CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 171

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5917	DK. WARM STEEL	Ford Motor	7N8CXXH	5926	CLUSTER WHITE	Ford Motor	3VBA
1501	LANDAU BLACK	154.6	309.1	1554	TINTING WHITE	339.8	679.6
1508	SILVER	284.3	568.7	1302	LOW LUSTER CLEAR	424.4	848.7
1300	HIGH GLOSS CLEAR	361.6	723.1	1559	YELLOW OXIDE	426.7	853.5
1552	FAST RED	387.2	774.4	1501	LANDAU BLACK	428.7	857.5
1551	INDO YELLOW	405.5	810.9	1553	FAST BLUE	429.4	858.8
5918	MAZDA SILVER ME	Ford Motor	3QCCXXE	5927	Dark Rust	Ford Motor	7R7A
1508	SILVER	375.6	751.3	1550	RED OXIDE	120.4	240.8
1501	LANDAU BLACK	394.6	789.3	1559	YELLOW OXIDE	236.8	473.6
1552	FAST RED	402.9	805.8	1302	LOW LUSTER CLEAR	322.3	644.6
1551	INDO YELLOW	408.4	816.8	1501	LANDAU BLACK	398.5	797.0
				1554	TINTING WHITE	410.0	820.1
5919	LT. WARM STEEL	Ford Motor	7NCC	5928	DUSK GRAY	Ford Motor	7Y7A
1508	SILVER	271.9	543.8	1501	LANDAU BLACK	117.4	234.8
1300	HIGH GLOSS CLEAR	356.8	713.6	1302	LOW LUSTER CLEAR	229.2	458.5
1501	LANDAU BLACK	393.5	787.0	1559	YELLOW OXIDE	325.4	650.8
1551	INDO YELLOW	400.3	800.7	1550	RED OXIDE	376.0	752.0
1552	FAST RED	406.8	813.6	1554	TINTING WHITE	409.5	819.1
5921	MERCURY RED	Ford Motor	JDKAXXJ	5929	MED. DARK CAMEL	Ford Motor	4T4A
1552	FAST RED	200.4	400.7	1559	YELLOW OXIDE	150.3	300.6
1551	INDO YELLOW	327.8	655.7	1302	LOW LUSTER CLEAR	266.8	533.5
1302	LOW LUSTER CLEAR	373.4	746.7	1554	TINTING WHITE	354.2	708.3
1554	TINTING WHITE	406.1	812.3	1550	RED OXIDE	390.0	780.0
				1501	LANDAU BLACK	414.1	828.2
5922	Very Lt. Linen	General Motors	WA521Q	5930	EBONY	General Motors	D794
1554	TINTING WHITE	245.1	490.3	1501	LANDAU BLACK	196.1	392.2
1302	LOW LUSTER CLEAR	366.0	732.0	1302	LOW LUSTER CLEAR	295.4	590.7
1559	YELLOW OXIDE	413.7	827.4	1559	YELLOW OXIDE	369.8	739.7
1501	LANDAU BLACK	420.9	841.7	1550	RED OXIDE	390.9	781.9
1550	RED OXIDE	423.0	846.0	1554	TINTING WHITE	407.3	814.5
5923	Very Lt. Titanium	Ford Motor	WA310N	5933	BRIGHT BLUE	Chrysler Motors	BN
1554	TINTING WHITE	261.5	523.1	1553	FAST BLUE	240.7	481.5
1302	LOW LUSTER CLEAR	380.3	760.6	1302	LOW LUSTER CLEAR	356.0	711.9
1559	YELLOW OXIDE	406.3	812.6	1554	TINTING WHITE	398.6	797.2
1501	LANDAU BLACK	416.9	833.8	1501	LANDAU BLACK	404.4	808.8
1550	RED OXIDE	423.9	847.9	1552	FAST RED	405.6	811.1
5924	MULBERRY	General Motors	WA524Q	5934	LIGHT LINEN	General Motors	WA513Q
1552	FAST RED	274.1	548.2	1554	TINTING WHITE	274.3	548.5
1302	LOW LUSTER CLEAR	373.4	746.9	1302	LOW LUSTER CLEAR	345.5	691.0
1553	FAST BLUE	396.3	792.7	1551	INDO YELLOW	384.7	769.3
1554	TINTING WHITE	400.8	801.6	1501	LANDAU BLACK	406.7	813.4
1551	INDO YELLOW	403.6	807.1	1550	RED OXIDE	424.8	849.7

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 172

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5935	Royale	Chrysler Motors		R1	5944	Camel	
1558	BRITE RED	310.8	621.7	1559	YELLOW OXIDE	257.9	515.8
1302	LOW LUSTER CLEAR	406.0	812.0	1302	LOW LUSTER CLEAR	340.3	680.5
1554	TINTING WHITE	413.6	827.3	1554	TINTING WHITE	376.4	752.9
1556	FAST GREEN	413.8	827.7	1557	MAGENTA	402.6	805.1
				1501	LANDAU BLACK	411.9	823.8
5936	CREAM	Ford Motor		3LAA	5946	Teal	
1554	TINTING WHITE	286.1	572.3	1554	TINTING WHITE	156.9	313.7
1302	LOW LUSTER CLEAR	416.3	832.6	1556	FAST GREEN	313.0	626.0
1551	INDO YELLOW	422.5	844.9	1553	FAST BLUE	370.8	741.7
1501	LANDAU BLACK	424.1	848.2	1501	LANDAU BLACK	415.8	831.7
1557	MAGENTA	424.9	849.9				
5937	Greige	Toyota		454B	5947	Aqua P1	
1554	TINTING WHITE	203.1	406.3	1554	TINTING WHITE	176.5	353.1
1559	YELLOW OXIDE	307.9	615.7	1556	FAST GREEN	263.2	526.3
1302	LOW LUSTER CLEAR	373.1	746.1	1553	FAST BLUE	342.1	684.3
1550	RED OXIDE	401.2	802.3	1551	INDO YELLOW	417.1	834.3
1501	LANDAU BLACK	414.5	829.0				
1553	FAST BLUE	422.1	844.1				
5940	RED ROCK	Toyota		5948	Titan Gray		General Motors
1559	YELLOW OXIDE	172.3	344.5	1554	TINTING WHITE	258.6	517.3
1302	LOW LUSTER CLEAR	266.2	532.4	1501	LANDAU BLACK	370.1	740.1
1557	MAGENTA	356.2	712.4	1550	RED OXIDE	413.8	827.7
1551	INDO YELLOW	396.8	793.7	1551	INDO YELLOW	425.1	850.2
1556	FAST GREEN	407.0	814.1				
5941	Sand Beige	Toyota		5949	Aqua P2		Oldsmobile
1559	YELLOW OXIDE	147.7	295.5	1300	HIGH GLOSS CLEAR	390.5	781.0
1554	TINTING WHITE	272.6	545.2	3520	PLATINUM PEARL	403.0	806.0
1302	LOW LUSTER CLEAR	368.8	737.6	3524	GREEN PEARL	406.1	812.2
1550	RED OXIDE	393.1	786.2				
1501	LANDAU BLACK	416.8	833.6				
5942	Bone	Toyota		5950	Thunderbird Red		Ford Motor
1554	TINTING WHITE	174.1	348.2	1558	BRITE RED	167.3	334.5
1559	YELLOW OXIDE	277.4	554.7	1552	FAST RED	327.9	655.8
1302	LOW LUSTER CLEAR	374.2	748.3	1302	LOW LUSTER CLEAR	395.3	790.5
1501	LANDAU BLACK	397.8	795.6	1554	TINTING WHITE	402.3	804.6
1550	RED OXIDE	419.5	839.0	1556	FAST GREEN	404.1	808.1
						0.0	0.0
5943	Oak	Toyota		5950	Thunderbird Red		Ford Motor
1554	TINTING WHITE	171.5	342.9	1558	BRITE RED	176.1	352.1
1559	YELLOW OXIDE	270.4	540.8	1552	FAST RED	345.2	690.4
1302	LOW LUSTER CLEAR	359.8	719.5	1302	LOW LUSTER CLEAR	416.1	832.2
1501	LANDAU BLACK	392.3	784.6	1554	TINTING WHITE	423.4	846.9
1550	RED OXIDE	419.4	838.8	1556	FAST GREEN	425.3	850.7

Yes (see 5949)

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 173

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5951	Pearl White	Buick		5964	Dark Chocolate	Ford Motor	7T8A
1554	TINTING WHITE	395.5	790.9	1501	LANDAU BLACK	147.6	295.1
1559	YELLOW OXIDE	432.7	865.5	1550	RED OXIDE	238.8	477.5
1556	FAST GREEN	433.9	867.7	1302	LOW LUSTER CLEAR	306.7	613.4
1501	LANDAU BLACK	435.0	870.0	1551	INDO YELLOW	373.2	746.5
				1554	TINTING WHITE	408.9	817.8
Yes							
5952	Pearl White Topcoat	Buick		5966	Light Pebble Beige	Chrysler Motors	K2
1300	HIGH GLOSS CLEAR	385.1	770.2	1554	TINTING WHITE	168.8	337.5
3520	PLATINUM PEARL	408.2	816.4	1302	LOW LUSTER CLEAR	277.0	554.0
				1551	INDO YELLOW	331.8	663.6
				1550	RED OXIDE	379.6	759.2
				1501	LANDAU BLACK	417.4	834.8
Topcoat for 5951							
5953	Inferno Orange	General Motors	WA736S	5966	Light Pebble Beige	Chrysler Motors	DK2
1558	BRITE RED	135.3	270.5	1554	TINTING WHITE	168.8	337.5
1302	LOW LUSTER CLEAR	240.3	480.7	1302	LOW LUSTER CLEAR	277.0	554.0
1559	YELLOW OXIDE	321.0	642.1	1551	INDO YELLOW	331.8	663.6
1551	INDO YELLOW	396.8	793.6	1550	RED OXIDE	379.6	759.2
1550	RED OXIDE	405.3	810.5	1501	LANDAU BLACK	417.4	834.8
5954	Jet Black	General Motors	WA600R	5967	Bark Brown	Chrysler Motors	TV
1302	LOW LUSTER CLEAR	201.6	403.2	1501	LANDAU BLACK	156.8	313.6
1501	LANDAU BLACK	366.6	733.3	1550	RED OXIDE	268.8	537.5
1558	BRITE RED	397.8	795.5	1551	INDO YELLOW	349.5	698.9
1551	INDO YELLOW	401.5	803.0	1303	FLATTENER	391.1	782.3
1554	TINTING WHITE	403.2	806.4	1554	TINTING WHITE	408.2	816.4
5955	Sterling Gray	Ford Motor	8N7A	5968	Corvette Red	General Motors	
1501	LANDAU BLACK	174.8	349.6	1558	BRITE RED	220.2	440.5
1554	TINTING WHITE	285.3	570.7	1559	YELLOW OXIDE	387.5	775.0
1302	LOW LUSTER CLEAR	367.8	735.6	1554	TINTING WHITE	409.4	818.7
1551	INDO YELLOW	398.5	797.0				
1557	MAGENTA	412.3	824.6				
5956	Alloy Metallic	Ford Motor	8N8C	5968	Corvette Red	General Motors	
1501	LANDAU BLACK	185.6	371.2	1558	BRITE RED	220.2	440.5
1302	LOW LUSTER CLEAR	266.5	533.0	1559	YELLOW OXIDE	387.5	775.0
1552	FAST RED	329.5	659.0	1554	TINTING WHITE	409.4	818.7
1508	SILVER	373.1	746.3			0.0	0.0
1556	FAST GREEN	404.4	808.9			0.0	0.0
						0.0	0.0
5957	Medium Greystone	Chrysler Motors	D3	5973	Blue	General Motors	
1554	TINTING WHITE	193.6	387.2	1553	FAST BLUE	177.7	355.4
1302	LOW LUSTER CLEAR	302.1	604.1	1501	LANDAU BLACK	284.0	567.9
1501	LANDAU BLACK	351.5	703.1	1554	TINTING WHITE	369.9	739.8
1551	INDO YELLOW	388.8	777.7	1556	FAST GREEN	410.1	820.2
1550	RED OXIDE	418.9	837.8				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 174

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5973	Blue	General Motors		5980	Canyon	Ford Motor	AU5A
1553	FAST BLUE	177.7	355.4	1302	LOW LUSTER CLEAR	197.4	394.8
1501	LANDAU BLACK	284.0	567.9	1559	YELLOW OXIDE	381.8	763.6
1554	TINTING WHITE	369.9	739.8	1550	RED OXIDE	411.2	822.4
1556	FAST GREEN	410.1	820.2	1554	TINTING WHITE	422.2	844.5
		410.1	820.2	1501	LANDAU BLACK	429.6	859.2
					0		
5974	Burnt Orange	Porsche		5981	Latte	General Motors	WA408N
1559	YELLOW OXIDE	161.1	322.2	1302	LOW LUSTER CLEAR	171.6	343.2
1557	MAGENTA	268.2	536.4	1554	TINTING WHITE	280.6	561.2
1303	FLATTENER	349.6	699.1	1559	YELLOW OXIDE	376.4	752.9
1551	INDO YELLOW	398.4	796.8	1550	RED OXIDE	421.5	842.9
1556	FAST GREEN	406.9	813.7	1553	FAST BLUE	435.6	871.2
					0		
5976	Colbert Beige	Pontiac		5982	Steel Gray	Ford Motor	9MCA
1554	TINTING WHITE	245.6	491.1	1554	TINTING WHITE	165.8	331.6
1559	YELLOW OXIDE	426.6	853.2	1302	LOW LUSTER CLEAR	312.5	625.0
1501	LANDAU BLACK	445.8	891.5	1501	LANDAU BLACK	406.9	813.7
1557	MAGENTA	448.1	896.1	1551	INDO YELLOW	427.0	854.0
	0	0.0	0.0	1552	FAST RED	437.2	874.3
	0				0		
	Satin Clear						
5976	Colbert Beige	Pontiac		5983	Agate	Ford Motor	9M7A
1554	TINTING WHITE	245.6	491.1	1302	LOW LUSTER CLEAR	143.5	286.9
1559	YELLOW OXIDE	426.6	853.2	1501	LANDAU BLACK	271.5	542.9
1501	LANDAU BLACK	445.8	891.5	1554	TINTING WHITE	353.3	706.6
1557	MAGENTA	448.1	896.1	1551	INDO YELLOW	400.2	800.5
	0	0.0	0.0	1550	RED OXIDE	431.6	863.3
	0	0.0	0.0		0		
	Satin Clear						
5977	BLUE RACER SOHO	Ford Motor	AD6A	5984	Brownstone	General Motors	WA702S
1302	LOW LUSTER CLEAR	198.4	396.9	1559	YELLOW OXIDE	126.9	253.8
1553	FAST BLUE	395.7	791.5	1501	LANDAU BLACK	232.3	464.6
1554	TINTING WHITE	414.7	829.4	1302	LOW LUSTER CLEAR	328.9	657.7
1551	INDO YELLOW	424.2	848.4	1550	RED OXIDE	418.4	836.9
1557	MAGENTA	424.6	849.1		0		
	0				0		
5978	CHERRY RED SOH	Ford Motor	3R7A	5985	Ferrari Beige	Ferrari	
1302	LOW LUSTER CLEAR	280.6	561.1	1554	TINTING WHITE	188.4	376.8
1557	MAGENTA	399.3	798.6	1559	YELLOW OXIDE	373.2	746.3
1551	INDO YELLOW	422.4	844.7	1550	RED OXIDE	425.6	851.3
1553	FAST BLUE	423.0	845.9	1553	FAST BLUE	434.0	868.0
1501	LANDAU BLACK	423.2	846.4		0		
	0				0		
5979	Tinted Topcoat for 46			5986	Bumper Medium Dark	Honda	NH633M
1300	HIGH GLOSS CLEAR	416.9	833.9	1501	LANDAU BLACK	230.9	461.8
3520	PLATINUM PEARL	425.3	850.5	1508	SILVER	352.9	705.7
	0	425.3	850.5	1551	INDO YELLOW	384.7	769.3
	0			1557	MAGENTA	415.8	831.6
	0						
	0						
	0						

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 175

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
5987	Honda		NH365L	5994	KI Ivory	Honda	YR-239L
1501	LANDAU BLACK	256.1	512.3	1554	TINTING WHITE	269.6	539.2
1557	MAGENTA	338.4	676.7	1550	RED OXIDE	319.4	638.8
1551	INDO YELLOW	414.5	829.0	1551	INDO YELLOW	368.9	737.9
				1303	FLATTENER	415.6	831.3
				1501	LANDAU BLACK	435.9	871.7
				0			
Yes 5988							
5988	Topcoat for 5987			5995	Dark Atlas Gray	Honda	NH-597L
1301	SATIN GLOSS CLEAR	396.1	792.2	1501	LANDAU BLACK	206.5	412.9
1508	SILVER	413.5	827.1	1554	TINTING WHITE	273.0	546.0
				1550	RED OXIDE	323.7	647.4
				1551	INDO YELLOW	372.1	744.2
				1303	FLATTENER	420.5	841.0
				0			
5989	Medium Grayge	Honda	NH-557L	5996	TU Light Beige	Honda	YR309L
1302	LOW LUSTER CLEAR	174.1	348.2	1554	TINTING WHITE	193.0	386.1
1554	TINTING WHITE	293.0	586.1	1559	YELLOW OXIDE	334.6	669.2
1501	LANDAU BLACK	354.1	708.1	1303	FLATTENER	384.4	768.7
1551	INDO YELLOW	392.6	785.2	1550	RED OXIDE	409.4	818.9
1550	RED OXIDE	422.9	845.7	1501	LANDAU BLACK	432.5	865.0
				0			
5990	Light Titanium	Honda	YR-244L	5997	Classy Gray	Honda	NH-264L
1554	TINTING WHITE	193.4	386.9	1501	LANDAU BLACK	240.6	481.2
1302	LOW LUSTER CLEAR	369.8	739.6	1554	TINTING WHITE	295.6	591.1
1501	LANDAU BLACK	395.3	790.5	1557	MAGENTA	342.0	684.0
1551	INDO YELLOW	413.9	827.7	1551	INDO YELLOW	380.6	761.3
1550	RED OXIDE	428.2	856.4	1303	FLATTENER	418.5	837.1
				0			
5991	Graphite Black	Honda	NH-167L	5998	Light Cream Ivory	Honda	YR240L
1501	LANDAU BLACK	225.4	450.8	1554	TINTING WHITE	213.4	426.9
1302	LOW LUSTER CLEAR	354.3	708.6	1559	YELLOW OXIDE	349.1	698.2
1559	YELLOW OXIDE	406.1	812.3	1303	FLATTENER	399.0	798.0
1554	TINTING WHITE	413.6	827.2	1550	RED OXIDE	428.7	857.5
1556	FAST GREEN	415.4	830.8	1553	FAST BLUE	434.0	868.0
0				0			
5992	TU New Beige	Honda	YR308L	5999	QP Light Warm Gray	Honda	NH-686L
1559	YELLOW OXIDE	191.0	382.0	1554	TINTING WHITE	200.8	401.5
1554	TINTING WHITE	288.3	576.6	1559	YELLOW OXIDE	309.8	619.7
1303	FLATTENER	343.9	687.9	1303	FLATTENER	366.2	732.3
1550	RED OXIDE	387.4	774.9	1501	LANDAU BLACK	410.6	821.2
1501	LANDAU BLACK	426.6	853.2	1557	MAGENTA	431.8	863.6
0				0			
5993	Premium Ivory	Honda	YR-372L	6000	TU Warm Gray	Honda	NH574L
1554	TINTING WHITE	244.4	488.7	1501	LANDAU BLACK	128.5	257.0
1559	YELLOW OXIDE	351.5	702.9	1554	TINTING WHITE	244.6	489.3
1303	FLATTENER	408.3	816.6	1551	INDO YELLOW	313.4	626.7
1550	RED OXIDE	429.9	859.8	1550	RED OXIDE	375.6	751.2
1553	FAST BLUE	435.5	871.1	1303	FLATTENER	424.4	848.8
0				0			

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 176

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6001	Premium Black	Honda	NH-690L	6008	Umber Tan	Honda	YR-386L
1501	LANDAU BLACK	208.2	416.4	1559	YELLOW OXIDE	187.7	375.4
1557	MAGENTA	314.3	628.6	1558	BRITE RED	315.0	629.9
1303	FLATTENER	368.3	736.6	1303	FLATTENER	369.4	738.8
1551	INDO YELLOW	404.8	809.7	1551	INDO YELLOW	404.5	809.0
1553	FAST BLUE	413.9	827.8	1501	LANDAU BLACK	417.8	835.7
	0				0		
6002	Moon Lake Gray	Honda	NH-528L	6009	Sienna Beige	Honda	YR-400L
1554	TINTING WHITE	187.9	375.9	1554	TINTING WHITE	185.7	371.4
1559	YELLOW OXIDE	283.7	567.3	1559	YELLOW OXIDE	315.1	630.3
1501	LANDAU BLACK	368.2	736.4	1303	FLATTENER	368.2	736.3
1303	FLATTENER	410.9	821.8	1501	LANDAU BLACK	401.1	802.1
1557	MAGENTA	430.7	861.4	1550	RED OXIDE	431.8	863.6
	0				0		
6003	TU Light Green	Honda	G66L	6010	TU Green	Honda	G65L
1554	TINTING WHITE	234.7	469.4	1550	RED OXIDE	163.0	326.0
1559	YELLOW OXIDE	342.3	684.6	1554	TINTING WHITE	285.9	571.7
1303	FLATTENER	392.3	784.6	1556	FAST GREEN	347.0	693.9
1501	LANDAU BLACK	423.0	846.1	1303	FLATTENER	402.6	805.3
1558	BRITE RED	434.5	868.9	1551	INDO YELLOW	426.8	853.7
	0				0		
6004	Light Tan	Honda	YR167L	6011	Olive	Honda	G64L
1559	YELLOW OXIDE	232.8	465.7	1554	TINTING WHITE	210.4	420.8
1554	TINTING WHITE	351.2	702.4	1559	YELLOW OXIDE	331.4	662.9
1303	FLATTENER	390.2	780.4	1303	FLATTENER	384.6	769.2
1550	RED OXIDE	421.4	842.7	1501	LANDAU BLACK	429.4	858.8
1501	LANDAU BLACK	428.9	857.9	1557	MAGENTA	432.9	865.8
	0				0		
6005	CF Gray	Honda	NH-361L	6012	Clear Gray	Honda	NH-220L
1501	LANDAU BLACK	130.9	261.7	1554	TINTING WHITE	329.5	659.0
1559	YELLOW OXIDE	244.2	488.5	1303	FLATTENER	380.1	760.2
1554	TINTING WHITE	357.1	714.2	1501	LANDAU BLACK	414.6	829.2
1303	FLATTENER	406.0	812.1	1551	INDO YELLOW	430.3	860.5
1557	MAGENTA	425.3	850.6	1557	MAGENTA	439.4	878.9
	0				0		
6006	Porpoise Gray	Honda	NH-425L	6013	Truffle	Honda	NH-767L
1554	TINTING WHITE	263.1	526.2	1554	TINTING WHITE	132.9	265.8
1501	LANDAU BLACK	343.2	686.4	1501	LANDAU BLACK	252.0	504.0
1303	FLATTENER	382.7	765.3	1550	RED OXIDE	331.3	662.7
1551	INDO YELLOW	411.3	822.5	1551	INDO YELLOW	380.5	760.9
1557	MAGENTA	434.4	868.8	1303	FLATTENER	426.1	852.2
	0				0		
6007	Bumper Dark Gray	Honda	NH-533	6014	Pure Blue	Honda	B-135L
1501	LANDAU BLACK	299.1	598.2	1553	FAST BLUE	166.4	332.9
1551	INDO YELLOW	333.8	667.7	1501	LANDAU BLACK	244.6	489.1
1554	TINTING WHITE	366.0	731.9	1557	MAGENTA	321.6	643.1
1557	MAGENTA	397.2	794.4	1554	TINTING WHITE	379.6	759.3
1303	FLATTENER	417.1	834.1	1303	FLATTENER	417.6	835.2
	0				0		

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 177

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6015	Baltic Blue	Honda	B-167L	6022	Dark Titanium	Honda	YR-232L
1501	LANDAU BLACK	244.0	488.0	1554	TINTING WHITE	144.8	289.7
1554	TINTING WHITE	298.9	597.7	1501	LANDAU BLACK	261.1	522.1
1303	FLATTENER	343.7	687.4	1550	RED OXIDE	323.8	647.6
1556	FAST GREEN	384.0	767.9	1551	INDO YELLOW	384.4	768.8
1553	FAST BLUE	418.4	836.8	1303	FLATTENER	426.7	853.4
	0				0		
6016	Bumper Medium Dark	Honda	NH-590	6023	Titanium	Honda	YR-233L
1550	RED OXIDE	104.1	208.2	1554	TINTING WHITE	189.9	379.7
1556	FAST GREEN	202.7	405.4	1559	YELLOW OXIDE	312.9	625.7
1501	LANDAU BLACK	300.6	601.2	1303	FLATTENER	362.5	725.1
1554	TINTING WHITE	346.8	693.6	1501	LANDAU BLACK	406.6	813.2
1302	LOW LUSTER CLEAR	419.7	839.3	1550	RED OXIDE	431.9	863.8
	0				0		
6017	Atlas Gray	Honda	NH-598L	6024	TU Dark Gray	Honda	NH-607L
1554	TINTING WHITE	142.3	284.6	1501	LANDAU BLACK	250.1	500.1
1559	YELLOW OXIDE	247.0	494.0	1303	FLATTENER	298.1	596.3
1501	LANDAU BLACK	330.9	661.8	1554	TINTING WHITE	345.7	691.4
1303	FLATTENER	383.5	767.0	1551	INDO YELLOW	382.1	764.2
1550	RED OXIDE	428.3	856.6	1557	MAGENTA	417.9	835.9
	0				0		
6018	Pearl Ivory	Honda	YR-327L	6025	Seagull Gray	Honda	NH-293L
1554	TINTING WHITE	267.3	534.6	1554	TINTING WHITE	139.2	278.4
1551	INDO YELLOW	334.1	668.2	1559	YELLOW OXIDE	259.1	518.1
1303	FLATTENER	390.8	781.5	1501	LANDAU BLACK	362.4	724.7
1557	MAGENTA	412.8	825.6	1303	FLATTENER	408.2	816.3
1501	LANDAU BLACK	434.5	868.9	1557	MAGENTA	427.5	854.9
	0				0		
6019	Grayge	Honda	NH-556L	6026	Light Quartz Gray	Honda	NH-284L
1554	TINTING WHITE	314.2	628.4	1554	TINTING WHITE	231.0	462.0
1303	FLATTENER	368.1	736.1	1501	LANDAU BLACK	308.8	617.6
1501	LANDAU BLACK	396.1	792.2	1550	RED OXIDE	369.6	739.2
1550	RED OXIDE	420.8	841.7	1303	FLATTENER	409.0	817.9
1551	INDO YELLOW	438.8	877.5	1551	INDO YELLOW	433.3	866.6
	0				0		
6020	Pale Quartz	Honda	NH-302L	6027	Quartz Gray	Honda	NH-283L
1554	TINTING WHITE	328.4	656.8	1501	LANDAU BLACK	171.6	343.1
1303	FLATTENER	375.6	751.1	1554	TINTING WHITE	279.8	559.6
1550	RED OXIDE	403.4	806.8	1550	RED OXIDE	350.6	701.3
1501	LANDAU BLACK	429.7	859.3	1303	FLATTENER	399.4	798.8
1551	INDO YELLOW	440.0	880.0	1551	INDO YELLOW	424.1	848.2
	0				0		
6021	Bright Ivory	Honda	YR-412L	6028	Dark Saddle	Honda	YR202L
1554	TINTING WHITE	247.1	494.2	1550	RED OXIDE	111.1	222.1
1559	YELLOW OXIDE	377.6	755.2	1551	INDO YELLOW	213.1	426.1
1303	FLATTENER	424.3	848.6	1501	LANDAU BLACK	294.9	589.9
1501	LANDAU BLACK	431.9	863.7	1554	TINTING WHITE	373.9	747.8
1557	MAGENTA	435.9	871.8	1303	FLATTENER	422.5	845.0
	0				0		

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 178

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6029	Saddle	Honda	YR203L	6034	Dk. Frost Beige	Chrysler Motors	HL9
1554	TINTING WHITE	159.9	319.8	1557	MAGENTA	135.1	270.3
1550	RED OXIDE	257.9	515.8	1302	LOW LUSTER CLEAR	253.3	506.5
1551	INDO YELLOW	339.4	678.8	1551	INDO YELLOW	338.8	677.5
1303	FLATTENER	388.7	777.4	1556	FAST GREEN	378.6	757.2
1501	LANDAU BLACK	428.4	856.8	1559	YELLOW OXIDE	413.7	827.4
	0						
6030	Light Saddle	Honda	YR204L	6035	Adobe	Ford Motor	AT7A
1559	YELLOW OXIDE	163.2	326.4	1554	TINTING WHITE	159.1	318.3
1554	TINTING WHITE	317.8	635.6	1559	YELLOW OXIDE	302.9	605.7
1303	FLATTENER	367.3	734.6	1302	LOW LUSTER CLEAR	388.8	777.6
1550	RED OXIDE	409.0	818.0	1550	RED OXIDE	416.6	833.3
1501	LANDAU BLACK	430.4	860.8	1501	LANDAU BLACK	429.7	859.4
	0						
6031	Beige	Volkswagon		6036	Sienna	Ford Motor	8U8A
1554	TINTING WHITE	229.5	459.0	1302	LOW LUSTER CLEAR	156.6	313.2
1302	LOW LUSTER CLEAR	353.1	706.1	1559	YELLOW OXIDE	247.2	494.4
1559	YELLOW OXIDE	408.5	817.1	1501	LANDAU BLACK	335.1	670.2
1550	RED OXIDE	421.3	842.6	1550	RED OXIDE	407.9	815.7
1501	LANDAU BLACK	432.6	865.2	1554	TINTING WHITE	417.5	835.1
6031	Beige	Volkswagon		6038	Dark Slate Gray Meta	Ford Motor	AM6E
1554	TINTING WHITE	229.5	459.0	1300	HIGH GLOSS CLEAR	138.4	276.9
1302	LOW LUSTER CLEAR	353.1	706.2	1501	LANDAU BLACK	248.2	496.4
1559	YELLOW OXIDE	408.5	817.0	1508	SILVER	324.0	647.9
1550	RED OXIDE	421.3	842.6	1559	YELLOW OXIDE	371.3	742.5
1501	LANDAU BLACK	432.6	865.2	1552	FAST RED	403.6	807.3
				1553	FAST BLUE	415.3	830.6
6032	Rust Red	Volkswagon		6040	Turquoise	Pontiac	
1550	RED OXIDE	222.2	444.4	1508	SILVER	183.4	366.8
1302	LOW LUSTER CLEAR	352.5	705.0	1556	FAST GREEN	286.4	572.7
1559	YELLOW OXIDE	411.3	822.5	1553	FAST BLUE	385.7	771.5
1554	TINTING WHITE	416.0	832.1	1501	LANDAU BLACK	415.6	831.1
1501	LANDAU BLACK	419.8	839.6				
6032	Rust Red	Volkswagon		6040	Turquoise	Pontiac	
1550	RED OXIDE	222.2	444.4	1508	SILVER	183.4	366.8
1302	LOW LUSTER CLEAR	352.5	705.0	1556	FAST GREEN	286.4	572.8
1559	YELLOW OXIDE	411.3	822.5	1553	FAST BLUE	385.7	771.4
1554	TINTING WHITE	416.0	832.1	1501	LANDAU BLACK	415.6	831.2
1501	LANDAU BLACK	419.8	839.6				
6033	Light Grey	Nissan	W	6041	Dune	General Motors	WA514Q
1554	TINTING WHITE	290.4	580.8	1302	LOW LUSTER CLEAR	158.9	317.8
1559	YELLOW OXIDE	385.4	770.9	1554	TINTING WHITE	285.7	571.4
1501	LANDAU BLACK	414.8	829.7	1551	INDO YELLOW	334.8	669.5
1550	RED OXIDE	439.4	878.9	1501	LANDAU BLACK	381.5	763.0
				1550	RED OXIDE	423.8	847.6

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 179

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
6043	Dark Gray	Nissan		G	6061	Walnut Extended Kan	BMW	PASY
1501	LANDAU BLACK	169.8	339.6		1559	YELLOW OXIDE	210.1	420.2
1559	YELLOW OXIDE	316.1	632.2		1302	LOW LUSTER CLEAR	382.3	764.6
1554	TINTING WHITE	354.5	708.9		1550	RED OXIDE	413.5	826.9
1302	LOW LUSTER CLEAR	392.8	785.5		1551	INDO YELLOW	416.8	833.6
1550	RED OXIDE	421.1	842.2		1553	FAST BLUE	418.2	836.4
6044	Medium Frost Beige	Chrysler Motors		HL5	6062	Beige Extended Kansa	BMW	PACY
1302	LOW LUSTER CLEAR	158.1	316.1		1302	LOW LUSTER CLEAR	176.2	352.5
1559	YELLOW OXIDE	291.8	583.5		1554	TINTING WHITE	350.7	701.4
1554	TINTING WHITE	351.4	702.8		1559	YELLOW OXIDE	408.9	817.7
1550	RED OXIDE	388.1	776.3		1550	RED OXIDE	424.6	849.2
1501	LANDAU BLACK	421.4	842.9		1553	FAST BLUE	428.0	856.0
6046	Caramel	Ford Motor			6063	Beige Dakota Leather	BMW	LCB4
1559	YELLOW OXIDE	281.4	562.9		1302	LOW LUSTER CLEAR	174.7	349.5
1302	LOW LUSTER CLEAR	365.7	731.4		1559	YELLOW OXIDE	286.2	572.4
1550	RED OXIDE	409.0	818.1		1554	TINTING WHITE	397.6	795.2
1554	TINTING WHITE	416.5	833.0		1550	RED OXIDE	415.3	830.7
1501	LANDAU BLACK	421.3	842.6		1501	LANDAU BLACK	424.4	848.8
6057	Taupe Leatherette	BMW		KAAS	6064	Chestnut Brown Dako	BMW	LCC2
1554	TINTING WHITE	151.8	303.7		1302	LOW LUSTER CLEAR	170.7	341.4
1302	LOW LUSTER CLEAR	294.3	588.5		1551	INDO YELLOW	260.2	520.4
1559	YELLOW OXIDE	374.3	748.6		1550	RED OXIDE	343.8	687.5
1501	LANDAU BLACK	401.5	802.9		1557	MAGENTA	409.6	819.1
1550	RED OXIDE	427.3	854.6		1556	FAST GREEN	414.5	829.1
6058	Coral Red Extended K	BMW		PAD1	6065	Black Extended Kansa	BMW	PASW
1558	BRITE RED	195.3	390.5		1501	LANDAU BLACK	243.2	486.3
1302	LOW LUSTER CLEAR	350.1	700.2		1302	LOW LUSTER CLEAR	413.4	826.8
1552	FAST RED	382.3	764.7					
1551	INDO YELLOW	409.8	819.7					
1501	LANDAU BLACK	412.8	825.7					
6059	Oyster and Black	BMW		LCCX	6080	Blue Standard	General Motors	715
1302	LOW LUSTER CLEAR	176.1	352.2		1553	FAST BLUE	132.8	265.6
1554	TINTING WHITE	345.8	691.6		1300	HIGH GLOSS CLEAR	229.1	458.2
1559	YELLOW OXIDE	398.1	796.3		1501	LANDAU BLACK	315.8	631.6
1550	RED OXIDE	421.2	842.4		1554	TINTING WHITE	370.8	741.6
1553	FAST BLUE	427.7	855.3		1556	FAST GREEN	417.4	834.8
6060	Walnut Kansas Leath	BMW		LYSY	6081	Light Blue Metallic	General Motors	M12
1559	YELLOW OXIDE	210.1	420.2		1300	HIGH GLOSS CLEAR	223.7	447.3
1302	LOW LUSTER CLEAR	382.3	764.6		1554	TINTING WHITE	300.3	600.6
1550	RED OXIDE	413.5	826.9		1553	FAST BLUE	353.3	706.6
1551	INDO YELLOW	416.8	833.6		3520	PLATINUM PEARL	398.0	796.0
1553	FAST BLUE	418.2	836.4		1501	LANDAU BLACK	423.6	847.2
					1551	INDO YELLOW	431.6	863.2

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 180

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

	Tan	Chrysler Motors	GT5
6086			
1302	LOW LUSTER CLEAR	158.6	317.3
1559	YELLOW OXIDE	316.9	633.9
1554	TINTING WHITE	394.6	789.3
1550	RED OXIDE	416.8	833.6
1501	LANDAU BLACK	423.0	846.0
No			

	Pastel Greystone	Chrysler Motors	HDA
6129			
1554	TINTING WHITE	316.8	633.6
1303	FLATTENER	374.1	748.2
1559	YELLOW OXIDE	420.3	840.7
1501	LANDAU BLACK	432.1	864.1
1550	RED OXIDE	439.6	879.1
No			

	Lt Frost Beige	Chrysler Motors	HL1
6087			
1554	TINTING WHITE	194.5	389.0
1302	LOW LUSTER CLEAR	355.3	710.5
1551	INDO YELLOW	385.9	771.7
1550	RED OXIDE	410.4	820.9
1501	LANDAU BLACK	428.6	857.3
No			

	Ivory	Chrysler Motors	JW4
6131			
1554	TINTING WHITE	233.9	467.9
1302	LOW LUSTER CLEAR	387.2	774.4
1559	YELLOW OXIDE	422.2	844.5
1501	LANDAU BLACK	428.0	855.9
1552	FAST RED	432.0	863.9
No			

	Lt Frost	Chrysler Motors	HL1
6087			
1554	TINTING WHITE	194.5	389.0
1302	LOW LUSTER CLEAR	355.3	710.5
1551	INDO YELLOW	385.9	771.7
1550	RED OXIDE	410.4	820.9
1501	LANDAU BLACK	428.6	857.3
No			

	Chestnut	Chrysler Motors	JTL
6132			
1559	YELLOW OXIDE	176.2	352.3
1302	LOW LUSTER CLEAR	348.3	696.6
1550	RED OXIDE	405.6	811.3
1501	LANDAU BLACK	414.7	829.4
1551	INDO YELLOW	418.1	836.1
No			

	Moss Green	General Motors	721
6109			
1559	YELLOW OXIDE	315.0	630.0
1554	TINTING WHITE	365.4	730.8
1556	FAST GREEN	386.4	772.8
1508	SILVER	407.4	814.8
1501	LANDAU BLACK	425.3	850.6
MUST TOPCOAT WITH 6110			

	Meteorite Black	Ford Motor	BA9E
6134			
1501	LANDAU BLACK	151.7	303.4
1552	FAST RED	248.6	497.2
1302	LOW LUSTER CLEAR	344.1	688.2
1556	FAST GREEN	394.2	788.5
1508	SILVER	413.9	827.7
No			

	Topcoat For 6109	General Motors	721
6110			
1302	LOW LUSTER CLEAR	404.2	808.4
3520	PLATINUM PEARL	409.8	819.6
3522	GOLD PEARL	413.0	826.0
No			

	Enhanced Alloy Metal	Ford Motor	9N9C
6135			
1501	LANDAU BLACK	241.8	483.6
1508	SILVER	321.3	642.6
1552	FAST RED	381.3	762.6
1556	FAST GREEN	415.4	830.8
No			

	Radar Red	Chrysler Motors	RR
6127			
1552	FAST RED	155.4	310.8
1302	LOW LUSTER CLEAR	310.3	620.7
1558	BRITE RED	405.1	810.1
1554	TINTING WHITE	409.7	819.5
1501	LANDAU BLACK	413.2	826.4
No			

	Torque Grey	Ford Motor	5MW
6136			
1501	LANDAU BLACK	160.2	320.4
1302	LOW LUSTER CLEAR	290.5	581.1
1554	TINTING WHITE	369.8	739.5
1551	INDO YELLOW	403.8	807.7
1550	RED OXIDE	420.0	840.0
No			

	Dark Saddle	Chrysler Motors	T9
6128			
1559	YELLOW OXIDE	299.9	599.8
1303	FLATTENER	354.8	709.7
1557	MAGENTA	393.5	787.0
1501	LANDAU BLACK	412.8	825.6
1554	TINTING WHITE	421.0	842.0
No			

	Dark Pewter	Ford Motor	6DEA
6137			
1302	LOW LUSTER CLEAR	176.4	352.8
1550	RED OXIDE	287.8	575.7
1553	FAST BLUE	340.7	681.3
1556	FAST GREEN	387.4	774.8
1554	TINTING WHITE	417.3	834.7
No			

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 181

PINTS	QUARTS
GRAMS	

PINTS	QUARTS
GRAMS	

6142	Pecan	Ford Motor	BT6
1302	LOW LUSTER CLEAR	177.6	355.2
1551	INDO YELLOW	322.3	644.6
1550	RED OXIDE	394.2	788.4
1501	LANDAU BLACK	414.4	828.7

6167	Saddle	Pontiac	
1559	YELLOW OXIDE	236.1	472.2
1302	LOW LUSTER CLEAR	318.8	637.5
1550	RED OXIDE	378.3	756.5
1554	TINTING WHITE	401.4	802.8
1501	LANDAU BLACK	421.9	843.9

6161	Butterscotch	Datson	
1559	YELLOW OXIDE	289.3	578.6
1302	LOW LUSTER CLEAR	373.5	747.0
1550	RED OXIDE	415.2	830.5
1554	TINTING WHITE	421.0	841.9
1501	LANDAU BLACK	421.3	842.6

6169	Dark Blue	Pontiac	201
1553	FAST BLUE	148.4	296.7
1302	LOW LUSTER CLEAR	286.6	573.2
1556	FAST GREEN	343.7	687.4
1501	LANDAU BLACK	380.8	761.6
1554	TINTING WHITE	415.1	830.2

6162	Dk. Rose	Ford Motor	
1552	FAST RED	249.0	497.9
1508	SILVER	347.8	695.6
1551	INDO YELLOW	381.0	762.0
1553	FAST BLUE	409.6	819.2
1501	LANDAU BLACK	414.9	829.7

6170	Turquoise	Ford Motor	7X
1554	TINTING WHITE	256.3	512.5
1556	FAST GREEN	397.4	794.9
1550	RED OXIDE	428.6	857.2
1553	FAST BLUE	434.6	869.3
		434.6	869.3

6163	LT. Rose	Ford Motor	
1508	SILVER	250.9	501.8
1550	RED OXIDE	355.9	711.8
1552	FAST RED	411.0	822.0
1551	INDO YELLOW	430.8	861.6

6172	Dark Camel	Pontiac	62
1559	YELLOW OXIDE	278.4	556.8
1302	LOW LUSTER CLEAR	362.5	725.0
1557	MAGENTA	399.8	799.6
1501	LANDAU BLACK	410.3	820.6
1554	TINTING WHITE	420.4	840.9

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

6164	BF Red	Ford Motor	BF
1552	FAST RED	250.5	501.0
1551	INDO YELLOW	339.6	679.2
1302	LOW LUSTER CLEAR	409.2	818.4
1554	TINTING WHITE	426.2	852.4

6173	Green	Cessna	Aerospace
1559	YELLOW OXIDE	179.1	358.2
1553	FAST BLUE	299.0	598.0
1302	LOW LUSTER CLEAR	368.8	737.6
1501	LANDAU BLACK	396.8	793.6
1554	TINTING WHITE	418.8	837.6

6165	Chantilly Beige	Ford Motor	
1508	SILVER	215.0	430.0
1559	YELLOW OXIDE	381.0	762.0
1550	RED OXIDE	418.5	837.0
1501	LANDAU BLACK	432.5	865.0

6174	Champagne Metallic	Fiat	512F
1554	TINTING WHITE	145.5	291.1
1302	LOW LUSTER CLEAR	278.2	556.5
1559	YELLOW OXIDE	405.9	811.7
1550	RED OXIDE	418.1	836.2
1501	LANDAU BLACK	427.6	855.2

MUST TOP COAT WITH 1300 HIGH GLOSS CLEAR

6166	Blue	General Motors	
1554	TINTING WHITE	183.7	367.4
1553	FAST BLUE	301.6	603.2
1559	YELLOW OXIDE	385.6	771.1
1501	LANDAU BLACK	429.8	859.7

6175	Blue	Ford Motor	M6
1554	TINTING WHITE	190.0	379.9
1302	LOW LUSTER CLEAR	300.9	601.8
1501	LANDAU BLACK	366.3	732.6
1553	FAST BLUE	427.1	854.2
1551	INDO YELLOW	427.9	855.9

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 182

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6176	Dark Blue	General Motors	725	6183	Brown	Chrysler Motors	KUH
1672	LOW LUSTER CLEAR	162.1	324.1	1551	INDO YELLOW	161.6	323.3
1653	THALO BLUE	282.8	565.6	1557	MAGENTA	297.9	595.8
1656	THALO GREEN	377.2	754.3	1303	FLATTENER	352.0	703.9
1601	BLACK	441.0	882.1	1559	YELLOW OXIDE	404.6	809.1
1654	WHITE	486.2	972.3	1556	FAST GREEN	414.5	829.1
6177	Biscuit	Jaguar	XJ9	6184	Jeep Brown	Chrysler Motors	LU5
1654	WHITE	192.0	383.9	1558	BRITE RED	185.3	370.6
1672	LOW LUSTER CLEAR	357.4	714.9	1501	LANDAU BLACK	355.3	710.7
1651	INDO YELLOW	443.2	886.4	1303	FLATTENER	414.0	827.9
1652	QUINDO RED	486.5	973.0				
1601	BLACK	496.4	992.9				
6178	Black	Chrysler Motors	JXW	6185	Ruby Red	Chrysler Motors	LR5
1501	LANDAU BLACK	360.4	720.9	1558	BRITE RED	257.1	514.3
1303	FLATTENER	414.5	829.0	1557	MAGENTA	332.5	665.0
				1303	FLATTENER	386.3	772.5
				1559	YELLOW OXIDE	409.5	819.0
				1501	LANDAU BLACK	414.0	827.9
6179	Gucci White	Chrysler Motors	KW2	6186	Black Berry	General Motors	246V
1554	TINTING WHITE	402.2	804.4	1557	MAGENTA	121.3	242.5
1303	FLATTENER	442.6	885.3	1550	RED OXIDE	220.4	440.9
1559	YELLOW OXIDE	444.9	889.7	1553	FAST BLUE	297.1	594.2
1553	FAST BLUE	445.0	890.1	1559	YELLOW OXIDE	362.4	724.8
1552	FAST RED	445.2	890.3	1303	FLATTENER	416.8	833.6
6180	Steam	Chrysler Motors	LW9	6187	Kalahari	General Motors	119X
1554	TINTING WHITE	387.0	774.0	1559	YELLOW OXIDE	243.8	487.6
1303	FLATTENER	427.4	854.8	1550	RED OXIDE	333.5	666.9
1559	YELLOW OXIDE	441.3	882.7	1303	FLATTENER	388.4	776.8
1501	LANDAU BLACK	443.6	887.2	1551	INDO YELLOW	413.7	827.5
1557	MAGENTA	444.2	888.5	1501	LANDAU BLACK	421.1	842.3
6181	Wine	Chrysler Motors	KC9	6188	Redline	General Motors	124X
1552	FAST RED	360.3	720.6	1558	BRITE RED	187.0	374.0
1303	FLATTENER	397.1	794.3	1559	YELLOW OXIDE	299.3	598.6
1557	MAGENTA	406.0	811.9	1557	MAGENTA	360.0	720.1
1553	FAST BLUE	411.2	822.5	1303	FLATTENER	414.3	828.6
1554	TINTING WHITE	413.8	827.6	1556	FAST GREEN	416.0	832.0
6182	Diesel Gray	Chrysler Motors	A8	6189	Sangria	General Motors	173X
1501	LANDAU BLACK	129.9	259.8	1552	FAST RED	194.5	389.1
1559	YELLOW OXIDE	249.4	498.8	1559	YELLOW OXIDE	268.1	536.3
1554	TINTING WHITE	328.7	657.4	1557	MAGENTA	335.3	670.5
1303	FLATTENER	399.1	798.3	1303	FLATTENER	389.4	778.8
1557	MAGENTA	422.7	845.3	1553	FAST BLUE	415.0	830.0

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 183

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6190	Med Ash Gray	General Motors	9883	6197	Choccachino	General Motors	WA923T
1554	TINTING WHITE	275.1	550.3	1559	YELLOW OXIDE	296.2	592.4
1501	LANDAU BLACK	335.4	670.8	1303	FLATTENER	351.2	702.4
1303	FLATTENER	392.2	784.4	1557	MAGENTA	391.6	783.1
1550	RED OXIDE	417.5	835.0	1554	TINTING WHITE	412.3	824.5
1551	INDO YELLOW	435.8	871.6	1553	FAST BLUE	421.8	843.6
6191	Dk Atmosphere	General Motors	303X	6198	Spice Red	General Motors	WA771S
1554	TINTING WHITE	130.5	261.1	1557	MAGENTA	155.3	310.5
1501	LANDAU BLACK	242.4	484.8	1550	RED OXIDE	303.0	606.0
1550	RED OXIDE	311.7	623.5	1303	FLATTENER	357.5	715.0
1551	INDO YELLOW	370.1	740.2	1559	YELLOW OXIDE	405.3	810.5
1303	FLATTENER	425.6	851.2	1501	LANDAU BLACK	417.8	835.6
6192	Grey Leather	Toyota		6199	New Saddle	Chrysler Motors	TL
1554	TINTING WHITE	198.8	397.6	1559	YELLOW OXIDE	251.3	502.7
1559	YELLOW OXIDE	279.1	558.3	1552	FAST RED	362.5	725.0
1501	LANDAU BLACK	356.9	713.8	1303	FLATTENER	400.6	801.2
1303	FLATTENER	413.2	826.4	1551	INDO YELLOW	410.0	820.0
1550	RED OXIDE	431.5	863.1	1556	FAST GREEN	419.4	838.7
6193	Bisque	Toyota		6199	Chestnut	Chrysler Motors	TL
1554	TINTING WHITE	311.8	623.6	1559	YELLOW OXIDE	251.3	502.7
1303	FLATTENER	358.8	717.6	1552	FAST RED	362.5	725.0
1551	INDO YELLOW	388.6	777.3	1303	FLATTENER	400.6	801.2
1501	LANDAU BLACK	416.7	833.4	1551	INDO YELLOW	410.0	820.0
1550	RED OXIDE	438.6	877.1	1556	FAST GREEN	419.4	838.7
6194	Dark Grey	Toyota		6200	Turquoise	Ford Motor	XM
1559	YELLOW OXIDE	138.9	277.9	1554	TINTING WHITE	264.8	529.5
1501	LANDAU BLACK	274.0	548.1	1556	FAST GREEN	351.4	702.8
1554	TINTING WHITE	343.0	686.0	1553	FAST BLUE	417.7	835.3
1303	FLATTENER	398.2	796.4	1501	LANDAU BLACK	434.0	868.0
1550	RED OXIDE	423.0	846.0	1551	INDO YELLOW	434.4	868.8
6195	Dark Charcoal	Toyota		6201	Radiant Turquoise	Ford Motor	34
1501	LANDAU BLACK	351.8	703.6	1508	SILVER	278.0	556.0
1303	FLATTENER	406.0	811.9	1556	FAST GREEN	400.1	800.3
1554	TINTING WHITE	415.2	830.4	1553	FAST BLUE	416.8	833.7
6196	Cream Beige	Mercedes Benz	8412	6202	White	Mastercraft	693078
1559	YELLOW OXIDE	153.4	306.8	1554	TINTING WHITE	444.7	889.5
1554	TINTING WHITE	279.6	559.2	1501	LANDAU BLACK	446.7	893.4
1302	LOW LUSTER CLEAR	401.5	803.1	1551	INDO YELLOW	448.0	896.0
1550	RED OXIDE	421.1	842.2	1550	RED OXIDE	448.7	897.5
1553	FAST BLUE	426.9	853.7				

Yes (SEM# 6205)

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 184

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6203	Dove	Mastercraft	693081	6210	Carmel	Chrysler Motors	LK5
1554	TINTING WHITE	431.7	863.3	1559	YELLOW OXIDE	304.0	608.1
1550	RED OXIDE	438.8	877.6	1303	FLATTENER	374.1	748.2
1501	LANDAU BLACK	444.9	889.7	1552	FAST RED	417.7	835.4
1551	INDO YELLOW	447.9	895.7	1553	FAST BLUE	420.3	840.7
Yes (SEM# 6205)							
6204	Flint	Mastercraft	693084	6211	Onyx	General Motors	WA355N
1554	TINTING WHITE	353.3	706.5	1501	LANDAU BLACK	274.6	549.2
1501	LANDAU BLACK	403.9	807.7	1303	FLATTENER	343.9	687.9
1550	RED OXIDE	428.0	856.0	1559	YELLOW OXIDE	405.1	810.3
1551	INDO YELLOW	442.2	884.5	1550	RED OXIDE	411.5	823.0
				1554	TINTING WHITE	416.1	832.1
Yes (SEM# 6205)							
6205	Tinted Topcoat(SEM#	Mastercraft		6212	Cognac	Chrysler Motors	KT9
1300	HIGH GLOSS CLEAR	405.9	811.8	1550	RED OXIDE	198.0	395.9
3520	PLATINUM PEARL	414.0	828.1	1551	INDO YELLOW	340.1	680.2
				1303	FLATTENER	394.6	789.3
				1501	LANDAU BLACK	418.1	836.2
						418.1	836.2
6206	Sepia	Chrysler Motors	LV5	6213	Steam	Chrysler Motors	LW9
1302	LOW LUSTER CLEAR	185.1	370.3	1554	TINTING WHITE	379.5	758.9
1559	YELLOW OXIDE	307.0	614.1	1303	FLATTENER	437.3	874.5
1551	INDO YELLOW	360.1	720.3	1551	INDO YELLOW	440.1	880.2
1550	RED OXIDE	411.6	823.2	1501	LANDAU BLACK	442.1	884.2
1501	LANDAU BLACK	416.6	833.2	1550	RED OXIDE	443.2	886.5
6207	Sandstorm	Chrysler Motors	LTU	6214	Camel	Acura	D
1302	LOW LUSTER CLEAR	186.7	373.4	1559	YELLOW OXIDE	252.3	504.7
1559	YELLOW OXIDE	290.4	580.8	1554	TINTING WHITE	347.2	694.4
1554	TINTING WHITE	388.4	776.7	1303	FLATTENER	386.1	772.1
1550	RED OXIDE	409.7	819.4	1550	RED OXIDE	419.0	838.0
1501	LANDAU BLACK	423.2	846.3	1501	LANDAU BLACK	427.6	855.1
6208	Russet Red	Chrysler Motors	JER	6215	Dk Ash Gray	General Motors	WA999K
1302	LOW LUSTER CLEAR	163.6	327.3	1554	TINTING WHITE	162.1	324.3
1551	INDO YELLOW	287.5	575.0	1559	YELLOW OXIDE	267.0	534.0
1550	RED OXIDE	403.0	806.1	1501	LANDAU BLACK	361.0	722.0
1556	FAST GREEN	415.4	830.8	1303	FLATTENER	400.0	800.1
				1550	RED OXIDE	429.6	859.3
6209	Mink	General Motors	WA210V	6216	Twilight Blue	General Motors	WA712U
1550	RED OXIDE	192.6	385.2	1501	LANDAU BLACK	140.1	280.2
1559	YELLOW OXIDE	316.8	633.6	1552	FAST RED	245.5	491.0
1553	FAST BLUE	376.7	753.3	1553	FAST BLUE	323.1	646.3
1303	FLATTENER	414.9	829.8	1554	TINTING WHITE	380.2	760.3
1556	FAST GREEN	420.6	841.2	1303	FLATTENER	418.2	836.3

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 185

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6217	Saddle Up	General Motors	WA859T	6224	Ultimate Mystic White	Bentley	V2706600
1550	RED OXIDE	183.4	366.9	1554	TINTING WHITE	268.7	537.5
1551	INDO YELLOW	298.4	596.7	1302	LOW LUSTER CLEAR	431.4	862.9
1554	TINTING WHITE	355.1	710.1	1559	YELLOW OXIDE	433.4	866.8
1303	FLATTENER	393.5	786.9	1552	FAST RED	433.7	867.5
1501	LANDAU BLACK	422.3	844.7	1553	FAST BLUE	433.9	867.7
6218	Fig	General Motors	WA193V	6225	Prodigy Cream	Bentley	V2575500
1552	FAST RED	254.4	508.7	1554	TINTING WHITE	238.5	477.0
1559	YELLOW OXIDE	311.1	622.2	1559	YELLOW OXIDE	362.7	725.4
1303	FLATTENER	365.2	730.3	1303	FLATTENER	402.3	804.6
1553	FAST BLUE	407.9	815.7	1550	RED OXIDE	429.1	858.2
1551	INDO YELLOW	414.6	829.3	1556	FAST GREEN	435.7	871.5
6219	Mojave	General Motors	WA955T	6227	Honey Beige	General Motors	448
1559	YELLOW OXIDE	267.7	535.4	1554	TINTING WHITE	424.1	848.2
1303	FLATTENER	323.0	646.1	1559	YELLOW OXIDE	444.9	889.8
1550	RED OXIDE	376.0	751.9	1551	INDO YELLOW	447.4	894.7
1554	TINTING WHITE	422.2	844.3	1553	FAST BLUE	447.6	895.1
1553	FAST BLUE	424.4	848.8				
6220	Orion Gray	Mercedes Benz	268	TOPCOAT WITH 1300 CLEAR			
1554	TINTING WHITE	265.7	531.4	6228	Light Ash Gray	General Motors	WA9874
1501	LANDAU BLACK	351.0	702.1	1554	TINTING WHITE	264.4	528.7
1303	FLATTENER	390.5	781.1	1550	RED OXIDE	360.9	721.8
1551	INDO YELLOW	420.0	840.0	1303	FLATTENER	400.6	801.1
1557	MAGENTA	434.6	869.3	1556	FAST GREEN	435.4	870.8
				1551	INDO YELLOW	436.5	873.0
6221	Silvertex Champagne	Bentley	V2704400	6229	Medium Urban	General Motors	WA845T
1559	YELLOW OXIDE	204.3	408.6	1554	TINTING WHITE	210.7	421.4
1554	TINTING WHITE	401.1	802.2	1559	YELLOW OXIDE	339.8	679.5
1550	RED OXIDE	428.8	857.7	1303	FLATTENER	379.2	758.4
1553	FAST BLUE	434.6	869.1	1501	LANDAU BLACK	415.6	831.3
				1550	RED OXIDE	433.6	867.1
TOPCOAT WITH 6222							
6222	Topcoat for 6221	Bentley		6230	Vy Lt Platinum	General Motors	WA834T
1302	LOW LUSTER CLEAR	405.2	810.5	1554	TINTING WHITE	356.6	713.1
3520	PLATINUM PEARL	413.5	827.0	1303	FLATTENER	396.7	793.5
				1501	LANDAU BLACK	413.8	827.5
				1551	INDO YELLOW	430.1	860.2
				1550	RED OXIDE	441.9	883.7
6223	Brilliant White Pegasus	Bentley	V2706500	6231	Dk Urban	General Motors	WA844T
1554	TINTING WHITE	264.5	529.0	1554	TINTING WHITE	194.5	389.0
1302	LOW LUSTER CLEAR	427.1	854.2	1501	LANDAU BLACK	282.7	565.5
1559	YELLOW OXIDE	432.1	864.2	1551	INDO YELLOW	347.1	694.3
1550	RED OXIDE	433.2	866.3	1550	RED OXIDE	391.0	782.0
1553	FAST BLUE	433.6	867.2	1303	FLATTENER	430.1	860.2

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 186

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6232		General Motors		77	6242	KI Taupe	
1559	YELLOW OXIDE	173.6	347.2		1551	INDO YELLOW	106.5
1302	LOW LUSTER CLEAR	338.0	675.9		1501	LANDAU BLACK	208.9
1554	TINTING WHITE	394.2	788.4		1550	RED OXIDE	290.8
1550	RED OXIDE	415.1	830.2		1554	TINTING WHITE	366.6
1501	LANDAU BLACK	421.6	843.2		1303	FLATTENER	421.6
6233	Lt Aqua	Ford Motor		87	6243	Burgandy Brown	
1302	LOW LUSTER CLEAR	166.7	333.4		1559	YELLOW OXIDE	177.6
1554	TINTING WHITE	275.8	551.6		1557	MAGENTA	268.8
1559	YELLOW OXIDE	361.4	722.7		1501	LANDAU BLACK	329.5
1553	FAST BLUE	401.9	803.8		1303	FLATTENER	384.1
1501	LANDAU BLACK	423.1	846.3		1550	RED OXIDE	418.4
6237	Light Brown	Mercedes Benz		274A	6244	Dark Lapis	
1559	YELLOW OXIDE	290.8	581.6		1501	LANDAU BLACK	254.6
1554	TINTING WHITE	352.2	704.4		1554	TINTING WHITE	331.7
1303	FLATTENER	390.8	781.7		1303	FLATTENER	386.6
1557	MAGENTA	419.0	838.1		1553	FAST BLUE	408.1
1553	FAST BLUE	425.0	850.0		1551	INDO YELLOW	420.2
6238	Lt. Nugget Gold	Ford Motor		6Y	6245	Jewel Blue	
1508	SILVER	150.5	301.0		1501	LANDAU BLACK	153.7
1302	LOW LUSTER CLEAR	288.7	577.4		1553	FAST BLUE	249.9
1551	INDO YELLOW	348.4	696.8		1550	RED OXIDE	322.5
1558	BRITE RED	406.0	811.9		1303	FLATTENER	377.1
1556	FAST GREEN	414.6	829.2		1554	TINTING WHITE	418.4
6239	Earth Taupe	Honda		YR-325L	6246	Metallic Blue	
1551	INDO YELLOW	112.7	225.4		1508	SILVER	225.3
1554	TINTING WHITE	206.5	413.0		1553	FAST BLUE	373.2
1501	LANDAU BLACK	297.0	594.1		1556	FAST GREEN	415.7
1550	RED OXIDE	367.6	735.2				
1303	FLATTENER	422.7	845.4				
6240	Surf Blue	Honda		B137L	TOPCOAT WITH FORMULA 6247		
1554	TINTING WHITE	122.5	244.9		6247	Topcoat for 6246	
1501	LANDAU BLACK	243.7	487.4		1301	SATIN GLOSS CLEAR	412.2
1553	FAST BLUE	357.1	714.3		3520	PLATINUM PEARL	413.8
1303	FLATTENER	395.6	791.2				
1557	MAGENTA	423.0	846.1				
6241	Oasis Blue	Honda		B-138L	6248	Turquoise	
1554	TINTING WHITE	358.2	716.4		1554	TINTING WHITE	276.7
1303	FLATTENER	398.4	796.7		1556	FAST GREEN	388.1
1501	LANDAU BLACK	434.3	868.5		1553	FAST BLUE	431.4
1550	RED OXIDE	438.3	876.6		1501	LANDAU BLACK	435.4
1551	INDO YELLOW	441.9	883.7				

TOPCOAT WITH 1300 CLEAR

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 187

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6249	Truffle	Rolex Vans		6256	Light Jewel Gray	Honda NH-802L	
1302	LOW LUSTER CLEAR	141.5	283.0	1554	TINTING WHITE	299.2	598.5
1554	TINTING WHITE	274.9	549.8	1303	FLATTENER	356.2	712.5
1501	LANDAU BLACK	352.3	704.6	1501	LANDAU BLACK	400.0	800.0
1550	RED OXIDE	395.7	791.5	1551	INDO YELLOW	424.3	848.7
1551	INDO YELLOW	424.6	849.1	1557	MAGENTA	437.0	874.1
6250	Gray	Honda 8142M		6257	Kurdi Black	Chrysler Motors JXP	
1554	TINTING WHITE	152.7	305.5	1302	LOW LUSTER CLEAR	138.2	276.4
1559	YELLOW OXIDE	246.8	493.6	1501	LANDAU BLACK	273.3	546.6
1501	LANDAU BLACK	329.5	658.9	1552	FAST RED	324.0	648.0
1303	FLATTENER	385.4	770.8	1559	YELLOW OXIDE	366.1	732.2
1550	RED OXIDE	428.8	857.7	1556	FAST GREEN	391.3	782.5
				1508	SILVER	414.5	829.1
6251	Beige	Honda 3161M		6258	Cattle Tan	Chrysler Motors LT5	
1554	TINTING WHITE	181.1	362.3	1551	INDO YELLOW	206.1	412.2
1559	YELLOW OXIDE	342.8	685.7	1550	RED OXIDE	329.5	659.0
1303	FLATTENER	399.2	798.3	1303	FLATTENER	383.8	767.7
1550	RED OXIDE	418.1	836.1	1553	FAST BLUE	402.4	804.8
1501	LANDAU BLACK	431.8	863.7	1559	YELLOW OXIDE	416.6	833.2
6252	Max Ivory	Honda YR-416L		6260		Buick 173A	
1554	TINTING WHITE	342.8	685.7	1551	INDO YELLOW	147.9	295.8
1303	FLATTENER	400.4	800.8	1554	TINTING WHITE	292.6	585.2
1559	YELLOW OXIDE	434.1	868.3	1550	RED OXIDE	402.1	804.2
1501	LANDAU BLACK	439.0	878.0	1553	FAST BLUE	421.2	842.4
1557	MAGENTA	441.1	882.2	1556	FAST GREEN	427.6	855.3
6253	Pale Moss Green	Honda G-69L		6261	Blue Metallic	General Motors 191	
1554	TINTING WHITE	228.1	456.3	1553	FAST BLUE	157.3	314.6
1559	YELLOW OXIDE	340.2	680.5	1302	LOW LUSTER CLEAR	275.4	550.7
1303	FLATTENER	396.8	793.7	1508	SILVER	339.6	679.2
1501	LANDAU BLACK	431.5	863.0	1501	LANDAU BLACK	392.8	785.6
1557	MAGENTA	434.0	868.0	1557	MAGENTA	413.3	826.5
6254	Dark Royal Blue	Honda B-157L		6263	Siena Elephant Grey	Bombardier 5400	
1501	LANDAU BLACK	144.7	289.4	1654	WHITE	265.3	530.6
1553	FAST BLUE	252.6	505.1	1659	YELLOW OXIDE	354.3	708.5
1550	RED OXIDE	325.1	650.1	1601	BLACK	433.1	866.3
1303	FLATTENER	379.6	759.2	1680	SURE-COAT FLATTEN	498.6	997.3
1554	TINTING WHITE	418.1	836.3	1658	BRITE RED	502.2	1004.3
6255	Premium Deep Black	Honda NH-752L		6264	Sea Blue Metallic	Volkswagon 72	
1501	LANDAU BLACK	266.9	533.8	1508	SILVER	158.2	316.4
1552	FAST RED	327.1	654.2	1302	LOW LUSTER CLEAR	276.7	553.3
1303	FLATTENER	381.1	762.2	1556	FAST GREEN	334.6	669.2
1553	FAST BLUE	414.1	828.2	1558	BRITE RED	388.9	777.7
				1559	YELLOW OXIDE	414.6	829.3
				1553	FAST BLUE	415.4	830.8

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 188

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
6269	Brown	Nissan		C	6278	Lt Platinum	General Motors	WA803T
1559	YELLOW OXIDE	284.9	569.7		1554	TINTING WHITE	223.4	446.8
1558	BRITE RED	352.1	704.2		1559	YELLOW OXIDE	323.0	646.0
1303	FLATTENER	390.3	780.6		1303	FLATTENER	379.6	759.1
1501	LANDAU BLACK	420.2	840.4		1501	LANDAU BLACK	415.6	831.1
					1550	RED OXIDE	433.8	867.6
6270	Mushroom	Mercedes Benz			6279	Saffron	General Motors	WA839T
1554	TINTING WHITE	197.2	394.4		1554	TINTING WHITE	189.2	378.3
1559	YELLOW OXIDE	356.9	713.7		1551	INDO YELLOW	330.3	660.6
1303	FLATTENER	396.3	792.5		1303	FLATTENER	386.3	772.5
1550	RED OXIDE	418.3	836.6		1550	RED OXIDE	426.5	853.1
1501	LANDAU BLACK	433.2	866.5		1553	FAST BLUE	429.2	858.5
6273	Razor	General Motors		758S	6280	Gucci Black	Chrysler Motors	KX9
1501	LANDAU BLACK	171.8	343.5		1501	LANDAU BLACK	297.1	594.1
1554	TINTING WHITE	277.7	555.4		1553	FAST BLUE	360.1	720.1
1551	INDO YELLOW	337.6	675.2		1303	FLATTENER	414.1	828.2
1303	FLATTENER	392.8	785.5					
1550	RED OXIDE	423.0	845.9					
6274	Canyon Brown	Chrysler Motors		LU7	6281	Lt Diesel Gray	Chrysler Motors	LA3
1558	BRITE RED	231.7	463.3		1554	TINTING WHITE	322.8	645.7
1553	FAST BLUE	319.9	639.7		1303	FLATTENER	380.1	760.2
1302	LOW LUSTER CLEAR	373.8	747.5		1501	LANDAU BLACK	410.6	821.2
1551	INDO YELLOW	413.2	826.3		1551	INDO YELLOW	429.5	859.1
					1557	MAGENTA	438.8	877.7
6275	Lt Urban	General Motors		331N	6282	Graphite	Toyota	FJ13
1554	TINTING WHITE	304.5	609.0		1501	LANDAU BLACK	264.5	529.1
1303	FLATTENER	361.6	723.3		1554	TINTING WHITE	308.6	617.3
1551	INDO YELLOW	394.2	788.3		1551	INDO YELLOW	349.7	699.4
1550	RED OXIDE	416.0	832.1		1303	FLATTENER	387.8	775.5
1501	LANDAU BLACK	437.9	875.8		1550	RED OXIDE	418.5	837.0
6276	Morello Red	General Motors		WA747U	6283	Lt Beige	Ford Motor	54
1557	MAGENTA	282.8	565.7		1554	TINTING WHITE	423.8	847.7
1551	INDO YELLOW	337.2	674.4		1551	INDO YELLOW	434.6	869.2
1303	FLATTENER	391.1	782.3		1550	RED OXIDE	444.6	889.2
1559	YELLOW OXIDE	409.8	819.6		1501	LANDAU BLACK	447.3	894.6
1553	FAST BLUE	413.6	827.1					
6277	Caramel Tan	General Motors		WA706U	TOPCOAT WITH FORMULA 6285			
1554	TINTING WHITE	219.8	439.6		6284	Flannel Grey	Volkswagon	GQ
1551	INDO YELLOW	323.7	647.5		1554	TINTING WHITE	241.6	483.1
1303	FLATTENER	380.0	760.1		1501	LANDAU BLACK	321.0	642.0
1550	RED OXIDE	418.9	837.8		1303	FLATTENER	377.5	755.1
1501	LANDAU BLACK	431.6	863.3		1551	INDO YELLOW	406.6	813.1
					1550	RED OXIDE	433.2	866.5

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 189

		PINTS	QUARTS			PINTS	QUARTS	
		GRAMS				GRAMS		
6285	Topcoat for 6283	Ford Motor		54	6293	Mussell(Opal Gray)/	Audi	EC
1300	HIGH GLOSS CLEAR	404.5	809.0		1559	YELLOW OXIDE	128.1	256.2
3520	PLATINUM PEARL	414.6	829.2		1554	TINTING WHITE	235.3	470.6
					1501	LANDAU BLACK	333.8	667.7
					1550	RED OXIDE	387.9	775.8
					1303	FLATTENER	426.4	852.9
6286	Medium Blue Met	Ford Motor		5747	6294	Blue	Nissan	B
1300	HIGH GLOSS CLEAR	128.4	256.7		1553	FAST BLUE	173.4	346.9
1553	FAST BLUE	232.5	465.1		1501	LANDAU BLACK	267.1	534.2
1501	LANDAU BLACK	308.0	615.9		1554	TINTING WHITE	323.3	646.6
1508	SILVER	371.1	742.2		1556	FAST GREEN	379.6	759.2
1557	MAGENTA	399.4	798.8		1303	FLATTENER	417.6	835.2
1552	FAST RED	413.6	827.2					
6288	Blond	Nissan		C	6295	White Elk	General Motors	743
1559	YELLOW OXIDE	178.9	357.8		1554	TINTING WHITE	286.6	573.2
1554	TINTING WHITE	276.8	553.6		1302	LOW LUSTER CLEAR	421.7	843.4
1501	LANDAU BLACK	339.1	678.3		1551	INDO YELLOW	429.6	859.2
1550	RED OXIDE	387.9	775.7		1501	LANDAU BLACK	433.0	866.0
1303	FLATTENER	426.6	853.3		1550	RED OXIDE	435.5	870.9
6289	Med Saddle	General Motors		80	6296	Formula Boats Red	rossover to M25233	
1559	YELLOW OXIDE	193.5	386.9		1302	LOW LUSTER CLEAR	103.0	206.0
1302	LOW LUSTER CLEAR	291.1	582.2		1552	FAST RED	203.9	407.8
1554	TINTING WHITE	362.4	724.8		1559	YELLOW OXIDE	303.3	606.6
1550	RED OXIDE	408.1	816.2		1557	MAGENTA	377.9	755.9
1501	LANDAU BLACK	424.3	848.6		1558	BRITE RED	411.4	822.9
					1551	INDO YELLOW	415.4	830.7
6290	Dune	Ford Motor		DN3A	6297	Teal Metallic	Plymouth	WL2
1554	TINTING WHITE	228.5	457.0		1501	LANDAU BLACK	122.2	244.4
1559	YELLOW OXIDE	368.5	737.1		1556	FAST GREEN	241.1	482.3
1303	FLATTENER	408.1	816.1		1508	SILVER	348.5	696.9
1501	LANDAU BLACK	422.4	844.8		1553	FAST BLUE	415.1	830.2
1552	FAST RED	434.7	869.5					
6291	Hazelnut	Ford Motor		DT7A	6299	Bronze	General Motors	76I
1559	YELLOW OXIDE	179.4	358.9		1552	FAST RED	258.0	516.0
1552	FAST RED	269.5	539.0		1551	INDO YELLOW	365.0	729.9
1501	LANDAU BLACK	333.8	667.6		1303	FLATTENER	402.6	805.2
1554	TINTING WHITE	383.4	766.9		1501	LANDAU BLACK	413.7	827.3
1303	FLATTENER	421.8	843.6					
6292	Lt Dune	Ford Motor		DN1A	6300	Sterling Burgandy	rossover to M25243	
1554	TINTING WHITE	313.8	627.6		1557	MAGENTA	186.2	372.4
1559	YELLOW OXIDE	389.7	779.5		1552	FAST RED	340.6	681.3
1303	FLATTENER	429.7	859.5		1559	YELLOW OXIDE	401.6	803.2
1501	LANDAU BLACK	437.5	875.1		1551	INDO YELLOW	410.7	821.5
1557	MAGENTA	439.9	879.9		1553	FAST BLUE	415.0	830.0

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 190

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6301	Stingray Yellow	ssover to M25223		6308	Stingray Taupe	ssover to M25153	
1554	TINTING WHITE	179.8	359.6	1554	TINTING WHITE	291.4	582.7
1551	INDO YELLOW	357.4	714.8	1302	LOW LUSTER CLEAR	364.3	728.6
1559	YELLOW OXIDE	426.0	852.0	1559	YELLOW OXIDE	407.3	814.6
1552	FAST RED	429.5	858.9	1550	RED OXIDE	423.0	846.0
1553	FAST BLUE			1501	LANDAU BLACK	437.6	875.2
6302	Carver Coco	ssover to M25213		6309	Chaparel Beige/Platin	ssover to M25143	
1302	LOW LUSTER CLEAR	138.5	277.0	1554	TINTING WHITE	330.6	661.2
1552	FAST RED	269.2	538.4	1302	LOW LUSTER CLEAR	403.9	807.8
1559	YELLOW OXIDE	387.1	774.2	1559	YELLOW OXIDE	433.0	866.0
1553	FAST BLUE	401.6	803.1	1501	LANDAU BLACK	438.3	876.5
1556	FAST GREEN	415.6	831.1	1557	MAGENTA	439.9	879.9
6303	Formula Boats Grey	ssover to M25203		6310	Carver Light Tan	ssover to M25133	
1554	TINTING WHITE	305.4	610.8	1302	LOW LUSTER CLEAR	142.3	284.6
1559	YELLOW OXIDE	347.7	695.3	1554	TINTING WHITE	281.9	563.7
1303	FLATTENER	387.6	775.2	1559	YELLOW OXIDE	391.6	783.2
1550	RED OXIDE	425.0	850.0	1550	RED OXIDE	411.4	822.8
1553	FAST BLUE	439.3	878.6	1501	LANDAU BLACK	426.8	853.7
6304	Light Grey	ssover to M25193		6311	Carver Dade Bisque	ssover to M25123	
1554	TINTING WHITE	305.9	611.8	1554	TINTING WHITE	342.2	684.5
1300	HIGH GLOSS CLEAR	430.8	861.6	1559	YELLOW OXIDE	405.1	810.3
1501	LANDAU BLACK	435.6	871.1	1550	RED OXIDE	435.3	870.7
1559	YELLOW OXIDE	437.2	874.4	1556	FAST GREEN	442.8	885.6
6305	Ranger Gunmetal Gre	ssover to M25183		6312	Sea Ray Champagne	ssover to M25113	
1554	TINTING WHITE	134.5	269.0	1554	TINTING WHITE	323.9	647.7
1559	YELLOW OXIDE	230.9	461.8	1559	YELLOW OXIDE	393.4	786.9
1501	LANDAU BLACK	325.1	650.1	1303	FLATTENER	433.5	867.0
1302	LOW LUSTER CLEAR	410.3	820.7	1550	RED OXIDE	438.1	876.1
1552	FAST RED	426.3	852.6	1501	LANDAU BLACK	440.7	881.3
6306	Ranger Charcoal	ssover to M25173		6313	Sea Ray Alabaster	ssover to M25103	
1302	LOW LUSTER CLEAR	139.8	279.6	1554	TINTING WHITE	294.0	587.9
1501	LANDAU BLACK	247.9	495.8	1302	LOW LUSTER CLEAR	418.6	837.3
1559	YELLOW OXIDE	353.7	707.5	1559	YELLOW OXIDE	434.4	868.9
1554	TINTING WHITE	394.5	789.0	1557	MAGENTA	435.5	871.1
1550	RED OXIDE	419.4	838.8	1501	LANDAU BLACK	436.4	872.8
6307	Ranger Beige	ssover to M25163		6314	Sea Ray Mystic White	ssover to M25093	
1559	YELLOW OXIDE	138.0	276.1	1554	TINTING WHITE	336.5	673.0
1302	LOW LUSTER CLEAR	258.9	517.9	1302	LOW LUSTER CLEAR	437.9	875.8
1550	RED OXIDE	328.8	657.6	1559	YELLOW OXIDE	439.5	879.1
1554	TINTING WHITE	398.6	797.1	1558	BRITE RED	439.6	879.2
1553	FAST BLUE	423.2	846.3				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 191

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6315	Carver White	ssover to M25083		6322	Ultra Turquoise	ssover to M25013	
1554	TINTING WHITE	400.5	801.0	1556	FAST GREEN	165.2	330.5
1302	LOW LUSTER CLEAR	441.0	881.9	1554	TINTING WHITE	304.4	608.8
1559	YELLOW OXIDE	442.7	885.4	1302	LOW LUSTER CLEAR	389.3	778.5
1558	BRITE RED	444.3	888.6	1552	FAST RED	420.6	841.3
1556	FAST GREEN	445.0	890.0	1501	LANDAU BLACK	424.0	847.9
				1559	YELLOW OXIDE	424.2	848.5
6316	Ranger Off-White	ssover to M25073		6323	Ultra Purple	ssover to M25003	
1554	TINTING WHITE	353.1	706.1	1557	MAGENTA	161.9	323.8
1302	LOW LUSTER CLEAR	426.6	853.2	1553	FAST BLUE	245.4	490.9
1559	YELLOW OXIDE	440.0	879.9	1302	LOW LUSTER CLEAR	328.6	657.3
1557	MAGENTA	440.8	881.6	1558	BRITE RED	366.6	733.1
1553	FAST BLUE	441.3	882.7	1554	TINTING WHITE	404.3	808.7
				1550	RED OXIDE	416.0	832.0
6317	Ranger White	ssover to M25063		6324	Graphite Grey	Porsche	CY
1554	TINTING WHITE	332.0	663.9	1559	YELLOW OXIDE	141.4	282.9
1302	LOW LUSTER CLEAR	433.3	866.7	1554	TINTING WHITE	272.2	544.4
1559	YELLOW OXIDE	438.7	877.3	1501	LANDAU BLACK	357.7	715.4
1501	LANDAU BLACK	439.3	878.6	1303	FLATTENER	396.6	793.2
				1550	RED OXIDE	428.0	856.1
6318	Ranger Black	ssover to M25053		6325	Orange	Plymouth	H6
1501	LANDAU BLACK	248.7	497.4	1555	FAST ORANGE	287.0	574.0
1552	FAST RED	341.9	683.9	1551	INDO YELLOW	337.6	675.2
1302	LOW LUSTER CLEAR	411.0	821.9	1558	BRITE RED	371.4	742.7
1559	YELLOW OXIDE	412.6	825.2	1303	FLATTENER	405.1	810.2
1553	FAST BLUE	414.1	828.3	1554	TINTING WHITE	418.6	837.1
				1501	LANDAU BLACK	419.7	839.5
6319	Ranger Admiral Blue	ssover to M25043		6350	Palladium Silver	BMW	NCH1
1553	FAST BLUE	162.3	324.5	1554	TINTING WHITE	188.0	376.0
1302	LOW LUSTER CLEAR	317.2	634.4	1559	YELLOW OXIDE	281.0	561.9
1501	LANDAU BLACK	371.7	743.4	1501	LANDAU BLACK	373.3	746.7
1557	MAGENTA	400.8	801.5	1303	FLATTENER	412.5	825.0
1554	TINTING WHITE	413.2	826.5	1553	FAST BLUE	430.6	861.3
6320	Ultra Blue	ssover to M25033		6351	Sandlewood	General Motors	715
1553	FAST BLUE	381.0	761.9	1554	TINTING WHITE	250.9	501.8
1554	TINTING WHITE	401.3	802.5	1559	YELLOW OXIDE	350.7	701.3
1556	FAST GREEN	413.9	827.8	1302	LOW LUSTER CLEAR	423.2	846.4
				1501	LANDAU BLACK	432.4	864.8
				1557	MAGENTA	435.3	870.7
6321	Ranger Orchid Green	ssover to M25023		6352	Dk Sandlewood	General Motors	715
1559	YELLOW OXIDE	126.1	252.2	1559	YELLOW OXIDE	205.8	411.6
1553	FAST BLUE	201.4	402.8	1554	TINTING WHITE	301.0	602.0
1556	FAST GREEN	276.5	552.9	1302	LOW LUSTER CLEAR	372.1	744.1
1302	LOW LUSTER CLEAR	345.8	691.6	1501	LANDAU BLACK	399.9	799.7
1552	FAST RED	400.3	800.6	1550	RED OXIDE	426.2	852.4
1551	INDO YELLOW	416.0	832.0				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 192

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6353	Dk Beige	General Motors	715	6359	Indigo	Chrysler Motors	LC5
1559	YELLOW OXIDE	212.7	425.5	1501	LANDAU BLACK	228.5	457.1
1302	LOW LUSTER CLEAR	283.4	566.9	1553	FAST BLUE	370.5	741.1
1554	TINTING WHITE	349.6	699.2	1303	FLATTENER	408.2	816.4
1501	LANDAU BLACK	393.2	786.4	1554	TINTING WHITE	414.1	828.3
1550	RED OXIDE	424.3	848.5				
6354	Java	Ford Motor	EL6A	6360	Vecchio	General Motors	WA153X
1557	MAGENTA	140.4	280.9	1551	INDO YELLOW	186.4	372.9
1302	LOW LUSTER CLEAR	236.1	472.2	1552	FAST RED	277.7	555.4
1551	INDO YELLOW	300.5	600.9	1550	RED OXIDE	367.1	734.2
1559	YELLOW OXIDE	359.1	718.3	1303	FLATTENER	404.9	809.8
1501	LANDAU BLACK	414.5	829.1	1553	FAST BLUE	415.6	831.3
6355	Dk Galvanized	General Motors	WA792S	6361	Wagoner Blue	General Motors	WA863S
1501	LANDAU BLACK	162.2	324.3	1553	FAST BLUE	275.1	550.2
1302	LOW LUSTER CLEAR	282.7	565.4	1559	YELLOW OXIDE	327.8	655.5
1554	TINTING WHITE	384.0	767.9	1303	FLATTENER	365.5	730.9
1551	INDO YELLOW	407.0	814.0	1550	RED OXIDE	401.3	802.7
1550	RED OXIDE	421.8	843.6	1501	LANDAU BLACK	414.6	829.1
6356	Deep Mocha	Chrysler Motors	ML8	6362	Black	Chrysler Motors	MX9
1559	YELLOW OXIDE	190.2	380.4	1501	LANDAU BLACK	147.4	294.8
1550	RED OXIDE	303.6	607.2	1300	HIGH GLOSS CLEAR	270.6	541.1
1501	LANDAU BLACK	364.4	728.8	1551	INDO YELLOW	330.7	661.5
1303	FLATTENER	402.7	805.3	1554	TINTING WHITE	386.2	772.3
1551	INDO YELLOW	420.7	841.4	1557	MAGENTA	417.9	835.8
6356	Dark Mocha	Chrysler Motors	LL8	6363	Iceland Gray	Chrysler Motors	LAA
1559	YELLOW OXIDE	190.2	380.4	1554	TINTING WHITE	154.3	308.6
1550	RED OXIDE	303.6	607.2	1559	YELLOW OXIDE	262.6	525.2
1501	LANDAU BLACK	364.4	728.8	1501	LANDAU BLACK	357.7	715.3
1303	FLATTENER	402.7	805.3	1303	FLATTENER	396.7	793.3
1551	INDO YELLOW	420.7	841.4	1550	RED OXIDE	429.2	858.3
6357	Med Ash Gray	General Motors	WA9883	6365	Ivory Pearl	General Motors	791
1554	TINTING WHITE	215.2	430.4	1554	TINTING WHITE	392.8	785.6
1302	LOW LUSTER CLEAR	338.2	676.4	1559	YELLOW OXIDE	445.2	890.3
1501	LANDAU BLACK	391.7	783.4	1556	FAST GREEN	445.8	891.7
1550	RED OXIDE	412.3	824.7				
1551	INDO YELLOW	430.5	861.0				
6358	Oasis	Ford Motor	E15A	6366	Topcoat for 6365	General Motors	791
1302	LOW LUSTER CLEAR	132.1	264.2	1301	SATIN GLOSS CLEAR	399.2	798.4
1559	YELLOW OXIDE	251.1	502.2	3520	PLATINUM PEARL	419.2	838.3
1554	TINTING WHITE	366.1	732.3				
1550	RED OXIDE	401.8	803.6				
1501	LANDAU BLACK	425.6	851.2				

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 193

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6367	Oxford White	Ford Motor	Z	6382	Dark Ruby	Chrysler Motors	LR9
1554	TINTING WHITE	359.0	718.0	1550	RED OXIDE	153.0	306.1
1302	LOW LUSTER CLEAR	416.7	833.3	1557	MAGENTA	276.9	553.9
1559	YELLOW OXIDE	438.0	876.1	1558	BRITE RED	367.2	734.4
1501	LANDAU BLACK	441.5	883.1	1303	FLATTENER	405.1	810.2
1550	RED OXIDE	442.1	884.2	1553	FAST BLUE	416.9	833.8
6373	Adrenaline Red	General Motors	336X	6383	Wheat	Chrysler Motors	NC1
1558	BRITE RED	367.5	735.0	1554	TINTING WHITE	307.9	615.8
1303	FLATTENER	405.1	810.3	1559	YELLOW OXIDE	372.3	744.6
1554	TINTING WHITE	412.6	825.2	1303	FLATTENER	412.3	824.6
1553	FAST BLUE	414.2	828.4	1550	RED OXIDE	435.6	871.2
				1553	FAST BLUE	439.7	879.4
6375	White Sands	Ford Motor	ET3A	6384	Brandy	General Motors	WA245V
1554	TINTING WHITE	339.7	679.4	1554	TINTING WHITE	159.3	318.5
1559	YELLOW OXIDE	393.9	787.8	1551	INDO YELLOW	304.1	608.1
1303	FLATTENER	434.0	868.1	1557	MAGENTA	369.7	739.4
1501	LANDAU BLACK	438.9	877.8	1303	FLATTENER	408.4	816.9
1557	MAGENTA	441.5	882.9	1501	LANDAU BLACK	426.1	852.1
6378	Ambassador Blue	Chrysler Motors	MBB	6385	Octane Metallic	General Motors	WA123X
1501	LANDAU BLACK	200.2	400.4	1501	LANDAU BLACK	203.5	406.9
1553	FAST BLUE	329.4	658.7	1300	HIGH GLOSS CLEAR	341.6	683.2
1554	TINTING WHITE	379.6	759.3	1508	SILVER	379.0	757.9
1303	FLATTENER	417.6	835.2	1550	RED OXIDE	398.8	797.5
				1553	FAST BLUE	414.5	829.0
6379	Linen	Chrysler Motors	ML2	6386	Oasis	Ford Motor	EX2A
1554	TINTING WHITE	257.9	515.8	1554	TINTING WHITE	202.2	404.4
1302	LOW LUSTER CLEAR	381.9	763.9	1302	LOW LUSTER CLEAR	325.3	650.7
1559	YELLOW OXIDE	423.4	846.7	1559	YELLOW OXIDE	399.1	798.1
1501	LANDAU BLACK	431.1	862.2	1550	RED OXIDE	417.2	834.3
1557	MAGENTA	434.2	868.4	1501	LANDAU BLACK	431.0	862.0
6380	Black	Chrysler Motors	LXH	6387	Med Soft Oasis	Ford Motor	CN4A
1501	LANDAU BLACK	324.4	648.7	1554	TINTING WHITE	231.2	462.4
1553	FAST BLUE	376.6	753.3	1302	LOW LUSTER CLEAR	365.4	730.8
1303	FLATTENER	414.3	828.6	1559	YELLOW OXIDE	414.1	828.1
				1501	LANDAU BLACK	426.4	852.9
				1550	RED OXIDE	432.4	864.7
6381	Ski Grey	Chrysler Motors	PS4	6387	Med Soft Ceramic	Ford Motor	CN4A
1554	TINTING WHITE	349.5	699.0	1554	TINTING WHITE	231.2	462.4
1303	FLATTENER	389.6	779.3	1302	LOW LUSTER CLEAR	365.4	730.8
1559	YELLOW OXIDE	422.3	844.5	1559	YELLOW OXIDE	414.1	828.1
1501	LANDAU BLACK	439.7	879.4	1501	LANDAU BLACK	426.4	852.9
1557	MAGENTA	441.8	883.5	1550	RED OXIDE	432.4	864.7

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 194

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6388	Red Line	Ford Motor	FR5	6404	Dk Blue	Pontiac	W25A4106
1558	BRITE RED	111.5	223.0	1553	FAST BLUE	182.5	364.9
1550	RED OXIDE	211.2	422.5	1501	LANDAU BLACK	270.7	541.3
1559	YELLOW OXIDE	309.5	619.1	1554	TINTING WHITE	345.5	691.1
1557	MAGENTA	380.0	760.1	1556	FAST GREEN	419.3	838.5
1303	FLATTENER	418.0	836.1				
				1300			
6389	Mayan Gray	Ford Motor	DJ6	6405	Med Pewter	Pontiac	W25A4103
1501	LANDAU BLACK	181.7	363.4	1554	TINTING WHITE	206.2	412.5
1559	YELLOW OXIDE	313.4	626.8	1559	YELLOW OXIDE	316.2	632.5
1554	TINTING WHITE	384.3	768.5	1501	LANDAU BLACK	379.7	759.3
1303	FLATTENER	422.7	845.4	1551	INDO YELLOW	406.7	813.3
				1553	FAST BLUE	432.6	865.2
				1300			
6391	Mustang King Ranch	Ford Motor	7U7A	6406	Med Tan	Pontiac	W25A4256
1552	FAST RED	211.7	423.4	1559	YELLOW OXIDE	376.9	753.8
1559	YELLOW OXIDE	357.9	715.9	1557	MAGENTA	415.8	831.6
1303	FLATTENER	395.9	791.7	1553	FAST BLUE	421.8	843.5
1501	LANDAU BLACK	410.2	820.4	1501	LANDAU BLACK	422.4	844.8
1551	INDO YELLOW	417.0	834.0				
				1300			
6397	Loft Brown	General Motors	704S	6407	Dk Sienna	Pontiac	W25A4134
1550	RED OXIDE	239.7	479.4	1559	YELLOW OXIDE	200.6	401.2
1302	LOW LUSTER CLEAR	309.7	619.3	1550	RED OXIDE	400.1	800.2
1556	FAST GREEN	361.7	723.4	1501	LANDAU BLACK	421.7	843.4
1559	YELLOW OXIDE	402.0	804.0	1556	FAST GREEN	423.1	846.1
1551	INDO YELLOW	419.8	839.6				
				1300			
6401	Med Red Metallic	Pontiac	W60A3370	6408	Ivory	Pontiac	W25A3988
1557	MAGENTA	202.3	404.5	1554	TINTING WHITE	427.0	854.0
1552	FAST RED	352.1	704.2	1559	YELLOW OXIDE	445.1	890.3
1551	INDO YELLOW	391.3	782.6	1501	LANDAU BLACK	447.3	894.6
3521	RED PEARL	401.9	803.8	1553	FAST BLUE	447.7	895.5
3527	AZTEC GOLD PEARL	411.3	822.5				
1553	FAST BLUE	416.0	831.9				
1301				1300			
6402	Dk Green	Pontiac	W25A4252	6409	Ivory White	Pontiac	W25A4250
1559	YELLOW OXIDE	223.0	446.0	1554	TINTING WHITE	425.6	851.2
1552	FAST RED	336.6	673.3	1559	YELLOW OXIDE	444.7	889.5
1556	FAST GREEN	419.0	838.0	1501	LANDAU BLACK	446.8	893.6
				1552	FAST RED	447.5	895.0
				1553	FAST BLUE	447.7	895.3
1300				1300			
6403	Dk Jade	Pontiac	W25A4108	6410	Red Fox	BMW	NCH2
1550	RED OXIDE	149.6	299.2	1557	MAGENTA	144.2	288.4
1554	TINTING WHITE	236.2	472.3	1559	YELLOW OXIDE	279.9	559.8
1551	INDO YELLOW	319.9	639.7	1302	LOW LUSTER CLEAR	363.4	726.8
1556	FAST GREEN	401.0	802.1	1550	RED OXIDE	414.2	828.3
1553	FAST BLUE	424.0	848.0	1556	FAST GREEN	417.4	834.7
1300							

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 195

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6411	Ivory White Napa	BMW	NAEX	6420	Dk Blue Metallic	Pontiac	C-AP5834
1554	TINTING WHITE	251.5	503.0	1553	FAST BLUE	286.5	572.9
1302	LOW LUSTER CLEAR	338.3	676.5	1501	LANDAU BLACK	347.6	695.2
1551	INDO YELLOW	373.6	747.2	1556	FAST GREEN	393.0	786.0
1559	YELLOW OXIDE	401.4	802.7	1508	SILVER	404.7	809.4
1558	BRITE RED	422.7	845.3	3523	BLUE PEARL	416.4	832.8
1501	LANDAU BLACK	433.7	867.3				
				1300			
6412	Alaska Gray	BMW	LEAK	6421	Medium Red	Pontiac	C-AP4867
1554	TINTING WHITE	220.6	441.3	1558	BRITE RED	196.0	391.9
1550	RED OXIDE	307.9	615.9	1557	MAGENTA	298.0	596.1
1302	LOW LUSTER CLEAR	394.4	788.9	1559	YELLOW OXIDE	375.7	751.3
1556	FAST GREEN	418.7	837.5	1552	FAST RED	413.1	826.2
1553	FAST BLUE	432.5	865.0	1501	LANDAU BLACK	415.5	831.1
6415	Cinnamon	General Motors	WA407A	6422	Parchment	Pontiac	C-AP8360
1559	YELLOW OXIDE	285.5	571.1	1554	TINTING WHITE	384.7	769.4
1302	LOW LUSTER CLEAR	369.5	739.0	1559	YELLOW OXIDE	436.9	873.9
1557	MAGENTA	416.7	833.4	1501	LANDAU BLACK	442.9	885.8
1501	LANDAU BLACK	419.8	839.5	1557	MAGENTA	445.2	890.4
6416	Dk Olive	Chrysler Motors	JFJ	6423	Dk Turquoise Metallic	Pontiac	C-AP13008
1559	YELLOW OXIDE	180.9	361.8	1553	FAST BLUE	178.8	357.7
1501	LANDAU BLACK	279.1	558.2	1556	FAST GREEN	301.0	602.1
1551	INDO YELLOW	329.8	659.7	1508	SILVER	359.6	719.1
1552	FAST RED	372.5	744.9	1501	LANDAU BLACK	406.7	813.4
1303	FLATTENER	410.5	821.0	3524	GREEN PEARL	416.8	833.7
1550	RED OXIDE	418.2	836.4				
6417	Medium Gold	Pontiac	C-AP5054	6424	Dk Blue Metallic	Pontiac	C-AP13008
1559	YELLOW OXIDE	195.0	390.0	1553	FAST BLUE	298.7	597.5
1551	INDO YELLOW	287.7	575.4	1501	LANDAU BLACK	361.0	722.0
1552	FAST RED	335.1	670.2	1508	SILVER	409.0	818.0
1554	TINTING WHITE	366.8	733.5	3523	BLUE PEARL	415.1	830.3
1508	SILVER	393.8	787.6				
1501	LANDAU BLACK	415.7	831.5	1300			
1300							
6418	Med Gold Metallic	Pontiac	C-AP4886	6425	Dk Blue Metallic	Pontiac	C-AP5109
1508	SILVER	199.2	398.5	1553	FAST BLUE	284.2	568.4
1559	YELLOW OXIDE	373.8	747.7	1501	LANDAU BLACK	368.7	737.3
1553	FAST BLUE	395.2	790.5	1508	SILVER	408.4	816.9
1551	INDO YELLOW	410.7	821.4	3523	BLUE PEARL	414.6	829.2
1552	FAST RED	415.5	831.0	3524	GREEN PEARL	415.4	830.8
3524	GREEN PEARL	421.7	843.5	1300			
1300							
6419	Medium Red	Pontiac	C-AP71276	6426	Dk Blue Metallic	Pontiac	C-AP5646
1557	MAGENTA	122.1	244.3	1553	FAST BLUE	287.5	575.0
1558	BRITE RED	232.9	465.8	1501	LANDAU BLACK	351.6	703.2
1559	YELLOW OXIDE	318.9	637.9	1508	SILVER	409.1	818.3
1550	RED OXIDE	370.6	741.1	3523	BLUE PEARL	415.3	830.6
1552	FAST RED	416.9	833.7				
				1300			

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 196

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6427	Dk Teal Metallic	Pontiac	C-AP4879	6434	Med Blue Metallic	Pontiac	C-AP12531
1553	FAST BLUE	184.5	368.9	1508	SILVER	234.0	468.0
1552	FAST RED	280.5	561.0	1553	FAST BLUE	364.9	729.7
1508	SILVER	346.7	693.3	1501	LANDAU BLACK	409.9	819.8
1556	FAST GREEN	406.1	812.3	1557	MAGENTA	416.0	832.0
3523	BLUE PEARL	412.9	825.8				
3524	GREEN PEARL	417.0	834.0				
1300				1300			
6428	Medium Red	Pontiac	C-AP71827	6435	Dk Green Metallic	Pontiac	C-AP5130
1558	BRITE RED	171.3	342.6	1556	FAST GREEN	184.3	368.7
1557	MAGENTA	321.5	642.9	1501	LANDAU BLACK	319.3	638.7
1559	YELLOW OXIDE	388.5	777.1	1551	INDO YELLOW	373.9	747.9
1552	FAST RED	413.5	827.0	1508	SILVER	414.7	829.4
1501	LANDAU BLACK	415.2	830.5				
6429	Dark Brown	Pontiac	C-AP5179	6436	Med Blue Metallic	Pontiac	C-AP5108
1551	INDO YELLOW	153.2	306.4	1553	FAST BLUE	239.9	479.8
1552	FAST RED	274.8	549.7	1508	SILVER	381.0	762.0
1554	TINTING WHITE	341.7	683.5	1501	LANDAU BLACK	406.2	812.5
1501	LANDAU BLACK	386.1	772.3	1557	MAGENTA	414.5	829.0
1557	MAGENTA	419.2	838.4				
				1300			
6430	Dark Saddle	Pontiac	C-AP22306	6437	Mineral Gray Met	General Motors	202X
1559	YELLOW OXIDE	249.7	499.4	1508	SILVER	164.5	329.1
1552	FAST RED	314.1	628.2	1501	LANDAU BLACK	306.7	613.5
1501	LANDAU BLACK	372.9	745.8	1559	YELLOW OXIDE	376.2	752.5
1550	RED OXIDE	420.8	841.7	1557	MAGENTA	406.9	813.8
				1556	FAST GREEN	417.6	835.2
1300							
6431	Med Sandalwood(197	Pontiac	C-AP5156	6438	Urban	General Motors	330N
1554	TINTING WHITE	237.7	475.4	1302	LOW LUSTER CLEAR	138.4	276.7
1302	LOW LUSTER CLEAR	349.8	699.6	1557	MAGENTA	262.5	524.9
1551	INDO YELLOW	380.5	761.1	1551	INDO YELLOW	336.6	673.2
1559	YELLOW OXIDE	406.0	812.0	1556	FAST GREEN	385.6	771.2
1558	BRITE RED	419.8	839.7	1554	TINTING WHITE	415.1	830.2
1501	LANDAU BLACK	432.3	864.7				
6432	Carib Dk Aqua Metall	Pontiac	C-AP12534	6439	Lt Wheat	General Motors	WA503F
1553	FAST BLUE	140.4	280.8	1554	TINTING WHITE	300.2	600.4
1300	HIGH GLOSS CLEAR	249.3	498.6	1302	LOW LUSTER CLEAR	401.2	802.3
1556	FAST GREEN	321.1	642.2	1559	YELLOW OXIDE	432.8	865.6
1508	SILVER	379.9	759.8	1501	LANDAU BLACK	436.5	872.9
1501	LANDAU BLACK	407.7	815.4	1557	MAGENTA	437.4	874.9
1554	TINTING WHITE	413.9	827.8				
6433	Dk Turquoise Metallic	Pontiac	C-AP5615	6440	Vy Dk Ash Gray	General Motors	970M
1553	FAST BLUE	168.6	337.1	1552	FAST RED	123.6	247.3
1556	FAST GREEN	311.4	622.9	1556	FAST GREEN	212.0	423.9
1508	SILVER	380.7	761.3	1557	MAGENTA	297.0	594.0
1501	LANDAU BLACK	414.0	828.1	1551	INDO YELLOW	347.4	694.9
				1303	FLATTENER	385.3	770.5
				1554	TINTING WHITE	415.9	831.8
1300							

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 197

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6441	Med Earth Grey	Ford Motor	DY5A	6447	Terra Cotta	Ford Motor	FR6
1554	TINTING WHITE	175.7	351.3	1552	FAST RED	182.4	364.8
1559	YELLOW OXIDE	253.5	506.9	1559	YELLOW OXIDE	356.0	711.9
1501	LANDAU BLACK	330.1	660.1	1303	FLATTENER	393.9	787.8
1303	FLATTENER	369.1	738.2	1501	LANDAU BLACK	415.9	831.8
1557	MAGENTA	401.5	803.0	1551	INDO YELLOW	417.6	835.3
1551	INDO YELLOW	429.3	858.6				
6442	Super Red	General Motors	717R	6448	Mojave	Ford Motor	GX4
1558	BRITE RED	160.3	320.5	1551	INDO YELLOW	178.7	357.5
1557	MAGENTA	313.6	627.3	1554	TINTING WHITE	279.8	559.6
1559	YELLOW OXIDE	368.7	737.4	1557	MAGENTA	346.9	693.7
1303	FLATTENER	406.4	812.9	1303	FLATTENER	385.7	771.3
1550	RED OXIDE	414.9	829.8	1558	BRITE RED	404.1	808.2
				1501	LANDAU BLACK	421.5	843.0
6443	Black Pearl	Chrysler Motors	MX9	6449	Cappucino	Ford Motor	GU3
1552	FAST RED	210.4	420.8	1554	TINTING WHITE	324.8	649.5
1556	FAST GREEN	312.1	624.1	1303	FLATTENER	364.8	729.6
1501	LANDAU BLACK	389.1	778.2	1550	RED OXIDE	401.5	803.1
1508	SILVER	403.2	806.4	1551	INDO YELLOW	421.5	842.9
1553	FAST BLUE	414.2	828.4	1559	YELLOW OXIDE	431.3	862.6
				1553	FAST BLUE	440.1	880.1
6444	Red	Chrysler Motors	XR4	6450	Brune	Ford Motor	FS9
1552	FAST RED	166.5	333.0	1552	FAST RED	304.5	609.1
1558	BRITE RED	258.3	516.7	1551	INDO YELLOW	346.0	692.0
1559	YELLOW OXIDE	339.9	679.8	1303	FLATTENER	383.2	766.4
1302	LOW LUSTER CLEAR	377.9	755.7	1501	LANDAU BLACK	408.3	816.7
1554	TINTING WHITE	400.3	800.5	1553	FAST BLUE	413.7	827.4
1550	RED OXIDE	417.6	835.3				
6445	Gray	Fiat	JD7	6451	Coffee	Ford Motor	DJ9
1557	MAGENTA	144.5	289.0	1302	LOW LUSTER CLEAR	129.5	259.0
1302	LOW LUSTER CLEAR	213.9	427.7	1501	LANDAU BLACK	227.9	455.9
1556	FAST GREEN	281.3	562.6	1551	INDO YELLOW	295.5	591.0
1551	INDO YELLOW	343.9	687.7	1554	TINTING WHITE	347.4	694.9
1501	LANDAU BLACK	381.0	761.9	1557	MAGENTA	396.6	793.2
1554	TINTING WHITE	416.1	832.2	1558	BRITE RED	417.3	834.5
6446	Light Atmosphere	General Motors	WA311X	6452	Medium Lt Camel	Ford Motor	4T2
1554	TINTING WHITE	324.2	648.4	1554	TINTING WHITE	185.4	370.8
1302	LOW LUSTER CLEAR	396.7	793.4	1559	YELLOW OXIDE	345.3	690.6
1559	YELLOW OXIDE	429.3	858.7	1303	FLATTENER	384.5	769.1
1501	LANDAU BLACK	435.6	871.2	1557	MAGENTA	402.6	805.3
1557	MAGENTA	439.5	879.1	1501	LANDAU BLACK	419.4	838.7
				1551	INDO YELLOW	431.8	863.6
6447	Light Atmosphere	General Motors	WA311X	6453	Deep Mocha	Chrysler Motors	ML8
1554	TINTING WHITE	324.2	648.4	1559	YELLOW OXIDE	176.3	352.7
1302	LOW LUSTER CLEAR	396.7	793.4	1558	BRITE RED	248.1	496.1
1559	YELLOW OXIDE	429.3	858.7	1501	LANDAU BLACK	293.6	587.2
1501	LANDAU BLACK	435.6	871.2	1551	INDO YELLOW	337.4	674.8
1557	MAGENTA	439.5	879.1	1550	RED OXIDE	380.7	761.4
				1303	FLATTENER	418.8	837.5

SEM Products, Inc. - COLOR COAT FORMULAS

SEM MIXING SYSTEM for exterior and interior vinyl, plastic, carpet and velour. Each formula is in grams and is shown on an accumulative basis. Be sure to agitate all basic tinting colors thoroughly before mixing each formula. See trim code listings for print and instrument panel information.

SMSF
REV. 09/16
PAGE 198

		PINTS	QUARTS			PINTS	QUARTS
		GRAMS				GRAMS	
6454	Maple Sugar	General Motors	WA395A	6462	Dk Ginger	Ford Motor	M3606G
1559	YELLOW OXIDE	193.1	386.1	1559	YELLOW OXIDE	177.7	355.4
1554	TINTING WHITE	316.4	632.7	1557	MAGENTA	307.9	615.8
1550	RED OXIDE	360.4	720.8	1551	INDO YELLOW	391.7	783.3
1303	FLATTENER	399.4	798.8	1556	FAST GREEN	417.8	835.5
1501	LANDAU BLACK	420.9	841.9				
1551	INDO YELLOW	428.7	857.5				
6455	Md Ivy Green Metalli	Ford Motor	M3608G	6463	Med Turquoise Metall	Pontiac	W60A3305
1559	YELLOW OXIDE	267.6	535.2	1508	SILVER	199.7	399.4
1501	LANDAU BLACK	342.2	684.3	3520	PLATINUM PEARL	274.6	549.1
1508	SILVER	387.9	775.8	1553	FAST BLUE	344.3	688.7
1553	FAST BLUE	409.4	818.7	1559	YELLOW OXIDE	404.0	808.1
1556	FAST GREEN	420.6	841.2	1556	FAST GREEN	438.9	877.9
1300				1300			
6456	Saddle	Pontiac	931	6220 Alt1	Orion Gray	Mercedes Benz	268
1559	YELLOW OXIDE	193.0	385.9	1554	TINTING WHITE	216.3	432.7
1302	LOW LUSTER CLEAR	313.7	627.4	1559	YELLOW OXIDE	310.1	620.2
1554	TINTING WHITE	377.9	755.8	1501	LANDAU BLACK	390.3	780.6
1552	FAST RED	410.8	821.7	1303	FLATTENER	429.6	859.3
1501	LANDAU BLACK	422.5	845.0	1557	MAGENTA	432.9	865.8
6457	Pewter	Ford Motor	6NCA	6249 Alt1	Truffle	Rolex Vans	
1550	RED OXIDE	177.0	353.9	1554	TINTING WHITE	165.9	331.8
1554	TINTING WHITE	333.3	666.6	1501	LANDAU BLACK	273.8	547.6
1556	FAST GREEN	401.0	801.9	1550	RED OXIDE	342.6	685.3
1553	FAST BLUE	430.0	860.1	1551	INDO YELLOW	389.5	779.1
				1303	FLATTENER	428.5	857.0
6458	Gold	Oldsmobile	34/634	6440 Alt1	Vy Dk Ash Gray	General Motors	970M
1551	INDO YELLOW	185.8	371.7	1501	LANDAU BLACK	167.8	335.5
1508	SILVER	260.1	520.3	1559	YELLOW OXIDE	263.1	526.3
1302	LOW LUSTER CLEAR	322.1	644.1	1302	LOW LUSTER CLEAR	342.9	685.9
1501	LANDAU BLACK	368.5	737.0	1554	TINTING WHITE	383.6	767.3
1550	RED OXIDE	407.5	815.0	1558	BRITE RED	419.2	838.3
1557	MAGENTA	415.3	830.6				
6459	Lt Sandlewood	Pontiac	267				
1559	YELLOW OXIDE	276.2	552.5				
1554	TINTING WHITE	322.8	645.5				
1303	FLATTENER	361.3	722.5				
1501	LANDAU BLACK	394.9	789.8				
1557	MAGENTA	419.7	839.4				
1551	INDO YELLOW	423.6	847.2				
6461	Roof Interior Gray	British Motor C					
1554	TINTING WHITE	339.9	679.9				
1303	FLATTENER	380.0	760.1				
1559	YELLOW OXIDE	409.3	818.6				
1550	RED OXIDE	420.8	841.6				
1553	FAST BLUE	431.1	862.2				
1552	FAST RED	441.1	882.2				